INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

PAPER, TABULATING MACHINE, CONTINUOUS FLATFOLD

This interim amendment was developed by the General Services Administration, Office of Federal Supply and Services, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to Federal Specification UU-P-546C, dated January 11, 1974.

PAGE 2

Paragraph 2.2 add: "T 401 - Fiber Analysis of Paper and Paperboard."

Paragraph 3.2.1, delete and substitute the following:

"3.2.1 Paper. The paper shall be made from not less than 95 percent bleached chemical pulp, with not more than 5 percent unbleached and/or groundwood pulp, when tested as specified in 4.4.5. No polychlorinated biphenyls (PCB's) shall be added or used during the manufacture of the paper or in any coating operation on the base paper. As evidence of compliance, the contractor shall submit a certificate stating that no polychlorinated biphenyls have been added or used during the manufacturing or converting operations. (see 4.2.1)."

Paragraph 3.2.1.1, second line, delete and substitute the following:

"(see 6.2.), this is expressed as the weight of 500 sheets of paper of a basic".

PAGE 3

Paragraph 3.3.1.1, delete last sentence, "Perforation cuts shall not intersect cuts in horizontal perforations."

PAGE 4

Paragraph 3.4.1.1, last sentence, delete and substitute the following:

"Crimps shall be spaced at not more than 3 inch intervals and shall fall not closer than 3/8 inch to the horizontal tearlines."

Paragraph 3.5.1, last sentence, delete and substitute the following:

"Unless otherwise specified (see 6.2), the basis weight of the paper shall be 20 pounds."

PAGE 5

Paragraph 3.7.1, first sentence, delete and substitute the following:

"When specified, horizontal lines shall be printed on the face of each part in the form set with black, gray, or green ink."

PAGE 6

Paragraph 3.8, second line, delete and substitute the following:

"container shall have not more than one break per container, splices not permitted; unbroken".

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

Add new paragraph:

"4.2.1 Evidence of compliance. In lieu of using his own facilities, the contractor may submit a report of analysis of component materials from a laboratory acceptable to the Government whether an independent test facility or the laboratory of the raw material supplier, as evidence of compliance with the specification requirements. The report of analysis shall include, in addition to the actual test data, the manufacturer's name, name and address of the testing laboratory, date of test, and quantity of material represented by the test report. Where certification of compliance or reports of analysis are submitted, the Government reserves the right to check test such items to determine the validity of the certificates or analysis."

PAGE 8

In the table, under the Perforations Defects, delete "Horizontal and vertical cuts intersect."

PAGE 9

Paragraph 4.3.2, delete and substitute the following:

"4.3.2 Testing of the end item. The end item shall be tested in accordance with the methods as cited in 4.4.1, 4.4.2, 4.4.3, 4.4.4, and 4.4.5. For performance testing (4.4.1) and thickness determination (4.4.4), the sample unit shall be 100 (one-hundred) complete sets. For writing quality (4.4.2), basis weight (as applicable, 4.4.3), and fiber analysis (4.4.5) testing, the sample unit shall be 5 (five) complete sets. The lot size shall be expressed in units of 100 (one-hundred) sets of tabulating forms. The sample size shall be S-1 and there shall be no failure to pass the performance, writing quality, basis weight (as applicable), thickness or fiber analysis tests."

Paragraph 4.4.1, first and second sentences, delete and substitute the following:

"Feed 100 complete sets of the tabulating paper, single or multi-part forms, as applicable through a high speed printer at 1200 lines per minute. The printer shall be properly adjusted for the number of parts in the set and with the printer activated to print randomly selected information utilizing the working area of each complete set in the sample unit."

Paragraph 4.4.2, first sentence, delete and substitute the following:

"Characters shall be written on one part (chosen alternatively) of a set with a one (1) percent aqueous solution of Acid Red 1 Color Index Number 18050 or Acid Green 3 Color Index Number 42085 (see 6.3)."

Add new paragraph:

"4.4.5 Fiber analysis. The paper shall be tested in accordance with TAPPI Method T 401 to determine conformance with the composition requirement specified in 3.2.1."

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:21Z
Check the source to verify that this is the current version before use.