UU-P-561H
December 12, 1972
SUPERSEDING
Int. Fed. Spec. UU-P-00561G(GSA-FSS)
May 20, 1971 and
Fed. Spec. UU-P-561D
December 5, 1951

FEDERAL SPECIFICATION

PAPER, TRACING

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers tracing papers for use in the tracing of drawings, the development of original drawings, and for other purposes requiring high grade tracing papers.

1.2 Classification.

1.2.1 Types. Tracing papers shall be of the following types, as specified (see 6.2):

Type I - White, rag, medium strength, natural tracing paper, permanent quality.
Type II - White, chemical wood, untreated, good translucency, non-permanent quality.
Type III - White or tinted, rag, high translucency, permanent quality.
Type IV - White or tinted, rag, medium translucency, permanent quality.

1.2.2 Classes. All tracing papers shall be of one class, with slightly grained surface.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

SS-P-166 - Pencils, Lead.
TT-I-528 - Ink; Drawing, Waterproof, Black.
UU-P-268 - Paper, Kraft, Untreated, Wrapping.
UU-P-270 - Paper, Wrapping, Waxed (Dry).
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-F-320 - Fiberboard: Sheet Stock (Container Grade) and Cut Shapes.
PPP-T-45 - Tape, Gummed, Paper, Reinforced and Plain, For Sealing and Securing.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington DC 20406.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-L-10547 - Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Incorporated, Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the National Motor Freight Traffic Association, Inc., Agent, 1616 P Street N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies shoud be addressed to the Uniform Classification Committee, Tariff Publishing Officer, Room 1106, 222 South Riverside Plaza, Chicago IL 60606.)

Technical Association of the Pulp and Paper Industry (TAPPI) Standards:

T 401 - Fiber Analysis of Paper and Paperboard.
T 402 - Standard Conditioning and Testing Atmoshperes for Paper, Board, Pulp Handsheets and Related Products.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

T 410 - Weight per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T 423 - Folding Endurance of Paper (Schopper Tester).
T 425 - Opacity of paper.

(Application for copies shoud be addressed to the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, GA 30341.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and Federal agencies.)

3. REQUIREMENTS

3.1 Material. Tracing paper shall be made from fibrous, cellulosic material and shall conform to the requirements of table I.

Table I. Physical characteristics

Type	Weight 17 X 22 1000	Fiber Content Rag	Folding endurance before aging, min. av.ea.dir.Schopper	Folding endurance retention, after aging, each dir.	Tearing strength min.av. ea.dir.	Opacity max.av. before aging2/	Opacity increase after aging max.
	Pounds	Percent	Double folds	Percent	Grams	Percent	Percent
I	15-17	100	200	50	20	55	3
	19-22	100	300	50	28	62	3
	25-30	100	400	50	34	70	3
II	15-17	1/	50	--	9	25	9
	19-22	1/	75	--	12	28	9
	25-30	1/	100	--	15	30	9
	32-35	1/	150	--	18	35	9
III	25-29	100	300	50	30	35	5
	31-35	100	400	50	40	43	5
	37-41	100	500	50	50	50	5
IV	25-29	100	500	50	30	45	7
	32-36	100	600	50	40	53	7
	39-43	100	700	50	50	60	7
	48-53	100	900	50	60	63	7

1/ Type II. Free from unbleached or groundwood pulp.
2/ Variation between individual opacity readings shall be no more than 4 percentage points.

3.2 Color. Types I and II shall be white. Types III and IV shall be white or tinted blue, as specified (see 6.2). The color shall not change on aging (see 4.4.1).

3.2.1 Exposure to ultra-violet radiation. When tested as described in 4.4.5, types III and IV shall develop no change in color or character of sufficient amount to increase the printing time when used for either the diazo or blueprinting process of reproduction.

3.3 Finish. All tracing papers shall be of uniform texture with slightly grained surface.

3.4 Surface. All tracing papers shall be suitable for pencil and ink lines, yielding solid lines

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:21Z
Check the source to verify that this is the currentversion before use.

without skipping, feathering, spreading or smudging. Types III and IV shall not show surface cracks or abrasion with normal usage. Types III and IV shall have a non-greasy surface suitable for printing with offset inks. The printed copy shall yield solid, sharp impressions which cannot be easly erased with a soft, non-gritty eraser. The prepared finish shall be such that when passing through a reproduction machine at peak temperature, the finished surface will not lift, flake or peel from the paper.

3.5 Curl. Types III and IV paper shall be flat when removed from the package and shall develop no curl during printing.

3.6 Form. The tracing paper shall be furnished in rolls, flat-cut sheets, or pads as specified (see 6.2).

3.6.1 Sheets. Sheet paper shall be cut square on four sides, and cut to the sizes specified (see 6.2). Sheets shall be not less than the ordered size, and not more than + 1/16 inch over size in either dimension for sizes 8 x 10-1/2 through 15 x 18, and not more than + 1/8 inch oversize in either dimension for sheets larger than 15 x 18 inches. Measurements shall be made in atmospheric conditions specified in TAPPI method T402. Any flat paper with a long dimension 32 inches or less will be considered square-cut if the variation of the diagonals does not exceed 1/32 inch; over 32 inches, 1/16 inch.

3.6.2 Rolls. Rolls shall be furnished in widths and lengths as specified (see 6.2). Tolerance on roll width shall be plus 1/4 inch, minus 0. The paper shall be uniformly and smoothly wound with an even tension on a fiberboard core having an inside diameter of 1-7/8 inches, ± 1/4 inch, and shall be suitably restrained to prevent unwinding. The length of the core shall be equal to the width of the roll material with a tolerance of minus 0 and plus 1/8 inch.

3.6.3 Pads. Pads shall be furnished in widths and lengths as specified (see 6.2) with a tolerance of plus or minus 1/8 inch. The number of sheets per pad shall be as specified (see 6.2). Pads shall be securely padded at the top and the sheets bound together with a plastic compound or glue and cheesecloth. Backs of pads shall be chipboard or any suitable pulpboars.

3.7 Drafting quality. Types III and IV shall display the following qualities when tested as specified in 4.4.2.

3.7.1 Penciling and erasing. A pencil line shall be erasable without causing ghosting or smudging, or perceptible linting or any appreciable change of color of the erased surface when tested as specified in 4.4.2.1.

3.7.2 Inking and erasing. Inked lines shall show no appreciable spreading, feathering, ragged edges or skips, upon being drawn over a fresh or an erased area, when tested as specified in 4.4.2.3.

3.8 Oil leakage. Types III and IV shall exhibit no signs of oil leakage when tested as specified in 4.4.3.

3.9 Blocking. All tracing paper shall be free of any tendency for sheets to adhere to each other when tested as specified in 4.4.4.

3.10 Workmanship. Tracing paper in accordance with this specification shall be uniform throughout and shall be free from spots, wrinkles, pinholes or any defects which will interfere with the intended use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order,

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:21Z
Check the source to verify that this is the currentversion before use.

the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may use his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Sampling for inspection. Sampling for inspection shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For sampling purposes a lot shall consist of the same type, size, form, weight and color of tracing paper offered for inspection at one time.

4.2 Inspection of materials and components. In accordance with 4.1 above, the supplier is responsible for insuring that materials and components used where manufactured, tested and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. Examination of the end item shall be made in accordance with the classification of defects, inspection levels and acceptable quality levels (AQLs) set forth below. The lot size, for purpose of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of rolls, pads or packages of sheets, as applicable, of the specified type, weight, form, size and color of paper for examinations under 4.3.1.1 through 4.3.1.4 inclusive, and in units of shipping containers for examination under 4.3.1.5.

4.3.1.1 Examination of the end item for defects in appearance and general workmanship. For examination of defects within rolls, the sample unit shall be one yard by full width of the roll. For examination of pads, the sample unit shall be one sheet randomly selected from a pad. For examination of sheets, the sample unit shall be one sheet full size randomly selected from a package. No more than five (5) sample units, randomly distributed, shall be selected from any one roll, pad, or package of sheets, as applicable. Both sides of the material shall be examined.

Examine	Defect
Form	Not in rolls or flat cut sheets, as specified.
Appearance	Incorrect type, or color of material.
	Color and cleaniness do not compare favorably with comparison sample (when furnished).
	Color, finish, and formation not uniform throughout.
	Surfaces not thoroughly clean; not free of paper dust, presence of foreign or undigested matter, dirt or oil spots, lumps, lint, shives, or slime spots.
	Tear, cut, crease, puncture, split, wrinkle, fold, or holes (including pin-holes).
	Scuff mark which definitely affects the overall use of the paper.
Workmanship	Paper curls, does not lie flat, i.e., not flat after reasonable flexing.
	Sheets not trimmed square on four sides; not trimmed clean; ragged, torn, uneven, or crushed edges.

4.3.1.2 Examination of the end item for defects in construction. The sample unit for this

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

examination shall be one roll, one pad or one package of sheets, as applicable.

Examine	Defect
Assembly of sheets	Not evenly and uniformly stacked. Any splice within sheet.
Pads	Padding and backing not as specified. Pad edges not smoothly or evenly cut, corners broken or bent.
Assembly of roll	Not suitably restrained to prevent unwinding. Material not wound uniformly and tightly on roll causing soft or uneven edges, or telescoping of the roll. Edges not clean cut; ragged, nicked, crushed or uneven edges. Material not wound on a substantial rigid fiberboard core; core broken, collapsed, crushed or mutilated.
Unwinding of roll (examine both sides)	Material slips over core when unwinding. When unwound, material sticks together to the extent that unrolling causes tearing or injury to any surface. Roll wound unevenly causing wrinkles, sharp creases, or folds within roll.

4.3.1.3 Examination of the end item for dimensional defects. the sample unit for this examination shall be one roll, one pad, or one full size sheet, as applicable.

Examine	Defect
Rolls; Width	Varies by more than minus 0 or plus 1/4 inch from width specified.
Core	Length less than width of roll material, or greater by more than 1/8 inch.
Pads	Varies by more than plus or minus 1/8 inch from dimensions specified.
Sheets	Length or width less than specified.
Sheets 8 by 10-1/2 inches up to and including 15 by 8 inches.	Oversize by more than 1/16 inch in either direction from size specified.
Sheets over 15 by 18 inches.	Oversize by more than 1/8 inch in either direction from size specified.
Squareness of sheet	Difference between the length of the two diagonals exceeds 1/32 inch for sheets 32 inches or less in length, or exceed 1/16 inch for sheets over 32 inches in length.

4.3.1.4 Examination of the end item for count and length, as applicable. The sample unit for this examination shall be one roll, one pad, or one package of sheets as applicable.

Examine	Defect
Sheets	The average count of sheets per package less than specified.
Pads	The average count of sheets per pad less than specified.
Roll length	The average length per roll less than specified.

4.3.1.5 Examination of preparation for delivery. An examination shall be made to determine

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

whether the packaging, packing and marking comply with the requirements of section 5. The sample unit shall be one shipping container fully prepared for delivery. Defects shall be scored as indicated below.

Examine	Defect
Container	Not as specified.
Contents	Not as specified.
Markings	Omitted; incorrect; illegible; improper size, location, sequence or method of application.
Materials	Component missing or damaged.
Workmanship	Bulging or distortion of containers. Cushioning inadequate, improper or missing.

4.3.1.5.1 Examination of closure and reinforcement of containers. When shipping containers are required to comply with PPP-B-636, examination for defect in closure shall be in accordance with the appendix of that specification.

4.3.1.6 Inspection levels and acceptable quality levels (AQLs) for examinations. The inspection levels for determining the sample size, and the acceptable quality levels (AQLs) expressed in defects per hundred units, shall be as follows:

Examination paragraph 1/	Inspection level	AQLs
4.3.1.1	I	4.0
4.3.1.2	S-2	1.5
4.3.1.3	S-2	2.5
4.3.1.4	S-2	-----
4.3.1.5	S-2	2.5

1/ The same rolls, sheets, pads, or packages of sheets, as applicable, of the specified material shall be used for examinations under 4.3.1.1 through 4.3.1.4 inclusive. The yardage or sheets used for examinations under 4.3.1.1 and the rolls, sheets, pads, or packages of sheets used for examinations under 4.3.1.3 and 4.3.1.4 shall be within the rolls, pads, or packages of sheets randomly selected under 4.3.1.2.

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics as indicated in table II for each lot presented for examination for each type, size, weight ,color, and form of material. The sample unit, as referenced herein, is defined as the amount of material required to perform all tests one time. No more than one sample unit shall be drawn from any one roll, pad, or package of sheets. Five sample units, randomly selected throughout the lot, shall be tested with no evidence of failure to meet the specified requirements. All samples shall be conditioned and tested in accordance with TAPPI method T 402 except where indicated.

Table II. Instructions for testing the end item.

(continued on next page)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

Table II. Instructions for testing the end item.

Characteristic	Specification Rqmt.	Reference Test Method	Requirements Applicable to Individ Unit	Lot Av.	Number Determin-ations Per Unit	Results Pass or Fail	Reported As Numerically to Nearest
Atmospheric conditions	4.3.2	T 402 1/	All testing except drafting qualities and exposure to uv radiation				
Basis weight	Table I	T 410 1/		X	One		1 pound
Fiber content	Table I	T 401 1/			One on composite2/		1 percent
Folding endurance	Table I	T 423 1/		X	5 each direction		1 fold
Folding endurance retention	Table I	T 423 1/ & 4.4.1		X	5 each direction		1 fold
Tearing strength	Table I	T 414		X	5 each direction		1 gram
Opacity	Table I	T 425 1/		X	five		1 percent
Opacity increase	Table I	T 425 1/ & 4.4.1		X	five		1 percent
Oil leakage	3.8	4.4.3	X		one	X	
Blocking	3.9	4.4.4	X		one	X	
Drafting qualities							
Pencil/erase	3.7.1	4.4.2.1	X		one	X	
Ink/erase	3.7.2	4.4.2.3	X		one	X	
Exposure to uv radiation	3.2.1	4.4.5	X		one	X	

1/ Refers to TAPPI test method.
2/ The composite sample shall consist of approximately equal amounts drawn from all the sample units into a single sample.

4.4 Test Methods.

4.4.1 Accelerated aging test. Twenty specimens of paper of the proper size for Schopper folding endurance, and suitable specimens for determining opacity (see 4.3.2) shall be heated for 72 plus or minus 1/4 hours, in a circulating air oven at a temperature of 100 plus or minus 1°C. (212°F.). The folding endurance of the aged specimens shall be determined after conditioning, and the percentage loss calculated (see 4.3.2). The opacity of the aged specimens shall be determined on the same area of the specimen as was tested for compliance with the specification, and the percentage points increase in opacity recorded. The specimens shall also be compared with unaged specimens to determine if any change in color is apparent (see 3.2).

4.4.2 *Drafting tests*.

4.4.2.1 Penciling and erasing. The sample of paper shall be placed on a drawing board cover having a Durometer reading between 89 and 93 on a Short type A-2 Durometer at 70°F., and single lines 0.37 and 0.39 mm. in width and approximately two inches long shall be drawn upon different portions of the sample with a black graphite No. 2 pencil conforming to SS-P-166, held in a vertical position under a pressure of 165 grams, and then erased with a soft, non-gritty eraser. There shall be no appreciable change of color of the erased surface, no preceptible linting of the surface, no smudging and no ghosting. For Types III and IV the surface shall withstand at least four (4) such

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

erasures of lines drawn and redrawn in exact line of previous drawing, without leaving ghost or trace of sufficient intensity to produce an image either on blueprints or whiteprints or on microfilm negatives meeting Department of Defense background density specifications, and without impairing the surface for future reproductions of all types.

4.4.2.2 Inking. Single lines of varying widths of black waterproof drawing ink which meets the requirements of TT-I-58 shall be drawn upon different portions of the sample and carefully inspected; there shall be no appreciable spreading, feathering, ragged edges, or skips.

4.4.2.3 Inking and erasing. No sooner than five minutes after the lines (see 4.4.2.2) have been drawn, they shall be erased with a soft, non-gritty eraser. Ink lines (as described in 4.4.2.2) shall be drawn upon the erased surface and examined; there shall be no appreciable spreading and feathering. For type III and IV, all weights up to and including 38-43 pounds shall withstand at least two erasures with soft, non-gritty erasers (Ruby or equal) of lines drawn with black waterproof drawing ink, without the redrawn ink line spreading, feathering, or skipping on the erased surface. The 48-53 pound weight for type IV paper shall withstand at least four such erasures and redrawing of lines.

4.4.3 Oil leakage test. Test specimens of types III and IV papers shall be placed between two sheets of plain bond paper and kept under a pressure of 0.05 pounds per square inch for 48 hours. At the end of the test period examine the bond papers which have been in contact with the test specimens for signs of oil leakage from the tracing paper.

4.4.4 Test for blocking. Twenty-five sheets shall be placed under a pressure of 0.05 pounds per square inch and maintained at a temperature of 90° ± 2°F. for 24 hours. At the end of this period, examine for evidence of adhesion; to be considered satisfactory all sheets should separate easily.

4.4.5 Exposure to ultra-violet radiation. Types III and IV tracing papers shall be exposed to the radiation from a glass-enclosed carbon-arc lamp such as the Fadeometer, type FDA-R or its equivalent, for 10 hours. There shall be no change in color or appearance of the papers so exposed to the extent that it be found necessary to increase the printing time on either the diazo or blueprinting machine in order to produce prints comparable to prints produced from unexposed paper.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2). The package shall protect the paper to conform to 3.5.

5.1.1 Level A.

5.1.1.1 Sheets. Sheets of tracing paper of one type and size specified (see 3.6.1) in quantities as specified (see 6.2) shall be assembled and shall have a sheet of the same size, nonbending paperboard not less than 0.030 inch thick on the top and bottom. The sheets shall be wrapped with paper conforming to UU-P-270, type II, class 3. The package shall be overwrapped with paper conforming to UU-P-268, grade B, minimum 60-pound basis weight and sealed with tape conforming to PPP-T-45, class 2, 3-inch wide.

5.1.1.2 Rolls. Each roll of tracing paper of one type and size specified in 3.6.2 shall be completely wrapped with dry waxed paper conforming to UU-P-270, type II, class 3. The roll shall be overwrapped with paper conforming to UU-P-268 grade B, minimum 60-pound basis weight and sealed with tape conforming to PPP-T-45, class 2, 3-inch wide.

5.1.1.3 Pads. Pads of tracing paper specified in 3.6.3 of one type and size in quantities as specified

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:21Z
Check the source to verify that this is the currentversion before use.

(see 6.2) shall be wrapped with dry waxed paper conforming to UU-P-270, type II, class 3. The pads shall be overwrapped with paper conforming to UU-P-268, grade B, minimum 60-pound basis weight and sealed with tape conforming to PPP-T-45, class 2, 3-inch wide.

5.1.2 Level B. The sheets, rolls and pads of tracing paper shall be packaged as specified in 5.1.1.1, 5.1.1.2 and 5.1.1.3 respectively, except that wrapping with dry waxed paper conforming to UU-P-270, type II, class 3 shall not be required.

5.1.3 Level C. Tracing paper shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving agency.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A. Sheets, rolls or pads of tracing paper packaged as specified in 5.1 shall be packed in a box and liner conforming to PPP-B-636, grade V3c or V3s, style FTC-L. Alternatively, shipping containers conforming to PPP-B-601, overseas type or PPP-B-621, class 2, overseas. Each shipping container shall be provided with a seal case liner conforming to MIL-L-10547, type I or II, grade B or C. Each container shall be closed and strapped in accordance with the appendix of the applicable box specification.

5.2.2 Level B. Sheets, rolls or pads of tracing paper packaged as specified in 5.1 shall be packed in a box and liner conforming to PPP-B-636, class domestic, style FTC-L.

5.2.3 Level C. Tracing paper in form and quantities as specified (see 6.2) packaged as specified in 5.1 shall be packed in containers to assure carrier acceptance and safe arrival at destination in compliance with Uniform Freight Classification or National Motor Freight Classification, as applicable.

5.3 Marking. In addition to any special marking required in the procurement documents, marking of the interior packages and exterior shipping containers shall be in accordance with Fed. Std. No. 123 for civil agencies or MIL-STD-129 for military agencies, as applicable (see 6.2).

6. NOTES

6.1 Intended use. Type I paper, which is an all-rag natural tracing paper that will not deteriorate with age, is intended for permanent drawings. Type II paper is a chemical wood paper of very good translucency for use where neither permanency nor strength are necessary qualities. Types III and IV paper are a high-grade, all-rag tracing paper, transparentized with materials which are considered permanent in nature. Type III paper possesses good translucency and is intended for tracing from existing records as well as for the development of permanent original drawings which must be suitable for making subsequent reproductions. Type IV paper is not so translucent as type III and is intended for use in the development of permanent drawings for use in reproduction work and for printing charts, maps, and other matter by multicolor offset lithography.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and weight (See 1.2 and 3.1).
(c) Color (see 3.2).
(d) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(e) Form, size of sheets, length and width of rolls and pads (see 3.6, 3.6.1, 3.6.2, and 3.6.3).
(f) Number of sheets per pad (see 3.6.3).
(g) Applicable marking document (see 5.3).
(h) Quantities required (see 5.2.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

6.3 The Department of Defense waives coordination of this specification.

MILITARY INTEREST:	Preparing activity:
Army-GL	GSA-FSS

Civil Agency Coordinating Activity:

GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.