UU-S-625a
April 19, 1965
SUPERSEDING
Int. Fed. Spec. UU-S-00625(GSA-FSS)
November 25, 1964 and
Fed. Spec. UU-P-543d
January 29, 1960

FEDERAL SPECIFICATION

STENCILBOARD

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers stencilboard suitable for marking with stencil-inks and stencil-paints.

1.2 Classification.

1.2.1 *Types and grades.* Stencilboard shall be of the following types and grades, as specified (see 6.2):

Type I—Unoiled

Grade 1—Heavy weight

Grade 2—Moderate weight

Type II—Oiled

Grade 1—Heavy weight

Grade 3—Light weight

1.2.2 *Size.* The size of the stencilboard shall be as specified (see 6.2).

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standards, of the issues in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

UU-P-31—Paper; General Specifications and Methods of Testing.

PPP-B-636—Box, Fiberboard.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies).

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications, and Standards, required by suppliers in connection with specific procurement functions should be otbained from the procuring activity or as directed by the contracting officer).

3. REQUIREMENTS

3.1 Material. Stencilboard shall be made from chemical wood pulp and additives necessary to meet the requirements of this specification. Not more than a trace of groundwood shall be permitted.

3.1.1 *Type I.* Unoiled grades of stencilboard shall conform to the physical requirements of table I when tested as specified in 4.3.2.

TABLE I.—*Physical properties, type I stencilboard*

Grade	Basis weight, pounds per 1000 square feet [1]	Thickness inch [2]	Bursting strength, minimum average, points
1	71	0.015	150
2	62	0.012	110

[1] A tolerance of plus or minus 5 percent will be permitted.

[2] A tolerance of plus or minus 0.001 inch will be permitted.

3.1.2 *Type II.* Oiled grades of stencilboard shall conform to the physical requirements of table II when tested as specified in 4.3.2.

TABLE II.—*Physical properties, type II stencilboard*

Grade	Basis weight, pounds per 1000 square feet		Thickness, inch		Bursting strength, minimum, average
	Pounds Minimum	*Pounds* Maximum	*Minimum*	*Maximum*	*Points*
1	77	92	0.015	0.018	170
3	47	55	0.010	0.012	85

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

3.1.2.1 *Aging.* Type II stencilboard shall be aged by the manufacturer until the oil is oxidized and the stencilboard shows no evidence of self heating when tested as specified in 4.3.2.

3.2 **Size.** The width and length of stencilboard shall be as specified in the contract or order with a tolerance of ± 1/8 inch (see 6.2). Edges shall be cleancut and dustfree and square to the extent that the difference between the two diagonals shall be not greater than 1/4 inch.

3.3 **Grain.** The grain of stencilboard shall be in the long dimension.

3.4 **Finish.** Stencilboard shall have a hard smooth finish and shall be free from checks, blows, or indentations. Point finish or sheet density shall not exceed 1600 points when tested as specified in 4.3.2.

3.5 **Curl.** Stencilboard shall contain no edge curl greater than 1/8 inch when tested as specified in 4.3.2.

3.6 **Workmanship.** Stencilboard shall be free from tears and dirt and the quality shall conform to the levels established in this specification.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 **Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessory to insure that supplies and services conform to prescribed requirements.

4.1.1 *Sampling for inspection.* Sampling for inspection and tests shall be performed in accordance with the provisions set forth in MIL–STD–105, except where otherwise indicated.

4.2 **Materials and components.** The supplier is responsible for insuring that all materials and components used were inspected in accordance with the requirements of this specification and of referenced specifications.

4.3 **Inspection of the end item.**

4.3.1 *Examination of the end item.* The end item shall be examined for the defects set forth in the applicable paragraphs at the inspection levels and acceptable quality levels (AQLs) in 4.3.1.5. No more than two sheets randomly selected shall be drawn from any one shipping container from each lot of material offered for inspection of visual and dimensional characteristics. For purposes of determining the sample size in accordance with MIL–STD–105, the lot size for examinations under 4.3.1.1 and 4.3.1.2 shall be expressed in units of sheets, and for examinations under 4.3.1.3 and 4.3.1.4 shall be expressed in units of shipping containers loaded with material of the specified type and grade.

4.3.1.1 *Examination of the end item for visual defects.* The sample unit for this examination shall be one sheet of stencilboard. Each side of the stencilboard shall be examined.

Examine	Defect
Appearance and workmanship	Not type or grade specified.
	Edges not clean cut, dusty.
	Surface not smooth finish; blows, checks or indentations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

4.3.1.2 *Examination for defects in dimensions.* The sample unit shall be one sheet of stencilboard.

Examine	Defect
Dimension	Greater than ± 1/8 inch of specified size.
Squareness	Difference in diagonals greater than 1/4 inch.

4.3.1.3 *Examination of the end item for count.* The sample unit for this examination shall be one container, or package, as applicable. The average count of stencilboards per container or package, as applicable, shall be not less than the specified or indicated quantity.

4.3.1.4 *Examination for preparation for delivery.* An examination shall be made to determine that markings, materials and workmanship comply with the requirements of section 5. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

Examine	Defect
Markings, exterior and interior	Incorrect; incomplete, illegible; omitted; of improper size, location, sequence or method of application.
Materials	Any nonconforming component; component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose or inadequate sealing, strapping or stapling.
	Bulged or distorted containers.

4.3.1.5 *Inspection levels and acceptable quality levels for examinations.* The inspection levels for determining the sample size, and the acceptable quality levels (AQL's) expressed in defects per hundred sample units, shall be as follows:

Examination paragraph	Inspection level	AQL's
4.3.1.1	S–4	4.0
4.3.1.2	S–2	2.5
4.3.1.3	S–2	—
4.3.1.4	S–2	2.5

4.3.2 *Testing of the end item.* The methods of testing specified in UU–P–31, where applicable, and as listed in table III, shall be followed. The test sample unit shall consist of a sufficient number of sheets to provide not less than 1000 square inches of stencilboard. The lot size shall be expressed in units of 500 sheets and no more than one sample unit shall be selected from any shipping container. The inspection level, for the purpose of determining the sample size in accordance with MIL–STD–105 shall be S–2 and the acceptable quality level (AQL), shall be 2.5 expressed as defects per one hundred sample units. The composite shall consist of representative portions of small pieces selected from all sample units and combined into a single sample.

4.4 **Tests.**

4.4.1 *Self-heating test.* The test for self-heating shall be conducted after conditioning as specified in method 102 of UU–P–31 using a Mackey or similar apparatus, having a cylindrical screen not less than 2½ inches in diameter and 6 inches in height inclosed in a water jacket. The specimens shall be taken from the center of the sample reams of stencilboard to be tested. The test

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

TABLE III.—*Instructions for testing the end item*

Characteristic	Specification reference		Requirements applicable to		Number determinations per sample unit [2]	Results reported as—	
	Requirement	Test method	Individ unit	Lot aver		Pass or fail	Numerically to nearest [3]
Atmospheric conditions	4.3.2	[1] 102	All testing				
Fiber identification	3.1	[1] 300	—	—	2 on composite		5 percent
Basis weight, pound per 1000 square feet:							
Type I	3.1.1	[1] 110	—	X	1 on 1000 sq. in. specimen		0.1 pound
Type II	3.1.2	[1] 110	—	X	1 on 1000 sq. in. specimen		0.1 pound
Thickness, inches:							
Type I	3.1.1	[1] 173	—	X	Average of 10		0.0001 inch
Type II	3.1.2	[1] 173	—	X	Average of 10		0.0001 inch
Bursting strength:							
Type I	3.1.1	[1] 112	—	X	10 (5 on each side)		1 point
Type II	3.1.2	[1] 112	—	X	10 (5 on each side)		1 point
Self heating, type II only:	3.1.2.1	4.4.1	—	—	1—composite		0.1 degree
Grain	3.3	[1] 140	X	—	1	X	
Point finish	3.4	4.4.2	X	—	1	—	unit
Curl	3.5	4.4.3	X	—	1	X	1/64 inch

[1] Indicates applicable test method of UU–P–31.
[2] Multiple determinations shall be randomly distributed throughout the sample unit.
[3] Test report shall include all values on which results are based.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

specimen shall be composed of representative portions from all sample units and then packed firmly in the screen of the apparatus to within about ½ inch from the top. A partial-immersion thermometer shall be inserted with its bulb near the center of the test specimen. The water in the jacket shall be maintained at a gentle boil and its temperature shall be measured with a thermometer. If the temperature of the test specimen does not exceed that of the boiling water by more than 5°F. at the end of 4 hours, the stencilboard shall be considered to be non-self-heating (see 3.1.2.1).

4.4.2 *Finish.* Point finish or sheet density is computed as follows (see 3.4):

$$\text{Point finish} = \frac{7200}{B} \times C$$

B = Lot average basis weight.

C = Lot average caliper in points (A point of caliper is 0.001 inch in thickness).

Example: From table in 3.1.1, grade 2 specifies a basis weight of 62 pounds per 1000 square feet, and a thickness of 0.012 inch, or 12 points caliper.

$$\text{Point finish} = \frac{7200}{62} \times 12 = 1394$$

4.4.3 *Curl test.* Two specimens, 12 by 12 inches shall be placed on a clean, dry, flat surface; one specimen with the felt side up and the other with the wire side up. If the specimen shows an edge curl, measure the distance from the surface upon which the specimen is laying to the down face of the specimen to the nearest 1/64 inch (see 3.5).

5. PREPARATION FOR DELIVERY

Fed. Std. No. 102 shall be referred to for definitions and application of the various levels of packaging and packing for civil agency procurements.

5.1 **Packaging.** Packaging shall be level C.

5.1.1 *Level C.* The stencilboard shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets these requirements.

5.2 **Packing.** Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 *Level A.* Five hundred sheets of stencilboard of one type, grade, and size, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to V3c or V3s, class weather-resistant, style FTC of PPP–B–636, except that the weight limitation shall be waived. Each shipping container shall be closed and reinforced with flat steel strapping or tape banding in accordance with the appendix of the container specification.

5.2.2 *Level B.* Unless otherwise specified (see 5.2.2.1), five hundred sheets of stencilboard of one type, grade, and size, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style FTC, type CF or SF, class domestic of PPP–B–636, except when the gross weight exceeds 120 pounds the minimum bursting strength of the fiberboard shall be 350 pounds per square inch. Each shipping container shall be reinforced with flat steel strapping or tape banding as specified in 5.2.1.

5.2.2.1 When specified (see 6.2) the shipping container shall be as specified in 5.2.1.

5.2.3 *Level C.* The stencilboard packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Con-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

tainers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 **Marking.**

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 **Intended use.** Stencilboard is intended for repeated use with stencil-ink or stencil-paint and should be suitable for use with brushes, spray guns, or roller applicator (see 1.1). Additional data regarding recommended use of each type and grade is as follows:

Type I—Unoiled.

Grade 1—For stenciling purposes where high resistance to wear is required.

Grade 2—For stenciling purposes where only a moderate degree of use is required.

Type II—Oiled.

Grade 1—For stenciling and other purposes where a high resistance to wear is required.

Grade 3—For stenciling purposes where only limited degree of use is required.

6.2 **Ordering data.** Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.

(*b*) Type, grade, and size required.

(*c*) Selection of applicable levels of packaging, packing, and marking (see 5.1, 5.2, and 5.3).

(*d*) Whether weather-resistant shipping containers are required for level B shipments (see 5.2.2.1).

6.3 Paragraph 3.1.2.1 is included specifically for type II, oiled stencilboard for prevention of spontaneous combustion, which has been experienced in some instances with shipments of oiled stencilboard.

6.4 **Transportation description.** Transportation descriptions and minimum weights applicable to this commodity are:

TYPE I—UNOILED

Rail:

Paper, surface coated, not otherwise indexed by name.

Carload minimum weight 36,000 pounds.

Motor:

Paper, surface coated, not otherwise indexed.

Truckload minimum weight 36,000 pounds, subject to Rule 115, National Motor Freight Classification.

TYPE II—OILED

Rail:

Oil Board, Paper.

Carload minimum weight 36,000 pounds.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:21Z
Check the source to verify that this is the currentversion before use.

Motor:

Oil Board, Paper.

Truckload minimum weight 36,000 pounds, subject to Rule 115, National Motor Freight Classification.

6.5 Type II, grade 2 of the previous revision has been deleted. Type II, grade 1 may be used as a replacement.

CUSTODIANS:

Army—GL

Navy—SA

Air Force—69

Review activities:

Army—GL, MU, EL

Navy—SA

Air Force—69

User activities:

Army—MR

Navy—MC, CG

Air Force—26

Preparing activity:

Army—GL

Review and User information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Copies of this specification may be purchased for 5 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.