L-F-00334E(GSA-FSS)
October 29, 1974
INTERIM REVISION OF
Fed. Spec. L-F-334D
May 15, 1967

INTERIM FEDERAL SPECIFICATION

FILM, PHOTOGRAPHIC, MICROFILM (ROLL; BLACK AND WHITE)

This Interim Federal Specification was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this Interim Federal Specification as a valid exception to Federal Specification L-F-334D dated May 15, 1967.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for sensitized photographic 16 mm, 35 mm, 70 mm, 82.5 mm (3.25 inches) and 105 mm microfilms of the gelatin-silver halide type emulsions coated on flexible transparent bases.

1.2 Classification.

1.2.1 Types, classes, kinds, and styles. The microfilms covered by this specification shall be of the following types, classes, kinds, and styles.

Types:

I - Panchromatic.
II - Blue sensitive (duplicating/print).

Classes:

A - Low speed
B - Medium speed
C - High speed

Kinds (Support type):

1 - Cellulose ester regular (triacetate base).
2 - Synthetic resin (polyester base).

Styles (Antihalation Protection):

a - Undercoating or inner coating.
b - Dye backcoating.
c - Other than above.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

PPP-B-621 - Box, Wood, Nailed and Lock-Corner.
PPP-B-636 - Box, Shipping, Fiberboard.
PPP-B-640 - Box, Fiberboard, Corrugated, Triple Wall.
PPP-T-60 - Tape: Pressure-Sensitive Adhesive, Waterproof, for Packaging.

FSC 6750

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).
Fed. Std. No. 170 - Film, Photographic, Black and White, Classification and Testing Methods.
Fed. Test Method Std. No. 406 - Plastics: Methods of Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American National Standards Institute (ANSI) Standards:

PH 1.13 - Cores for Photographic Film Rolls (Plastic, Wood or Metal) Dimensions for.
PH 1.20 - 70mm Unperforated and Perforated Film for Camera other than Motion Picture Cameras, Dimensions for.
PH 1.25 - Safety Photographic Film, Specifications for.
PH 1.28 - Photographic Film for Archival Records, Silver-Gelatin Type, on Cellulose Ester Base, Specifications for.
PH 1.41 - Photographic Film for Archival Records, Silver-Gelatin Type, on Polyester Base, Specifications for.
PH 1.31 - Brittleness of Photographic Film, Method for Determining the.
PH 1.33 - 16mm 100-Foot, 16mm 200-Foot, 35mm 100-Foot, and 70mm 100-Foot Spools for Recording Instruments and for Microfilm and Still-Picture Cameras, Dimensions for.
PH 2.19 - Diffuse Transmission Density (ISO R5).
PH 5.3 - 16mm and 35mm Silver Gelatin Microfilms for Reel Applications, Specifications for (ISO R193 and R260).
PH 22.38 - Raw Stock Cores for 16mm Motion-Picture Film, Dimensions of (ISO R1039).

(Application for copies should be addressed to the American National Standards Institute, Inc., 1430 Broadway, New York, NY 10018.)

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza., Chicago, IL 60606.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

3. REQUIREMENTS

3.1 Materials. When materials not specifically designated are used, they shall be entirely suitable for the purpose intended and of high quality.

3.1.1 Radioactive contamination. All materials used in the manufacture, packaging and packing, incuding the finished product, shall be free from radioactive contamination which would be harmful to the product.

3.2 Film base. The film base shall be an optically homogeneous, transparent medium of uniform thickness and shall be non-color selective and non-perforated. All films shall meet the requirements defined in ANSI PH 1.28 and ANSI PH 1.41 as applicable.

3.2.1 Safety base. All films shall be "Safety Photogaphic Film" as defined in ANSI PH 1.25.

3.3 Antihalation protection. Antihalation protection shall be provided in microfilm and shall be in the form of the specified styles (see 1.2.1). The antihalation coatings or layers shall be bleached or completely removed when processed in accordance with the manufacturer's recommendations.

3.4 Base density. When prepared in accordance with Fed. Std. 170, the density of an unexposed fixed-out strip shall not exceed 0.06 for classes A and B and 0.10 for class C, using the method described in ANSI PH 2.19.

3.5 Physical defects. When tested as specified in 4.4.2, the microfilm shall be free from any defect of a physical nature that will impair the end use of the product. This includes such defects as scratches, pinholes, bubbles, dirt, streaks, spots, or areas of marked higher or lower density than the surrounding area.

3.6 Film dimensions. See tables I and II.

3.6.1 Thickness. The total thickness designated in tables I and II determines the range for the "Nominal film thickness" (before processing), a term used by industry to specify the thickness of the product. The total thickness of a specific film shall not deviate by more than $\pm$ 8 percent from the thickness cited by the manufacturer when the film is measured at equilibrium with a temperature of 70°F and a relative humidity of 50 percent (see 4.4.3).

3.6.2 Width. The microfilms specified herein shall be furnished in widths in accordance with ANSI PH 5.3 or ANSI PH 1.20, as applicable (see tables I and II).

3.6.3 Length. Unless otherwise specified, types I and II microfilm shall be furnished in lengths indicated in tables I and II. A combined integral leader and trailer, not less than a total of 6 feet in length, shall be included for each roll of type I microfilm.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

TABLE I. Film dimensions for type I - panchromatic

Kind & class	Width (mm)	Total thickness (mil)	Length, minimum (feet)
Kind 1, class B & C	16	5.2 - 6.5	100 & 200
Kind 1, class B & C	35	5.2 - 6.5	100
Kind 1, class B	70	5.2 - 6.5	100
Kind 1, class B	105	5.2 - 6.5	100
Kind 2, class B & C	16	2.5 - 3.8	215
Kind 2, class B	35	2.5 - 3.8	215
Kind 2, class B & C	16	3.9 - 5.1	125 & 250
Kind 2, class B	35	3.9 - 5.1	125
Kind 2, class B	105	3.9 - 5.1	100

Note: Kinds 1 & 2, class C microfilms are available in style b only.
Kinds 1 & 2, class B microfilms are available in styles a & b.

TABLE II. Film dimensions for type II - blue sensitive

Kind & class	Width (mm)	Total thickness (mils)	Length, minimum (feet)
Kind 1, class A	16	5.2 - 6.5	400 & 1000
Kind 1, class A	35	5.2 - 6.5	1000
Kind 1, class A	70	5.2 - 6.5	1000
Kind 1, class A	82.5 (3 1/4 in.)	8.3 - 10.0	500
Kind 1, class A	105	8.3 - 10.0	500
Kind 2, class A	16	2.5 - 3.8	2500
Kind 2, class A	35	2.5 - 3.8	2500
Kind 2, class A	16	3.9 - 5.1	1600
Kind 2, class A	35	3.9 - 5.1	1600
Kind 2, class A	105	6.6 - 8.2	500

Note: Kinds 1 & 2, class A microfilm are available in style a or c.

3.7 Spools and cores. Unless otherwise specified, types I and II microfilm shall be supplied on standard spools or cores. The spools and cores shall conform to the ANSI standards specified in 2.2, as applicable.

3.8 Edge printing. Unless no edge printing is specified by the procuring activity, manufacturer's commercial code designation will be permitted provided the edge printing is along one edge only, is smaller than that normally used on film products, and is kept within 0.020 inches of the edge of the film.

3.9 Physical characteristics.

3.9.1 Tensile strength. Kind 1 microfilm shall have a tensile strength of at least 10,000 pounds per square inch in the lengthwise direction and kind 2 microfilm shall have a tensile strength of at least 20,000 pounds per square inch in the lengthwise direction when tested as specified in 4.4.4.1.

3.9.2 Brittleness. When tested in accordance with ANSI PH 1.31, the value obtained shall not exceed 0.275 inch, with readings based on the first sign of a crack or tear (see 4.4.4.2).

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:09Z
Check the source to verify that this is the current version before use.

3.9.3 Dimensional stability. The dimensional stability of the film shall be in accordance with the characteristics shown in table III when tested as specified in Fed. Std. No. 170 (see 4.4.4.3).

TABLE III.

Kind (support type)	Humidity coefficient of expansion (percent of 1 percent RH)	Thermal coefficient of linear expansion (percent per degree F)	Dimensional change due to processing (percent)	Dimensional change due to processing and aging (percent)
1	0.10	0.004	0.15	0.35
2	0.05	0.002	0.15	0.35

3.10 Sensitometric characteristics. The sensitometric characteristics of the developed films shall conform to the speed limits and gamma shown in table IV. The characteristics shall be determined in accordance with test methods, equipment and procedures specified in Fed. Std. No. 170. For types I and II microfilm, use illuminant 2, development formula No. 1, development time of 5 minutes and speed method D. Exposure time in seconds for type I microfilm shall be 1/2 second and for type II microfilm, 1/10 second (see 4.4.5).

TABLE IV. Sensitometric characteristics

Type	Class	Kind	Style	Relative sensitometric speed limits	Gamma	Mfgr.'s listed * speed value or meter setting
I	B	1	a	40 - 80	2.70 - 4.25	80 - 125
I	B	1	b	40 - 80	2.70 - 4.25	80 - 125
I	B	2	a	40 - 80	2.70 - 4.25	80 - 125
I	B	2	b	40 - 80	2.70 - 4.25	80 - 125
I	C	1	b	120 - 220	3.00 - 5.00	200 - 400
I	C	2	b	120 - 220	3.00 - 5.00	200 - 400
II	A	1	a or c	2 - 30	1.50 - 3.00	-----
II	A	2	a or c	2 - 30	1.50 - 3.00	-----

*Note: Manufacturer's listed speed value or meter setting indicates a suitable starting point for microfilm operations.

3.11 Resolution. Type I, class B film shall be capable of resolving a minimum of 600 lines per millimeter; type I, class C a minimum of 300 lines per millimeter; type II, class A a minimum of 240 lines per millimeter. The films specified herein shall be tested for resolution in accordance with Fed. Std. No. 170 and with the use of a high-contrast test chart (see 4.4.6).

3.12 Uniformity. Uniformity of physical and sensitometric characteristics among specimens of the same emulsion number, and among specimens of different emulsion numbers, shall be maintained within the limits and tolerances specified herein.

3.13 Expiration date. Unless otherwise specified the expiration date of the microfilm shall be not less than 18 months from date of shipment from the manufacturer.

3.14 Workmanship. Workmanship shall be in accordance with high grade commercial practice covering the manufacture of sensitized photographic materials of the gelatin-silver halide type. The film shall be completely suitable for the purpose intended.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:09Z
Check the source to verify that this is the current version before use.

4.2 Sampling and inspection for acceptance. Unless otherwise specified (see 6.2), sampling for inspection and acceptance shall be performed in accordance with the provisions of MIL-STD-105. For purposes of sampling, an inspection lot shall consist of all material of the same type and class submitted for delivery at one time. Alternate manufacturer's sampling and inspection procedures may be utilized providing such sampling and inspection methods will assure quality equal to or better than that obtained from MIL-STD-105, and provided the manufacturer's methods have been approved by the procuring activity.

4.2.1 Inspection of material and components. In accordance with 4.1, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.2.2 Inspection and quality of the end item.

4.2.2.1 Quality of the end item. The quality of the end item is the manufacturer's responsibility and shall be determined by means of inspection and sampling set forth in 4.2. However, the quality of the end item must be equal to or better than the quality obtained by the requirements set forth in the following paragraphs.

4.2.2.1.1 Physical examination of the end item. Examination of the end item shall be made in accordance with the classification of defects, inspection levels, and acceptance levels (AQL's) set forth below. Not more than one roll of roll film shall be drawn from any one shipping container for each lot, for each type and class of film offered for acceptance for visual and dimensional characteristics. The lot size for purposes of determining sample size in accordance with MIL-STD-105 shall be expressed in units of rolls for examinations under 4.2.2.1.2, 4.2.2.1.3, and 4.2.2.1.4, and in units of shipping containers for examination in 4.2.2.1.5. Examination included in 4.2.2.1.2, 4.2.2.1.3, and 4.2.2.1.4 may be performed at any point immediately before, during or after spooling operation.

4.2.2.1.2 Examination of the end item for defects in appearance and workmanship. The sample unit for this examination shall be one linear foot of sensitized roll film as applicable. Not more than three samples shall be drawn from any roll.

Examine	Defect
Appearance and workmanship	Film not completely or evenly coated.
	Film contains scuffs, scratches, foreign matter, or abrasions on emulsion surface.
	Abnormal longitudinal curl.
	Holes, tears, cuts, cracks, or sharp creases.

4.2.2.1.3 Examination of the end item for dimensional defects. The sample unit for this examination shall be one roll of film.

Examine	Defect
Dimensions:	Not within tolerance.
Width	
Thickness	
Length	
Leader and trailer	

4.2.2.1.4 Examination of the end item for defects in roll construction and blocking.

Examine	Defect
Roll film	Rolls not evenly or neatly wound on specified core or spool.
	Core or spool cracked, chipped, mutilated or broken.
	Not spooled as required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Examine	Defect
Unwinding of roll	Does not unroll evenly and uniformly. Film blocks during unwinding.

4.2.2.1.5 Examination of preparation for delivery. An examination will be made to determine whether marking, materials, workmanship, contents, and weights comply with requirements of section 5 of this specification. Defects will be scored in accordance with the classification below. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects. The lot size shall be the number of shipping containers fully prepared for delivery, submitted for acceptance at one time.

Examine	Defect
Packaging and preservation (as applicable)	Not as specified, not in accordance with contract requirements.
	Rolls not unit wrapped and packaged as specified.
	Unit packages not uniform.
Packing	Containers of improper construction.
	Containers not packed as specified.
	Packaging material not as specified; closures not accomplished as specified or by required methods or materials.
	Number of rolls, boxes, per carton less than indicated or specified.
Markings (interior and exterior)	Data on labels, when specified, not in accordance with contract specifications.
	Labels not properly attached.
	Exterior labels or markings illegible, incorrect, incomplete, or not in accordance with contract requirements.
Weight (interior and exterior)	Gross or net weight exceeds contract requirements.

4.2.2.1.6 Inspection levels and acceptable quality levels (AQL's) for examination. The inspection levels, for determining the sample size and acceptable quality level (AQL's), expressed in defects per 100 units, shall be as follows:

Examination	Inspection Level	AQL
4.2.2.1.1	I	1.0
4.2.2.1.2	S-3	2.5
4.2.2.1.3	S-2	2.5
4.2.2.1.4	S-2	4.0
4.2.2.1.5	S-2	4.0

4.3 Testing of the end item. Testing of the end item shall be conducted in accordance with table V for the characteristics indicated therein on each lot submitted for acceptance. The sample unit for all testing shall consist of one roll of film. Three sample units, each drawn from a different shipping container, shall be tested with no evidence of failure to meet test requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

4.3.1 Test procedures, equipment and terms. Except as specified herein, the test procedures, equipment and terms shall be in accordance with Fed. Std. No. 170.

4.4 Test methods.

4.4.1 Base density. The base density of the film shall be determined as specified in Fed. Std. No. 170.

4.4.2 Physical defects. Two pieces of film each equal to nine square inches shall be exposed in accordance with the physical defects test in Fed. Std. No. 170 and visually examined to determine compliance with the requirement specified in 3.5.

TABLE V. Instructions for testing (sample unit)

Characteristic	Specification reference: Requirement	Specification reference: Test method	Rqmts appl to: Individual unit	Number determinations per sample unit	Results reported as: Pass or fail	Results reported as: Numerically to nearest
Base density *	3.4	4.4.1	X	Average of 2		0.01 Density
Physical defects *	3.5	4.4.2	X	1	X	
Film thickness *	3.6.1	4.4.3	X	1	X	
Physical characteristics*	3.9	4.4.4				
Tensile strength *	3.9.1	4.4.4.1	X	1	X	
Brittleness *	3.9.2	4.4.4.2	X	Average of 10		
Dimensional stability*	3.9.3	4.4.4.3				
Humidity amplitude*	Table III	4.4.4.3	X	Average of 5		0.01 percent per percent RH
Thermal amplitude*	Table III	4.4.4.3	X	Average of 5		0.001 percent per degree F
Process shrinkage*	Table III	4.4.4.3	X	Average of 5		0.01 percent
Aging shrinkage*	Table III	4.4.4.3	X	Average of 5		0.01 percent
Sensitometric characteristics	3.10	4.4.5				
Relative sensitivity	Table IV	4.4.5	X			Speed range
Gamma	Table IV	4.4.5	X			0.01
Resolution	3.11	4.4.6	X			Integer

NOTE: *Contractor may furnish certificate of compliance stating that, in previous tests conducted on the same product and type of material, the material conforms to these requirements.

4.4.3 Film thickness. The thickness of the film shall be measured with a micrometer or any instrument capable of measuring within 0.0001 inch. Tests shall be made on the roll film at a minimum of four points; one at the beginning, one at the end, and one each side of the roll.

4.4.4 Physical characteristics. The following physical tests shall be conducted. The test samples shall be cut in an atmosphere of approximately 70°F and 50 percent relative humidity.

4.4.4.1 Tensile strength test. The test procedure used for measuring the tensile strength of the film shall be in accordance with method 1013 of Fed. Std. No. 406. Ten samples cut from the lengthwise direction of the film shall be tested.

4.4.4.2 Brittleness test. Using specimens cut from samples, conduct the wedge brittleness test in accordance with Method B of ANSI PH 1.31.

4.4.4.3 Dimensional stability. The film shall be tested for dimensional stability in accordance with the applicable test methods specified in Fed. Std. No. 170.

4.4.5 Sensitometric characteristics. The sensitometric tests shall be conducted in accordance with the applicable test methods of Fed. Std. No. 170 and the test conditions specified in 3.10.

4.4.6 Resolving power test. The equipment and procedure for determination of resolution shall be in accordance with Fed. Std. No. 170.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A. The film shall be packaged in a metal, light-tight, water, vapor-resistant container of suitable size and design. The metal container shall be adequately sealed against moisture and light with a water-resistant tape conforming to PPP-T-60 or a water-resistant tape of equal or better equality which will give equivalent protection.

5.1.2 Level C. Films shall be packaged to insure protection during shipment and safe delivery to destination.

5.2 Packing. Packing shall be A, B, or C as specified (see 6.2).

5.2.1 Level A. Film preserved and packaged to meet 5.1.1 shall be packaged in exterior type shipping containers in accordance with PPP-B-636, V3c; PPP-B-621, class 2; or PPP-B-640, class 2, style E. As far as practical, exterior containers shall be of uniform shape and size, be of minimum cube and tare consistent with the protection required, and contain identical quantities. The gross weight of each pack shall be limited to approximately 90 pounds. Container strength and design shall be adequate to insure protection against damage during shipment, handling, intermediate storage, and world wide redistribution. Containers shall be closed in accordance with the specification appendix. Strapping shall not be required.

5.2.2 Level B. Film packaged to meet 5.1.1 shall be packed in exterior-type shipping containers in accordance with PPP-B-636, class domestic; or PPP-B-640, class 1, style E. As far as practical, exterior containers shall be of uniform shape and size, be of minimum cube and tare consistent with the protection required, and contain identical quantities. The gross weight of each pack shall be limited to approximately 90 pounds. Container strength and design shall be adequate to insure protection against damage during multiple domestic shipments, handling, and covered storage. Closure of the boxes shall be in accordance with the appendix to the applicable box specification utilizing method II for the PPP-B-636 boxes.

5.2.3 Level C. The film packaged as specified in 5.1 shall be packed to comply with the National Motor Freight Classification rules or the Uniform Freight Classification rules.

5.3 Marking. In addition to the special marking required herein and any additional marking required by the contract or order, all markings shall be in accordance with 5.3.1 or 5.3.1 (see 6.2). The nomenclature shall be:

FILM PHOTOGRAPHIC, MICROFILM
(ROLL, BLACK AND WHITE)

5.3.1 Military agencies. Markings shall be in accordance with MIL-STD-129.

5.3.2 Civil agencies. Markings shall be in accordance with Fed. Std. No. 123.

5.3.3 Special marking. The following precautionary marking shall be permanently, prominently and legibly marked in a vivid color, preferably red, and in bold faced letters:

PHOTO SENSITIVE MATERIALS
STORE IN COOL (MAX. 50°F) DRY (50% MAX.
HUMIDITY) LOCATION AWAY FROM RADIOACTIVE
MATERIALS

5.4 Labeling. A label containing all the appropriate information for the contents (see 5.4.1) shall be firmly attached to each can and unit package. The labels shall be attached in such a manner that they will not be damaged when the package is opened.

5.4.1 Label data. The following information shall be included in the labeling provided: Classification (types, classes, kinds and styles), manufacturer's name, manufacturer's commercial designation, width and length, stock number, emulsion number, expiration date and speed value or meter setting.

6. NOTES

6.1 Intended use. The films covered by this specification are intended for use in microfilm equipment for the reproduction of negative or positive photographic images.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Film classification, type, class, kind, style (see 1.2).
(c) Thickness and width required (3.6.1 and 3.6.2).
(d) Length and quantity required (see 3.6.3).
(e) Type of spool or core required (see 3.7).
(f) Edge printing required (see 3.8).
(g) Processing, if required.
(h) Expiration date (see 3.13).
(i) Selection of samples (see section 4).
(j) Level of packing, packaging, and marking required (see section 5).

6.3 Remarks. It shall be noted that the classification of microfilm in accordance with Fed. Std. No. 170 (designator system) has been eliminated from this Interim Federal Specification.

MILITARY CUSTODIANS:

Army - EL
Navy - AS
Air Force - 70

Review activities:

Army - EL
Navy - AS
Air Force - 70, 85

User activities:

Army - DepSO
Navy - MC, SH

Preparing activity:

GSA-FSS

DC 78-8217

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
3b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	7b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
7c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION is OBSOLETE.

Source: https://assist.dla.mil – Downloaded: 20261O-26T11:09Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Mobility Equipment Research & Development
Command
ATTN: DRDME-DS
Fort Belvoir, VA 22060

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:09Z
Check the source to verify that this is the current version before use.