L-F-334d
May 15, 1967

SUPERSEDING
Int. Fed. Spec. L-F-334c (GSA-FSS)
October 31, 1966 and
Fed. Spec. L-F-334b
June 24, 1964

FEDERAL SPECIFICATION

FILM, PHOTOGRAPHIC, ROLL, MICROFILM (BLACK AND WHITE)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for use of all Federal Agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for sensitized photographic 16mm, 35mm and 70mm microfilms of the gelatin-silver halide type emulsions coated on flexible transparent bases.

1.2 Classification.

1.2.1 Film classification. The microfilms covered by this specification shall be alpha-numerically classified, for physical and sensitometric characteristics, in accordance with the film classification system shown in table I of this specification and Fed. Std. No. 00170 (see 6.3).

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

PPP-B-621—Box, Wood, Nailed and Lock-Corner.
PPP-B-636—Box, Fiberboard.
PPP-B-640—Box, Fiberboard, Corrugated, Triple Wall.
PPP-T-60 —Tape: Pressure-Sensitive Adhesive, Waterproof, for Packaging.

Federal Standards:

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian agencies).

Fed. Std. No. 00170 (GSA-FSS)—Film, Photographic, Black and White, Classification and Testing Methods.

Fed. Test Method Std. No. 406—Plastics: Methods of Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Auburn, Wash.

(Federal Government activities may obtain copies of Federal Specifications Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

FSC 6750

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:09Z
Check the source to verify that this is the current version before use.

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

United States of America Standards Institute Standards:

PH1.13-1953	—Molded Type Cores for Photographic Film and Paper Rolls.
PH1.20-1963	—70mm Unperforated and Perforated Film for Cameras other than Motion Picture Cameras, Dimensions for.
PH1.25-1956 (R-1962)	—Safety Photographic Film, Specification for.
PH1.28-1957	—Specifications for Films for Permanent Records.
PH1.33-1961	—16mm 100-Foot Spools for Recording Instruments and for Microfilm and Still Picture Cameras.
PH1.34-1961	—16mm 200-Foot Spools for Recording Instruments and for Microfilm and Still Picture Cameras.
PH1.35-1961	—35mm 100-Foot Film Spools for Recording Instruments and for Microfilm and Still Picture Cameras.
PH1.36-1961	—70mm 100-Foot Spools for Recording Instruments and for Microfilm and Still Picture Cameras.
PH2.19-1959	—Diffuse Transmission Density.
PH5.3-1958	—Specifications for 16mm and 35mm Microfilms on Reels or in Strips.
PH22.38-1952	—Raw Stock Cores for 16mm Motion Picture Film.

(Copies may be obtained from the United States of America Standards Institute, Inc., 10 East 40th Street, New York 10016.)

3. REQUIREMENTS

3.1 General requirements. Films covered by this specification shall meet the requirements and tests specified herein and in Fed. Std. No. 00170 as applicable. In case of conflict between the requirements and tests of this specification and the testing methods in Fed. Std. No. 00170, the requirements of this specification shall take precedence.

3.1.1 Materials. When materials not specifically designated are used, they shall be entirely suitable for the purpose intended and of high quality.

3.1.2 Radioactive contamination. A sample of all materials used in the manufacture, packaging, and packing, including the finished product, shall be free from radioactive contamination which would be harmful to the product. A system acceptable to the procuring activity, shall be installed for monitoring "fall-out" in the plant area. All materials produced elsewhere and brought into the plant and used for inter-leaving, wrapping, packaging, or shipping containers, shall be tested in an approved manner for the presence of radioactivity.

3.2 Data requirement. No data is required by this specification, or by applicable documents referenced in section 2, unless specified in the contract or order (see 6.2).

3.3 Detail requirements.

3.3.1 Film base. Unless otherwise specified, the film base shall be an optically homogeneous, clear transparent medium, and shall be subjectively non-color selective and non-perforated. All films shall meet the requirements defined in USASI—PH1.28-1957, Specifications for Films for Permanent Records.

3.3.2 Safety base. The film shall be "Safety Photographic Film"; as defined in USASI—PH1.25-1956.

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T11:09Z
Check the source to verify that this is the current version before use.

3.3.3 Antihalation coating. When a bleachable or removable antihalation coating is required for manufacturing convenience or product usage, it shall be bleached or removed completely during processing without interfering with the normal functioning of the standard processing solutions and without requiring any special manipulation of the film.

3.3.4 Base density. When prepared in accordance with Fed. Std. 00170, the density of an unexposed fixed-out strip shall not exceed 0.06, using the method described in USASI—PH2.19–1959 for American Standard Diffuse Visual Density Type VIb.

3.3.5 Physical defects. When tested as specified in Fed. Std. 00170, the microfilm shall be free from any defect of a physical nature that will impair the end use of the product. This includes such defects as scratches, pinholes, bubbles, dirt, streaks, spots, or areas of marked higher or lower density than the surrounding area.

3.4 Film dimensions.

3.4.1 Thickness. The total thickness designator in table I determines the range for the nominal thickness of the product. The thickness of a specific film shall not deviate by more than ±0.5 mils from the nominal thickness.

TABLE I. Film classification system

Designator: 6 1 1 4 5 5 g*

Product	Type	Support type	Total thickness (Mils)	Spectral sensitivity	Gamma	Relative sensitivity
6—Microfilm	1—Negative 4—Duplicating	1—Cellulose Ester Reg	4—5.2–6.5	2—Blue sensitive 5—Panchromatic	3—1.01–1.50 4—1.51–3.00 5—3.01–5.00	C–3 g–50

* Sample Designator

** Plus or Minus ½ Stop Tolerance

3.4.1.1 Width. The microfilm specified herein, shall be furnished in widths in accordance with USASI —PH5.3–1958 or USASI—PH1.20–1963, as applicable.

3.4.1.2 Length. Unless otherwise specified, type 1 and 4 microfilm specified herein, shall be furnished in 100, 200, and 1,000 foot lengths. A combined integral leader and trailer, not less than a total of 3 feet in length for type 1, and 6 feet in length for type 4 shall be included for each roll furnished.

3.5 Spools and cores. Unless otherwise specified, types 1 and 4 microfilm shall be supplied on standard spools or cores. The spools and cores shall conform to the United States of America Standards Institute Standards (USASI) specified in 2.2, as applicable.

3.6 Resolution. Type 1 film shall be capable of resolving a minimum of 400 lines per millimeter. Type 4 film shall be capable of resolving a minimum of 300 lines per millimeter. The films specified herein shall be tested for resolution in accordance with 4.4.2.

3.7 Edge printing. Unless no edge printing is specified by the procuring activity, manufacturer's commercial code designation will be permitted provided the edge printing is along one edge only, is smaller than that normally used on film products, and is kept within .020 inches of the edge of the film.

3.8 Sensitometric characteristics. The sensitometric characteristics of the developed films shall be in accordance with table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

TABLE II. Sensitometric characteristics, test methods, equipment, and procedures are specified in Fed. Std. No. 00170

Type	Illuminant	Exposure Time (Seconds)	Development formula	Development time (Minutes)	Speed method	Relative sensitometric speed limits	Gamma
1	2	½	No. 1	5	D	30–60	2.75–4.25
4	2	1/10	No. 1	5	D	2–6	1.5–2.7

3.8.1 Relative sensitivity speed group range. The relative sensitivity speed group range shall be within the limits shown in table III.

TABLE III

Type	Relative sensitivity	Relative sensitivity speed group range	Commercial exposure index
1	g–50	36–70	20–125
4	c–3	2.2–4.2	------

3.9 Physical characteristics.

3.9.1 Tensile strength. Support type 1 microfilm shall have a tensile strength of at least 10,000 pounds per square inch in the lengthwise direction, when tested as specified in 4.4.3.

3.9.1.1 Brittleness. The film brittleness shall conform to the following limits when tested in accordance with Fed. Std. No. 00170. When method B (wedge) is used, the average limit for the first failure shall not be greater than 0.50 inch either along the length or the width of the film. When method C (vise) is used, the average spacing of the parallel planes for first failure shall not be greater than 0.15 inch for either dimension of the film. The limit for first failure shall not be greater than 0.30 inch for either dimension.

3.9.1.2 Dimensional stability. The dimensional stability of the film shall be in accordance with the characteristics shown in table IV when tested as specified in Fed. Std. No. 00170 (see 4.4.4).

TABLE IV

Designator support type	Humidity coefficient of expansion percent of 1 percent RH	Differential humidity coefficient of expansion percent of 1 percent RH	Thermal coefficient of linear expansion percent per degree F.	Dimensional change due to processing percent	Differential dimension change due to processing percent	Dimensional change due to processing and aging percent	Differential change due to processing and aging percent
1	0.10	----	0.004	0.15	----	0.35	----

3.10 Uniformity. Uniformity of physical and sensitometric characteristics among specimens of the same emulsion number, and among specimens of different emulsion numbers, shall be maintained within the limits and tolerances specified herein.

3.11 Expiration date. Unless otherwise specified, the expiration date of the microfilm specified herein, shall be not less than 18 months from date of shipment from the manufacturer.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:09Z
Check the source to verify that this is the currentversion before use.

3.12 Workmanship. Workmanship shall be in accordance with high grade commercial practice covering the manufacture of sensitized photographic materials of the gelatin-silver halide type.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling for inspection and acceptance. Unless otherwise specified, sampling for inspection and acceptance shall be performed in accordance with provisions set forth in MIL-STD-105. The manufacturer's sampling and inspection procedures may be utilized providing such sampling and inspection methods will assure quality equal to or better than that obtained by following the provisions set forth in MIL-STD-105, and provided the manufacturer's methods have been approved by the procuring activity. For purposes of sampling, an inspection lot shall consist of all material of the same film classification designator submitted for inspection and delivery at one time.

4.2.1 Inspection of materials and components. In accordance with 4.1 above, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.2.2 Inspection and quality of the end item.

4.2.2.1 Quality of the end item. The quality of the end item is the manufacturer's responsibility and can be determined by either of the means of inspection and sampling set forth in 4.2. However, the quality of the end item must be equal to or better than the quality obtained by the requirements specified in the following paragraphs.

4.2.2.1.1 Examination of the end item. Examination of the end item shall be made in accordance with the classification of defects, inspection levels and acceptable quality levels (AQL's) set forth below. Not more than three rolls of film shall be drawn from any one shipping container for each lot, for each designator type, and emulsion number of film offered for acceptance for visual and dimensional characteristics. The lot size for purposes of determining sample size in accordance with MIL-STD-105 shall be expressed in units of rolls for examinations under 4.2.2.1.2, 4.2.2.1.3, and 4.2.2.1.4, and in units of shipping containers for examination in 4.2.2.1.5. Examinations included in 4.2.2.1.2, 4.2.2.1.3, and 4.2.2.1.4 may be performed at any point immediately before during, or after the spooling operation.

4.2.2.1.2 Examination of the end item for defects in appearance and workmanship. The sample unit for this examination shall be one linear foot of film. Not more than three samples shall be drawn from any roll.

4.2.2.1.3 Examination of the end item for dimensional defects. The sample unit for the examination shall be one roll or one linear foot of film, as applicable.

Examine	Defect
Width	—Not within tolerance.
Thickness	

4.2.2.1.4 Examination of the end item for defects in construction and length. The sample unit for this examination shall be one roll of film.

Examine	Defect
Roll	Film blocks. Not wound on specified core or spool not as specified; core or spool cracked, broken, chipped, mutilated or collapsed. Length not as specified.

4.2.2.1.5 Examination of preparation for delivery. An examination will be made to determine that marking, materials, workmanship, contents, and weights comply with the requirements of section 5 of this specification. Defects will be scored in accordance with the classification below. The sample unit shall be one shipping container, fully packed, selected just prior to closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:09Z
Check the source to verify that this is the current version before use.

Examine	Defect
Packaging and preservation	Not as specified, not in accordance with contract requirements. Rolls not unit wrapped and packaged as specified. Unit packages not uniform. Containers of improper construction.
Packing	Not packed as specified. Packing materials not as specified: closures not accomplished by specified or required methods or materials. Number of rolls per carton less than indicated or specified.
Markings (interior and exterior)	Marking not in accordance with contract specifications. Labels, when used, not properly attached, markings illegible, incorrect, incomplete, omitted, or not in accordance with contract requirements.
Weight (interior and exterior)	Gross or net weight exceeds contract requirements.

4.2.2.1.6 Inspection levels and acceptable quality levels (AQL's) for examination. The inspection levels for determining the sample size and acceptable quality levels (AQL's), expressed in defects per 100 units, shall be as follows:

Examination	Inspection level	AQL
4.2.2.1.1	II	1.0
4.2.2.1.2	S-3	2.5
4.2.2.1.3	S-2	2.5
4.2.2.1.4	S-2	4.0

4.3 Testing of the end item. Testing of the end item shall be conducted in accordance with table V for the characteristics indicated therein on each lot submitted for acceptance. The sample unit, as reference herein is defined as the amount of material required to perform all tests one time. The sample unit for all testing shall consist of one roll of film. Three sample units drawn from a different shipping container, shall be tested with no evidence of failure to meet sample requirements. As an alternate, samples for testing for sensitometric characteristics, resolutions, brittleness, tensile strength, tear resistance, and dimensional stability characteristics may be drawn at any point after the emulsion coating operation. Sample testing for maximum fog and film edge marking shall be taken at any point not sooner than immediately prior to the beginning of the packaging operation.

4.4 Test methods.

4.4.1 Testing. The testing shall be as specified herein or in accordance with the test methods of Fed. Std. No. 00170, as applicable and as indicated in table V. Conditions, methods and tests shall be selected for the film designator being procured (see table I).

4.4.2 Resolving power test. The equipment and methods shall be in accordance with Fed. Std. No. 00170.

4.4.3 Tensile strength. The test procedure used for measuring the tensile strength of the film shall be in accordance with method 1013 of Fed. Std. No. 406. Ten samples shall be cut from the lengthwise direction of the film and shall be subjected to the above test.

4.4.4 Brittleness test. The film shall be tested in accordance with Fed. Std. No. 00170 for brittleness

4.4.5 Dimensional stability. The film shall be tested for dimensional stability in accordance with the applicable test methods specified in Fed. Std. No. 00170.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

TABLE V. Instruction for testing (Sample Unit)

Characteristic	Specification reference		Rqmts appl to		Number determinations per sample unit	Results reported as	
	Requirement	Test method	Indiv unit	Lot Average		Pass or fail	Numerically to nearest
*Thickness	3.4.1	Fed. Std. 00170	X	—	Avg of 2	—	0.0001
*Resolution	3.6	Fed. Std. 00170 (4.4.2)	X	—	Avg of 5	—	Integer
Gamma	Table II	Fed. Std. 00170	X	—	Avg of 2	—	.01 Density
*Tensile strength	3.9.1	4.4.3	X	—	Avg of 2	—	lb/sq inch
Brittleness	3.9.1.1	Fed. Std. 00170 (4.4.4)	X	—	Avg of 2	—	—
*Dimensional stability	3.9.1.2.	Fed. Std. 00170 (4.4.5)					
Humidity amplitude	Table IV	Fed. Std. 00170	X	—	Avg of 2	—	0.001 percent/ 1 percent RH
Humidity amplitude, differential distortion (when applicable)	Table IV	Fed. Std. 00170	X	—	Avg of 2	—	0.001 percent/ 1 percent RH
Process shrinkage	Table IV	Fed. Std. 00170	X	—	Avg of 2	—	0.01 percent
Process shrinkage, differential distortion (when applicable)	Table IV	Fed. Std. 00170	X	—	Avg of 2	—	0.01 percent
Aging shrinkage	Table IV	Fed. Std. 00170	X	—	Avg of 2	—	0.01 percent
Aging shrinkage, differential distortion (when applicable)	Table IV	Fed. Std. 00170	X	—	Avg of 2	—	0.01 percent

* Contractor may furnish certificate of compliance in previous tests conducted on the same product and type of material, that the material conforms to these requirements.

5.1.1 Level A. The film shall be packaged in a metal, light-tight, water, vapor-resistant container of suitable size and design. The metal container shall be adequately sealed against moisture and light with a water-resistant tape conforming to PPP–T–60 or a water-resistant tape of equal or better quality which will give equivalent protection.

5.1.2 Level C. Films shall be packaged in accordance with the contractor's commercial practice.

5.2 Packing.

5.2.1 Level A. Film preserved and packaged to meet 5.1.1 shall be packed in exterior-type shipping containers in accordance with PPP–B–636 class V3C; PPP–B–621, class 2; or PPP–B–640, class 2, grade A, style E. As far as practical, exterior containers shall be of uniform shape and size, be of minimum cube and tare consistent with the protection required, and contain identical quantities. The gross weight of each pack shall be limited to approximately 90 pounds. Container strength and design shall be adequate to insure protection against damage during shipment, handling, intermediate storage, and world-wide redistribution. Containers shall be closed in accordance with the specification appendix. Strapping shall not be required.

5.2.2 Level B. Film packaged to meet 5.1.1 shall be packed in exterior-type shipping containers in accordance with PPP–B–636, type CF, class domestic; or PPP–B–640, class 1, grade A, style E. As far as

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

practical, exterior containers shall be of uniform shape and size, be of minimum cube and tare consistent with the protection required, and contain identical quantities. The gross weight of each pack shall be limited to approximately 90 pounds. Container strength and design shall be adequate to insure protection against damage during multiple domestic shipments, handling, and covered storage.

5.2.3 Level C. Film preserved and packaged to meet 5.1.2 shall be packed in exterior-type shipping containers in accordance with PPP–B–636, type CF, class Domestic. As far as practical, exterior containers shall be of uniform shape and size, be of minimum cube and tare consistent with the protection required, and contain identical quantities. The gross weight of each pack shall be limited to approximately 90 pounds. Container strength and design shall be adequate to insure protection against damage during direct shipment from the supply source to the first receiving activity for immediate use. This level, in general, will conform to applicable carrier rules and regulations.

5.2.3.1 Refrigeration transportation. Unless otherwise specified, shipments will be made under refrigeration at the discretion of the manufacturer, but in keeping with his standard practice for insuring maintenance of product quality while in transit to destination. (see 6.2)

5.3 Marking.

5.3.1 Military agencies. All shipping containers shall be marked in accordance with MIL–STD–129, except that the dimensions of the exterior container need not be included. The nomenclature shall be:

FILM PHOTOGRAPHIC, MICROFILM
(BLACK AND WHITE)

5.3.1.1 Civil agencies. Marking shall be in accordance with Fed. Std. No. 123.

5.3.1.2 Other markings. The following precautionary marking shall be permanently, prominently and legibly marked in a vivid color preferably red, and in bold faced letters.

PHOTO SENSITIVE MATERIALS
STORE IN COOL DRY LOCATION AWAY
FROM RADIOACTIVE MATERIALS

5.4 Labeling. A label containing all the appropriate information for the contents (see 5.4.1) shall be firmly attached to each can and unit package. The labels shall be attached in such a manner that they will not be damaged when the package is opened.

5.4.1 Label data. The following information shall be included in the labeling provided: Film classification designator, manufacturer's name, manufacturer's commercial designation, width and length, stock number, emulsion number, expiration date, and exposure index.

5.4.1.1 Color of labels. Labels shall be printed in heavy black on colored paper stock as shown below for the spectral sensitivity designators.

Spectral Sensitivity	Color of Labels
2—Blue Sensitive	White
5—Panchromatic	Green

6. NOTES

6.1 Intended use. The films covered by this specification are intended for use in microfilm equipment for the reproduction of negative or positive photographic images.

6.2 Ordering data. Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Film classification system designator.
(c) Stock number.
(d) Data, when required (see table V, 4.1, and 5.4).
(e) Length and width (see 3.4.1.1, 3.4.1.2).
(f) Spools and cores (see 3.5).
(g) Expiration date (see 3.11).
(h) Selection of samples (see section 4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

(i) Inspection responsibility (see 4.1).
(j) Test methods (see 4.4).
(k) Level of packaging and packing required (see section 5).
(l) Marking if other than specified (see 5.3).

6.3 Definitions.

6.3.1 Film classification system. The film classification system is an alpha-numerical system used to classify a given film in accordance with table I and Fed. Std. No. 00170. A sample designator is shown below:

Product	Type	Support type	Total thickness (Mils)	Spectral sensitivity	Gamma	Relative sensitivity
6	1	1	4	5	5	g

Reading left to right (61–14–55g)

6 = Micro film
1 = Negative type
1 = Cellulose ester regular base
4 = Thickness range (5.2–6.5)
5 = Panchromatic
5 = Gamma range (3.01–5.00)
g = Relative sensitivity

(When ordering, the full film classification designator must be used).

6.4 Cross reference of classification. The film classification has been completely revised. The items covered by this specification may be binned with prior items. The film classification system specified in this specification will replace the previous system of designation classification under L–F–334a, and L–F–334b. The main differences between the basic specifications and this specification are shown in the cross reference below:

Basic specification		This specification
Type	is now	Product
Classes	is now	Spectral Sensitivity

In addition, other classifications have been added (see table I) such as Type, Total Thickness, Gamma and Relative Sensitivity which will allow users to select a complete designator for microfilms of their choice to meet their particular requirements.

MILITARY INTERESTS:

Custodians:
Army—EL
Navy—NASC
Air Force—70

Preparing Activity:
Navy—NASC

Reviewer activities:
Army—EL
Navy—NASC
Air Force—70, 85

User Activities:
Army—MO
Navy—MC, NSSC

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.