L-L-330B
January 11, 1974
SUPERSEDING
Fed. Spec. L-L-330A
April 6, 1967

FEDERAL SPECIFICATION

LINER PLASTIC, WASTE RECEPTACLE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 This specification covers one type and size polyethylene (PE) plastic liner or insert for placement inside of a square swinging door type metal waste receptacle.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issues in effect on the date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein:

Federal Specifications:

PPP-B-585 - Boxes, Wood, Wirebound.
PPP-B-591 - Boxes, Fiberboard, Wood-Cleated.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Box, Fiberboard.
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple-Wall.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspections by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

FSC 7240

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street, NW, Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Preproduction sample. When specified (see 6.2), before production sample liners shall be submitted or made available to the contracting officer or his authorized representative for examination and approval in accordance with 4.2. Approval of the preproduction sample authorizes the commencement of production but does not relieve the supplier of the responsibility for compliance with the detailed provisions of this specification. The preproduction sample shall be manufactured in the same facilities to be used for the production items.

3.2 Material. Polyethylene shall be virgin material or virgin material blended with clean rework material, generated from the manufacturer's own production. When reworked material is used it shall be blended back into the same type and kind of virgin compound to produce a container equal in quality to the one molded from virgin material.

3.3 Dimensions. The liner shall conform to the following dimensions: The outside dimensions under the reinforcing lip shall be 15 ± 1/4 inch by 15 ± 1/4 inch and the height shall be 22-1/2 ± 1/4 inch. The height and width of the reinforcing lip shall not exceed 1 inch and 1/2 inch, respectively. The wall thickness shall be not less than 0.080 inch. The weight of the liner shall be not less than 4 pounds.

3.4 Construction. The liner shall be molded in one piece and shall be watertight in accordance with 4.4.2.

3.5 Finish. There shall be no holes, pockets, or voids in the surface of the liner. All surfaces and corners (inside and outside) shall be molded smooth, free of cracks, broken surfaces, pits, over crevices. The radius on all corners shall be not less than 3/16 inch.

3.6 Color. Unless otherwise specified (see 6.2), the liner shall be gray.

3.7 Impact. Liners shall not crack when tested in accordance with 4.4.2 and 4.4.4.

3.8 Bending. Liners shall not crack or retain a permanent set when tested in accordance with 4.4.5.

3.9 Workmanship. Liners shall be free from sharp edges, burrs, and scratches. The finish shall be smooth, free from grit, dirt, or defects affecting appearance or serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

4.2 Preproduction sample inspection. When a preproduction sample is required, it shall be examined for defects in table I, dimensions specified, and tested in accordance with 4.5.1 through 4.5.5. The presence of any visual defects or any dimension not meeting specified requirements or failure to meet the test requirements shall be cause for rejection of the preproduction sample.

4.3 Sampling and inspection.

4.3.1 Lot. Unless otherwise specified (see 6.2), a lot shall consist of all liners submitted for inspection at one time.

4.3.3 Visual examination of end item. Sampling for this examination shall be according to level S-3 in MIL-STD-105. The acceptable quality levels (AQL's) for defects listed in table I shall be 2.5 percent defective for major defects and 6.5 percent for total defects.

4.3.4 Sampling for tests. Sampling for tests shall be in accordance with level S-3 in MIL-STD-105. The AQL for tests shall be 6.5 on the basis of percent defective. Any deviation from requirements shall be classified as a defect.

4.4 Examination.

4.4.1 End item. Receptacles and covers selected in accordance 4.2.2 shall be examined for defects listed in table I.

TABLE I. Classification of defects, end item

Defects	Major	Minor
Dimensions not as specified	X	
Wall thickness less than 0.080 inches	X	
Weight not as specified	X	
Scratches in liner		X
Dirt, grit, or foreign matter imbedded in finish	X	
Liners malformed or damaged	X	
Sharp or burred edges present	X	
Damage or defects not affecting function or serviceability		X
Damage or defects affecting function or serviceability	X	
Any corner fillet less than 3/16 inch	X	

4.4.2 Inspection of preparation for delivery. An inspection shall be made to determine that the packaging, packing, and marking comply with the requirements in section 5. Defects shall be scored in accordance with table II. For examination of interior packaging the sample unit shall be one shipping container fully prepared for delivery, selected at random just prior to the closing operations. Sampling shall be in accordance with MIL-STD-105. Defects of closure listed in table II shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 with an AQL of 4.0 defects per hundred units.

TABLE II. Classification of preparation for delivery defects

Examine	Defects
Markings (exterior and interior)	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps loose strapping, inadequate stapling. Distortion of container.
Weight	Gross weight exceeds requirements.

4.5 Tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

4.5.1 General. Liners selected in accordance with 4.3.4 shall be tested to verify compliance with this specification.

4.5.2 Room temperature. All sample liners shall be dropped 3 times from a height of 6 feet onto a concrete floor striking the base, side, and top edge. The liners shall show no indication of cracks as a result of this test (see 3.6). The liners shall then be filled with water and allowed to stand for one hour. Examination shall then be made to determine compliance with 3.3.

4.5.3 Conditioning liner. Fill 1/2 of the sample liners with 80 pounds of crushed ice each, and place them together with the remaining empty liners, in an environmental chamber for a minimum of 12 hours at a temperature of 0° ± 2°F. After conditioning, the liners shall be tested in accordance with 4.5.4 and 4.5.5.

4.5.4 Low temperature. Liner (s) with the prescribed amount of ice shall be taken from the environmental chamber. Raise the container 3 feet above a concrete floor and tilt at an angle of approximately 45°. Release and allow to fall freely striking the bottom edge. The linner shall show no indication of cracks as a result of this test. The test shall commence within 5 seconds after removal from the environmental chamber and shall be completed within 60 seconds from the time of removal (see 3.6).

4.5.5 Deformation. Remove the empty container (s) from the environmental chamber and within 5 seconds place it on its side on a concrete floor. Step on the container at a point 4 to 6 inches below the top rim with enough weight to make one side touch the opposite side. This completed test shall be conducted within 15 seconds from the removal from the environmental chamber (see 3.7).

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A. Unless otherwise specified (see 6.2), 4 liners of like description shall be nested together and packaged in a close-fitting box conforming to PPP-B-636, type CF, class domestic. The box shall be closed in accordance with the appendix to the box specification.

5.1.2 Level C. The liners shall be packaged in accordance with the suppliers' commercial practice.

5.2 Packing. Packing shall be level A, B, or C, as specified.

5.2.1 Level A. Unit packages of liners of like description shall be packed in close-fitting boxes conforming to PPP-B-585, class 3; PPP-B-591, class II; PPP-B-601, overseas type; PPP-B-621, class 2; PPP-B-636, class weather-resistant; or PPP-B-640, class 2. The boxes shall be closed and strapped in accordance with the applicable specification or appendix thereto. The gross weight of the triple-wall fiberboard box and the wood boxes shall not exceed 200 pounds. The gross weight of the PPP-B-636, fiberboard box shall not exceed the weight limitations of the box specification.

5.2.2 Level B. No packing required.

5.2.3 Level C. The liners shall be packed for shipment in a manner which will insure acceptance by common carrier and safe delivery at destination. Containers shall conform to the requirements of the National Motor Freight Classification rules or Uniform Freight Classification rules, as applicable.

5.3 Marking.

5.3.1 Civil agencies. In addition to markings required by the contract or order, the packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military agencies. In addition to markings required by the contract or order, the packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The liners covered by this specification are intended for refuse and waste prior to bulk disposal. The liners are not to be used for hot ashes or near an open flame.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Color (see 3.5).
(c) Size of lot, if different from 4.2.1.
(d) Selection of applicable levels of packaging and packing required (see 5.1 and 5.2).
(e) Special marking required (see 5.3.1 and 5.3.2).
(f) If a preproduction sample is required (see 3.1).

User activity:

Navy - MS

Preparing activity:

GSA-PSS

Review activities:

Army - GL
Navy - YD
Air Force - 84

Civil Agency Coordinating Activity:

HEW-NIH

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents rerferenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:09Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.