L-T-0075(ARMY-MO)
26 April 1965

INTERIM FEDERAL SPECIFICATION

TAPE, PIPE-COATING; PRESSURE-SENSITIVE, POLYETHYLENE

This Interim Federal Specification was developed by the U. S. Army Mobility Equipment Center, Research, Development and Engineering Directorate, Fort Belvoir, Virginia, 22060, based upon currently available technical information. It is recommended that Federal Agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers tape, with primer, for application to exterior surfaces of metal pipe.

1.2 Classification. The tape shall be of the following types, as specified (see 6.2):

Type I - Polyethylene.
Type II - Plasticized polyvinyl chloride.

2. APPLICABLE PUBLICATIONS

2.1 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

E96	- Methods of Test for Measuring Water Vapor Transmission of Materials in Sheet Form.
D-1000	- Methods of Testing Pressure-Sensitive Adhesive Coated Tapes Used for Electrical Insulation.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103.)

3. REQUIREMENTS

3.1 Physical properties. The tape shall conform to the physical requirements shown in table I.

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:09Z
Check the source to verify that this is the current version before use.

Table I. Physical Properties.

Property	Requirements	
	Type I	Type II
Width, inches deviation from nominal, max.	0.1	0.1
Thickness, mils, min.	10	15
Adhesive strength, oz/in. width		
To bare stainless steel, min.	25	-
To primed stainless steel, min.	32	48
To backing, min.	20	-
Breaking strength, lb/in. width, min.	20	30
Elongation, percent, min.	100	50
Water-vapor transmission rate gm/24 hr/ 100 sq in., max	0.2	0.1
Dielectric breakdown after standard conditioning, volts	900	900
After 24-hr water immersion, volts	800	800

3.2 Rolls. The tape shall be furnished in rolls with no separator between rolls. The rolls shall be furnished in the width, length, and core diameter, as specified (see 6.2 and 6.3).

3.3 Primer. The primer shall be a liquid free from foreign particles and shall not settle in the container. The primer shall have good brushing and spraying properties when applied at normal room temperature. The primer shall permit immediate application of the tape without loss of adhesive strength. The primer shall be furnished in 55-gallon drums, 5-gallon pails, or 1-gallon cans, as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

3.4 Type I tape. Type I tape shall be an elastomeric film backing of either polyethylene or plasticized polyvinyl chloride (or its copolymers), coated on one side with a uniform film of pressure-sensitive adhesive.

3.5 Type II tape. Type II tape shall be a laminate of plasticized polyvinyl chloride (or its copolymers) and uncured butyl rubber.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Sampling. Inspection test samples shall be selected in accordance with ASTM Method D-1000.

4.3 Test procedures. The examinations and tests of the tape shall be made in accordance with the ASTM Methods shown in table II. Failure to comply with table I shall constitute failure of the test.

Table II. Test Methods.

Tests	Method
Width	D-1000
Thickness	D-1000
Length of tape in roll	D-1000
Adhesion strength, type I to unprimed steel	D-1000
Adhesive strength, type I and II to primed steel	D-1000 (1)
Adhesive strength, to backing type I	D-1000
Breaking strength and elongation	D-1000
Water-vapor transmission rate	E-96, proc. B
Dielectric breakdown	D-1000 (2)

(1) The steel strips shall be coated with the primer furnished by the tape manufacturer. It shall be used at the minimum thickness recommended by the manufacturer for field use. The tape shall be applied immediately to the primed test plate. Type I plate then shall be conditioned at 73.4° plus or minus 2° F. for 7 hours. Type II shall be conditioned at the same temperature for 72 hours. After conditioning, the adhesion of the tape to the test plate shall be determined.

Source: https://assist.dla.mil -- Downloaded: 20260-26T11:09Z
Check the source to verify that this is the current version before use.

(2) Conditioning of 96 hours at 73.4° plus or minus 2° F. and 96 percent relative humidity shall be omitted.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Unless otherwise specified in the contract or order, commercial preservation and packaging standard in the industry is acceptable for the primer and rolls of tape.

5.2 Marking. The primer container or the carton in which containers are packaged shall be labelled to show the manufacturer's name, primer name or number, lot number, date of manufacture, application instructions, and the name and number of the tape with which it is to be used. If the carton is labelled with this information, each container in the carton shall bear at least the manufacturer's name and application instructions. The visible side of the core of each roll of tape shall be marked with the manufacturer's name and tape number. The carton containing the tape shall be marked with the manufacturer's name, tape name and number, lot number, this specification number, date of manufacture, and designation of primer to be used with the tape.

6. NOTES

6.1 Intended use. The plastic tapes covered by this specification are intended to be used for corrosion prevention of exterior surfaces of metal pipe and conduit to be exposed underground, underwater, in damp galleries, and similar places where corrosive conditions exist. Either of the two types of tape is considered to provide adequate long-term corrosion prevention against all naturally occurring soils and waters. The tapes are normally applied in spiral fashion by hand-operated or motorized pipe wrapping machines.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type of tape required (see 1.2).
(c) Width, length, and core diameter of roll required (see 3.2).
(d) Size of container required for the primer (see 3.3).

6.3 The tape covered by this specification is available commercially in the following sizes:

Core diameter (inside) - 1-1/2 inches
Widths - 1, 2, 3, 4, 6, and 9 inches
Lengths - 100 and 300 feet

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Core diameter (inside) - 3 inches
Widths - 2, 3, 4, 6, 9, and 12 inches
Lengths 400, 600, and 800 feet.

Custodian:

Army - MO(ERDL)

Preparing activity:

Army - MO(ERDL)

Project No. 9330-A067

GSA DC 68-9395

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:09Z
Check the source to verify that this is the current version before use.