L-T-100C
July 9, 2013
Supersedes
L-T-100B
July 12, 1988

FEDERAL SPECIFICATION

TAPE, PRESSURE-SENSITIVE ADHESIVE, POLYESTER FILM

This specification is approved by the Commissioner, Federal Acquisition Service, GSA, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1. Scope. – This specification defines the requirements for pressure-sensitive tapes possessing a high degree of stability, solvent resistance, and designed for applications where the properties of a polyester film are desired (see 6.1).

1.2. Classification

1.2.1. Types. – The pressure-sensitive tapes covered by this specification shall be of the following types (see 6.2):

Type I – Transparent polyester solvent resistant.
Type II – Colored polyester solvent resistant.

2. APPLICABLE DOCUMENTS

2.1. Government Publications: The following documents, of the issues in effect on date of invitation for bids or request for proposal form a part of this specification:

Federal Specifications:

ASTM D471 – Rubber Property-Effects of Liquids
ASTM B209 – Aluminum and Aluminum-Alloy Sheet and Plate
PPP-T-680E – T ape, Pressure-Sensitive Adhesive, Packaging and Packing of

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from General Services Administration in Boston, MA; New York, NY; Washington, DC; Atlanta, GA; Chicago, IL; Kansas City, MO; Fort Worth, TX; Denver, CO; San Francisco, CA; Los Angeles, CA; and Auburn, WA.)

Military Specifications;

MIL-DTL-5624V - Turbine Fuel, Aviation, Grades JP-4 and JP-5
MIL-PRF-7808L - Lubricating Oil, Aircraft Turbine Engine, Synthetic Base
MIL-PRF-5606H - Hydraulic Fluid, Petroleum Base, Aircraft, Missile, and Ordnance

(Copies of Military specifications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

FSC 7510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

2.2. Other Publications: The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal will apply.

American Society for Testing and Materials (ASTM):

D3330 – Peel Adhesion of Pressure-Sensitive Tape at 180 degrees Angle, Test for
D3652 – Thickness of Pressure-Sensitive and Gummed Tapes, Test for
D3715 – Quality Assurance of Pressure-Sensitive Tapes, Practice for
D3759 – Tensile Strength and Elongation of Pressure-Sensitive Tapes, Test for
D6551 – Accelerated Weathering of Pressure-Sensitive Tapes by Xenon-Arc Exposure Apparatus, Practice for

Application for copies of ASTM documents should be addressed to the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

Technical Association of the Pulp and Paper Industry (TAPPI):

T402 - Standard Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets and Related products.

Application for copies of TAPPI documents should be addressed to the Technical Association of the Pulp and Paper Industry; 15 Technology Parkway South, Norcross, GA 30092.

3. REQUIREMENTS

3.1. Material. – The tape backing shall consist of a non-hydroscopic solvent resistant polyester film coated on one side with a solvent resistant, water insoluble, pressure-sensitive adhesive requiring no moisture, heat or other preparation prior to application.

3.2. Physical Properties. – The mean average of the test values for the tape shall comply with the Physical Property requirements listed in Table I.

3.3. Corrosion. – There shall be no evidence of corrosion or pitting of the aluminum panels under the tape after the elevated temperature aging test (see 4.3.7).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

TABLE I. Physical Properties

Property	Type I	Type II	Test Paragraph
Thickness, in. max.	0.003	0.003	4.3.4
Tensile strength, lbs/in width (minimum)	17	17	4.3.4
Elongation at Break (Percent minimum)	70	70	4.3.4
Adhesion (oz/in width) minimum			
Initial	20	20	4.3.4
After accelerated weathering	50	50	4.3.5
After 24 hrs. immersion in distilled water	20	20	4.3.6
After 72 hrs. immersion in Jet Engine Fuel Grade JP-4, (MIL-T-5624V)	20	20	4.3.6
After 24 hrs. immersion in Standard Test Fluid Test II - (ASTM D471)	15	---	4.3.6
After 72 hrs. immersion in Hydraulic Fluid (MIL-PRF-5606H)	20	20	4.3.6
After 24 hrs. immersion in Lubricating Oil (MIL-PRF-7808L)	20	20	4.3.6
After 168 hrs. at 180 deg. F $\pm$ 5 deg. F	50	---	4.3.7
After 20 hrs. adhesive aging	15	15	4.3.9
Printing Stability	---	---	4.3.8

3.4. Rolls. – The tape shall be furnished in evenly and uniformly wound rolls, adhesive side in, on cores made of paper fiber or non-fibrous plastic. The core shall have sufficient rigidity to prevent distortion of the roll under normal conditions of transportation, storage, and use. The inside diameter of the core shall be 3 inches, -0, +1/16 inch in diameter. When the roll is unwound, the backing shall not tear, and adhesive shall not transfer or split from the face of the tape to the back of the adjacent layout.

3.5. Length and Width. – The length of the rolls shall be 72 yards (minimum). The width of the roll shall be 1/4, 1/2, 3/4, 1, 1-1/2, or 2 inches or other commercially available widths, as specified (see 6.2). A tolerance of plus or minus 1/32 inch shall be allowed on widths up to and including 3/4 inch. The tolerance for widths over 3/4 inch will be plus or minus 1/16 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

3.6. Splices. – The tape shall consist of a single length of tape, except any single roll may contain a maximum of 3 splices. The splices shall be such that they will not separate when the roll is unwound.

3.7. Printing. – The Type I tape shall be capable of being printed on the adhesive side. When printing is required by the contract or purchase order, it shall be distinct, clear, and of proper size required hereto.

3.7.1. Print Transfer. – There shall be no transferring or offsetting of the ink from one lap of the tape to the adjacent lap either initially or after the print stability test. (See 4.3.8 and 4.3.8.1)

3.8. Color and Transparency. – Type I tape shall be furnished transparent only without added pigment. Type II tape shall be furnished in gold and silver or other commercially available colors as specified in the contract or order (see 6.2).

3.9. Workmanship. – Tapes shall be free from defects that affect serviceability or appearance in accordance with 4.2.1.

3.10 Age. – The tape shall be not more than 90 days of age from the date of manufacture to date of shipment.

4. QUALITY ASSURANCE PROVISIONS

4.1. Responsibility for Inspection. – The contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the contractor may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examinations and tests shall be kept complete and available to the Government. The Government reserves the right to perform any of the inspections as deemed necessary to assure supplies and services conform to prescribed requirements.

4.2. INSPECTION PROCEDURES

4.2.1. End Item Inspection. – Lot size, sampling and examination for this inspection shall be specified in paragraph 6.3 of ASTM D 3715.

4.3. TEST PROCEDURES

4.3.1. End Item Testing. – Lot size, sampling and examination for this inspection shall be specified in paragraph 6.4 of ASTM D 3715. The AQL shall be 4.0 percent defective. Each unit of product shall be tested to the applicable requirements of Table I of this federal specification.

4.3.2. Specimens. – The first three plies of tape shall be removed from the rolls before taking specimens for testing. An equal number of specimens from all sample rolls shall be tested.

4.3.3. Conditioning. – The tape shall be conditioned for testing for not less than 24 hours at 73 degrees ± 3.5 degrees F and 50 ± 2 percent relative humidity, and shall be tested under these conditions.

4.3.4. Test Methods. – The following tests shall be conducted according to the following methods, as indicated:

Test	Method
Adhesion, initial	ASTM D 3330, Method A
Tensile, Elongation	ASTM D 3759
Thickness	ASTM D 3652

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

4.3.5. Accelerated Weathering. – Three 1-inch specimens of tape, selected and applied as described in ASTM D 3330 to aluminum alloy 5" by 2" plates conforming to ASTM B209, shall be exposed as described in ASTM D 6551 for a total of 96 hours. After exposure and conditioning for 24 hours, the specimens shall be tested for adhesion as described in ASTM D 3330. The tapes shall not be removed from the aluminum panels prior to testing.

4.3.6. Adhesion After Immersion. – Two 1-inch wide specimens, selected and applied as described in ASTM D 3330 to aluminum alloy 2" by 5" plates conforming to ASTM B209, shall be prepared for every fluid in which the adhesion of the tape to the test panel is to be evaluated. Two panels shall be completely immersed in each of the following test fluids: Distilled water; turbine fuel (MIL-T-5624V, Grade JP-4); standard test fluid (ASTM D471); hydraulic fluid (MIL-PRF-5606H); and lubrication oil (MIL-PRF-7808L). After immersion for the time specified in Table I, the panels shall be removed from the test fluid, and drained of excess fluid for 15 minutes. The specimens shall be tested for adhesion as described in ASTM D 3330. The tape shall not be removed from the aluminum panels prior to testing.

4.3.7. Elevated Temperature Aging. – Five 1-inch specimens of the tape, selecte4d and applied as described in ASTM D 3330 to aluminum alloy 2" by 5" plates conforming to ASTM B209 shall be exposed in an air circulation maintained at 180 ± 5 degrees F for 168 hours. Evaluate for compliance to the requirements of Table I. Cool the specimens at room temperature for 2 hours and test for adhesion as described in ASTM D 3330. After conducting the adhesion test examine the aluminum test panels for corrosion to determine compliance with the requirements of 3.3.

4.3.8. Printing Stability. – A roll of printed tape, previously tested for print transfer and offsetting (3.7) shall be placed on a perforated rack in an air-circulating oven maintained at 100 degrees plus or minus 5 degrees for a period of 24 hours. At the end of this period, the roll shall be removed from the oven and conditioned for 2 hours under conditions cited in TAPPI test method T 402. The tape shall then be unwound from the freely rotating roll at 15-20 inches per second. The printing shall be distinct and clear and shall comply with the requirements of 3.7.

4.3.8.1. Printing Transfer. – Tape shall be unwound from a freely rotating roll at a rate of 15-20 inches per second. The tape removed in this manner shall be evaluated to determine whether it complies with the requirement of paragraph 3.7.1.

4.4. Exposed Adhesive Aging. – A specimen of tape as described in ASTM D 3330 taken from each sample roll shall be tested as follows: Each strip shall be placed adhesive side exposed on a separate steel plate as described in ASTM D 3330. The tape specimen shall be secured to the panel so that a full 4-inch length of the test specimen remains exposed. The test assemblies shall be vertically mounted, exposing the adhesive side to the light, in a weathering apparatus as described in ASTM D 6551 and conditioned as specified in this method for a total exposure time of 20 hours. In this test, no water spray shall be used. After exposure is completed, the test assemblies shall be removed from the weathering unit and conditioned at standard conditions, as described in ASTM D 3330 for 24 hours. The tape specimens shall then be removed from the steel panels and subjected to the adhesion test according to Method A of ASTM D 3330. Only the area of the tape specimen where the adhesive was openly exposed shall be tested.

5. PREPARATION FOR DELIVERY

5.1. Tape shall be prepared for delivery in accordance with the applicable levels of protection of Federal Specification PPP-T-680E.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1. Intended Use.

6.1.1. Type I. – Type I tape is intended for uses where a high degree of resistance to solvents, oils and hydraulic fluid is required. Examples of such applications are in dissimilar metal separation on aircraft and covering of pressure-sensitive identification tapes used on fluid lines and wiring harnesses in aircraft, missiles and vehicles. It is also recommended for covering labels on shipping containers where exterior exposure is anticipated. Printing on the adhesive side of type I tape is intended for use where the printed message must be protected from weathering, solvents and abrasion.

6.1.2. Type II. – Type II tape is intended for uses where weather resistant, long aging label (printed form) or decorative stripping or color coding is required. For a solvent resistant printed label, Type II, printed, and overlaid with Type I tape should be used.

6.2. Ordering Data. – Procurement documents should specify the following:

a) Title, number and date of this specification.
b) Type, width, and color (see 1.2.1, 3.5 and 3.8).
c) Selection of applicable levels of packaging and packing (see 5.1).

MILITARY INTERESTS:

Military coordinating activity:
Army – GL
Navy – SA
Air Force – 99

Preparing Activity:
GSA – FAS

Review activities:
Army – EA, ME
Air Force – 84
DNA – DS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.