METRIC

A-A-694E
21 February 2013
SUPERSEDING
A-A-694D
30 May 2002

COMMERCIAL ITEM DESCRIPTION

SODIUM CHLORIDE, TECHNICAL

The General Services Administration has authorized the use of this commercial item description for all federal agencies.

1. SCOPE. This commercial item description (CID) covers two types and three forms of crystalline sodium chloride (salt) used for water conditioning. It shall be suitable for ion-exchange columns in which sodium chloride is used for regeneration.

2. CLASSIFICATION. The sodium chloride shall conform to the following types and forms:

2.1 Type. The type of sodium chloride shall be as specified in the acquisition order (see 7.3(b)).

Type I - 97.5 percent purity
Type II - 99.5 percent purity

2.2 Form. The form of sodium chloride shall be as specified in the acquisition order (see 7.3(c)).

Form 1 - Compressed pellets
Form 2 - Large granules (rock, solar, or evaporated)
Form 3 - Small granules (table salt size)

3. SALIENT CHARACTERISTICS

3.1 Material. The sodium chloride provided shall be homogeneous and shall be free from dirt, fibers, lint, trash, or other foreign matter. Anti-caking or iodizing agents shall not be added.

3.2 Color. The product shall be white, grayish pink, or brownish white.
3.3 Chemical properties. The sodium chloride shall meet the chemical requirements of table I when tested in accordance with American Water Works Association (AWWA) B 200, "Sodium Chloride".

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: STDZNMGT@dla.mil or Defense Logistics Agency - Aviation, ATTN: DLA Aviation-VEB, 8000 Jefferson Davis Highway, Richmond, VA 23297-5616. Since contact information can change, you may want to verify the currency of this address information using the ASSIST database at https://assist.dla.mil.

AMSC N/A FSC 6810

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:10Z
Check the source to verify that this is the current version before use.

TABLE I. Chemical properties.

Chemical requirements	Limits	
	Type I	Type II
Moisture, percent, maximum	0.5	0.5
Sodium chloride, percent, minimum (dry basis)	97.5	99.5
Water-soluble impurities, percent, maximum (dry basis) Calcium & magnesium (Ca & Mg) Sulfate (SO_4)	 0.75 1.25	 0.15 0.35
Water-insoluble impurities, percent, maximum (dry basis)	0.50	0.05
Soluble & insoluble impurities, percent, maximum (dry basis)	2.50	0.50
Grease, fat, and oil, percent, maximum	0.01	0.01
pH	5.0 to 9.5	5.0 to 9.5

3.4 Physical properties. The sodium chloride shall meet the physical requirements of table II when tested in accordance with American Society for Testing and Materials (ASTM) C 136, "Standard Test Method for Sieve Analysis of Fine and Coarse Aggregates" (DoD adopted), and ASTM E 11, "Standard Specification for Wire Cloth and Sieves for Testing Purposes" (DoD adopted).

TABLE II. Physical properties.

Particle size analysis, cumulative percent passing review							
Sieve	19.0 mm (3/4 in.)	9.5 mm (3/8 in.)	6.35 mm (1/4 in.)	3.35 mm No. 6	2.00 mm No. 10	1.70 mm No. 12	150 µm No. 100
Form 1	100 min.	-	15 max.	8 max.	-	-	-
Form 2	100 min.	95 min.	-	-	20 max.	5 max.	-
Form 3	-	-	-	-	100 min.	-	5 max.

4. REGULATORY REQUIREMENTS

4.1 Recovered materials. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:10Z
Check the source to verify that this is the current version before use.

5. PRODUCT CONFORMANCE PROVISIONS

5.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

5.2 Market acceptability. The product offered must have been previously sold either to the government or on the commercial market.

6. PACKAGING

6.1 Preservation, packing, and marking. Preservation, packing, and marking shall be as specified in the contract or order (see 7.3(d)).

7. NOTES

7.1 Part or identification number (PIN). The following PIN procedure is for government purposes and does not constitute a requirement for the contractor.



7.2 Sources of documents.

7.2.1 ASTM standards. Copies of ASTM standards may be obtained from the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959. Electronic copies of ASTM standards may be obtained from http://www.astm.org/.

7.2.2 AWWA standards. Copies of AWWA standards may be obtained from the American Water Works Association, 6666 West Quincy Avenue, Denver, CO 80235. http://www.awwa.org/

7.2.3 FAR. The FAR may be obtained from the US Government Printing Office, 732 North Capitol Street N.W., Washington, DC 20401. Electronic copies of FAR documents may be obtained from http://www.acquisition.gov/far/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:10Z
Check the source to verify that this is the current version before use.

7.3 Ordering data. Acquisition documents must specify the following information:

a. CID document number, revision, and CID PIN.
b. Type of sodium chloride (see 2.1).
c. Form of sodium chloride (see 2.2).
d. Preservation, packing, and marking requirements (see 6.1).

7.4 Subject term (key word) listing.

crystalline
ion exchange
salt
water conditioning

CIVIL AGENCY
COORDINATING ACTIVITY:

GSA - FAS

Preparing activity:
DLA - GS3

(Project 6810-2013-015)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST database at https://assist.dla.mil/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:10Z
Check the source to verify that this is the current version before use.