MIL-T-25363D(USAF)

26 September 1973

SUPERSEDING
MIL-T-25363C(USAF)
2 June 1969

MILITARY SPECIFICATION

TANK, PNEUMATIC PRESSURE, AIRCRAFT, GLASS FIBER

1. SCOPE

1.1 This specification covers the requirements for glass fiber pneumatic tanks.

2. APPLICABLE DOCUMENTS

*2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATIONS

Federal

PPP-B-636	Box, Fiberboard

Military

MIL-P-116	Preservation, Methods of
MIL-G-4343	Grease, Pneumatic Systems
MIL-P-5518	Pneumatic Systems, Aircraft, Design, Installation and Data, Requirements For
MIL-H-5606	Hydraulic Fluid, Petroleum Base, Aircraft, Missile and Ordnance
MIL-T-5624	Turbine Fuel, Aviation, Grades JP-4 and JP-5
MIL-L-6085	Lubricating Oil, Instrument, Aircraft, Low Volatility
MIL-L-7808	Lubricating Oil, Aircraft Turbine Engine, Synthetic Base
MIL-C-8188	Corrosion-Preventive Oil, Gas Turbine Engine, Aircraft Synthetic Base
MIL-P-8564	Pneumatic System Components, Aeronautical, General Specification For
MIL-R-9300	Resin, Epoxy, Low Pressure, Laminating
MIL-R-60346	Roving, Glass, Fibrous (For Filament Winding Applications)

FSC: 1650

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the currentversion before use.

STANDARDS

Federal

FED-STD-406	Plastic, Methods of Testing

Military

MIL-STD-129	Marking for Shipment and Storage
MIL-STD-130	Identification Marking of U.S. Military Property
MIL-STD-794	Part and Equipment, Procedures for Packaging and Packing Of
MIL-STD-810	Environmental Test Methods
MIL-STD-831	Test Reports, Preparation of
MIL-STD-838	Lubrication of Military Equipment
MS 27201	Tank, Pneumatic Pressure, Aircraft, Glass Fiber Sphere
MS 33649	Bosses, Fluid Connection, Internal Straight Thread

Air Force - Navy Aeronautical

AND 10064	Fitting-Installation of Flared Tube, Straight Threaded Connectors

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

*3.1 Qualification. Pneumatic tanks furnished under this specification shall be products which are qualified for listing on the applicable qualified products list at the time set for opening of bids (see 4.2 and 6.4).

3.2 General specification. The requirements of MIL-P-8564 apply as requirements of this specification with the exceptions and additions called out herein. When the two specifications conflict, this specification shall govern.

3.3 Design and construction.

3.3.1 Construction. A transparent moisture-proof-barrier coating shall be applied to the exterior surface of the pneumatic tank. The wall of the tank shall be free of voids.

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the current version before use.

3.3.1.1 Control. The manufacturer shall establish and maintain rigid process controls to insure compliance with the following conditions:

a. Completely impregnated yarn.
b. Resin content between 19 and 26 percent evenly distributed throughout the wall laminate.
c. Void-free tank walls.

3.3.1.2 Process details. The following manufacturing process details shall be adhered to in fabricating the tanks:

a. Guide rolls shall be a minimum of 3 inches in diameter for dry roving and a minimum of 1 1/2 inches in diameter for resin impregnated roving to avoid unnecessary chafing and flexing of the glass filaments.

b. Under no circumstances shall dry roving be permitted to come into sliding contact with any elements of the winding machine.

c. Wetting time shall be 0.5 second, minimum, if the wet-winding process is used.

d. A prony-brake device or an eddy-current brake device or equivalent device shall be used to maintain the proper tension in the glass roving during winding.

e. The tension schedule used in winding the tanks shall be such that the inner plies of the glass roving are not deformed out of their initial configuration by succeeding plies of roving.

*3.3.2 Materials. The pneumatic tank shall be constructed of continuous-filament wound-glass fiber and resin. The glass shall be a roving conforming to MIL-R-60346, Type III, G filament, Class 1. Unless otherwise specifically approved by the qualifying activity, resin shall be in accordance with MIL-R-9300. Liner materials shall be such that the tank will meet the tests spcified in 4.6.3. and 4.6.6.

3.3.2.1 Material deterioration. Any materials that are easily deteriorated by lubricants or moisture suspended in the air within the specified pressure and temperature range shall not be used in fabrication of the tank (see 6.1). The exterior surface of the tank shall not be affected by contact with MIL-H-5606, MIL-L-6085, MIL-C-8188, and MIL-L-7808 fluids and MIL-T-5624 fuels.

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the currentversion before use.

*3.3.3 Shape. Spherical tanks shall be as specified on MS27201 or as required by the procuring activity.

*3.3.4 Bosses. The size of the bosses shall be as specified on MS27201 or as required by the procuring activity. MS33649 bosses shall be made of stainless steel of a type specifically approved by the qualifying activity or as required by the procuring activity.

3.3.5 Temperature range. The tank shall be designed to withstand a temperature range of -65° to +200°F.

3.3.5.1 Strength at elevated temperature. The tank shall be designed to withstand volumetric expansion and burst pressure testing at +200°F after 80 hours of exposure to 200°F.

*3.3.6 Volume. The internal volume of the unpressurized tank shall not be less than the rated size listed in MS27201 or as required by the procuring activity. The volume shall be determined after the volumetric expansion test.

3.3.7 Structural strength. The tank shall have ample strength and rigidity to withstand 250 percent of maximum wrench torques required by AND10064 for connection of tube fittings without permanent deformation of the tank.

3.4 Performance. The tank shall meet the following performance requirements:

3.4.1 Volumetric expansion. The production tanks shall not have an elastic expansion that exceeds the maximum value determined during qualification testing. Elastic expansion is the total expansion less the residual expansion.

3.4.2 Leakage. Upon subjection to the leakage test, the rate of leakage of the tank shall not exceed 0.05 cubic centimeter per hour per square inch of internal surface area at -65° or at room temperature. Leakage at 200°F shall not exceed a rate of 1 cubic centimeter per hour per square inch of internal surface area.

*3.4.3 Endurance. Tanks subjected to an endurance test shall not show deterioration and shall be capable of withstanding 5400 psi hydrostatic burst test pressure.

3.4.4 Temperature-shock. Tanks subjected to the temperature-shock test shall not show deterioration and shall pass the normal temperature leakage test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:31Z
Check the source to verify that this is the current version before use.

3.4.5 Vibration. After the vibration test, tanks shall not show deterioration.

3.4.6 Gunfire. When struck by gunfire, tanks shall remain in one piece and the greatest dimension of the opening (cut and tear) created by the projectile shall not exceed the dimensions of the hole (cut) created by the projectile by more than 3 inches in any one direction. Cutting shall be considered to be the actual section of the tank cut by contact with the projectile and a tear shall be considered to be an extension beyond the cut. Tanks that are less than two (2) inches in diameter which have been cut in two by tumbled projectile shall not be considered as having failed the tests because of separation provided the tear does not exceed three (3) inches in length.

*3.4.7 Soak cycle. After subjection to the soak cycle test, the tank shall pass the hydrostatic burst test at a pressure of 5400 psi.

*3.4.8 Pressure storage. The tank subjected to the pressure storage test shall withstand the hydrostatic burst test at a pressure of 7200 psi.

*3.4.9 Humidity cycle. The tank subjected to the humidity cycle test shall pass the hydrostatic burst test at a pressure of 5400 psi.

3.5 Marking. The following shall be marked in red letters on the surface in two places, 180° apart: 3250 PSI AIR PRESSURE
FRAGILE-DO NOT DROP
Letters and numbers shall not be less than 3/8 inch high.

3.6 Identification of product. The tanks shall be marked for identification in accordance with MIL-STD-130, specifying the following information only:

Tank, Pneumatic Pressure
FSC 1650
MS Part No.
Manufacturer's Part No.
Manufacturer's Serial No.
Manufacturer's Name or Trade Mark (Omit address)
Size
Date of Manufacture (Month and year)
Date of Test (Month and year)

The method of applying the identification data is subject to the approval of the procuring activity.

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the current version before use.

Identification data shall be applied in two places, 180° apart, in accordance with MS27201.

3.7 Workmanship. Workmanship shall be of the quality necessary to produce tanks free from defects which will affect proper functioning in service.

3.7.1 Surfaces. The interior and exterior surfaces of the tank shall be clean and free of all foreign matter.

4. QUALITY ASSURANCE PROVISIONS

*4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspections. The inspection and testing of pneumatic tanks shall be classified as follows:

a. Qualification Inspection

b. Quality Conformance Inspection

4.3 Test conditions.

4.3.1 Test media. Tests shall be performed with air except that volumetric expansion, endurance, hydrostatic burst, soak cycle, and humidity cycle tests may be performed with a liquid.

4.3.2 Temperatures. Unless otherwise specified, tests shall be conducted at room temperature that is between 60° to 100°F. The temperature of the air supply shall also be maintained within these limits for room temperature tests. The actual ambient temperatures shall be recorded.

4.3.3 Rate of pressure rise. The rate of pressure rise for the volumetric expansion test and the hydrostatic burst test shall be 25,000 psi per minute maximum.

4.3.4 Standard air. Standard air shall be considered to be dry air at a temperature of 69°F, pressure of 14.7 psi, and weighing 0.075 pcf (density).

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:31Z
Check the source to verify that this is the current version before use.

4.4 Qualification inspection.

*4.4.1 Test sample. The test sample shall consist of five tanks of each size and shape representative of the production equipment. The samples shall be identified with the manufacturer's part number and such other information as required by the procuring activity. The weight of test tanks shall be within the lower quarter of the weight range indicated by the production drawings.

4.4.2 Test report, test sample, and data for the qualifying activity. When the tests are conducted at a location other than the laboratory of the qualifying activity, the following data shall be furnished to that activity:

a. Test report: Three copies of a test report in accordance with MIL-STD-831. The qualification test report shall include the results of any qualification tests on all tanks tested, including failures, that have the same part number.

b. Test sample: The sample that was tested.

c. Detail drawings of the test tanks.

*4.4.3 Qualification tests. The qualification tests shall be conducted in accordance with the following schedule in the order specified:

a. One tank shall be subjected to the following tests:

(1) Volumetric expansion test
(2) Examination of product
(3) Leakage tests
(4) Gunfire test
(5) Resin content determination

b. Two tanks shall be subjected to the following tests:

(1) Volumetric expansion test
(2) Examination of product
(3) Leakage tests
(4) Endurance test, Procedure II

c. One tank shall be subjected to the following tests:

(1) Volumetric expansion test
(2) Examination of product

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the currentversion before use.

(3) Leakage tests
(4) Soak cycle test
(5) Resin content determination

d. One tank shall be subjected to the following tests:

(1) Volumetric expansion test
(2) Examination of product
(3) Leakage tests
(4) Vibration test
(5) Temperature-shock test
(6) Pressure-storage test

4.5 Quality conformance inspection. Quality conformance inspection shall consist of the following tests:

a. Individual tests.

b. Sampling plan and tests.

4.5.1 Individual tests. Each pneumatic tank shall be subjected to the following tests in the order listed:

a. Volumetric expansion test

b. Examination of product

c. Normal temperature leakage test

4.5.2 Sampling plan and tests.

4.5.2.1 Sampling plan. Two tanks shall be selected at random from each lot of 50 tanks or fraction thereof.

4.5.2.1.1 Sampling tests. Sampling tests shall be conducted in the order listed:

a. One tank shall be subjected to the following tests:

(1) Volumetric expansion test
(2) Examination of product
(3) Normal temperature leakage test
(4) Endurance test, Procedure I
(5) Resin content determination

b. One tank shall be subjected to the following tests:

(1) Volumetric expansion test

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:31Z
Check the source to verify that this is the current version before use.

(2) Examination of product
(3) Normal temperature leakage test
(4) Humidity cycle test

4.5.2.2 Sampling units. Two fully prepared shipping containers, containing tank(s) fully prepared for delivery, made from essentially the same materials and components, shall be selected at random from each lot of 50 tanks or fraction thereof. The sample unit shall be one shipping container, containing tank(s) fully prepared for delivery with the exception that it need not be sealed.

4.5.3 Rejection and retest. When an item selected from a production run fails to meet the specification, no items still on hand or later produced shall be accepted until the extent and cause of failure have been determined and appropriately corrected. The contractor shall explain to the Government representative the cause of failure and the action taken to preclude recurrence. After correction, all of the tests shall be repeated.

4.5.3.1 Individual tests may continue. For production reasons, individual tests or other sampling plans may be continued pending the investigation of a sampling test failure. But final acceptance of items on hand or produced later shall not be made until it is determined that all items meet all the requirements of the specification.

4.5.4 Defects in items already accepted. The investigation of a test failure could indicate that defects may exist in items already accepted. If so, the producer shall fully advise the procuring activity of all the defects likely to be found and the method of correcting them.

4.6 Test methods.

4.6.1 Volumetric expansion test. The volumetric expansion test shall be determined by subjecting the tank to 5400 +100, -0 psi pressure and maintaining that pressure for 30 to 60 seconds. The test shall be performed individually and the volumetric expansion of the tank shall be determined to 0.1 milliliter or to 1 percent accuracy, and recorded in milliliters. No pressure in excess of 3000 psi shall be applied prior to this test. The total expansion and the residual expansion shall be recorded. Subsequent tests on production tanks shall meet the requirements of 3.4.1. The rate of pressure rise shall be in accordance with 4.3.3.

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the current version before use.

4.6.2 Examination of product. Each component shall be carefully examined to determine conformance to the requirements of this specification and the manufacturer's assembly drawings which were approved by the procuring activity for design, volume, weight, workmanship, marking, and for any visible defects.

4.6.3 Leakage tests.

4.6.3.1 Normal temperature leakage test. The tank shall be subjected to a pneumatic leakage test at 3250 +50, -0 psi. The leakage test period shall be a minimum of 4 hours for qualification and sampling tests and a minimum of 1 hour for individual tests. Leakage shall not exceed the rate allowable in 3.4.2. The method used to determine the rate of leakage shall be reported and shall be subject to the approval of the procuring activity.

4.6.3.2 Extreme temperature leakage test. The tank shall be subjected to a pneumatic leakage test at 3250 +50, -0 psi at -65°±5°F ambient temperature. Leakage shall be measured for a period of not less than 4 hours after the temperature of the tank has stabilized. The leakage rate shall not exceed the permissible rate stated in 3.4.2. This test shall be repeated at 200°±5°F ambient temperature. Leakage at 200°F shall not exceed the rate permissible in 3.4.2.

*4.6.4 Vibration test. The tank shall be subjected to a vibration test as outlined in MIL-STD-810 for Method 514, equipment category b, procedure I, Part I (curve D), Part 2 (curve H). The tank shall be pressurized to 3250 +50, -0 psi with air and mounted with brackets to simulate an aircraft installation as nearly as possible. The tank shall pass the requirements of 3.4.5.

4.6.5 Temperature shock test. The tank shall be pneumatically pressurized to 3250 psi and soaked at -65° ±2°F for a period of 6 hours. The tank shall be transferred to an atmosphere of +200°F or above, and soaked for a period of 2 hours. The tank shall then be transferred to an atmosphere of -65°F or lower, and allowed to soak for a period of 2 hours. The tank shall then be transferred to an atmosphere of +200°F or higher, and allowed to soak for 2 hours. Throughout this test, the pressure in the tank shall be maintained at 3250±100 psi. The transfer of the tank from one temperature chamber to another shall be made within 5 minutes. The tank shall meet the requirements of 3.4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:31Z
Check the source to verify that this is the current version before use.

4.6.6 Endurance test.

*4.6.6.1 Endurance test, procedure I. The tank shall be soaked in air at -65 ± 5°F for 72 hours and shall then be subjected to 20,000 cycles of pressure application from 0 to 3450 ± 50 to 0 psi at a rate not to exceed 10 cycles per minute at room temperature. The tank shall then be subjected to the hydrostatic burst test per 4.6.7 and shall meet the requirements of 3.4.3.

*4.6.6.2 Endurance test, procedure II. Two tanks which have been soaked in air temperature of 200° ± 5°F for 72 hours shall be subjected to 20,000 cycles of pressure application from 0 to 3450 ± 50 to 0 psi at a rate not to exceed 10 cycles per minute as follows:

a. Apply 5000 cycles at 200° ± 5°F for both the tank and pressurizing fluid.

b. Apply 11000 cycles at room temperature.

c. Apply 1000 cycles at -65° ± 5°F temperature with fluid temperature no warmer than -50°F.

d. Apply 3000 cycles with the tanks in a chamber having a temperature of 120° ± 5°F and relative humidity of 95 ± 5 percent.

Upon completion of this test, one tank shall be subjected to the hydrostatic burst test per 4.6.7 and shall comply with the requirements of 3.4.3. The endurance test of the other tank shall then be continued at room temperature until failure or until an additional 20,000 cycles of pressure has been applied, whichever occurs first.

*4.6.7 Hydrostatic burst test. The tank shall be hydrostatically pressurized for three minutes to the specified pressure at a temperature of +65°F to +95°F. Loss in pressure due to expansion or leakage shall be offset by restoring the pressure to the original value each time repressurization is necessary. After the 3-minute period the pressure shall then be increased to failure of the tank. The burst pressure and type of failure shall be recorded. The rate of pressure rise shall be in accordance with 4.3.3.

4.6.8 Gunfire test. The gunfire test shall be conducted in the manner outlined below.

4.6.8.1 Pressure. The tank shall be charged to 3250 +50, -0 psi air pressure at the ambient temperature of the gun range.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:31Z
Check the source to verify that this is the current version before use.

4.6.8.2 Gunfire test conditions. The ammunition shall be 50 caliber armor piercing with a muzzle velocity of 2800 ±100 feet per second. The range of gunfire shall be 50 yards maximum. The projectile shall be tumbled before striking the tank.

4.6.8.3 Position . The tank shall be mounted in a manner that will simulate an aircraft installation and positioned with the axis through the closed-end fitting of the tank 45 degrees from normal away from the gun position. The tank mounting fixture may be restrained.

4.6.8.4 Failure criteria. The tank shall meet the requirements of 3.4.6.

*4.6.9 Soak cycle test. The tank shall be placed in a chamber that has an environment of 120°F and 95 percent relative humidity. The tank shall be continuously pressurized hydrostatically to 4300 ±100 psi. Each day the tank shall be cycled from 4300 ±100 psi to zero pressure to 4300 ±100 psi for a total of 4 cycles at a rate of approximately 1 cycle per minute. This test shall be continued for at least 30 consecutive days without evidence of damage. The tank shall then be subjected to the hydrostatic burst test per 4.6.7 and shall meet the requirements of 3.4.7.

*4.6.10 Pressure storage test. The tank shall be pneumatically pressurized to 3250 +50, -0 psi while under a continuous environmental condition of 120°F and 95 percent relative humidity for 15 days. The tank shall then be subjected to the hydrostatic burst test per 4.6.7 and shall comply with the requirements of 3.4.8.

*4.6.11 Humidity cycle test. The tank shall be placed in an environment of 120°F and 95 percent relative humidity and subjected to 5000 cycles from 0 - 3450 ±50, -0 psi without failure. The cycle rate shall be 2 to 7 cycles per minute. The tank shall then be subjected to the hydrostatic burst test per 4.6.7 and shall meet the requirements of 3.4.9.

4.6.12 Resin content determination. Resin content shall be determined in accordance with FED-STD-406, method 7061. Samples for qualification testing shall be taken from four (4) locations on the tank; one (1) adjacent to the port fitting, one (1) adjacent to the opposite or blind fitting, and two(2) approximately 180° apart about the midpoint or equator of the tank. Each sample shall be delaminated into at least two layers for individual determination to demonstrate uniformity of distribution throughout the wall.

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the currentversion before use.

For production sample testing, a sample shall be taken from only one (1) location on the tank wall. The production sample shall be taken alternately from adjacent to one of the fittings and from the midpoint of the tank on consecutive lot sample units. The sample shall pass the requirements of 3.3.1.1.

*4.6.13 Inspection for preparation for delivery. Each of the fully prepared shipping containers, containing tank(s) selected as a sample unit from the lot shall be examined to determine that the preservation, packaging, packing and marking conform to this specification and the requirements stated in the contract. Exterior and interior markings shall be complete, correct, legible; of proper size, location, sequence, method of application; and identical on interior and exterior containers. Packaging and packing materials and components shall conform to the level specified, shall be complete, and shall show no evidence of defects or damage. Application of components such as closure materials and straps shall exhibit good workmanship. Container flaps shall be secure and there shall be no bulging or distortion of containers. Exterior and interior weight or content shall be as specified.

5. PREPARATION FOR DELIVERY

5.1 Preparation for packaging. Each tank shall be cleaned and dried and all ports shall then be plugged or capped with oil and moisture resistant material to protect bosses and threads from damage and to prevent entrance of air or foreign matter to the interior or the tank.

5.2 Levels of preservation and packaging.

5.2.1 Level A. Unless otherwise specified by the procuring activity, each tank shall be preserved in accordance with MIL-P-116, method III, and packed in containers meeting PPP-B-636.

5.2.2 Level C. Each tank shall be packaged in a manner which will afford protection against corrosion, deterioration and physical damage during shipment from supply source to the first receiving activity for immediate use. This level may conform to the suppliers commercial practice when such meets the requirement of this level.

5.3 Intermediate packaging. Intermediate packaging, if required, shall be as specified by the procuring activity.

5.4 Levels of packing.

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the currentversion before use.

5.4.1 Level A. Tanks, preserved and packaged to meet 5.2.1 and 5.3, shall be packed in accordance with MIL-STD-794, Level A. The gross weight of each pack shall be limited to approximately 200 pounds.

5.4.2 Level B. Tanks, preserved and packaged to meet 5.2.1 and 5.3, shall be packed in accordance with MIL-STD-794, Level B. The gross weight of each pack shall be limited to approximately 500 pounds.

5.4.3 Level C. Tanks packaged to meet 5.2.2 shall be packed in accordance with MIL-STD-794, Level C.

5.5 Marking. Interior and exterior containers shall be marked in accordance with MIL-STD-129. The shipment marking nomenclature shall be as follows:

Tank, Pneumatic Pressure, Aircraft, Glass Fiber

6. NOTES

6.1 Intended use. Pneumatic tanks covered by this specification are intended for use in aircraft pneumatic systems conforming to MIL-P-5518 to store a supply of compressed air in a class-3000-psi system with a relief valve.

6.1.1 Draining. It is intended that provision be made for discharge of accumulated water, either by gravity or air pressure, with the tank in the mounted position. Outlets and inlets, if located at the bottom of the tank, will be extended into the tank approximately 30 percent of its length to permit trapping of water and prevent possible plugging of air passages by ice.

6.1.2 Temperature limitation. It is intended that the tanks be used in applications where cumulative exposure to elevated temperatures is no severer than 80 hours at 200°F.

6.1.3 Replacement. It is intended that calendar time be a factor when establishing replacement schedules specified in appropriate technical orders.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of specification

b. Size and MS part number

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:31Z
Check the source to verify that this is the current version before use.

c. Applicable levels of preservation and packaging and levels of packing.

6.3 Lubrication. Present compressors are lubricated in accordance with MIL-STD-838 and use MIL-L-6085, MIL-L-8188, and MIL-L-7808 oil. Pneumatic systems are lubricated with MIL-G-4343 grease.

*6.4 Qualification. With respect to products requiring qualification, awards will be made only for products which are at the time set for opening of bids, qualified for inclusion in the applicable Qualified Products List whether or not such products have actually been so listed by that date. The attention of the suppliers is called to this requirement, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. The activity responsible for the Qualified Products List is OCAMA (MMEO) Tinker AFB Okla 73145 and information pertaining to qualification of products may be obtained from that activity.

NOTE: The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian Activity
Air Force - 71

Preparing Activity
Air Force - 71

Project Number:
1650 - F041

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. *DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product* are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:31Z
Check the source to verify that this is the current version before use.