MILITARY SPECIFICATION

ACCUMULATOR, PNEUMATIC, AIRCRAFT, GLASS FIBER

This amendment forms a part of Military Specification MIL-T-25363D(USAF), dated 26 September 1973 and is approved for use by the Department of the Air Force, and is available for use by all Agencies and Department of the Department of Defense.

PAGE 1

Due to the change of the document title from "TANK, PNEUMATIC PRESSURE, AIRCRAFT, GLASS FIBER" to "ACCUMULATOR, PNEUMATIC, AIRCRAFT, GLASS FIBER", any reference to the word "tank" should be considered as "accumulator".

*Add boxed paragraph to bottom of page:

> Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Oklahoma City Air Logistics Center/MMEDO, Tinker AFB OK 73145 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

PAGE 2

*Under "STANDARDS, Federal", add the following:

"FED-STD-123 - Marking for Shipment (Civil Agencies)"

*Under "SPECIFICATIONS, Federal" add:

"PPP-T-60 - Tape, Packaging, Waterproof

PPP-T-76 - Tape, Packaging, Paper (for Carton Sealing)"

*Under "SPECIFICATIONS, Military "add the following:

"MIL-C-5501 - Cap and Plug, Protective, Dust and Moisture Seal"

Under "STANDARDS, Military", add the following:

"MS 21344 - Fitting-Installation of Flared Tube, Straight Threaded Connectors, Design Standard for"

Under "STANDARDS, Air Force - Navy Aeronautical", delete "AND 10064".

*3.3.1: Delete paragraph and substitute the following:

Source: https://assist.dla.mil -- Downloaded: 202610-20T04:31Z
Check the source to verify that this is the current version before use.

"3.3.1 Construction. A transparent moisture-proof barrier coating shall be applied to the exterior surface of the pneumatic accumulator. The glass-resin laminate of the accumulator wall shall be free of voids. Unbonded areas between the glass-resin laminate and the liner are not to be considered as voids."

PAGE 3

*3.3.1.1,b: Delete "19" and substitute "18".

*3.3.1.1,c: Delete entirely.

*3.3.1.2,a,line 2: Delete "1-1/2" and substitute "1".

*3.3.2: Delete paragraph and substitue the following:

"3.3.2 Materials. The pneumatic accumulator shall be constructed of continuous-filament wound-glass fiber and resin. The glass shall be a roving, conforming to MIL-R-60346, Type III, G filament, class 1, except horizontal shear shall be 6,000 psi, minimum, after 2-hour boil. The resin shall be in accordance with MIL-R-9300, of a formulation approved by the procuring activity and qualified in the item listed on Qualified Products List 25363. Liner materials shall be such that the accumulator will meet the tests specified in 4.6.3 and 4.6.6.

PAGE 4

3.3.7, line 3: Delete "AND 10064" and substitute "MS 21344".

PAGE 12

*4.6.12, third sentence: Delete "wall" and substitute "glass-resin laminate".

PAGE 13

*Section 5: Delete entirely and substitute new Section 5 as follows:

"5". PACKAGING

5.1 Preservation-packaging. Preservation packaging shall be level A.

5.1.1 Level A.

5.1.1.1 Cleaning. Accumulators shall be cleaned in accordance with MIL-P-116, process C-1.

5.1.1.2 Drying. Accumulators shall be dried in accordance with MIL-P-116.

5.1.1.3 Preservation application. Preservatives shall not be used.

Source: https://assist.dla.mil -- Downloaded: 2026l0-20T04:31Z
Check the source to verify that this is the currentversion before use.

5.1.1.4 Unit packaging. Unless otherwise specified (see 6.2), accumulators shall be individually packaged in accordance with MIL-P-116, method III insuring compliance with the applicable requirements of that specification. All parts shall be capped or plugged in accordance with MIL-C-5501.

5.2 Packing. Packing shall be level B or C, as specified (see 6.2).

5.2.1 Level B. The packaged accumulators shall be packed in fiberboard containers conforming to PPP-B-636 class weather resistant, style optional. In lieu of the closure and waterproofing requirements in the appendix of PPP-B-636, closure and waterproofing shall be accomplished by sealing all seams, corners and manufacturer's joint with tape, two inches minimum width, conforming to PPP-T-60, class 1 or PPP-T-76. Banding (reinforcement requirements) shall be applied in accordance with the appendix to PPP-B-636 using non-metallic or tape banding only.

5.2.2 Level C. The packaged accumulators shall be packed in fiberboard continers conforming to PPP-B-636, class domestic, style optional. Closures shall be in accordance with the appendix thereto.

5.3 Marking. In addition to any special marking required by the contact (see 6.2), each unit package, intermediate and exterior container and unitized load shall be marked in accordance with MIL-STD-129. When specified (see 6.2), the marking of domestic shipments for Civil Agencies shall be in accordance with FED-STD-123."

PAGE 15

*6.5: Delete entirely and substitute the following:

"6.5 Reclaimed materials. Due to the extreme critical safety hazard created by any failure of this item, the use of reclaimed materials shall be limited to identification labels and decals only."

NOTE: The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Govemnment assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Air Force - 99

Preparing activity:
Air Force - 71

Project No: 1650-F081

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T04:31Z
Check the source to verify that this is the current version before use.