MIL-C-17415E
16 April 1964
SUPERSEDING
MIL-C-17415D(SHIPS)
5 August 1960

MILITARY SPECIFICATION

CLOTH, COATED, AND WEBBING, INFLATABLE BOAT AND MISCELLANEOUS USE

This specification has been approved by the Department of Defense and is mandatory for use by the Departments of the Army, the Navy and the Air Force.

1. SCOPE

1.1 Scope. - This specification covers cured coated cloth and webbing as it appears in finished inflatable boats and accessories.

1.2 Classification. - The coated cloth and webbing shall be of the following types, classes, and nominal weights, as specified (see 6.1):

Type 1 - 5.0 ounces per square yard.

Type 2 -

Class A - 8.5 ounces per square yard.
Class B - 6.8 ounces per square yard.
Class C - 20.5 ounces per square yard.

Type 3 - 7.6 ounces per square yard.

Type 4 -

Class A - 15.0 ounces per square yard (natural rubber).
Class B - 10.0 ounces per square yard (synthetic rubber).

Type 5 - 23.4 ounces per square yard.

Type 6 - 21.5 ounces per square yard.

Type 7 -

Class A - 30.0 ounces per square yard (natural rubber).
Class B - 32.0 ounces per square yard (synthetic rubber).

Type 8 -

Class A - 6.5 ounces per square yard (natural rubber).
Class B - 6.5 ounces per square yard (synthetic rubber).

Type 9 -

Class A - 30.4 ounces per square yard (synthetic rubber).
Class B - 33.4 ounces per square yard (natural rubber).

Type 10 - 31.5 ounces per square yard.

Type 11 - 35.5 ounces per square yard.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

Type 12 - 45.1 ounces per square yard.

Type 13 - 12.1 ounces per square yard.

Type 14 - 45.3 ounces per square yard.

Type 15 - Webbing, 3 inch-width, undyed.

Type 16 -

Class A - 24.5 ounces per square yard (synthetic rubber).
Class B - 24.5 ounces per square yard (natural rubber).

Type 17 - 40.5 ounces per square yard.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL
CCC-T-191 - Textile Test Methods.

MILITARY
MIL-W-17337 - Webbing, Woven, Nylon.

STANDARDS

FEDERAL
FED-STD-601 - Rubber: Sampling and Testing.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Materials. -

3.1.1 Cloth. - The base material used in the construction of coated cloth shall be cotton or nylon which meets the requirements specified herein and the physical properties specified in table I. Cotton cloth shall be unbleached and chemically neutral having a pH between 6.5 and 7.6. Cotton cloth weighing up to and including 5 ounces per square yard shall be singed. Nylon cloth shall be high tenacity, improved heat and light resistant (Dupont 330 or Chemstrand A02, or equal) heat set and cured, unbleached and have a PH between 5 and 8. Length and width shall be as specified (see 6.1).

Table I - Cloth and webbing construction.

Used in Type	Fiber	Breaking strength, minimum pounds per inch of width		Weight, maximum ounces per square yard
		Warp	Filling	
1 and 8	Nylon	40	40	1.00
2	Nylon	150	140	2.50
3	Cotton	40	40	2.10
4	Cotton	80	80	4.50
5 and 9	Nylon	300	300	5.40

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

Table I - Cloth and webbing construction - Continued.

Used in Type	Fiber	Breaking strength, minimum pounds per inch of width		Weight, maximum ounces per square yard
		Warp	Filling	
6, 10 and 11	Nylon 1/	---	---	8.50
7	Cotton	150	145	7.50
12	Nylon (pile cloth) 2/	---	---	8.20
13	Nylon	195	195	3.10
14	Nylon	600	600	13.3
15	Nylon webbing	3000 3/	---	2.2 linear yd.
16	Nylon	---	---	4.8
17	Nylon	400	400	8.5

1/ Types 6, 10 and 11 cloth shall be composed of two nylon fabrics joined by a minimum of 30 pile yarns per square inch so that the fabrics are spaced a minimum of 2-1/4 inches apart or a maximum of 3 inches apart after heat setting. The warp yarn shall be 2 ply, 70 denier yarn, and the filling shall be a singles, 210 denier yarn. The pile warp yarn shall be either 2 ply, 70 denier yarn or a singles, 210 denier yarn.

2/ The pile cloth of type 12 shall be composed of two nylon fabrics joined by a minimum of 30 pile yarns per square inch so that the fabrics are spaced a minimum of 2 inches apart or a maximum of 2-1/4 inches apart after heat setting. Ply and denier of the warp, filling, and pile warp yarns shall be as specified for types 6, 10, and 11.

3/ Full width.

3.1.1.1 Nylon webbing. - The nylon webbing used shall conform to MIL-W-17337 except it shall be undyed and coated in accordance with table II.

Table II - Coatings and sequence of plies.

Type and class	Coating	Cloth	Coating	Cloth Weight 1/ max. ozs. per sq. yard	Coating	Cloth	Coating	Total weight 1/ Ozs. per sq. yard	
								Min.	Max.
1	---	---	1.5 synthetic	1.0 nylon	2.5 synthetic	---	---	4.7	5.6
2A	---	---	3.0 synthetic	2.5 nylon	3.0 synthetic	---	---	8.0	9.0
2B	---	---	1.5 synthetic	2.5 nylon	2.8 synthetic	---	---	6.3	7.8
2C	---	---	9 synthetic	2.5 bias nylon	9 synthetic	---	---	19.0	22.0
3	---	---	1.0 synthetic	2.1 cotton (bias)	4.5 synthetic	---	---	7.2	8.0
4A	---	---	2.0 natural	4.5 cotton (straight)	8.5 natural	---	---	14.0	15.0
4B	---	---	2.0 synthetic	4.5 cotton (bias)	3.5 synthetic	---	---	9.5	10.5
5	---	---	1.5 synthetic	5.4 nylon	16.5 synthetic	---	---	22.2	24.6

1/ To ascertain the weight of the coating on either side, the coating shall be peeled by using a volatile solvent such as benzine and the specimen dried thoroughly.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

Table II - Coatings and sequence of plies - Cont'd.

Type and class	Coating	Cloth	Coating	Cloth Weight 1/ max. ozs. per sq. yard	Coating	Cloth	Coating	Total weight 1/ Ozs. per sq. yard	
								Min.	Max.
6	---	---	6.0 synthetic	8.5 nylon	6.0 synthetic	---	---	18.5	20.5
7A	---	---	11.5 natural	7.0 cotton (straight)	11.5 natural	---	---	28.5	31.5
7B	---	---	12.5 synthetic	7.0 cotton (straight)	12.5 synthetic	---	---	28.5	35.0
8A	---	---	2.0 natural	1.0 nylon (bias)	3.5 natural	---	---	6.2	6.8
8B	---	---	2.0 synthetic	1.0 nylon (bias)	3.5 synthetic	---	---	6.2	6.8
9A	---	---	12.5 synthetic	5.4 nylon	12.5 synthetic	---	---	28.5	31.5
9B	---	---	14.0 natural	5.4 nylon	14.0 natural	---	---	30.0	34.0
10	1.5 synthetic	1.0 nylon	8.5 synthetic	8.5 nylon	8.5 synthetic	1.0 nylon	1.5 synthetic	27.8	30.8
11	5.0 synthetic	2.0 nylon	6.0 synthetic	8.5 nylon	6.0 synthetic	2.0 nylon	5.0 synthetic	31.8	35.2
12	10.8 synthetic	1.0 nylon	8.3 synthetic	8.2 nylon	8.3 synthetic	1.0 nylon	1.5 synthetic	42.0	46.0
13	---	---	4.5 synthetic	3.1 nylon	4.5 synthetic	---	---	11.5	12.7
14	---	---	16 synthetic	13.3 nylon	16 synthetic	---	---	43.3	47.3
15	---	---	2/ synthetic	nylon webbing	2/ synthetic	---	---	---	---
16A	---	---	9 synthetic	4.8 nylon	9 synthetic	---	---	22.0	27.0
16B	---	---	9 natural	4.8 nylon	9 natural	---	---	22.0	27.0
17	---	---	16 synthetic	8.5 nylon	16 synthetic	---	---	38	42

1/ To ascertain the weight of the coating on either side, the coating shall be peeled by using a volatile solvent such as benzine and the specimen dried thoroughly.

2/ Friction or spread coated to protect against sunlight aging and to provide a base for cementing. Coating to be not less than 1 mil thick.

3.1.2 Coating compound. - The compounds used shall be such that when equivalently cured in sheet form as in the coated cloth, they shall have a minimum tensile strength of 1800 pounds per square inch (p.s.i.) and a minimum elongation of 500 percent when tested as specified in 4.2.1.1. No materials which will result in a waxy finish, or which will be water soluble shall be used. The synthetic rubber coating compounds after being cured and after exposure to accelerated light aging as specified in 4.2.1.1 shall retain a tensile strength of not less than 75 percent of the original strength.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

3.1.2.1 Natural rubber. - The natural rubber compound shall contain not less than 78 percent by volume of new plantation rubber.

3.1.2.2 Synthetic rubber. - The synthetic rubber compound shall contain not less than 60 percent nor more than 75 percent by volume of polymerized chloroprene.

3.2 Coatings. - The base fabric may be treated before coating with an adhesive compound or a dip treatment to insure adhesion of the coating compound if desired. Coatings shall be applied by either the spreader or calender process so that the finished fabric will meet the requirements of this specification. The fabric weight, weight of coating, and finished fabric weight of each of the types of coated cloth shall be as shown in tables I and II.

3.3 Color. - Unless otherwise required by the specification for the end item, the color shall be that which naturally evolves as a result of the compounding ingredients used except for type 2, class B coated cloth which shall be sea rescue color orange or a close match. (See 6.2.)

3.4 Physical properties of coated cloth. -

3.4.1 Breaking and tearing strength. - The breaking and tearing strength of the finished coated cloth shall conform to table III.

3.4.2 Coating adhesion. - The adhesion of the coating to the base cloth shall conform to table III.

Table III - Strength requirements of coated fabrics.

Type	Coating adhesion (pounds per inches) (minimum)	Breaking strength (pounds) (minimum) per inch of width		Tearing strength (pounds) (minimum)	
		Warp	Filling	Warp	Filling
1	5	50	50	---	---
2A	5	---	---	---	---
2B	5	180	165	8.0	8.0
2C	5	---	---	---	---
3	5	---	---	---	---
4A	5	---	---	---	---
4B	5	---	---	---	---
5	15	360	360	25.0	25.0
6	8	110	180	7	13
7A	10	165	160	4.0	4.0
7B	15	165	160	4.0	4.0
8A	5	---	---	---	---
8B	5	---	---	---	---
9A	12	360	360	21.0	21.0
9B	8	360	360	15.0	15.0
10	1/ 8	---	---	---	---
11	1/ 8	---	---	---	---
12	1/ 8	---	---	---	---
13	8	225	225	12.0	12.0
14	12	600	600	60.0	60.0
15	No requirement	2/3000	---	No requirement	
16A	16	300	300	16	16
16B	8	300	300	16	16
17	16	400	400	25	25

1/ The adhesion of the plies shall be tested and one face of the pile cloth. Specimens shall be prepared by apparatus of method 5970 of CCC-T-191 except that the two strips shall be plied before curing and the assembled specimens shall be cured along with and identically to the end item being made from the coated fabric.

2/ Full width.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

3.4.3 Aging. -

3.4.3.1 Resistance to accelerated aging. - The coating of the cloth and webbing shall show no signs of becoming stiff and brittle or soft and tacky when exposed for 4 days to the accelerated aging test specified in 4.3. Loss in initial tensile strength after aging shall not exceed 15 percent for fabrics coated with natural rubber compound or 10 percent for fabrics coated with synthetic rubber compound.

3.4.3.2 Resistance to accelerated weathering. - Synthetic rubber coating shall not crack when material is bent, more heavily coated side out, over a 1/8-inch diameter rod after exposure for 100 hours without "Corex D" filters as specified in 4.3. One side of the cloth only is to be tested which shall be the side facing the arc in the testing apparatus. After weathering, the synthetic rubber coated cloth shall not show a loss in initial tensile strength exceeding the following:

Nominal finished weight	Percent loss (maximum)
Above 10 ounces	10
7 to 10 ounces	20
Under 7 ounces	No requirement

3.4.4 Temperature resistance. -

3.4.4.1 Resistance to heat (blocking). - The coated cloth and webbing shall show a rating of not more than 2 when tested as specified in 4.3.

3.4.4.2 Resistance to low temperature. - The coating shall not crack when tested as specified in 4.3.

3.4.5 Permeability. - When tested as specified in 4.3 the permeability to hydrogen of the coated cloth, expressed in liters per square meter per 24 hours, shall not exceed the following:

Finished fabric	Permeability (liters) (maximum)
Types 6, 7, 9, 10, 11, 12, 14, 16, and 17	2.0
Types 4, 8, 13	11.8
Types 1, 2, 3, 5, and 15	No requirement

3.4.6 Tearing strength. - The tearing strength of the coated fabrics shall conform to table III.

3.4.7 Hydrostatic resistance. - The hydrostatic resistance of types 2, 3, and 5 cloth shall not be less than 100 p. s. i. when tested as specified in 4.3.

3.5 Workmanship. - The finished cloth and webbing shall conform to the quality and grade of product established by this specification, and the occurrence of defects shall not exceed the quality level specified.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. - Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Quality conformance inspection. - Inspection shall be in accordance with the provisions of MIL-STD-105, except where otherwise indicated.

4.2.1 Testing of components. - In addition to the quality assurance provisions of the subsidiary specifications, testing shall be performed on components listed below for the characteristics shown.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

4.2.1.1 Coating compound. - The rubber used for coating shall be tested as specified in table IV. The methods of testing specified in FED-STD-601, wherever applicable, and as listed in table IV shall be followed. The physical and chemical values specified in 3.1.2 apply to each unit of product tested. The unit of product for test purposes shall be one 6 inch by 6 inch by 0.07 inch to 0.080 inch sheet of rubber, cured in the same degree and manner as the finished product. The sample size shall be as shown in table VI. The lot shall be unacceptable if any unit fails to meet one or more of the specified requirements.

Table IV - Rubber sheets.

Characteristic	Specification reference		Number determinations per individual unit of product	Results reported as
	Requirement	Test method		
Coating compound identification	Table II	15011 of FED-STD-601 or STD commercial	1	Pass or fail
Tensile strength Initial	3.1.2	4111 of FED-STD-601	3	Median value 3 determinations to nearest 10 p.s.i.
After accelerated heat-light aging	3.1.2	7311 and 4111 of FED-STD-601	3	To the nearest 1.0 percent, based on comparison of the median value, with the median of the initial tensile strength
Percent natural rubber (by volume)	78 Min.	1/	-	---
Percent synthetic rubber (by volume)	60 Min. 75 Max.	1/	-	---
Elongation	3.1.2	4121 of FED-STD-601	3	Median value of the 3 determinations to nearest 5.0 percent

1/ The contractor shall furnish a certified copy of his compound formula, showing that:

(a) For natural rubber - his compound contains not less than 78 percent new plantation rubber.
(b) For synthetic rubber - his compound contains not less than 60 percent nor more than 75 percent polymerized chloroprene.

4.2.1.2 Base Cloth. - The base fabric shall be tested as specified in table V. The methods of testing as specified in CCC-T-191, wherever applicable, and as listed in table V shall be followed. The physical and chemical values specified in 3.1.1 and table I apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test method. The unit of product shall be 1 yard, full width, of the base fabric (uncoated). The sample size shall be in accordance with table VI. The lot shall be unacceptable if one or more units fail to meet one or more of the requirements specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

Table V - Test methods.

Characteristic	Specification reference		Number determinations per individual unit of product	Results reported as
	Requirement	Test method		
Cotton cloth: Color	3.1.1 (unbl)	Visual	1	Pass or fail
Nonfibrous Materials, percent maximum	3.1.1 (3 percent maximum)	2611	2	Average of the two determinations to the nearest 0.1 percent
pH of water extract	3.1.1 pH 7 = neutral	2810 or 2811	2	Average of the two determinations to the nearest 0.2 pH
Weight, max. ozs/sq/yd	Table I	5040	5	Average of the 5 determinations to the nearest 0.1 oz.
Breaking strength lbs. min. warp Filling	Table I Table I	5100 5100	5 5	Average of the 5 determinations to the nearest 1.0 pound, separately for warp and filling
Nylon cloth: Material identification	All nylon	1530	1	Pass or fail
Weight, max. ozs/sq/yd	Table I	5040	5	Avg. of the 5 dets. to the nearest 0.1 ounce
Breaking strength, 1/ lbs., min. Warp Filling	Table I Table I	5100 5100	5 5	Avg. of the 5 dets. to the nearest 1.0 pound, separately for warp and filling
Weave 2/	3.1.1 and Table I	Visual	1	Pass or fail
Piles per inch, min. 2/	Table I	Visual	2	Avg. of the 2 counts to nearest full number
Spacing between the 2/ two fabric surfaces, min. and max.	Table I	Visual	3	Average of the 3 measurements to the nearest 1/8 inch
Yarn count (den) 2/ and yard ply	Table I	Visual	1	Pass or fail, reported separately for warp, filling and pile warp

1/ No breaking strength to be tested on the double (pile) fabrics (8.5 ozs. and 8.2 ozs.) used for types 6, 10, 11, 12.
2/ To be tested only on the double (pile) fabrics (8.5 oz. and 8.2 oz.) used for types 6, 10, 11 and 12.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

Table VI - Sample size.

Lot size (units)[1/]	Sample size
800 or less	2
801 to 22,000	3
22,001 and over	5

1/ Lot size expressed in units of pounds for 4.2.1.1 and in yards for 4.2.2.1 and 4.2.2.2.

4.2.1.3 Nylon webbing. - Nylon webbing shall be tested as required for the 3-inch webbing in MIL-W-17337, except that it shall be undyed.

4.2.2 Examination of the coated and cured cloth. - Defects found during the examination shall be classified in accordance with the list shown in 4.2.2.1, 4.2.2.2 and 4.2.2.3.

4.2.2.1 Yard-by-yard examination. - The required yardage of each roll shall be inspected and visual defects classified as listed. The material shall be examined on one side; however, the sample shall be alternated from roll to roll. The material shall also be through-lighted for pinholes. The defects listed below shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the more serious defects shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product for this examination shall be one linear yard. The inspection level shall be level II of MIL-STD-105. The acceptable quality level (AQL) shall be 4.0 defects per 100 units, one class. The lot size shall be expressed in units of 1 yard each. The number of pieces from which the sample is to be selected shall be in accordance with table VII. An approximate equal number of yards shall be examined in each piece of the sample.

Defects

Abrasion mark - resulting in a weak place or evidence of coating removed. 1/

Blister lump or tunnel - Any soft (hollow), clearly noticeable.

Hard lump (solid) 1/, more than 1/2 inch in its longest dimension.

Crease or wrinkle embedded, or resulting in doubling, or adhesion of surfaces against each other, or in incomplete coating.

Cut (including cuts through coating only), hole, tear or pin hole. Any light areas or windows (poor distribution of pigments). More than 3 per linear yard. 1/

Uneven coating - thin areas where coating compound is missing or insufficient. Heavily coated areas, noticeably stiffer than adjoining, unaffected cloth.

Salvage - scalloped, deepest identation 1/2 inch or more:
Tight, resulting in pucker or waviness in adjoining cloth.

Uneven tension - puckers, waviness, ridges that will not flatten under manual pressure.

Spot, stain or streak other than coating or pigment, and more than 1/2 inch in its longest dimension.

Width - less than specified.

1/ Clearly visible at normal inspection distance (about 3 feet).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

4.2.2.2 Overall examination. - Each defect listed below shall be counted not more than once in each piece examined. The unit of product for this examination shall be one piece. The sample size and acceptance number shall be in accordance with table VII. The lot shall be unacceptable if one or more of the defects listed below are found:

Table VII - Sampling for examination.

Lot size in yards	Sample size in pieces	Acceptance number
Up to 1,300 1/	3	0
1,301 to 3,200	5	0
3,201 to 8,000	7	1
8,001 to 22,000	10	1
22,001 and up	15	2

1/ If lot contains fewer than 3 pieces, each piece in the lot shall be examined.

Defects

Wrong color (See 3.3).

Objectionable odor.

Not clean throughout.

Adhering to successive layer on roll (resists unrolling), tacky, cracked or brittle.

Uneven coating throughout.

4.2.2.3 Examination for length. -

4.2.2.3.1 Individual pieces. - The piece shall be examined for gross length. Any gross length found to be less than the minimum specified or more than two yards below the gross length marked on the ticket shall be considered a defect with respect to length. The unit of product for this examination shall be one piece. The number of pieces selected as sample (sample size) for this examination and the acceptance number shall be in accordance with table VII.

4.2.2.3.2 Total yardage in sample. - The lot shall be unacceptable if the total of the actual gross lengths of pieces in the sample is less than the total of the gross lengths marked on the ticket.

4.3 Testing of end item. - The methods of testing specified in CCC-T-191 and FED-STD-601, wherever applicable, and as listed in table VIII shall be followed. The physical and chemical values specified in section 3 apply to each unit of product tested and shall be reported as specified in the applicable test provisions of table VIII, except for loss of strength after aging, and after weathering, which shall be based on the average of all determinations made for a lot. No "end item tests" are required for the coated webbing (type 15). The unit of product for test purposes shall be 3 continuous yards, full width of coated cloth cured in the same manner as the items for which it is used. The sample size (number of such units of products) shall be as shown in table VI. The lot shall be unacceptable if any unit fails to meet one or more of the requirements specified.

Table VIII - Instructions for testing.

Characteristic	Specification reference		Number determinations per individual unit of product	Results reported as
	Requirement	Test method		
Total weight oz/sq/yd min. and max.	Table II	5040	5	Avg. of the 5 det. to nearest 0.1 oz.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

Table VIII - Instructions for testing - Continued

Characteristic	Specification reference		Number determinations per individual unit of product	Results reported as
	Require-ment	Test method		
Sequence of plies (construction)	Table II	Visual exam-ination of cross-section	1	Pass or fail
Coating adhesion Lbs. per inch, min.	Table III	5970	5	Avg. of the 5 det. to the nearest 0.5 lbs., computed to a 1 inch width
Blocking, max.	3.4.4.1	5872	2	Applicable rating 1/
Permeability to hydrogen, max.	3.4.5	5460	3	Avg. of the 3 det. to the nearest liter
Tearing strength (lbs. min.):				
Warp	3.4.6	5134	5	Avg. of the 5 det. to
Filling	3.4.6	5134	5	the nearest 0.1 lb.
Breaking strength (lbs. min.):				
Warp	Table III	5100	5	Avg. of all det. for
Filling	Table III	5100	5	each direction separately to 1.0 lb. also lot avg. for comparison with avg. after aging and after weathering
Breaking strength after accelerated weathering max. loss, percent (100 hrs.) not applicable types 4A, 7A, 8A, 9B, and 16B				
Warp	3.4.3.2	5804, 5100	5	Avg. of all det. in
Filling	3.4.3.2	5804, 5100	5	each direction compared with avg. of all dets. before exposure, reported in percent loss for warp and filling
Resistance to 100 hrs. accelerated weathering	3.4.3.2	5804	5	Pass or fail (evidence of cracking)
Breaking strength after accelerated aging max. percent loss				

1/ To be reported separately for each determination in the unit of product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

Table VIII - Instructions for testing - Continued

Characteristic	Specification reference		Number determinations per individual unit of product	Results reported as
	Requirement	Test method		
Warp Filling	3.4.3.1 3.4.3.1	5852, 5100 5850, 5100	5	Avg. of all dets. in each direction separately, compared nearest 1.0 lb. with avg. of all dets. before exposure reported in percent loss
Resistance to accelerated aging	3.4.3.1	5852 and visual examination for brittleness, softness or tackiness	5	Pass or fail
Resistance to low temperature for (94 ± 1/2 hrs. at -20 ± 2° F.)	3.4.4.2	5874 2/	3	Pass or fail (evidence of cracking)
Hydrostatic resistance min. (types 2, 3, and 5 only)	3.4.7	5512	5	Average of the 5 determinations is nearest 1.0 p.s.i.

2/ Except that hydrostatic determination is not required and that specimen shall be subjected to minus 20 ± 2° F. for 94 ± 1/2 hours before testing.

5. PREPARATION FOR DELIVERY

5.1 This section is not applicable to this specification.

6. NOTES

6.1 Ordering data. - Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Type, class and weight required (see 1.2).
(c) Length and width of coated cloth or length of coated webbing required (see 3.1.1).

6.2 Color chips. - Color chips for sea rescue color may be obtained upon application to the Laboratory Officer, Chemical Laboratory, Norfolk Naval Shipyard, Portsmouth, Va. When requesting, specify for what purpose chips are desired.

Custodians:
Army - MO
Navy - Ships

Preparing activity:
Navy - Ships
(Project 8305-0254)

Reviewer:
Navy - MC, Ships

User:
Army - MO

Note: Review/user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*: _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check this source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

COMMANDER
NAVAL ELECTRONICS SYSTEMS COMMAND
DEFENSE STANDARIZATION PROGRAM BRANCH
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20360

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:07Z
Check the source to verify that this is the current version before use.