INCH-POUND
MIL-I-24768/27
25 February 1992

MILITARY SPECIFICATION SHEET

INSULATION, PLASTIC, LAMINATED, THERMOSETTING, GLASS-CLOTH, EPOXY-RESIN (GEE-F)

This specification is approved for use by all departments and agencies of the Department of Defense.

The requirements for acquiring the insulation material described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-I-24768.

REQUIREMENTS:

Construction: The material shall consist of plies or layers of glass-cloth or nonwoven parrallel aligned fibers impregnated and bonded with an epoxy-resin compound or binder, oriented and processed to conform to this specification.

Intended use: The laminated material covered by this specification is intended for use in electronics applications requiring moisture resistance and high mechanical strength.

Forms: Sheets, rolled tubes, and rods are recommended forms of laminated material covered by this specification.

Burning rate: The burning rate for the material covered by this specification shall be class 1.

Temperature indices: The laminated material covered by this specification has a mechanical strength test index of 140, and an electrical strength test index of 130.

Dimensions and part numbers:

Thickness of sheets: The thickness of laminated sheets, permissible variations, and the applicable part number shall be as specified in table I.

AMSC N/A FSC 5970
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 20261O-20T02:01Z
Check the source to verify that this is the current version before use.

TABLE I. *Thickness of laminated sheets.*

Part number	Nominal thickness (inches)	Permissible variations (± inch)
M24768/27-S-1	0.010	0.002
M24768/27-S-2	0.015	0.003
M24768/27-S-3	0.020	0.004
M24768/27-S-4	0.025	0.005
M24768/27-S-5	0.031	0.0065
M24768/27-S-6	0.047	0.0075
M24768/27-S-7	0.062	0.0075
M24768/27-S-8	0.094	0.009
M24768/27-S-9	0.125	0.012
M24768/27-S-10	0.156	0.015
M24768/27-S-11	0.188	0.019
M24768/27-S-12	0.219	0.021
M24768/27-S-13	0.250	0.022
M24768/27-S-14	0.312	0.026
M24768/27-S-15	0.375	0.030
M24768/27-S-16	0.438	0.033
M24768/27-S-17	0.500	0.036
M24768/27-S-18	0.625	0.040
M24768/27-S-19	0.750	0.043
M24768/27-S-20	0.875	0.046
M24768/27-S-21	1.000	0.049
M24768/27-S-22	1.125	0.053
M24768/27-S-23	1.250	0.055
M24768/27-S-24	1.375	0.058
M24768/27-S-25	1.500	0.061
M24768/27-S-26	1.625	0.064
M24768/27-S-27	1.750	0.067
M24768/27-S-28	1.875	0.070
M24768/27-S-29	2.000	0.073
M24768/27-S-30	2.125	0.079
M24768/27-S-31	2.500	0.085
M24768/27-S-32	2.750	0.091
M24768/27-S-33	3.000	0.097
M24768/27-S-34	3.500	0.110
M24768/27-S-35	4.000	0.122
M24768/27-S-36	4.500	0.134
M24768/27-S-37	5.000	0.142
M24768/27-S-38	5.500	0.156
M24768/27-S-39	6.000	0.172
M24768/27-S-40	6.500	0.180
M24768/27-S-41	7.000	0.195
M24768/27-S-42	7.500	0.210
M24768/27-S-43	8.000	0.216
M24768/27-S-44	8.500	0.232
M24768/27-S-45	9.000	0.240
M24768/27-S-46	9.500	0.255
M24768/27-S-47	10.000	0.270
M24768/27-S-48	—[1]	—[2]

See footnotes on next page.

Source: https://assist.dla.mil -- Downloaded: 202610-20T02:01Z
Check the source to verify that this is the current version before use.

[1]For part numbers of sheets not listed in this table, the thickness shall be included after the part number. Example of this for a 0.8125 inch thick sheet shall be: M24768/27-S-48-0.8125.
[2]On sheets of nominal thickness not listed in this table, the permissible variations shall be the same as for the next greater thickness.

Diameter of rolled round tubes: The range of sizes for rolled round tubes shall be as specified in table II. The inside diameter and outside diameter shall be included in the part number. An example of a part number for a rolled tube with an inside diameter of 0.125 inch and an outside diameter of 0.156 inch is: M24768/27-TRR-0.125/0.156. The wall thickness tolerances for rolled round tubes with an inside diameter up to 4 inches shall be as specified in table III greater thickness.

TABLE II. *Range of sizes for rolled round tubes.*

Inside diameter (inches)		Outside diameter (inches)		Wall thickness (inch)		Maximum ratio of wall thickness to inside diameter
Minimum	Maximum	Minimum	Maximum	Minimum	Maximum	
0.125	48.000	0.156	50.000	0.016	1.000	1/2

TABLE III. *Wall thickness tolerances.*

Wall thickness (inch)	Tolerances (± inch)
0.010 to 0.015	–
0.016 to 0.030	0.006
0.031 to 0.061	0.008
0.062 to 0.124	0.009
0.125 to 0.249	0.011
0.250 to 0.500	0.013

Diameter rods: The range of sizes and tolerances for rods shall be as specified in table IV. The outside diameter os the rod shall be included in the part number. An example of a part number for a rod with an outside diameter of 0.250 inch is: M24768/27-R-0.250.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.

TABLE IV. *Size and tolerances for rods.*

Diameter (inches)	Tolerances (± inch)
0.250 to 1.999	0.005
2.000	0.008

Performance requirements: Performance requirements for laminated materials shall be as specified in tables V, VI, and VII.

The following requirements do not apply to this plastic laminate:

a. Tracking resistance
b. Thermal endurance
c. Silicone content.

Testing: The laminated material covered by this specification shall be tested under qualification inspection requirements.

Source: https://assist.dla.mil -- Downloaded: 20261O-20T02:01Z
Check the source to verify that this is the currentversion before use.

TABLE V. *Performance requirements for sheets.*

Requirement	Cond.	Test para.	Unit	Thickness (inches)[1]									
				0.031	0.062	0.094	0.125	0.188	0.250	0.500	0.750	1.000	1.001 – Max.
Dielectric breakdown voltage	A D-48/50	4.6.4	Min. kV	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	
Dielectric constant[2]	A D-24/23 D-48/50	4.6.6	Max.	5.2 5.4	5.2 5.4	5.2 5.4	5.2 5.4 5.8	5.2 5.4	5.2 5.4	5.2 5.4	5.5 5.7	5.5 5.7	5.7
Dissipation factor	A D-24/23 D-48/50	4.6.6	Max.	0.025 0.035	0.025 0.035	0.025 0.035	0.025 0.035 0.045	0.025 0.035	0.025 0.035	0.025 0.035	0.025 0.035	0.025 0.035	0.025 0.035
Volume resistivity	C-96/35/90	4.6.7	Min. megohm cm				10^5						
Surface resistance	C-96/35/90	4.6.8	Min. megohm				1,000						
Arc resistance	D-48/50	4.6.9	Min. sec.										
Tracking resistance	A	4.6.10	Min. min.										
Impact strength Lengthwise: Crosswise:	E-48/50	4.6.11	Min. ft–lbs. per inch				7.0 5.5	7.0 5.5	7.0 5.5	7.0 5.5	7.0 5.5	7.0 5.5	7.0 5.5

See footnotes at the end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.

TABLE V. *Performance requirements for sheets – Continued.*

Requirement	Cond.	Test para.	Unit	Thickness (inches)[1]									
				0.031	0.062	0.094	0.125	0.188	0.250	0.500	0.750	1.000	1.001 – Max.
Flexural strength		4.6.12	Min. psi										
Lengthwise:	A			60,000	60,000	60,000	55,000	55,000	55,000	45,000	40,000	40,000	40,000
Crosswise:				50,000	50,000	50,000	45,000	45,000	45,000	35,000	30,000	30,000	30,000
Thermal endurance Flexural strength:		4.6.13	Min. psi										
Bonding strength	A	4.6.15	Min. pounds							2,000	2,000	2,000	2,000
	D-48/50									1,600	1,600	1,600	1,600
Water absorption	D_1-24/23	4.6.17	Max. percent	0.50	0.25	0.20	0.15	0.15	0.13	0.10	0.10	0.10	0.10
Silicone content	E-168/185	4.6.18	Max. ppm										
Flame resistance													
Ignition time:	A	4.6.19	Min. sec.							50			
Burning time:			Max. sec.							100			

[1]For intermediate thicknesses, the value for the next smaller thickness shall apply.
[2]For sheets with a thickness 0.501 inch or greater, the value for 0.750 inch thick sheet shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.

TABLE VI. *Performance requirements for rolled tubes.*

Requirement	Cond.	Test para.	Unit	Inside diameter (inches)	Wall thickness (inches)					
					0.031–0.047	0.048–0.062	0.063–0.094	0.095–0.125	0.126–0.188	0.189–0.250
Dielectric strength	A	4.6.5	Min. volts per mil	0.125–8.000						
Compressive strength	A	4.6.14	Min. psi	0.125–0.499 0.500–8.000						
Specific gravity	A	4.6.16	Min.	0.125–0.499 0.500–8.000						
Water absorption	D_1-24/23	4.6.17	Max. percent	0.125–8.000						

TABLE VI. *Performance requirements for rolled tubes – Continued.*

Requirement	Cond.	Test para.	Unit	Inside diameter (inches)	Wall thickness (inches)				
					0.250–0.375	0.376–0.500	0.501–0.750	0.751–1.000	1.000–Max.
Dielectric strength	A	4.6.5	Min. volts per mil	0.125–8.000					
Compressive strength	A	4.6.14	Min. psi	0.125–0.499 0.500–8.000					
Specific gravity	A	4.6.16	Min.	0.125–0.499 0.500–8.000					
Water absorption	D_1-24/23	4.6.17	Max. percent	0.125–8.000					

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.

TABLE VII. *Performance requirements for rods.*

Requirement	Conditioning	Test para.	Unit	Diameter (inches)			
				0.250–0.499	0.500–0.999	1.000	1.001–2.000
Flexural strength	A	4.6.12	Min. psi				
Compressive strength	A	4.6.14	Min. psi				
Specific gravity	A	4.6.16	Min.				
Water absorption	D_1-24/23	4.6.17	Max. percent				

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.

Custodians:
Army – ER
Navy – SH
Air Force – 20

Review activities:
Army – MI, AR, EA
Navy – EC, OS
Air Force – 85

User activities:
Army – ME
Navy – MC, AS

Preparing activity:
Navy – SH
(Project 5970-1015-27)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.