INCH-POUND
MIL-I-24768/29
25 February 1992

MILITARY SPECIFICATION SHEET

INSULATION, PLASTIC, LAMINATED, THERMOSETTING, CONTINUOUS FILAMENT, GLASS-CLOTH, EPOXY-RESIN (CEM-1)

This specification is approved for use by all departments and agencies of the Department of Defense.

The requirements for acquiring the insulation material described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-I-24768.

REQUIREMENTS:

Construction: The material shall consist of a continuous filament glass-cloth and a cellulose core impregnated and bonded with an epoxy-resin compound or binder, oriented and processed to conform to this specification.

Intended use: The laminated material covered by this specification is intended for use in electronics applications requiring moisture resistance and high mechanical strength with good punching qualities.

Forms: Sheets are the only recommended form of laminated material covered by this specification.

Burning rate: The burning rate for the material covered by this specification shall be class 0.

Temperature indices: The laminated material covered by this specification has a mechanical strength test index of 140, and an electrical strength test index of 130.

Dimensions and part numbers:

Thickness of sheets: The thickness of laminated sheets, permissible variations, and the applicable part number shall be as specified in table I.

AMSC N/A FSC 5970
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.

TABLE I. *Thickness of laminated sheets.*

Part number	Nominal thickness (inches)	Permissible variations (± inch)
M24768/29-S-1	0.010	0.002
M24768/29-S-2	0.015	0.003
M24768/29-S-3	0.020	0.004
M24768/29-S-4	0.025	0.005
M24768/29-S-5	0.031	0.0065
M24768/29-S-6	0.047	0.0075
M24768/29-S-7	0.062	0.0075
M24768/29-S-8	0.094	0.009
M24768/29-S-9	0.125	0.012
M24768/29-S-10	0.156	0.015
M24768/29-S-11	0.188	0.019
M24768/29-S-12	0.219	0.021
M24768/29-S-13	0.250	0.022
M24768/29-S-14	0.312	0.026
M24768/29-S-15	0.375	0.030
M24768/29-S-16	0.438	0.033
M24768/29-S-17	0.500	0.036
M24768/29-S-18	0.625	0.040
M24768/29-S-19	0.750	0.043
M24768/29-S-20	0.875	0.046
M24768/29-S-21	1.000	0.049
M24768/29-S-22	1.125	0.053
M24768/29-S-23	1.250	0.055
M24768/29-S-24	1.375	0.058
M24768/29-S-25	1.500	0.061
M24768/29-S-26	1.625	0.064
M24768/29-S-27	1.750	0.067
M24768/29-S-28	1.875	0.070
M24768/29-S-29	2.000	0.073
M24768/29-S-30	2.125	0.079
M24768/29-S-31	2.500	0.085
M24768/29-S-32	2.750	0.091
M24768/29-S-33	3.000	0.097
M24768/29-S-34	3.500	0.110
M24768/29-S-35	4.000	0.122
M24768/29-S-36	4.500	0.134
M24768/29-S-37	5.000	0.142
M24768/29-S-38	5.500	0.156
M24768/29-S-39	6.000	0.172
M24768/29-S-40	6.500	0.180
M24768/29-S-41	7.000	0.195
M24768/29-S-42	7.500	0.210
M24768/29-S-43	8.000	0.216
M24768/29-S-44	8.500	0.232
M24768/29-S-45	9.000	0.240
M24768/29-S-46	9.500	0.255
M24768/29-S-47	10.000	0.270
M24768/29-S-48	_[1]	_[2]

See footnotes on next page.

Source: https://assist.dla.mil -- Downloaded: 20260-20T02:01Z
Check the source to verify that this is the current version before use.

[1]For part numbers of sheets not listed in this table, the thickness shall be included after the part number. Example of this for a 0.8125 inch thick sheet is: M24768/29-S-48-0.8125.
[2]On sheets of nominal thickness not listed in this table, the permissible variations shall be the same as for the next greater thickness.

Performance requirements: Performance requirements for laminated sheets shall be as specified in table II.

The following performance requirements do not apply to this plastic laminate:

a. Dielectric strength
b. Specific gravity
c. Compressive strength
d. Tracking resistance
e. Silicone content
f. Flammability
g. Volume resistivity
h. Surface resistance
i. Arc resistance
j. Impact resistance
k. Thermal endurance
l. Bonding strength.

Testing: The laminated material covered by this specification shall be tested under qualification inspection requirements.

Source: https://assist.dla.mil -- Downloaded: 202610-20T02:01Z
Check the source to verify that this is the currentversion before use.

TABLE II. *Performance requirements for sheets.*

Requirement	Cond.	Test para.	Unit	Thickness (inches)[1]									
				0.031	0.062	0.094	0.125	0.188	0.250	0.500	0.750	1.000	1.001–Max.
Dielectric breakdown voltage	A D-48/50	4.6.4	Min. kV	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	45.0 40.0	
Dielectric constant	A D-24/23 D-48/50	4.6.6	Max.	5.0 5.2	5.0 5.0	4.6 4.8	4.6						
Dissipation factor	A D-24/23 D-48/50	4.6.6	Max.	0.035 0.035	0.035 0.040	0.035 0.040							
Volume resistivity	C-96/35/90	4.6.7	Min. meghom cm										
Surface resistance	C-96/35/90	4.6.8	Min. megohm										
Arc resistance	D-48/50	4.6.9	Min. sec.										
Tracking resistance	A	4.6.10	Min. minutes										
Impact strength Lengthwise: Crosswise:	E-48/50	4.6.11	Min. ft–lbs. per inch										

See footnotes at the end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.

TABLE II. *Performance requirements for sheets – Continued.*

Requirement	Cond.	Test para.	Unit	Thickness (inches)[1]									
				0.031	0.062	0.094	0.125	0.188	0.250	0.500	0.750	1.000	1.001 – Max.
Flexural strength Lengthwise: Crosswise:	A	4.6.12	Min. psi	50,000 40,000	35,000 28,000	30,000 25,000							
Thermal endurance Flexural strength Lengthwise:	E-1/150: T-150	4.6.13	Min. psi										
Bonding strength	A D-48/50	4.6.15	Min. pounds										
Water absorption	D_1-24/23	4.6.17	Max. percent	0.50	0.30	0.25							
Silicone content	E-168/185	4.6.18	Max. ppm										
Flame resistance Ignition time: Burning time:	A	4.6.19	Min. sec. Max. sec.										

[1]For intermediate thicknesses, the value for the next higher thickness shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.

Custodians:
Army – ER
Navy – SH
Air Force – 20

Review activities:
Army – MI, AR, EA
Navy – EC, OS
Air Force – 85

User activities:
Army – ME
Navy – MC, AS

Preparing activity:
Navy – SH
(Project 5970-1015-29)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:01Z
Check the source to verify that this is the current version before use.