TT-C-655
JUNE 17, 1957
SUPERSEDING
Int. Fed. Spec. TT–W–00560a (GSA–FSS)
August 17, 1956 and
Fed. Spec. TT–W–560
April 29, 1941

FEDERAL SPECIFICATION

CREOSOTE, TECHNICAL, WOOD PRESERVATIVE, (FOR) BRUSH, SPRAY, OR OPEN-TANK TREATMENT

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—Coal-tar creosote (crystal-free) covered by the requirements of this specification is a distillate of tar obtained from high temperature carbonization of bituminous coal. It is intended for brush, spray, or open-tank treatments where pressure treatments as covered in Federal Specification TT–W–571 are not practicable.

1.2 Classification.

1.2.1 *Types.*—Coal-tar creosote (crystal-free) shall be of one type, as herein described.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards.—The following specifications and standard, of the issues in effect on the date of invitation for bids, form a part of this specification:

Federal Specifications:

PPP–D–729—Drums; Metal, 55-Gallon (for Shipment of Non-Corrosive Materials).

PPP–D–760—Drums and Pails; Metal (5 and 16.64 Gallon).

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specifications:

MIL–C–124 — Containers (Cans, Pails and Drums), Metal (for Other Than Subsistence Items).

Military Standards:

MIL–STD–129—Marking for Shipment and Storage.

(Copies of Military specifications, standards, and drawings required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:18Z
Check the source to verify that this is the current version before use.

2.2 Other publications.—The following documents form a part of this specification. Unless otherwise indicated, the issue in effect on date of invitation for bids, shall apply.

Governmental:

Code of Federal Regulations:

Title 49, Transportation, Chapter 1, Interstate Commerce Commission, Parts 71-78; Explosives and Other Dangerous Articles.

(Copies of the publication, now a part of the Code of Federal Regulations, may be obtained upon application accompanied by money order, coupon, or cash to the Superintendent of Documents, Government Printing Office, Washington 25, D. C. Prices may be obtained from the Superintendent of Documents. Orders should cite "49–CFR 71–78."

Service and Regulatory Announcement No. 166:

Federal Insecticide, Fungicide, and Rodenticide Act.

(Application for copies should be addressed to the Superintendent of Documents, Government Printing Office, Washington 25, D. C.)

Nongovernmental:

American Wood Preservers' Association (AWPA):

A1—Standard Methods for Analysis of Creosote.

A4—Standard Methods of Sampling Creosote Oil in Tank Cars.

P7—Standards for Preservatives for Nonpressure Treatments.

(Copies of American Wood Preservers' Association (AWPA) Standards may be obtained from the Secretary-Treasurer at 839 Seventeenth Street, N.W., Washington 6, D. C. Prices may be obtained from the Secretary-Treasurer.

Uniform Freight Classification Rules.

(Copies of Uniform Freight Classification Rules may be obtained from the Uniform Freight Classification Committee, 1 Park Avenue, New York 16, N. Y.)

2.2.1 The technical requirements of this specification are the same as those of part 1 of AWPA Standard P7.

3. REQUIREMENTS

3.1 Material.—The material shall be a distillate derived entirely from tar produced by the carbonization of bituminous coal. It shall comply with the requirements of table 1.

3.1.1 *Crystal-free.*—The material shall be fluid and crystal free at 5° C. The creosote shall be rated crystal free if no crystals are formed when tested as outlined in 4.3.2.

TABLE 1.—*Requirements of creosote for brush, spray, or open-tank treatment*

	Not more than	Not less than
Composition:		
Coal-tar distillate, percent by volume		80.0
Water, percent by volume	1.0	
Material insoluble in benzol[1] percent by weight	0.5	
Coke residual[1], percent by weight	2.0	
Specific gravity at 38° C. compared with water at 15.5° C.		1.06
Distillation: The distillate percent by weight on a waterfree basis shall be within the following limits:		
Up to 210° C.	1.0	
Up to 235° C.	10.0	
Up to 355° C.		65.0
Specific gravity of fractions:		
Fraction 235° to 315° C. at 38° C. compared with water at 15.5° C. — not less than 1.025		
Fraction 315° to 355° C. at 38° C. compared with water at 15.5° C. — not less than 1.085		

[1] Samples of used creosote-coal-tar solutions may show increases in matter insoluble in benzol and in coke residue due to treating operations. If neither the percentage of matter insoluble in benzol nor the percentage of coke residue exceeds the specification limits by more than 1.0 and it can be shown that the original solution was of specified quality, the used solution shall be regarded as conforming to the specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:18Z
Check the source to verify that this is the current version before use.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Inspection.—The Government reserves the right to conduct any inspection or make any additional tests which it deems necessary to determine conformance to the requirements of this specification.

4.2 Sampling.

4.2.1 *Lot.*—For the purpose of sampling, a lot shall be defined as the quantity of creosote offered for inspection at one time from one manufacturing batch.

4.2.2 *Sampling.*—Sampling of tank cars shall be conducted according to AWPA Standard A4. When creosote is shipped in smaller quantities, the contents of the container shall be heated until crystal free and then mixed. A sample of at least one quart shall then be taken for inspection and test purposes. The contractor shall supply such samples and containers as may be requested at no cost to the Government.

4.3 Tests.

4.3.1 *Test procedures.*—Tests to determine the properties of creosote (see 3.1) shall be made in accordance with AWPA Standard A1.

4.3.2 The creosote shall be rated crystal free if no crystals are formed when 100 ml. of the sample are maintained at a temperature of 5° C. for 3 hours in a 125-ml. Erlenmeyer flask with occasional stirring.

5. PREPARATION FOR DELIVERY

The definitions and applications of the various levels of packaging and packing shall be in accordance with Federal Standard No. 102.

5.1 Packing.

5.1.1 *Level A.*—The creosote shall be furnished in 5-gallon steel containers conforming to the requirements of type I, class 1 of Federal Specification PPP–D–760, or in 55-gallon steel drums conforming to the requirements of type I of Federal Specification PPP–D–729. Five-gallon containers shall be furnished with pour spouts.

5.1.2 *Level B.*—The creosote shall be furnished in 5-gallon steel containers conforming to the requirements of type I, class 1 or 2 of Federal Specification PPP–D–760, or in 55-gallon steel drums conforming to the requirements of type I or II of Federal Specification PPP–D–729. When specified, tank car shipments shall be prepared in accordance with the Interstate Commerce Commission Regulations. Five-gallon containers shall be furnished with pour spouts.

5.1.3 *Level C.* — The creosote shall be packed in containers of the type, size, and kind commonly used for the purpose, in a manner that will insure acceptance by common carrier and safe delivery at destination. Shipping containers shall comply with the Uniform Freight Classification Rules, or Regulations of other carriers as applicable to the mode of transportation.

5.2 Marking.—All shipping containers shall be labeled in accordance with applicable Interstate Commerce Commission Regulations. Creosote is "economic poison" as defined by the Federal Insecticide, Fungicide, and Rodenticide Act and application for its registration and labeling requirements under that Act should be made to the Pesticide Regulation Section, Plant Pest Control Branch, Agricultural Research Service, U. S. Department of Agriculture, Washington 25, D. C. Unless otherwise specified, each individual container shall be plainly marked with the following information:

Wood Preservative: Creosote
Federal Specification TT–C–655
Quantity (gallons at 60° F.)
Gross weight
Name of manufacturer (and name of contractor if not the same)
Government order number (or contract number if no order number is assigned).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:18Z
Check the source to verify that this is the current version before use.

CAUTION

May cause skin irritation.
Avoid prolonged or repeated contact with skin.
Avoid prolonged breathing of vapor.
Use only with adequate ventilation.

5.2.1 *Military.*—In addition to the marking required in 5.2, marking shall be in accordance with Military Standard MIL–STD–129.

6. NOTES

6.1 Ordering data.—Contracting officers should specify the type desired and the packing required.

6.2 Intended use.—Creosote (crystal-free) may be used but not as alternated in bid proposals calling for pressure treatments, for the preservative treatment of wood by brush, spray, or dip methods. Federal Specification TT–W–571 does not provide for such treatments. When the treatments specified in TT–W–571 are out of question, however, and brush, spray, and dip treatments are the only ones practicable, they may be used, except in the case of poles of certain species which are treated by the hot-and-cold bath method to comply with the penetration requirements of table 1, Federal Specification TT–W–571.

6.3 Transportation description.—Transportation description applicable to this item is:

Creosote.
Carload minimum weights:
In steel pails, or in metal cans in boxes —30,000 pounds.
In bulk in barrels; also CL in tank cars, Rule 35—40,000 pounds.
Truckload weight 30,000 pounds.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise, as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—E M O Q Sig T
Navy—Or MC Y
Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:18Z
Check the source to verify that this is the current version before use.