METRIC

MIL-S-70745(AR)
AMENDMENT 1
31 May 1991

MILITARY SPECIFICATION

STRIP, AMMUNITION, METALLIC, 30mm

This Amendment forms a part of Military Specification MIL-S-70745(AR), dated 30 December 1988, and is approved for use within the U.S. Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.4, Delete in its entirety.

Change 3.5 as follows:

FROM: "3.5 Push out (nose). The force required ... shall be not less than (TBD) pounds nor more than (TBD) pounds."

TO: "3.5 Push out (nose). The force required to disassemble the nose end of an M848 dummy cartridge from the ammunition strip shall be as follows:

a. Individual minimum value - 8 pounds
b. Mean - 3 standard deviations - 6 pounds minimum
c. Mean + 5 standard deviations - 70 pounds maximum"

Change 3.6 as follows:

FROM: "3.6 Hardness. The uncoated ... requirement of Note 8 specified on Dwg. 12902719."

TO: "3.6 Hardness. The uncoated ... requirement of Note 7 specified on Dwg. 12902719."

Change 3.8 as follows:

FROM: "3.8 Corrosion resistance. The strip, finished in accordance with Note 7 of Dwg. 12902719, shall be exposed for 24 hours of salt spray (fog) testing. After exposure, the strip shall exhibit no corrosion in excess of (TBD) disregarding cut edges for this requirement."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:57Z
Check the source to verify that this is the current version before use.

TO: "3.8 Corrosion resistance. The strip, finished in accordance with Note 6 of Dwg. 12902719, shall be exposed for 24 hours of salt spray (fog) testing. After exposure, the strip shall exhibit no excessive corrosion (red rust). Up to 10% area covered by red rust is acceptable. Cut edges are expected for this requirement."

PAGE 4

Change 4.3.1 as follows:

FROM: "4.3.1 Submission. The contractor shall submit ... the provisions of 4.3.2. The first article ... as indicated."

PART DESCRIPTION	DRAWING	QUANTITY
Strip Ammunition Metallic, 30mm	12902719	TBD"

TO: "4.3.1 Submission. The contractor shall submit ... the provisions of 4.3.2. The first article ... as indicated."

PART DESCRIPTION	DRAWING	QUANTITY
Strip Ammunition Metallic, 30mm	12902719	494"

PAGE 6

Table I, Change From:

"Examination for defects	150	see 4.4.2.1	3.2	Visual
Snap-In Assembly	40	0-1	3.4	4.4.5.3
Push-Out (Nose)	40	0-1	3.5	4.4.5.4
Hardness	32	0-1	3.6	4.4.5.1"

To:

"Examination for defects	150	see 4.4.2.1	3.2	Visual
Push-Out (Nose)	40	0-1	3.5	4.4.5.3
Hardness	32	0-1	3.6	4.4.5.1"

Source: https://assist.dla.mil -- Downloaded: 202610-23T03:57Z
Check the source to verify that this is the currentversion before use.

PAGE 9

4.4.2.1, Change MAJOR from:

"110. Snap-In Assembly	see 4.4.2.1 1/	.40	3.4	4.4.5.3
111. Push-Out (Nose)		.40	3.5	4.4.5.4
112. Hardness		.40	3.6	4.4.5.1
113. Material Thickness		.40	3.8	4.4.5.6"

To:

"110. Push-Out (Nose)	see 4.4.2.1 1/	.40	3.5	4.4.5.4
111. Hardness		.40	3.6	4.4.5.1
112. Material Thickness		.40	3.8	4.4.5.6"

PAGE 10

4.4.5.3, Delete in its entirety.

PAGE 12

Figure 1, Delete in its entirety.

PAGE 13

In Figure 2, change the figure dimension position of the round in the Ammunition Strip:

FROM: "XX ± XX"

TO: 30 ± 5mm

Custodian:
Army-AR

Preparing activity
Army-AR

(Project 1305-AD34)

Source: https://assist.dla.mil -- Downloaded: 202610-23T03:57Z
Check the source to verify that this is the currentversion before use.