MILITARY SPECIFICATION

ADHESIVE, AIRCRAFT, FOR STRUCTURAL REPAIR

This amendment forms a part of MIL-A-85705A, dated 27 February 1987, and is approved for use within the Naval Air Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

Page 5

3.5.1.2, delete and substitute:

"3.5.1.2 Type II Adhesives. Type II adhesives shall be cured for a maximum of 1 hour at a maximum temperature of 149°C (300°F) and a vacuum of 25 to 29 inches of mercury using a vacuum bag technique or positive pressure of not more than 15 psi."

3.5.4, at end of paragraph add the following new sentence: "Scrim cloth may be used to control bondline thickness."

3.5.8 C, after "adhesive" add: "with warnings to mix completely".

Page 10

4.6.1.1, delete and substitute:

"4.6.1.1 Viscosity and Working Life. Viscosity of the mixed adhesive shall not drop below 100 poises when heated at a rate of 2°C (4°F) per minute. A rheometrics viscometer or equivalent shall be used."

Page 16

6.6, at end of paragraph, add the following new sentence: "This formulation has been designated AMLBOND."

Preparing Activity:
Navy-AS
(Project No. 8040-N137)

AMSC N/A FSC 8040

DISTRIBUTION STATEMENT A: Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:24Z
Check the source to verify that this is the current version before use.