NOT MEASUREMENT SENSITIVE
MIL-A-85705A(AS)
AMENDMENT 2
31 July 1991
SUPERSEDING
AMENDMENT 1
10 December 1987

MILITARY SPECIFICATION

ADHESIVE, AIRCRAFT, FOR STRUCTURAL REPAIR

This amendment forms a part of MIL-A-85705A, dated 27 February 1987, and is approved for use within the Naval Air Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

Page 4

3 2.1.3, Delete the second sentence in its entirety.

Page 5

3.5.1.2, delete and substitute·

"3.5.1.2 Type II Adhesives. Type II adhesives shall be cured for a maximum of 1 hour at a maximum temperature of 149°C (300°F) and a vacuum of 25 to 29 inches of mercury using a vacuum bag technique or positive pressure of not more than 15 psi."

3.5.4, at end of paragraph, add the following new sentence: "Scrim cloth may be used to control bondline thickness."

*3.8, delete and substitute.

"3.8 Instruction sheet. When requested, the manufacturer shall provide a dated and titled instruction sheet with each shipment of adhesive (see 5.3). The instruction sheet shall include the following information:

a. The general chemical type of the base material used in the adhesive system

b. Complete mixing instructions for the paste adhesive.

c. Typical time, temperature and pressure for each segment of the complete curing cycle giving maximum and minimum limits for each condition

d. Date of manufacture

AMSC N/A FSC 8040
DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:24Z
Check the source to verify that this is the current version before use.

Page 8

*4 4 1, delete and substitute

"4.4 1 Lot formation A lot shall consist of all the adhesive of one type manufactured at one time from the same batch (see 6.4) and submitted for inspection at the same time and place."

Page 9

*4.4.3.2, delete the first three (3) sentences and substitute: "The sample selected in 4.4 2.2 shall be tested for double lap tensile shear stress at 24°C (75°F) (Test #1) and at 104°C (220°F) after a 10 minute soak (Test #2). Two test panels (4.3.4.4) shall be prepared for each test Shear strength shall be reported "

Page 10

4.6.1.1, delete and substitute

"4 6.1.1 Viscosity and working life Viscosity of the mixed adhesive shall not drop below 100 poises when heated at a rate of 2°C (4°F) per minute. A Rheometrics viscometer or equivalent shall be used "

NOTE: The margins of this amendment are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inacurracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Preparing activity
Navy - AS
(Project No 8040-N170)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:24Z
Check the source to verify that this is the current version before use.