MILITARY SPECIFICATION

HOSE, FUEL, FLAME THROWER, M8

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one type of high pressure fuel hose.

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents of the issue in effect on date of invitation for bids or request for approval, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

TT-W-572	-	Wood Preservative, Water Repellant.
PPP-B-621	-	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	-	Box, Fiberboard.
PPP-F-320	-	Fiberboard; Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes.
PPP-T-76	-	Tape, Pressure-Sensitive Adhesive Paper, Water Resistant (For Carton Sealing).

MILITARY

MIL-P-116	-	Preservation, Methods of.
MIL-B-2427	-	Boxes, Ammunition Packing, Wood, Nailed.
MIL-C-52078	-	Cap-Plug, Cap and Plug, Protective, Plastic, Dust and Moisture Seal.

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:48Z
Check the source to verify that this is the currentversion before use.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-1168 - Lot Numbering of Ammunition.

DRAWINGS

US ARMY MUNITIONS COMMAND

EDGEWOOD ARSENAL

B81-1-6930 - Hose, Fuel, Flame Thrower, M8.

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification

(Application for copies of these ratings, rules and regulations should be addressed to Uniform Classification Committee, 202 Union Station, 516 West Jackson Boulevard, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Materials and components.

3.1.1 Materials. All materials cited on Drawing B81-1-6930 or on the subsidiary drawings shall conform to the specifications thereon or to the specific characteristics set forth on the drawing.

3.1.2 Components. All components of the hose assembly shall conform to the specifications and drawings listed on Drawing B81-1-6930.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:48Z
Check the source to verify that this is the current version before use.

3.2 Assembly. The hose shall be assembled as shown on Drawing B81-1-6930.

3.3 Construction.

3.3.1 Hose. The hose shall consist of an inner tube, reinforcement and cover. The hose shall weigh a maximum of 0.3 pound per linear foot.

3.3.2 Inner tube. The inner tube shall be an oil-resistant nitrile synthetic rubber of seamless construction with a uniform gage and smooth bore throughout.

3.3.3 Reinforcement. The reinforcement shall consist of an inner cotton braid and a wire braid, braided under tension so that no strand is loose. The wire used in the wire braid shall be a high tensile, carbon steel wire containing a minimum of 12.34 grams of zinc per kilogram of wire. The outer surface of the wire shall be plated with a minimum of 6.17 grams of brass per kilogram of wire. The wire braid shall be free from sharp edges, kinks, broken, loose or spliced strands.

3.3.4 Cover. The cover shall consist of a nylon braid impreganted with an oil-resistant chloroprene synthetic rubber.

3.4 Performance.

3.4.1 Flexibility. The hose shall not crack or break when tested as specified in 4.4.4.1.

3.4.2 Leakage. The hose assembly shall not leak at 625 ± 10 pounds per square inch gage (psig) when tested as specified in 4.4.4.2 and 4.4.4.6.

3.4.3 Bursting pressure. The hose assembly shall not bulge in spots, burst or blow off the fittings at less than 2000 psig when tested as specified in 4.4.4.2.

3.4.4 Tensile strength. The hose assembly shall not rupture or pull loose from the fittings at less than a 1000-pound minimum load when tested as specified in 4.4.4.3.

3.4.5 Solvent swell. The inside diameter of the hose shall not decrease to less than 90 percent of its original diameter when tested as specified in 4.4.4.4.

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:48Z
Check the source to verify that this is the current version before use.

3.5 Preproduction. Prior to the start of regular production, a preproduction sample of hoses shall be produced in accordance with this specification for examination and test (see 4.3).

3.6 Workmanship. The hose assembly shall be free from foreign matter (oil, dirt or grease) and damage such as cracks or deformation which could affect its intended use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.

4.1.1 Supplier's responsibility. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to specified requirements.

4.1.2 Objective evidence. The supplier shall provide objective evidence acceptable to the contracting officer that the requirements of 3.1 and section 5 for which specific inspection has not been provided in this specification have been satisfied.

4.2 Classification of inspections.

(a) Preproduction inspection (see 4.3)
(b) Quality conformance inspection (see 4.4)

4.3 Preproduction inspection.

4.3.1 Sample. A preproduction sample of eight hose assemblies and two 3-inch lengths of hose shall be manufactured using the same methods, materials, equipment and processes as will be used during regular production.

4.3.2 Inspection procedure.

4.3.2.1 For examination and nondestructive test. The sample hose assemblies shall be examined and tested in accordance with the classification of defects (4.4.3.4(a)). The AQL's do not apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:48Z
Check the source to verify that this is the current version before use.

4.3.2.2 For destructive tests. The sample hose assemblies after testing as specified in 4.4.4.6 shall be tested in accordance with 4.4.4.1, 4.4.4.2, 4.4.4.3, and 4.4.4.5. The 3-inch lengths of hose shall be tested as specified in 4.4.4.4.

4.3.3 Acceptance/rejection criteria. The preproduction sample shall comply with the examinations and tests specified in 4.3.2 to be acceptable. The acceptance number is zero. The supplier shall obtain written approval from the contracting officer prior to proceeding with regular production.

4.4 Quality conformance inspection.

4.4.1 Lotting. Each lot shall be identified and controlled in accordance with MIL-STD-1168. Contained in any one interfix number of hose assemblies, no more than one interfix number from one manufacturer of the following components is permitted.

Coupling

4.4.2 Sampling.

4.4.2.1 For examination and nondestructive test. Sampling shall be conducted in accordance with MIL-STD-105.

4.4.2.2 For destructive tests. Eight hose assemblies and two 3-inch lengths of hose shall be taken at random from each lot.

4.4.3 Inspection procedure.

4.4.3.1 For examination and nondestructive test. The sample hose assemblies and the level A preparation for delivery shall be examined and tested in accordance with the classification of defects and MIL-STD-105.

4.4.3.2 For destructive tests. The sample hose and hose assemblies shall be tested in accordance with 4.4.4.1, 4.4.4.2, 4.4.4.3, 4.4.4.4 and 4.4.4.5.

4.4.3.3 For critical defects. Each item in the lot shall be tested for the critical characteristic listed in the classification of defects.

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:48Z
Check the source to verify that this is the current version before use.

4.4.3.4 Classification of defects. (See inspection data list IDL81-1-6930 for inspection equipment required to perform the examinations specified in this section.)

(a) Hose, fuel, flame thrower, M8 (Drawing 881-1-6930).

Categories	Defects	Acceptance standards
Critical:		
1	Leakage	4.4.4.6
Major:	AQL 1.0 percent defective	
101	Component missing or incorrectly assembled	
102	Threads incorrect	
103	Inside diameter undersize	
104	Marking missing or incorrect	
105	Workmanship (3.6)	
Minor:	AQL 2.5 percent defective	
201	Overall length incorrect	
202	Protective finish missing or incorrect	

(b) Preparation for delivery (section 5).

Categories	Defects
Critical:	None defined
Major:	AQL 4.0 percent defective
101	Hose couplings not clean
102	Openings not capped or plugged
103	Containers incorrect
104	Quantity per container incorrect
105	Container closure incorrect
106	Contents loose in container
107	Container damaged (broken, torn, punctured, crushed or wracked)
108	Strapping loose or missing
109	Marking missing, illegible or incorrect

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:48Z
Check the source to verify that this is the current version before use.

4.4.4 Tests. Tests shall be conducted as follows: (See inspection data list IDL81-1-6930 for inspection equipment required to perform the tests specified in this section.)

4.4.4.1 Flexibility. Three of the sample hose assemblies shall be conditioned at 160° ± 5°F for 24 hours and three of the sample hose assemblies shall be conditioned at minus 65° ± 5°F for 24 hours. While being maintained at the conditioning temperatures, each hose shall be bent around a cylindrical form having a radius of 7 inches.

4.4.4.2 Leakage and bursting pressure. After testing as specified in 4.4.4.1, the hose assemblies tested at 160°F shall be brought to 125° ± 5°F and those tested at minus 65° °F shall be brought to minus 40° ± 5°F. The hose assemblies shall then be subjected to the specified hydrostatic pressure for a minimum period of 30 seconds and examined for leakage. The pressure shall then be increased to the hydrostatic pressure specified (3.4.3). During the test, the hose and test equipment shall be maintained at the specified temperature and the hydrostatic pressure shall be applied at a rate not exceeding 500 psig per minute using water as the test fluid, mixed with antifreeze for cold tests.

4.4.4.3 Tensile strength. The remaining two sample hose assemblies shall be cut into minimum lengths of 12-inches and tested in a tensile testing machine. Each end of the 12-inch length of hose shall be attached to the heads of the machine and the heads shall be separated at the rate of 1 inch per minute until the specified load has been applied.

4.4.4.4 Solvent swell. Two 3-inch length of hose shall be submerged for 7 days at ambient temperature in a mixture of 80 percent by volume iso-octane and 20 percent by volume benzol. Measurement of inside diameter shall be taken at a minimum of 1/2 inch from the end of the hose.

4.4.4.5 Hose construction. After completion of tests in 4.4.4.1 and 4.4.4.2, the couplings shall be removed and the hose weighed to determine compliance with 3.3.1. The hose shall then be cut open and the cover stripped off and the hose examined to determine compliance with 3.3.2, 3.3.3 and 3.3.4.

4.4.4.6 Leakage. The hose assembly shall be subjected to the specified hydrostatic pressure at ambient temperature for a minimum period of 30 seconds. The pressure shall be applied at a rate not exceeding 500 psig per minute using water as the test fluid. Drain and dry each hose assembly after testing.

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:48Z
Check the source to verify that this is the current version before use.

4.4.5 Acceptance/rejection criteria. If one or more hose assemblies fail any of the tests in 4.4.4.1, 4.4.4.2, 4.4.4.3, 4.4.4.4 and 4.4.4.5, the lot represented shall be rejected. If leakage is caused solely by looseness of the coupling components, the hose assemblies may be corrected and resubmitted for test. If a hose assembly fails the test in 4.4.4.6, that hose assembly shall be rejected.

5. PREPARATION FOR DELIVERY

5.1 Cleaning and drying. The hose couplings shall be cleaned and dried in accordance with cleaning method C-3 and any of the drying methods conforming to MIL-P-116.

5.2 Packaging, level A. The coupling threads on each end of the hose shall be protected with plastic caps conforming to MIL-C-52078. Twenty-five hose assemblies shall be packaged straight in five layers of five hose assemblies per layer in a fiberboard box conforming to style RSC, grade W5c of PPP-B-636. The inside dimensions of the container shall be approximately 38" x 7" x 7". Fiberboard pads conforming to grade W5c of PPP-F-320 shall completely separate each layer. Internal cushioning shall be applied as required to insure a tight pack. Closure of the box shall be in accordance with the appendix to PPP-B-636 using tape conforming to PPP-T-76.

5.3 Packing. Levels shall be as specified (see 6.2).

5.3.1 Level A. Four boxes of hose assemblies packaged as specified in 5.2 shall be packed in a class 2 style 4 1/2 wood box conforming to PPP-B-621. The inside dimensions of the container shall be approximately 38 1/2" x 15" x 15". The wood box and wood parts thereof shall be completely immersed for a minimum of three minutes in wood preservation conforming to composition A of TT-W-572. Prior to loading, the preservation shall be dry as evidenced by the dryness test in MIL-B-2427. The box shall be closed and strapped in accordance with the appendix to PPP-B-621 using galvanized strapping.

5.3.2 Level C. The coupling threads on each end of the hose shall be protected with plastic caps conforming to MIL-C-52078. Fifty hose assemblies shall be packaged straight in five layers of ten hose assemblies per layer in a fiberboard box conforming to style RSC, type CF, class domestic variety SW, grade 200 of PPP-B-636. The inside dimensions shall be approximately 38" x 14" x 8". Corrugated fiberboard class domestic, variety SW, grade NT complying with specification PPP-F-320 shall be used to separate each layer. Internal cushioning shall be applied as required to insure a tight pack. The container shall be closed in accordance with the appendix to PPP-B-636.

5.4 Marking. Unless otherwise specified in the contract or order, the unit packages shall be marked in accordance with MIL-STD-129. The shipping containers shall be marked in accordance with Drawing D81-1-9723.

Source: https://assist.dla.mil -- Downloaded: 202640-22T20:48Z
Check the source to verify that this is the currentversion before use.

6. NOTES

6.1 Intended use. This item is intended for use with a portable flame thrower and connects the gun to the fuel containers.

6.2 Ordering data. Procurement documents should specify the following:

(a) The title, number and date of this specification.

(b) The level of packing required.

(c) Preproduction.

(1) Time allowed for supplier submission of samples for Government test and evaluation after award of contract.
(2) Name and address of test facility and shipping instructions when testing is performed by the Government.
(3) Time required for the Government to notify the supplier whether or not to proceed with production.

6.3 Caution. Suppliers are hereby notified to provide adequate protection for personnel during testing with high pressures.

Custodian:

Army - MU
Navy - MC

Preparing activity:

Army - MU(EA)

Review activity:

Navy - MC

Project No. 4720-0275

User interest:

Navy - OS

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:48Z
Check the source to verify that this is the current version before use.

TO DETACH FORM - CUT ON THIS LINE

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

ORGANIZATION

CITY AND STATE | CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)* | DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 20261O-22T20:48Z
Check the source to verify that this is the current version before use.