MILITARY SPECIFICATION

CELLS, STORAGE, NICKEL-CADMIUM (FOR TALOS MISSILE)

This specification is approved for use by the Naval Ordnance Systems Command, Department of the Navy.

1. SCOPE

1.1 Scope. This specification covers vented, rechargeable nickel-cadmium cells for replacement of the original cells in batteries used in the TALOS missile.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

L-P-378	Plastic Sheet and Strip, Thin Gauge, Polyolefin
L-P-1183	Plastic Molding Material, Acrylonitrile-Butadiene-Styrene (ABS), Rigid
FF-N-836	Nut: Square, Hexagon, Cap, Slotted, Castle, Knurled, Welding and Single Ball Seat
FF-S-92	Screw, Machine: Slotted, Cross-Recessed or Hexagon Head
QQ-N-290	Nickel Plating (Electrodeposited)
PPP-F-320	Fiberboard; Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes
PPP-P-636	Boxes, Shipping, Fiberboard

Military

MIL-P-116	Preservation, Methods of
MIL-M-13231	Marking of Electronic Items
MIL-M-20693	Molding Plastic, Polyamide (Nylon) Rigid

FSC 6140

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

STANDARDS

Federal

FED-STD-601	Rubber: Sampling and Testing

Military

MIL-STD-129	Marking for Shipment and Storage
MS3510	Plugs, Venting, Electrolyte Access Hole, Cell, Aircraft Alkaline Storage Battery

DRAWING

Naval Ordnance Systems Command

Dwg. 1792118	Cell, Storage, Nickel-Cadmium

(Copies of specifications, standards, drawings, and publications required by the supplier in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 First article. Unless otherwise specified in the contract or purchase order, four (4) cells shall be manufactured for first article testing using the methods and procedures proposed for production. These first articles will be tested as specified in section 4 to determine if the proposed production method will yield an item which meets the technical and design requirements of this specification and the contract or purchase order. (See 6.2).

3.2 Parts samples. Unless otherwise specified, the first articles and each inspection lot of cells shall be accompanied by three samples of all metallic and elastomeric parts used in the production of those cells. (See 4.4.1)

3.3 Conflicts. In the event of any conflict between the requirements of this specification and any document referenced herein, this specification shall govern.

3.4 Condition. The cells shall be furnished in a discharged wet state with a shorting bar in place.

3.5 Design and construction. The cells shall be designed and constructed in conformance to the requirements specified herein and in NAVORD Dwg. 1792118.

3.5.1 Dimensions and weight. The dimensions and weight of the cells shall be in accordance with NAVORD Dwg. 1792118.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

3.5.2 Cell container. The cell container shall be made of high-strength, nonporous, alkali-resistant polyamide or ABS material. The surfaces of containers shall have a smooth finish, free from pits, blowholes, rough spots, or other deformations and shall maintain the specified dimensions during the life of the cell.

3.5.3 Electrolyte and hardware. The electrolyte level and cell hardware shall be in accordance with NAVORD Dwg. 1792118.

3.5.4 Seals. The seals between cell terminals and cover, and cover and cell container shall be so constructed that the cells shall be in accordance with 3.8 and 3.9.

3.5.5 Vent valves. Each cell shall be equipped with a vent valve conforming to MS3510-2 that vents at 6 ± 4 psig.

3.6 Materials and parts. Materials and parts used in the cells shall be in accordance with the applicable specification shown in the following tabulation:

Material or Part	Applicable Specification
Nickel Plating	QQ-N-290
Machine Screws, Studs and Nuts	FF-N-836 or FF-S-92
Polyamide	MIL-M-20693, Comp A, Type III
ABS	L-P-1183

3.7 Marking.

3.7.1 Cell terminal marking. Positive terminals shall be embossed and legibly indicated by a red +; the negative terminal may be identified by a black -. The polarity markings shall be placed as close as possible to the terminals on the cover of the cell. Paint on terminal studs shall not be used as a terminal marking. Terminal markings shall remain legible throughout the life of the cell.

3.7.2 Cell identification. Each cell shall be provided with a hot-stamped, ink-stamped, or printed identification resistant to 1.3 ± 0.1 specific gravity potassium hydroxide (KOH). Markings shall be in accordance with MIL-M-13231, shall show the information required in NAVORD Dwg. 1792118, and shall remain legible throughout the life of the cell.

3.8 Electrolyte leakage. There shall be no evidence of electrolyte leakage around the terminals, cover to case seal, filler cap or O-rings of any cell at any time prior to or during the performance of any of the tests specified in Section 4.

3.9 Leakage. The cell, with the vent valve disabled, shall not leak when internally pressurized to not less than 5 psig.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

3.10 Corrosion resistance. External metal or component parts of the cell shall not show evidence of cracking, pitting, chipping, scaling, corrosion or other deleterious effects after being tested as specified in 4.6.4.1.

3.11 Alkali resistance of elastomeric materials. All elastomeric materials used in the cell shall not crack, blister, or show signs of deterioration after being tested in accordance with 4.6.4.2. Gaskets shall have a permanent compression set of not more than 6 percent and O-rings not more than 2 percent after this test.

3.12 Potassium carbonate (K_2CO_3). The electrolyte shall not contain a K_2CO_3 concentration greater than 60 grams/liter when tested in accordance with 4.6.11.

3.13 Voltage output. Each initially charged cell shall maintain an output voltage of not less than 1.155 volts when discharged at 55 ± 1.1 ampere for not less than 8 minutes. This condition shall be met after 2 hours or up to 30 days stand time at room ambient conditions.

3.14 Voltage ripple. Peak-to-peak voltage ripple at any time during any discharge shall be not more than 2 millivolts.

3.15 Environmental requirements. The cell shall conform to 3.8, 3.13, and 3.14, and shall show no evidence of mechanical damage during or after the environmental conditions specified in 3.15.1 through 3.15.8.

3.15.1 Vibration, random. The cell shall conform to 3.15 during random vibration between 20 and 2000 Hz at accelerations of 17.5 ± 0.2 g's RMS for not less than 30 seconds and 8.8 ± 0.1 g's RMS for not less than 300 seconds.

3.15.2 Vibration, sine. The cell shall conform to 3.15 during sine vibration at 33 ± 3 Hz for not less than 30 minutes at 3 ± 0.5 g's.

3.15.3 Shock. The cell shall conform to 3.15 during a shock of not less than 30 g's for not more than 25 milliseconds.

3.15.4 Acceleration. The cell shall conform to 3.15 during an acceleration of not less than 25 g's for not less than 5 seconds in the forward longitudinal direction (connector end), and not less than 12 g's for not less than 10 seconds in any other direction.

3.15.5 Altitude. The cell shall conform to 3.15 when discharged for not less than 6 minutes while at a simulated altitude of not less than 80,000 feet.

3.15.6 Temperature. The cell shall conform to 3.15 when discharged for not less than 6 minutes during exposure to 350° ± 2° F.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

3.15.7 Humidity. The battery shall conform to 3.15 after exposure to not less than 90 percent relative humidity at 85° to 90° F for not less than 72 hours.

3.15.8 Stowage. The battery shall conform to 3.15 after stowage in a charged state for any period between 2 hours and 30 days at 80° ± 5° F.

3.16 Life. The life of each cell shall consist of not less than 100 charge-discharge cycles, not counting preconditioning or reconditioning cycles.

3.17 Workmanship. The cells shall be manufactured, assembled, and finished in a thoroughly workmanlike manner. Particular attention shall be paid to neatness and thoroughness of assembly and finishing. All material shall be of sound, uniform quality and condition, and shall contain no defects which adversely affect operation or serviceability. Material which has been treated to conceal defects shall not be used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities satisfactory to the Government for the performance of the inspection requirements specified herein. The Government reserves the right to perform any of the inspections set forth in this specification, where such inspection is deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Classification of tests. Inspections and tests specified herein for the cells and parts samples are classified as follows:

(a) First Article Inspection (See 4.3)

(b) Quality Conformance Inspection (See 4.4)

4.3 First article inspection.

4.3.1 Procedure. Four cells and parts samples associated with the cells as specified in 3.2 shall be inspected as specified herein and in the sequence shown in Table I.

4.3.2 Failure. Failure of a first article or a part sample to pass any of the examinations or tests specified herein shall be cause for the Government to withhold production approval.

4.4 Quality conformance inspection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

4.4.1 Sampling from inspection lots. An inspection lot shall consist of the number of cells specified in the contract which have been manufactured at essentially the same time from essentially the same raw materials and component parts. Samples shall be drawn at random from each inspection lot, as follows:

INSPECTION LOT SIZE	TEST SAMPLES
Up to 180	6
181 to 600	7
Over 600	8

Table I. First Article and Quality Conformance Inspection Schedule

Examination	Requirement	Method	Notes
Preparation for delivery	5	4.6.1	1
Dimensions and weight	3.5.1	4.6.2.1	
Design and construction	3.4, 3.5.2 through 3.5.5, 3.6, 3.7, and 3.17	4.6.2.2	
Visual examination	3.5.2, 3.17	4.6.3	
Corrosion resistance	3.10	4.6, 4.1, 4.6.3	2
Alkali resistance of elastomers	3.11	4.6.4.2, 4.6.3	2
Preconditioning and charging	-	4.6.5, 4.6.6	
Performance	3.13, 3.8	4.6.7	
Random vibration	3.15.1, 3.13 3.14, 3.8	4.6.8.1	
Sine vibration	3.15.2, 3.13, 3.14, 3.8	4.6.8.2	
Shock	3.15.3, 3.13, 3.14, 3.8	4.6.8.3	
Acceleration	3.15.4, 3.13, 3.8	4.6.8.4	
Altitude	3.15.5, 3.13, 3.8	4.6.8.5	
Temperature	3.15.6, 3.13, 3.8	4.6.8.6	
Humidity	3.15.7, 3.13, 3.8	4.6.8.7	
Stowage	3.15.8, 3.13, 3.8	4.6.8.8	
Vent valve test	3.5.5	4.6.9	
Cell leakage	3.9	4.6.10	
Potassium carbonate	3.12	4.6.11	
Life	3.16, 3.13, 3.8	4.6.12	

Notes:
1. This examination is not applicable to first articles or part samples.
2. This examination is applicable only to part samples, not the cell, and may be performed concurrently with cell tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

4.4.2 Procedure. The cell samples and part samples associated with the cells as specified in 3.2 shall be inspected as specified herein and in the sequence shown in Table I.

4.4.3 Failures. Failure of any sample to pass any of the quality conformance examinations or tests specified herein shall be cause for the Government to reject the production cells represented by the sample.

4.5 Inspection condition and equipment.

4.5.1 Ambient condition. Unless otherwise specified herein, all measurements and tests shall be made at a temperature of 75° ± 10° F.

4.5.2 Electrical indicating instruments. All voltmeters and ammeters shall be accurate within ± 1 percent of full scale readings. The range shall be such that the readings are taken off the upper half of the scale. Timers shall be accurate within ± 0.5 percent. The sensitivity of voltmeters shall be at least 5000 ohms per volt.

4.6 Methods of examination.

4.6.1 Preparation for delivery. The marking, packing, packaging, and preservation shall be inspected in accordance with MIL-P-116 to determine conformance to Section 5.

4.6.2 Physical examinations.

4.6.2.1 Dimensions and weight. The cell shall be weighed and its dimensions measured to determine conformance to 3.5.1. These measurements shall be made on discharged cells.

4.6.2.2 Design, construction, materials, and markings. The cell shall be examined to determine conformance to 3.4, 3.5.2 through 3.5.5, 3.6, 3.7, and 3.17.

4.6.3 Visual examination. A visual examination shall be conducted using a lens having a power of not less than 10x to determine conformance to 3.5.2 and 3.17.

4.6.4 Parts tests.

4.6.4.1 Corrosion resistance. Approximately one-half of each sample metal part of the cell shall be wetted along its length by placing it in a solution of 1.3 ± 0.1 specific gravity potassium hydroxide (KOH) electrolyte. The parts shall be allowed to stand for not less than 16 hours at 120° ± 2° F. The parts shall then be rinsed with distilled water, allowed to dry, and visually examined in accordance with 4.6.3 to determine conformance to 3.10.

Source: https://assist.dla.mil -- Downloaded: 2026l0-23T07:18Z
Check the source to verify that this is the currentversion before use.

4.6.4.2 Alkali resistance of elastomeric material. Each sample elastomeric part (such as gaskets, O-rings, etc.) shall be immersed in an aqueous 1.3 ± 0.1 specific gravity KOH electrolyte at ambient conditions and allowed to stand for not less than 30 days. The samples shall then be rinsed with distilled water and allowed to dry. They shall then be tested in accordance with Method 3311 of Federal Test Method Standard No. 601 and examined in accordance with 4.6.3 to determine conformance to 3.11.

4.6.5 Preconditioning. Each cell as received in the discharged condition shall be charged by constant current at the C/5 rate ± 0.5 percent until its potential is 1.55 ± 0.02 volts, then charging shall be continued at the same rate for 2 hours ± 0.5 percent. The cell shall then be discharged at the C ± 0.5 percent rate to an end potential of 1.00 ± 0.01 volt.

Note: "C" is the ampere-hour rating at the 1-hour rate.

4.6.6 Charging. The cell shall be charged at a constant potential of 1.55 ± 0.02 volts for a period of 1 hour ± 0.5 percent.

After charging, the cell shall be allowed to stand open circuit for not less than 2 hours nor more than 30 days before proceeding with further testing.

4.6.7 Performance. Unless otherwise specified herein, each cell, fully charged in accordance with 4.6.6, shall be discharged at a rate of 55 ± 1.1 amperes for not less than 8 minutes. During the discharging period, the voltage shall be monitored to determine conformance to 3.13. During shock or vibration tests, the output voltage ripple shall also be monitored to determine conformance to 3.14. During and after the discharging period, the cell shall be examined for evidence of leakage to determine conformance to 3.8.

After the discharging period, the cell shall be allowed to stand open-circuit for not less than 4 hours before proceeding with further testing.

4.6.8 Environmental tests. The cell shall be fully charged in accordance with 4.6.6 prior to performing any of the following environmental tests, and the battery package containing the test cells shall be mounted by the normal mountings as would be utilized when mounted in a missile.

4.6.8.1 Random vibration. The charged cell shall be subjected to random vibration along each of three mutually perpendicular axes with the following nominal spectral density characteristics at the battery mounting points. The cell shall be subjected to the performance test of 4.6.7 during the vibration and observed for conformance to 3.8, 3.13, and 3.14.

Source: https://assist.dla.mil -- Downloaded: 202610-23T07:18Z
Check the source to verify that this is the current version before use.

	g's Rms	Duration	Nominal Spectral Density Characteristics	
			g^2/Hz	Hz
a)	17.5 ± 0.2	30 + 30 seconds*	.153	20- 300
			.019	300- 500
			.115	500- 700
			.019	700- 900
			.306	900-1350
			.153	1350-2000
b)	8.8 ± 0.1	300 seconds	.038	20- 300
			.005	300- 500
			.028	500- 700
			.005	700- 900
			.076	900-1350
			.038	1350-2000

* 30 seconds ± 0.5 percent at 17.5 g's followed by 300 ± 0.5 percent seconds at 8.8 g's followed by 30 seconds ± 0.5 percent at 17.5 g's.

4.6.8.2 Sine Vibration. The charged cell shall be subjected to a fixed frequency sine vibration of 35 ± 3 Hz at 3 ± 0.5 g's for not less than 15 minutes each along the longitudinal and radial axes. The cell shall be subjected to the performance test of 4.6.7 during the final 10 minutes of vibration and observed for conformance to 3.8, 3.13, and 3.14.

4.6.8.3 Shock. The cell shall be subjected to shock while undergoing the performance test of 4.6.7 and while being observed for conformance to 3.8, 3.13, and 3.14. The shock pulse shall have a trapezoidal characteristic having a maximum rise time of 25 milliseconds to not less than 30 g's acceleration, and dwell at a minimum of 30 g's for at least 30 milliseconds. Shock shall be measured at the battery case mounting points.

4.6.8.4 Acceleration. The cell shall be subjected to acceleration while undergoing the performance test of 4.6.7 and while being observed for conformance to 3.8 and 3.13. The cell shall be accelerated at a minimum of 25 g's for a minimum of 5 seconds in the forward longitudinal direction (connector end), 12 g's min. for 10 seconds min. in the rearward longitudinal direction, and 12 g's min. for 10 seconds min. in any lateral direction. The discharge may be intermittent to allow for axes change the maximum open circuit for each axis change without boost charge shall be 5 minutes (total maximum of 20 minutes open circuit).

4.6.8.5 Altitude. The charged cell shall be subjected to a simulated altitude of not less than 80,000 feet. The rate of change from sea level to 80,000 feet shall be at a minimum rate of 1500 feet per second. The cell shall be subjected to the performance test of 4.6.7 for not less than 6 minutes while at the simulated 80,000 feet, and observed for conformance to 3.8 and 3.13.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

4.6.8.6 Temperature. The charged cell shall be temperature conditioned at 120° ± 2° F for not less than 4 hours, then immediately exposed to an environment of 350° ± 2° F and subjected to the performance test of 4.6.7 for a minimum of 6 minutes, and observed for conformance to 3.8 and 3.13.

4.6.8.7 Humidity. The charged cell shall be exposed to a relative humidity of not less than 90 percent at a temperature between 85° and 90° F for not less than 72 hours after which the cell shall be subjected to the performance test of 4.6.7 and observed for conformance to 3.8 and 3.13.

4.6.8.8 Stowage. The charged cell shall be stored open-circuit for not fewer than 30 days at 80° ± 5° F, and then subjected to the performance test of 4.6.7 and observed for conformance to 3.8 and 3.13.

4.6.9 Vent valve test. The filler cap of the cell shall be attached to an adapter to which a variable-pressure source of compressed air is connected. The adapter shall then be immersed in water and the air pressure adjusted from the lower limit to the higher limit and returned to the lower limit specified in 3.5.5. If there is an escape of air bubbles at the lower limit or if there is no escape of air bubbles at the upper limit, the vent plug has failed the test.

4.6.10 Cell leakage test. Using dry nitrogen, an internal pressure of 5 ± 1 psig shall be applied through an airtight adapter at the venting aperture, and the cell submerged in water for a minimum of 30 seconds and observed for indication of leakage.

4.6.11 Potassium Carbonate. Electrolyte from each cell shall be tested as follows:

a. Extract 1 ml of electrolyte from the cell with a clean dry syringe or pipette, when the cell is in the fully charged condition.

b. Transfer to beaker (250 ml) and dilute with carbon dioxide free distilled water.

c. Add 3-5 drops of phenolphthalein solution (1 gm of phenolphthalein per liter of 95% alcohol is suitable--do not use a saturated phenolphthalein solution).

d. Titrate with a 0.5 N solution HCl or H_2SO_4 to the end point which is the disappearance of the pink color.

e. Add a few drops of methyl purple to solution and again titrate to end point (violet to grey to green). This change is very sensitive going through the grey state when one drop will bring the solution to the green end-point.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

f. Record the titers in milliliters as follows:

A = Phenolphthalein end point,

B = Total titration, therefore;

B-A = C

g. If C is greater than 1.70 ml, the K_2CO_3 concentration exceeds 60 grams/liter, and the cell fails this test.

4.6.12 Life. The cell shall be cycled in accordance with 4.6.6 and 4.6.7 for a total of 100 charge-discharge cycles, including those cycles completed during previous tests, but not including preconditioning or reconditioning cycles. The cell shall be observed for conformance to 3.8 and 3.13 during all discharge cycles.

a. Maintenance. Maintenance of the cells during life cycle testing shall consist of only cleaning of spewed electrolyte and adjustment of electrolyte level with distilled or deionized water.

5. PREPARATION FOR DELIVERY

5.1 Cell condition. Each cell shall be cleaned externally and vented before shipment, and shall be shipped in the wet discharged condition with a shorting bar installed.

5.2 Packaging. Three cells shall be skin-packaged using the following materials:

a. A skin-packaging board, perforated and treated for adhesion, which meets the requirements for 200 pound test c-flute corrugated fiberboard in PPP-F-320.

b. 10-mil (prior to forming) polyethylene skin packaging material which meets the applicable requirements of L-P-378.

The skin-packaging board shall be so sized that there is no evidence of tenting of the formed polyethylene film.

5.3 Packing. Packing shall be Level A or C as specified. (see 6.3)

5.3.1 Level A. Thirty cells shall be packed in a fiberboard box conforming to Type CF. Class weather-resistant of PPP-B-636. Each skin-packaged unit of three individual cells shall be separated from its neighbor by a pad made from the same material as the box. The box closure shall be in accordance with the appendix to the specification.

5.3.2 Level C. Cells shall be so packed as to insure acceptance by common carrier for safe delivery to destination. (see 6.4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

5.4 Marking. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The cells described herein are intended for use as replacement cells for TALOS missile batteries.

6.2 Retention of first articles. The contract or purchase order will usually require that the procuring or testing activity retain first articles for the purpose of comparison with production units.

6.3 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification and any amendment thereto.

b. Number of cells required.

c. Shipping instructions.

d. Packing level A or C.

6.4 Applicability of Department of Transportation. These wet, electric storage calls are of a non-spillable type, are shipped in a completely discharged condition, and are completely and securely boxed. They are, therefore, exempt from Department of Transporation packaging and labeling requirements.

Custodians:
NAVY-OS

Preparing Activity:
NAVY-OS
Project Numbers 6140-N379

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

FOLD

Naval Ordnance Station
Indian Head, MD 20640

POSTAGE AND FEES PAID

DOD 316

OFFICIAL BUSINESS

Commanding Officer
Naval Ordnance Station
Standardization Division (502)
Indian Head, MD 20640

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION
MIL-C-82624(OS) Cells, Storage, Nickel-Cadmium (For TALOS Missile)

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED

S/N 0102-014-1801 (-25254

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:18Z
Check the source to verify that this is the current version before use.