INCH-POUND
MIL-DTL-24643/19F
1 October 2009
SUPERSEDING
MIL-DTL-24643/19E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +105 °C, 1000 VOLTS, TYPE LS6SGU

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Watertight with Circuit Integrity

First	-	Copper conductor, coated or uncoated (see table I for size).
Second	-	Thermoset insulation, extruded or taped (see table I for thickness). Standard identification code applied by Method 5 (two conductors each A, B, and C).
Third	-	The six conductors shall be cabled together with a lay in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be A, B, C, A, B, C.
Fourth	-	An optional binder.
Fifth	-	Cross-linked polyolefin jacket (see table I for thickness.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:00Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/19	Type and size	Conductor size AWG	Cable overall diameter max. (inches)	Insulation thickness min. avg. (inch)	Conductor resistance max. (ohms)	Jacket thickness min. avg. (inch)	Insulation resistance (megohms)	Accelerated service loading amperes
-01UN	LS6SGU-100	0 (Class D)	1.600	0.035	0.1060	0.060	160	475
-02UN	LS6SGU-125	00 (Class D)	1.790	0.040	0.0850	0.060	150	520
-03UN	LS6SGU-150	000 (Class D)	1.960	0.040	0.0674	0.060	135	570
-04UN	LS6SGU-200	0000 (Class D)	2.200	0.050	0.0530	0.075	125	650

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:00Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:	
Conductor resistance (ohms/1000 feet at 25 °C, max.)	(see table I)
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	5000
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	(see table I)
Conductor continuity	No failure
Group A:	
Visual and dimensional	No failure
Watertightness (see MIL-DTL-24643 for limits of water leakage)	No failure
Group B:	
Cold bending cable	No failure
Thermoset proof test (percent, max.)	
Insulation (extruded insulations only)	50
Jacket (when tested at 200 °C)	50
Drip (95±1 °C)	Zero
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35
Gas flame (1 hour)	No failure
Group C:	
Physicals (aged) air oven	
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:00Z
Check the source to verify that this is the current version before use.

Permanence of printing (insulation extruded coverings only) (cycles, min.)	25
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Cable fill (sealant) removability	No failure
Shrinkage	No failure
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Cold working (minus 20±2 °C)	No damage
Gas flame (3 hours)	No failure
Accelerated service (see table I for load current)	No failure
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:00Z
Check the source to verify that this is the current version before use.

Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption (extruded insulations only)	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS6SGU all sizes	800

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-023)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:00Z
Check the source to verify that this is the current version before use.