MIL-C-24643/26B
3 October 1986
SUPERSEDING
MIL-C-0024643/26A(SH)
8 November 1985
MIL-C-24643/26
28 September 1984

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, TYPES LSDPS, LSFPS, LSTPS AND LS7PS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the cable described herein shall consist of this specification and the latest issue of MIL-C-24643.

REQUIREMENTS:

Qualification required.

Construction (watertight with circuit integrity)

First - Copper conductor, nickel coated (see table I for size).
Second - Extruded silicone rubber insulation (see table I for dimensions).
Third - Glass braid (see table I for dimensions). Standard identification code applied by method 4.
Fourth - Braid covering. The specified number of conductors (see table I) cabled together with a lay not greater than 18 times the pitch diameter. Silicone fillers shall be used to form a firm, round assembly.
Fifth - Binder tape applied helically with overlap.
Sixth - Silicone rubber jacket (see table I for thickness).
Seventh - Braided metal armor.
Eighth - Paint.

(B) denotes changes.

AMSC N/A FSC 6145
DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:03Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/26	Cable type and size	Conductors				Cable jacket thickness minimum (inch)	Overall diameter maximum (inch)	Cold bending mandrel diameter maximum (inches)	Conductor resistance per 1000 feet at 25°C maximum (ohms)
		Number	AWG size	Diameter over insulation (minimum) (inch)	Diameter over braid (maximum) (inch)				
-01AN	LSDPS-3	2	16(class B)	0.100	0.125	0.030	0.455	6.0	5.39
-02AN	LSDPS-4	2	14(class B)	.116	.141	.030	.489	6.0	3.38
-03AN	LSDPS-6	2	12(class B)	.143	.170	.040	.585	7.5	2.13
-04AN	LSDPS-9	2	10(class B)	.166	.193	.040	.628	7.5	1.34
-05AN	LSDPS-14	2	9(class B)	.200	.230	.050	.730	8.0	1.060
-06AN	LSTPS-3	3	16(class B)	.100	.125	.030	.475	6.5	5.39
-07AN	LSTPS-4	3	14(class B)	.116	.141	.040	.553	7.0	3.38
-08AN	LSTPS-6	3	12(class B)	.143	.170	.040	.620	7.5	2.13
-09AN	LSTPS-9	3	10(class B)	.166	.193	.040	.657	7.5	1.34
-10AN	LSTPS-14	3	9(class B)	.200	.230	.050	.751	9.5	1.060
-11AN	LSTPS-23	3	7(class B)	.257	.291	.050	.866	10.5	.643
-12AN	LSTPS-30	3	5(class C)	.310	.348	.060	.989	12.0	.403
-13AN	LSFPS-14	4	9(class B)	.200	.230	.050	.815	10.0	1.060
-14AN	LS7PS-6	7	12(class B)	.143	.170	.050	.775	9.5	2.13
(B) -15AN	LS7PS-14	7	9(class B)	.200	.230	.050	.986	11.0	1.060

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C maximum...	(see table I)
Voltage withstand - volts, root mean square, minimum....	3000
Insulation resistance - megohms/1000 feet, minimum.....	500
Conductor continuity.....	No failure
Group A:	
Visual and dimensional.....	No failure
The nickel coating on the conductors of the completed cable shall not be nicked, scraped, or abraded as to expose the copper conductor.....	No failure
Watertightness - see MIL-C-24643 for limits of water leakage.....	No failure

Source: https://assist.dla.mil -- Downloaded: 202640-20T00:03Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS: (Continued)

	Requirements
Group B:	
Cold bending, cable (see table I for mandrel diameter)..	No damage
Gas flame, 1 hour at 230/130 volts root mean square.....	No failure
Physicals (unaged)	
Insulation	
Tensile strength - lbf/in^2, minimum.....	750
Elongation - percent, minimum.....	125
Jacket (cable)	
Tensile strength - lbf/in^2, minimum.....	800
Elongation - percent, minimum.....	250
Durometer (type A) hardness, minimum.....	60
Group C:	
Physicals - cable aging (260 ± 10°C)	
Jacket	
Tensile strength - lbf/in^2 minimum.....	600
Elongation - percent, minimum.....	150

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B and C, plus the following:

Cold working (minus 20 ± 2°C).....	No damage
Gas flame (3 hours) at 230/130 volts root mean square...	No failure
Armor - conformance to material, construction and coverage.....	No failure
Specific gravity of extruded silicone insulation, maximum.....	1.55
Cable aging and compatibility (125 ± 5°C).....	No failure
Flame propagation.....	No failure

UNIT ORDERING LENGTHS:

All types and sizes: 100 feet minimum

NOTE: Not for Air Force use.

Custodians:
Army - MI
Navy - SH

Preparing activity:
Navy - SH
(Project 6145-1005-26)

Review activities:
Army - AV, CR, ER
Navy - EC
DLA - IS

User activities:
Army - ME, AR, AL
Navy - CG

Source: https://assist.dla.mil -- Downloaded: 202640-20T00:03Z
Check the source to verify that this is the current version before use.