INCH-POUND
MIL-DTL-24643/27G
27 November 2023
SUPERSEDING
MIL-DTL-24643/27F
1 October 2009

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -4 DEGREES FAHRENHEIT (-20 DEGREES CELSIUS) TO +194 DEGREES FAHRENHEIT (+90 DEGREES CELSIUS), 600 VOLTS, TYPE LS2AU (INCLUDING VARIATION LS2AUS)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

This cable can be manufactured in two variations: LS2AU (single overall shield) and LS2AUS (double overall shield).

Construction (Non-Watertight)

First	-	Copper conductor, tin-coated, ASTM B286, size 22 through size 7 strands.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation. Minimum average wall thickness of 0.024 inch; telephone identification applied by method 3.
Fourth	-	Two conductors cabled together with a lay not greater than 1½ inches.
Fifth	-	Forty pairs cabled with a lay in accordance with 3.4.4 of MIL-DTL-24643. Fillers may be used as necessary to form a firm, well-rounded assembly. Cabling sequence shall be consecutive, starting with pair no. 1, from the center outward.
Sixth	-	An optional binder.
Seventh	-	Braided shield of tin-coated copper. Minimum coverage of 85 percent for type LS2AU only.

Construction for Variant Type LS2AU

Eighth	-	An optional binder.
Ninth	-	Cross-linked polyolefin jacket. Absolute minimum average wall thickness 0.060 inch. See table I for cable overall diameter.

NOTE: Manufacturer's identification tape is required (see 3.4.9 of MIL-DTL-24643).

Distribution Statement A. Approved for public release: distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:03Z
Check the source to verify that this is the current version before use.

Construction for Variant Type LS2AUS

Eighth - Spirally wrapped, 0.002-inch-thick polyethylene terephthalate (polyester film) separator tape with 25 percent minimum lap.

Ninth - Braided shield of tin-coated copper.

Tenth - An optional binder.

Eleventh - Cross-linked polyolefin jacket. Absolute minimum average wall thickness 0.060 inch. See table I for cable overall diameter.

NOTE: Manufacturer's identification tape is required (see 3.4.9 of MIL-DTL-24643).

TABLE I. Details.

Military part no. M24643/27	Type and size	Overall diameter (inches)	
		min.	max.
-01UO	LS2AU-40	1.320	1.370
-01UD	LS2AUS-40	1.380	1.430

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic electricals:

Conductor resistance (ohms/1,000 feet at 77 °F [25 °C], max.)	17.71
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2,500
Conductor to overall shield	2,500
Overall shield to overall shield (type LS2AUS only)	200
Insulation resistance (megohms/1,000 feet, min.)	
Conductor to conductor	5,000
Conductor to overall shield	500
Overall shield to overall shield (type LS2AUS only)	100
Conductor continuity	No failure
Shield continuity	No failure
Jacket flaws	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:03Z
Check the source to verify that this is the current version before use.

Group A:	
Visual and dimensional	No failure
Mutual capacitance (nominal at 1 megahertz [MHz]) (picofarad [pF]/100 feet)	20
Group B:	
Cold bending (cable) at 32±3.6 °F (0±2 °C) (16-inch maximum mandrel diameter)	No failure
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 392 °F [200 °C])	50
Physicals (unaged)	
Insulation (extruded insulation only)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1,300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35
Group C:	
Physicals (aged) (air oven)	
Insulation (extruded insulation only)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Shield (conformance to material, construction, and coverage) (type LS2AU only)	No failure
Surface transfer impedance (type LS2AUS only)	
Milliohms per meter (max.)	700
Electromagnetic pulse (EMP) response (dB, min.)	60

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:03Z
Check the source to verify that this is the current version before use.

Group D:

Flame propagation (cable)	No failure

Qualification inspection:

Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:

Aging and compatibility (cable) (257±9 °F [125±5 °C])	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) – type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS2AU-40 and LS2AUS-40	1,000

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:03Z
Check the source to verify that this is the current version before use.

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

CONCLUDING MATERIAL

Custodians:
Army – MI
Navy – SH

Preparing activity:
Navy – SH
(Project 6145-2013-043)

Review activities:
Army – AR, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:03Z
Check the source to verify that this is the current version before use.