FEDERAL SPECIFICATION

REMOVER, PAINT (ORGANIC SOLVENT TYPE)

This amendment, which forms a part of Federal Specification TT-R-251J, dated August 1, 1978, is approved by the Commissioner of Federal Supply Services, General Service Administration, for the use of all Federal agencies.

Page 2

2.2 Other Publication. Under American Society for Testing and Materials (ASTM) Standards: Delete D 2378 - Flash Point.

Page 3

3.3.5 Effect on wood. Delete in its entirety.

3.3.8 Flash Point. Delete and substitute "3.3.8 Flammability (Type III and IV only). When subjected to the test specified in 4.4.15, the remover shall not continue to burn longer than 3 seconds after removal of the flame."

3.3.9.1 Precautionary marking. If remover contains methylene chloride, add "Contains methylene chloride." to the label.

Page 4

4.3 Sampling of the end item for testing. Change the last sentence to "Samples from lot or batch shall be taken in accordance with MIL-STD-105 using inspection level S-1 and an acceptable quality level (AQL) of 4.0 defects per 100 units."

4.4 Test procedure. Delete second sentence.

TABLE II Test methods. Delete "Effect on wood" and all referenced paragraphs.

Delete "Flash point, 3.3.8 ---- D 2378 ----" and substitute "Flammability test, 3.3.8 ---- ---- 4.4.15"

Page 7

4.4.11. Effect on wood. Delete in entirety.

Page 8

Add 4.4.15 Flammability test (Type III and Type IV only).

4.4.15.Preparation of panel. A clean anodized aluminum alloy panel, 10 by 2 cm (4 by 3/4 inch), shall be held at an angle of approximately 45 degrees. Types III or IV removers shall be poured along the upper edge of the panel, allowing the remover to drain freely over the surface. Remover settling on the reverse side of the panel shall be wiped clean before proceeding with the test. A thin layer of remover shall be spread uniformly over the total area of one side of the panel.

4.4.15.2 Procedure. A micro-burner flame, not exceeding 0.5 cm (0.1875 inch) in length shall be passed, within a 2-second period, back and forth along the lower edge of the panel. This operation shall be repeated three times at 3-second intervals. If the remover ignites, the panel shall be removed from the burner flame and observation shall be made to ascertain whether the remover continues to burn. The above procedure shall be repeated on another similarly prepared panel except that it shall be placed in an oven for 15 minutes at 45 $\pm$ 2°C (113 $\pm$ 4°F). The panel shall then be removed from the oven and subjected to the flame test.

MILITARY INTERESTS:

Coordinating Activity
Army - ME

Review Activity
Army - MD

User Activities
Navy - YD
DoD - DS

PREPARING ACTIVITY:
GSA - FSS

Project Number
8010-1134

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:15Z
Check the source to verify that this is the current version before use.