TT-S-223B
AMENDMENT-2
January 26, 1993
SUPERSEDING
AMENDMENT-1
January 16, 1985

AMENDMENT TO FEDERAL SPECIFICATION

SEALER, SURFACE, FLOOR, WATER EMULSION TYPE

This amendment has been approved by the Commissioner, General Services Administration for the use of all Federal Agencies.

Page 1

Add under 2.1, Federal Standard:

FED-STD-313 - Preparation and Submission of Material Safety Data Sheets.

Page 3

Add 3.2.7 **Alkali resistance.** When tested as specified in 4.4.9, the sealer shall not whiten, discolor, soften, blister, or show any sign of detrimental effect.

Add 3.3 **Material Safety Data Sheets (MSDS).** An MSDS shall be submitted in accordance with FED-STD-313 (see 6.2).

In Table II, add following test method: Add "Alkali resistance" under Test, "D 1308" under ASTM, and "4.4.9" under Reference paragraph.

Page 4

Add 4.4.9 **Alkali resistance.** Flow the sealer on black and white vinyl composition tiles and dry vertically for 24 hours. Perform the test in accordance with the covered spot test procedure described in ASTM D 1308, using a 0.5 percent solution of reagent-grade sodium hydroxide. The reagent shall remain in contact with the sealer for 4 hours. Wipe dry and allow the panels to recover for 2 hours and examine for conformance to 3.2.7.

Page 5

Add under 6.2:

(e) Instructions and address for submission of MSDS (see 3.3).

CIVIL AGENCY INTERESTS

VA-OSS

PREPARING ACTIVITY

GSA-FSS

DISTRIBUTION STATEMENT A: Approved for public release. Distribution is unlimited. FSC 8010

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:15Z
Check the source to verify that this is the currentversion before use.