The documentation and process conversion measures necessary to comply with this revision shall be completed by 24 January 2006.

INCH-POUND

MIL-PRF-19500/642B
24 October 2005
SUPERSEDING
MIL-PRF-19500/642A
23 January 2003

* PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER RECTIFIER, DUAL, COMMON CATHODE OR ANODE CENTER TAP, ULTRAFAST, TYPES 1N6762 THROUGH 1N6765 AND 1N6762R THROUGH 1N6765R, JANTX, JANTXV, AND JANS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

* The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for silicon, dual ultrafast, power rectifier diodes in a center-tap configuration. Three levels of product assurance are provided for each device type as specified in MIL-PRF-19500.

1.2 Physical dimensions. See figure 1 (TO-254AA, isolated).

1.3 Maximum ratings.

Types	V_{RWM} (1) I_D = 10 µA dc	I_F (1) (2) T_C =+100°C	I_{FSM} (1) t_p= 8.3 ms	$R_{\theta JC}$ (1)	$R_{\theta JA}$ (1)	T_{STG} and T_J
	V dc	A dc	A(pk)	°C/W	°C/W	°C
1N6762, 1N6762R	50	12	165	2.0	40	-65 to +150
1N6763, 1N6763R	100					
1N6764, 1N6764R	150					
1N6765, 1N6765R	200					


(1) Each individual diode.
(2) Derate at 240 mA/°C above T_c = +100°C.

* 1.4 Primary electrical characteristics. Unless otherwise specified, characteristics are each diode at +25°C.

Types	V_{F1} I_F = 6 A dc	V_{F2} I_F =12 A dc	I_{R1} (see 1.3) V_R = 0.8 V_{RWM}	I_{R2} V_R = 0.8 V_{RWM} (see 1.3) T_C = +100°C	t_{rr}	C_J V_R = 5 V f = 1 MHz
	V dc	V dc	µA dc	µA dc	ns	pF
1N6762, 1N6762R	0.95	1.05	10	500	35	300
1N6763, 1N6763R						
1N6764, 1N6764R						
1N6765, 1N6765R						

* Comments, suggestions, or questions on this document should be addressed to Defense Supply Center, Columbus, ATTN: DSCC-VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dscc.dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at http://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.




Dimensions				
Symbol	Inches		Millimeters	
	Min	Max	Min	Max
BL	.535	.545	13.59	13.84
CH	.249	.260	6.32	6.60
LD	.035	.045	0.89	1.14
LL	.510	.570	12.95	14.48
LO	.150 typ		3.81 typ	
LS	.150 bsc		3.81 bsc	
MHD	.139	.149	3.53	3.78
MHO	.665	.685	16.89	17.40
TL	.790	.800	20.07	20.32
TT	.040	.050	1.02	1.27
TW	.535	.545	13.59	13.84

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. All terminals are isolated from case.
4 In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.


SCHEMATIC

1N6762, 1N6763, 1N6764, 1N6765



Terminal	Description
1	Anode 1
2	Cathode
3	Anode 2

1N6762R, 1N6763R, 1N6764R, 1N6765R



Terminal	Description
1	Cathode 1
2	Anode
3	Cathode 2

* FIGURE 1. Physical dimensions and configuration (TO-254AA, isolated).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

* 2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

* 2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

* (Copies of these documents are available online at http://assist.daps.dla.mil/quicksearch/ or http://assist.daps.dla.mil. or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

3.4 Interface and physical dimensions. Interface and physical dimensions shall be as specified in MIL-PRF-19500, and on figure 1.

3.4.1 Lead finish. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Polarity. Polarity and terminal configuration shall be in accordance with figure 1 herein.

3.5 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I.

3.6 Electrical test requirements. The electrical test requirements shall be group A as specified herein.

3.7 Marking. Marking shall be in accordance with MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

3.8 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

* 4.2.1 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.

* 4.3 Screening (JANTX, JANTXV, and JANS levels). Screening shall be in accordance with table IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table IV of MIL-PRF-19500)	Measurement	
	JANS level	JANTX and JANTXV levels
(1) 3c	Thermal impedance (see 4.3.2)	Thermal impedance (see 4.3.2)
7a and 7b	Optional	Optional
9 and 10	Not applicable	Not applicable
11	I_{R1} and V_{F1}	I_{R1} and V_{F1}
12	See 4.3.1, t = 240 hours	See 4.3.1, t = 48 hours
13	Subgroups 2 and 3 of table I herein; V_{F1} and I_{R1}; $\Delta I_{R1} \leq$ 100 percent of initial value or ±2.5 μA, whichever is greater; $\Delta V_{F1} \leq$ ±100 mV.	Subgroup 2 of table I herein; V_{F1} and I_{R1}; $\Delta I_{R1} \leq$ 100 percent of initial value or ±2.5 μA whichever is greater; $\Delta V_{F1} \leq$ ±100 mV.
14a and 14b	Required	Required

(1) Thermal impedance shall be performed any time after temperature cycling, screen 3a, and does not need to be repeated in screening requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

4.3.1 Power burn-in conditions. Power burn-in conditions are as follows: Method 1038 of MIL-STD-750, test condition A. T_C = +125°C; V_R = 0.8 of rated V_{RWM} (see 1.3).

* 4.3.2 Thermal impedance The thermal impedance measurements shall be performed in accordance with method 3101 or 4081 of MIL-STD-750. The thermal impedance conditions and maximum thermal impedance limit shall be derived by each vendor. The chosen thermal impedance measurement and conditions for each device in the qualification lot shall be submitted in the qualification report and a thermal impedance curve shall be plotted (see table II, subgroup 4 herein). Measurement conditions shall be in accordance with 4.4.1.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500 and table I, subgroup 2 herein. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps of table III herein. The following test conditions shall be used for $Z_{\theta JX}$, group A inspection

a. I_M measure current ---------- 15 mA.

b. I_H forward heating current ---------- 10-50 A.

c. t_H heating time ---------- 200 ms.

d. t_{MD} measurement delay time ---------- 35 μs.

e. V_H heating voltage ---------- 1 V.

The maximum limit for $Z_{\theta JX}$ under these conditions are $Z_{\theta JX}$(max) = 1.8°C/W

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VIa (JANS) and table VIb (JANTX and JANTXV) of MIL-PRF-19500 and as follows. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps of table III herein.

4.4.2.1 Group B inspection, table VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B4	1037	I_F or I_O = 1.25 A to 10 A; ΔT_J = +85°C minimum, for 2,000 cycles minimum.

4.4.2.2 Group B inspection, table VIb (JANTX and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
B3	1037	I_F or I_O = 1.25 A to 10 A; ΔT_J = +85°C minimum, for 2,000 cycles minimum.
B5		Not applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VII of MIL-PRF-19500 and as follows. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps of table III herein.

* 4.4.3.1 Group C inspection, table VII of MIL-PRF-19500.

Subgroup	Method	Condition
C2	2036	Test condition A, 5 pounds, t = 15 seconds ±3 seconds.
C5	4081	See 4.4.5.
C6	1037	I_F or I_O = 1.25 A to 10 A; ΔT_J = +85°C minimum, for 6,000 cycles minimum.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table II herein. Electrical measurements (end-points) and delta requirements shall be in accordance with the applicable steps and footnotes of table III herein.

4.4.5 Thermal resistance. Thermal resistance measurements shall be performed in accordance with method 3101 of MIL-STD-750. The maximum limits for $R_{\theta jc}$(max) shall be 2.0°C/W for devices in the TO-254AA case style. Each diode leg shall be measured. The following parameter measurements shall apply:

a. I_M measure current ---------- 15 mA.

b. I_H forward heating current ---------- 10A - 50 A.

c. t_H heating time ---------- Steady-state (see method 3101 of MIL-STD-750).

d. t_{MD} measurement delay time ---------- 35 μs.

e. V_H heating voltage ---------- 1 V.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection. 1/ 2/

Inspection	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2						
Thermal impedance	3101	See 4.3.2	$Z_{\theta JX}$		1.8	°C/W
Breakdown voltage 1N6762, 1N6762R 1N6763, 1N6763R 1N6764, 1N6764R 1N6765, 1N6765R	4022	I_R = 10 µA dc, pulsed 3/	V_{BR}	 50 100 150 200		V dc
Forward voltage	4011	I_F = 6 A dc, pulsed 3/ I_F = 12 A dc, pulsed 3/	V_{F1} V_{F2}		0.95 1.05	V dc V dc
Reverse leakage current	4016	DC method; pulsed 3/ V_R = 0.8 of V_{RWM} (see 1.3)	I_{R1}		10	µA dc
Subgroup 3						
High temperature operation:		T_C = +100°C				
Reverse leakage Current	4016	DC method; pulsed 3/ V_R = 0.8 of V_{RWM} (see 1.3)	I_{R2}		500	µA dc
Low temperature operation:		T_A = -55°C				
Forward voltage	4011	I_F = 12 A dc, pulsed 3/	V_{F3}		1.25	V dc
Subgroup 4						
Scope display evaluation 4/	4023					
Reverse recovery time measurements	4031	Condition B1; I_F = 1.0 A, di/dt = 50 A/µs	t_{rr}		35	ns

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection – Continued. 1/ 2/

Inspection	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroups 5 and 6						
Not applicable						
Subgroup 7						
Junction capacitance	4001	V_R = 5 V dc; f = 1.0 MHz	C_J		300	pF

1/ For sampling plan, see MIL-PRF-19500.
2/ Each individual diode.
3/ Pulse test: Pulse width = 300 μs, duty cycle ≤ 2 percent.
4/ The reverse breakdown characteristics shall be viewed on an oscilloscope with display calibration factors of 50 to 100 μA/division and 50 to 100 V/division. Reverse current over the knee shall be at least 500 μA. Each device may exhibit a slightly rounded characteristic and any discontinuity or dynamic instability of the trace shall be cause for rejection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

* TABLE II. Group E inspection (all quality levels) for qualification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			22 devices c = 0
Thermal shock	1051	500 cycles	
Hermetic seal	1071		
Fine leak		Test condition H 5×10^{-7} atm cc/s	
Gross leak		Test condition C or K	
Electrical measurements		See table III herein, steps 1, 2, 3, and 5.	
Subgroup 2			22 devices c = 0
Steady-state reverse bias	1038	Test condition A t = 1,000 hours, T_C = +125°C V_R = 0.8 of rated V_{RWM} (see 1.3)	
Electrical measurements		See table III herein, steps 1 and 2	
Subgroup 4			
Thermal impedance curves 1/ 2/ 3/		Each supplier shall submit a thermal impedance ($Z_{\theta JX}$) histogram of the entire qualification lot. The histogram data shall be taken prior to the removal of devices that are atypical for thermal impedance. Thermal impedance curves (from $Z_{\theta JX}$ test pulse time to $R_{\theta JX}$ minimum steady-state time) of the best device in the qual lot and the worst device in the qual lot (that meets the supplier proposed screening limit), or from the thermal grouping, shall be submitted. The optimal test conditions and proposed initial thermal impedance screening limit shall be provided in the qualification report. Data indicating how the optimal test conditions were derived for $Z_{\theta JX}$ shall also be submitted. The proposed specification maximum thermal impedance curve shall be submitted. The qualifying activity may approve a different $Z_{\theta JX}$ limit not to exceed the specification's thermal curve for conformance inspection end-point measurements as applicable. Equivalent data, procedures, or statistical process control plans may be used for part, or all, of the above requirements.	

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

* TABLE II. Group E inspection (all quality levels) for qualification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 5 Not applicable			

1/ The approved thermal impedance conditions and limit for $Z_{\theta JX}$ shall be used by the supplier in screening and table I, subgroup 2.

2/ The approved thermal resistance conditions for $R_{\theta JX}$ shall be used by the supplier for conformance inspection.

3/ For product families with similar thermal characteristics based on the same physical and thermal die, package, and construction combination (thermal grouping), the supplier may use the same thermal impedance curves.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

TABLE III. Groups A, B, C, and E electrical and delta measurements. 1/ 2/ 3/ 4/

Step	Inspection	MIL-STD-750		Symbol	Limits		Unit
		Method	Conditions		Min	Max	
1	Forward voltage	4011	I_F = 12 A dc pulsed	V_{F2}		1.05	V dc
2	Reverse leakage current	4016	V_R = 80 percent rated V_R (see 1.3) DC method, pulsed	I_{R1}		10	μA dc
3	Forward voltage	4011	I_F = 12 A dc pulsed	ΔV_{F2}		±100 mV dc from initial reading	
4	Reverse leakage current	4016	V_R = 80 percent rated V_R (see 1.3) DC method, pulsed	ΔI_{R1}		100-percent of initial value or ±2.5 μA dc whichever is greater.	
5	Thermal impedance	3101	See 4.3.2	$Z_{\theta JX}$		1.80	°C/W

1/ The electrical measurements for table VIa (JANS) of MIL-PRF-19500 are as follows:
- a. Subgroup 3, see table III herein, steps 1 and 2.
- b. Subgroup 4, see table III herein, steps 1, 2, 3, 4, and 5.
- c. Subgroup 5, see table III herein, steps 1, 2, 3, and 4.

2/ The electrical measurements for table VIb (JANTX and JANTXV) of MIL-PRF-19500 are as follows:
- a. Subgroup 2, see table III herein, steps 1, 2, and 5.
- b. Subgroup 3, see table III herein, steps 1, 2, and 5.
- c. Subgroup 6, see table III herein, steps 1 and 2.

3/ The electrical measurements for table VII of MIL-PRF-19500 are as follows:
- a. Subgroup 2, see table III herein, steps 1, 2, and 5 for all levels.
- b. Subgroup 6, see table III herein, steps 1, 2, and 5 for all levels.

4/ The electrical measurements for table IX of MIL-PRF-19500 are as follows:
- a. Subgroup 1, see table III herein, steps 1, 2, 3, and 5.
- b. Subgroup 2, see table III herein, steps 1 and 2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

5. PACKAGING

* 5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

* 6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The notes specified in MIL-PRF-19500 are applicable to this specification.

* 6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

d. Product assurance level and type designator.

* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Defense Supply Center, Columbus, ATTN: DSCC/VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil.

6.4 Cross reference list. Parts covered by this specification may be used to replace the following commercial Part or Identifying Numbers (PIN):

Preferred types	Commercial types
JANTX1N6762, JANTX1N6762R JANTX1N6763, JANTX1N6763R JANTX1N6764, JANTX1N6764R JANTX1N6765, JANTX1N6765R	1N6762, 1N6762R 1N6763, 1N6763R 1N6764, 1N6764R 1N6765, 1N6765R
JANTXV1N6762, JANTXV1N6762R JANTXV1N6763, JANTXV1N6763R JANTXV1N6764, JANTXV1N6764R JANTXV1N6765, JANTXV1N6765R	1N6762, 1N6762R 1N6763, 1N6763R 1N6764, 1N6764R 1N6765, 1N6765R

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.

* 6.4 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians
Army - CR
Navy - EC
Air Force - 11
NASA - NA
DLA -CC

Preparing activity:
DLA - CC

(Project 5961-3004)

* NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:26Z
Check the source to verify that this is the current version before use.