MIL-C-19635 (CG)
14 September 1956
SUPERSEDING
CGS-27C-1
6 August 1952

MILITARY SPECIFICATION

CLOTH, COATED; NON-SLIP TABLE COVERING

1. SCOPE

1.1 Scope.- This specification covers flexible, nonslip table covering for use on mess tables aboard vessels during rough weather, to prevent or minimize slipping of dishes and other tableware ordinarily used.

1.2 Classification.-

1.2.1 Type and grade.- The material furnished under this specification shall be of one type and grade as hereinafter specified.

1.2.2 Color.- Unless otherwise specified, the color of the upper and under surfaces of the table covering shall be as specified in 3.5.

2. APPLICABLE DOCUMENTS

2.1 The following specification, or superseding document, of the issue in effect on the date of invitation for bids, forms a part of this specification:

FEDERAL

TT-C-595 - Colors; (for) Ready-Mixed Paints

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Standard sample.- Unless otherwise specified, the table covering shall be equal to the standard sample in all respects not specifically covered by this specification (see 6.4).

FED. SUP. CLASS
8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.

3.2 Material.-

3.2.1 Chemically-blown sponge rubber.- The chemically-blown sponge rubber furnished under this specification shall be of the best grade of natural or synthetic rubber alone, or compounded of a suitable combination thereof. It shall be of soft, flame-resistant quality, with an adhesive rind or surface, homogeneous in character and free from any defect which may affect its appearance or impair its serviceability.

3.2.2 Fabric backing.- The fabric backing shall be of coarse-fibered, open-meshed material, plain in weave, with approximately 10 threads to the warp and 16 threads to the filling per square inch. It shall be of the best quality and suitable for the purpose intended.

3.2.3 Neoprene finish.- The neoprene coating shall be of the highest quality, of .005 to .010 inches in thickness after application. Normally a 3-coat application is necessary to obtain the desired thickness.

3.3 Form and construction.- The under surface of the table covering shall consist of a layer of the chemically-blown sponge rubber. One fold of the fabric backing shall be firmly imbedded and keyed to the rubber layer, but shall not show through it at any point. The exposed side of the fabric backing shall be finished with neoprene coating to form the upper surface of the material. The neoprene coating shall be of such consistency as to permit the imprint of the backing fabric to show and produce a somewhat rough, slip-resistant effect.

3.4 Dimensions.- Unless otherwise specified in the invitations for bids, the table covering shall be not less than .065 or more than .095 inches in over-all thickness, and 54 inches wide, ± ½ inch. It shall be furnished in roll lengths of 40 to 50 yards, consisting of not more than 3 pieces per roll, of which no piece shall be shorter than 5 yards in length

3.5 Color.-

3.5.1 Upper surface.- Unless otherwise specified, the neoprene-coated upper surface of the material shall be of a green shade to match Color No. 1475 of Federal Specification TT-C-595, Colors; (for) Ready-Mixed Paints (see 6.2 and 6.4).

3.5.2 Under surface.- Unless otherwise specified, the color of the sponge rubber under surface of the material may be at the option of the manufacturer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.

3.6 Weight.- The weight of the product shall be 1.060 to 1.090 pounds per yard.

3.7 Odor.- The rubber materials shall be free from objectionable odors under ordinary service conditions.

3.8 Physical characteristics.- The primary physical characteristics of the table covering shall be durability, slip-resistance, washability, and ease of stowage.

3.8.1 Tensile strength.- The breaking strength of the material shall be not less than 25 pounds for a 1 by 5 inch sample, and may be measured on a Scott Tensile Tester, where such equipment is available, or in lieu thereof, the breaking strength shall be determined by the dead weight method described in 4.4.1.

3.8.2 Accelerated aging.- When aged as described in 4.4.2, the material shall not become sticky, nor crack when bent sharply back upon itself.

3.8.3 Fire-resistance.- The table covering, as delivered, shall be flame resistant when tested as described in 4.4.3.

3.8.4 Nonslip properties.-

3.8.4.1 Upper surface.- The neoprene surface shall be non-porous and shall have a continuous skin free from blow holes. It shall be sufficiently nonslip in character to hold tableware in place on a surface inclined at an angle of 35° (see 4.4.4).

3.8.4.2 Under surface.- The rubber under side of the material shall be capable of adhering to the surface of a table, or similar surface, without the use of clips or other devices, when the table or contact surface is inclined at an angle of 35° (see 4.4.4).

3.8.5 Washability.- The upper neoprene surface of the material shall be capable of being easily cleaned with soap, water and a bristle brush, of stains resulting from spilled coffee, ketchup, egg, butter and other commonly used foods (see 4.4.5).

3.8.6 Flexibility.- For purposes of stowage, the material shall be capable of being rolled or folded in any direction without cracking or delamination (see 4.4.6).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.

3.8.7 Delamination.- The table covering shall show no evidence of separation into distinct layers or laminations when subjected to normal usage, or when tested in accordance with 4.4.1, 4.4.2, 4.4.3, 4.4.5 and 4.4.6.

3.9 Workmanship.- The workmanship shall be first class in every respect. The finished product shall be free from cracks, bloom, blow holes, imbedded foreign material, and other physical defects which may detract from its appearance and serviceability.

4. SAMPLING, INSPECTION AND TEST PROCEDURES

4.1 Lot.- Unless otherwise specified, a lot shall consist of 10 rolls or a fraction thereof of the table covering of the same thickness, composition, and produced by the same procedures.

4.2 Sampling.-

4.2.1 Finished product.- One roll shall be taken at random from a lot. A piece not less than one-half (1/2) yard in length and the full width of the product shall be cut from the roll. The specimen shall be carefully rolled and transmitted to the contracting officer for inspection and tests. If satisfactory, the remainder of the roll may be included as part of the delivery.

4.2.2 Fabric backing.- A piece of the fabric backing one-half (1/2) yard in length and of full width, taken from that used in the lot manufacture, shall be transmitted with the sample described in 4.2.1.

4.3 Inspection.- Inspection may be made at any time at the point of production, or at the point of delivery (see 4.2.1). The material shall be inspected for workmanship, quality, dimensions, surfaces, color, packaging, packing and marking, to determine compliance with the requirements of this specification that do not require tests.

4.4 Tests.-

4.4.1 Tensile strength.- The tensile strength of a test specimen 5 inches long and 1 inch wide may be determined on a Scott Tensile Tester with a drive of 2 feet per minute, or in the absence of such equipment, it shall be determined by the dead weight method, as follows: On each end of the sample, place a clamp evenly and firmly gripping the material across

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.

the entire width. Suspend the sample by one clamp in a perpendicular position at sufficient height that it will swing free when a 25-pound weight is attached to the clamp at the lower end. After suspension for a 10-minute period, if the specimen shows no delamination, rupture, tears, or scaling, the material shall be considered as having met the requirements of 3.8.1.

4.4.2 Heat resistance.- A specimen of the material, approximately 12 by 18 inches, shall be placed in an oven maintained at a constant temperature of 200° F. for 2 hours. Immediately after the sample has been removed from the oven, it shall be examined for softening under the action of the heat. After the sample has cooled to room temperature, dishes and/or other tableware placed upon the material and left for a period of 5 minutes, shall not show any tendency to stick to the neoprene surface.

4.4.3 Fire resistance.- On a specimen of the table covering, six inches square, place a lighted cigarette and flaming wooden match, and permit each to remain until burned to ash. No flash or flame shall issue from the material during or after contact with the burning objects, nor shall the material show discolor by burn beyond the area exposed to flame. This factor shall be determined on the average of 3 tests.

4.4.4 Nonslip properties.- The factor of adhesiveness shall be determined for both surfaces of the material in the following manner: Place a sample of the material 18 by 24 inches on a standard steel- or wood-surfaced table. Place upon the specimen an assortment of dishes and tableware normally used, up to 10 pounds in weight. When the table is inclined to an angle of 35° , the under surface shall be sufficiently nonslip to adhere to the table top, and the upper surface of the covering sufficiently adhesive to retain the dishes and miscellaneous tableware in place.

4.4.5 Washability.- A spoonful each of such commonly used foods as coffee, ketchup, egg, butter, etc., shall be spilled on the upper surface of an 8 by 12 inch sample. Allow the food stains to stand for 1 hour before subjecting the material to the following test: Using water, a standard soap powder and a bristle brush, scrub the stained surface with moderate pressure for 75 double strokes. The sample shall then be examined for surface abrasion, softening, stains, streaking and loss of color.

4.4.6 Flexibility.- Double and press a specimen of the table covering, 6 inches square, flat on itself in any direction with the neoprene surface outside. After a weight of 50 pounds has rested on the folded edge for a period of 15 minutes, the material shall show no evidence of cracking, flaking or lifting from the fabric backing. This test shall be repeated by folding the neoprene surface inward and proceeding as before.

4.4.7 Fabric backing.- The sample of the fabric backing shall be visually inspected for general appearance and workmanship.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging.- Unless otherwise specified, the finished product shall be put up in roll lengths, each containing from 40 to 50 linear yards. Each roll shall consist of not more than 3 pieces, of which no piece shall be less than 5 yards in length, as specified in 3.4. The material shall be wound on cores or mandrels of at least 4 inches in diameter, or otherwise be adequately prepared against damage, in accordance with standard commercial practice.

5.2 Packing.- Unless otherwise specified, the table covering, prepared as described in 5.1, shall be packed in standard commercial containers of the type, size and kind commonly used for the purpose, so constructed as to insure acceptance by common or other carrier, for safe transportation at the lowest rate, to the point of delivery.

5.3 Marking.- Individual rolls shall be marked or labeled to indicate the name, color and quantity of the material, the manufacturer's name and lot number. Shipping containers shall be marked with the stock number(s), name, color and quantity of the material, number of this specification, manufacturer's name and lot number, number of the contract or purchase order, name and address of consignee, and the gross weight.

6. NOTES

6.1 Intended use.- The table covering is to be placed directly on standard mess tables during rough weather, to retain dishes and miscellaneous tableware in place without the use of fiddle boards. It is not intended to be used as a matting underlay for other types of table covers used in normal weather.

6.2 Ordering data.- Invitations for bids, contracts and purchase orders should contain the number and title of this specification, the stock number(s), the requirements as to color and yardage of the roll(s), and delivery point.

6.3 Bid samples.- Bid samples shall be submitted to the contracting officer. Samples, each of which shall consist of not less than 1 linear yard of the full width of the material, will be inspected for determining conformity to this specification.

6.4 Standard sample.- A standard sample of the table covering may be obtained from the contracting officer. There is no practical method of getting the color and surfaces desired, except that of having the material processed to match color and/or surfaces of a sample mutually agreed upon.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.

NOTICE.- When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights, or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Custodian:
U. S. Coast Guard

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

ORGANIZATION *(Of submitter)*	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2 COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4 REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE C-8278

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

COMMANTANT
U.S. COAST GUARD HEADQUARTERS
STATION 6-19
WASHINGTON, D.C. 20226

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T06:26Z
Check the source to verify that this is the current version before use.