A-A-1827
April 19, 1982

COMMERCIAL ITEM DESCRIPTION

PLASTIC SHEET, (POLYETHYLENE, HEAT SHRINKABLE)

The General Services Administration has authorized the use of this commercial item description in preference to Type IV of Federal Specification L-P-378.

This description covers biaxially and preferentially oriented, heat shrinkable polyethylene film.

Salient characteristics.

The film furnished under this description shall be flexible unsupported polyethylene film. Unless otherwise specified, the film shall be colorless and transparent. When specified, the film shall be treated to allow printing.

The film shall conform to the physical property requirements listed in table I.

TABLE I

Characteristics	Requirement		Test Method
Density	0.914 to 0.929 g/cm^3		ASTM D 1505
Tensile strength, minimum	Class 3	Class 4	ASTM D 882
Machine direction	1700 psi	1900 psi	
Transverse direction	1700 psi	1700 psi	
Ultimate elongation, minimum			
Machine direction	225%	300%	ASTM D 882
Transverse direction	350%	350%	
Heat seal strength, minimum	1500 psi	1500 psi	ASTM D 882
Film shrinkage, minimum			ASTM D 2732
Machine direction	30%	40%	
Transverse direction	30%	10%	

The issue of the ASTM standards in effect on the date of the solicitation shall be used to determine compliance with these requirements.

The film thickness shall be as specified plus or minus 10 percent. The length and width of the film shall be as specified. The tolerance for dimensions up to 30 inches shall be plus or minus 3/16 inches. For dimensions 30 to 50 inches, the tolerance shall be plus or minus 3/8 inch, and for dimensions 50 to 60 inches, the tolerance shall be plus or minus 1/2 inch. For dimensions 60 to 120 inches, the tolerance shall be plus or minus 3/4 inch. For widths greater than 120 inches, the tolerance shall be plus or minus 1/8 inch per foot of width.

Roll length shall be not less than specified. Rolls of film shall be furnished on cores having a length equal to or up to 1 inch longer than the actual width or folded width of the film. Cores shall have an inside diameter of not less than 1-1/2 nor more than 6-1/4 inches.

Workmanship. The film shall be uniform in color, texture, and finish and shall be as free from gels, fish eyes, unmelted material and foreign material as commercially possible. The material shall be free of holes, tears, cracks, blistering, or mottling.

Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:17Z
Check the source to verify that this is the current version before use.

Preservation, packaging, packing, labeling, and marking. Preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

Note: Purchasers should specify sheet or roll, dimensions, class, finish and color, if required.

ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

MILITARY INTEREST:

Custodians

Army - GL
Navy - SA
Air Force - 69

Review Activities

Army - AR, CR, MD
Air Force - 69

User Activity

Navy - MC

PREPARING ACTIVITY

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:17Z
Check the source to verify that this is the current version before use.