GGG-H-131c
INTERIM AMENDMENT-5
October 31, 1966
SUPERSEDING
INTERIM AMENDMENT-4
September 26, 1963

FEDERAL SPECIFICATION

HATCHET (CLAW, HALF, LATHING, BROAD AND BARREL)

This Interim Amendment was developed by the General Services Administration, Federal Supply Service, Standardization Division, Washington, D. C. 20406, based upon currently technical available information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized Federal Agencies to use this Interim Amendment as a valid exception to Federal Specification GGG-H-131c dated May 31, 1957 and Amendment-3 dated January 11, 1962.

PAGE 1

Paragraph 2.1: Delete: "PPP-P-31 - Preservation, Packaging, Packing and Marking of Material; and Shipping Instructions (Domestic Shipment and Storage)". "Fed. Std. No. 102 - Preservation, Packaging, and Packing Levels." and "MIL-P-15424 - Packaging of Hand Tools for Domestic and Overseas Shipment and Storage."

Add: "Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies).", "Fed. Test Method Std. No. 151 - Metals; Test Methods." and "MIL-H-15424 - Hand Tools, Packaging of."

PAGE 3

Paragraph 3.3.5, add at the end of paragraph: "At the option of the manufacturer, handles need not be marked, as specified in 3.8 of MM-H-93 and may be secured and bonded to the head by means of a chemical adhesive that will prevent the handle from loosening under any normal working conditions. Hatchets having such chemical adhesive shall be subjected to the pull apart test specified in 4.4.4

PAGE 4

Paragraph 3.9, delete the 2nd sentence and substitute the following: "The near side of the head shall have a beveled slot suitable for drawing nails except that the slot need not be beveled on blades that are less than 3/16 inch thick in the area immediately adjacent to the slot."

PAGE 5

Delete Section 4 in its entirety and substitute the following: "4. QUALITY ASSURANCE PROVISIONS 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection of materials and components. In accordance with 4.1 above, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified herein or, if none, in accordance with this specification.

4.2 Sampling procedures. Sampling procedures shall be in accordance with MIL-STD-105. Data for sampling shall be as indicated in table VI.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:37Z
Check the source to verify that this is the current version before use.

Table VI. Sampling Data

Category	Sample Unit	Inspection Level	Acceptable Quality Level	AQL Expressed In Terms of	Reference
Visual examination	1 ea.	II	4.0	Defects per hundred units	Paragraph 4.3.1
Dimensional examination	1 ea.	II	4.0	Same	Paragraph 4.3.2
Testing	1 ea.	S-3	1.5	Same	Paragraph 4.4
Preparation for delivery	One Container	S-2	4.0	Same	Paragraph 4.5

4.3 Examination.

4.3.1 Visual examination. Each sample unit shall be examined for any nonconformance as set forth in Table VII.

Table VII. Classification of Defects

Examine	Defect
Finish	Indication of rust
	Not painted where specified
	Area of no film
	Touch-up not neat, affecting appearance
	Texture of natural metal finish not as specified
	Rot, mineral stains, splits, fractures, bird peck, shanks, cross grain or knots in handles
Design	Not type or size specified
Construction and Workmanship	Loose or not in proper alignment
	Burrs, pits, nodules, splits, fractures or other detrimental defects
	Sharp edges, other than cutting edge, that may be injurious
	Operation omitted or not properly performed
Marking	Missing, incomplete, not legible

4.3.2 Dimensional examination. Each sample unit shall be examined for any nonconformance with dimensional requirements.

4.4 Testing. Each sample unit shall be tested in accordance with 4.4.1 thru 4.4.4.

4.4.1 Hardness Test. Sufficient grinding shall be done on the areas to be tested to insure all carburization is removed and that the areas are parallel to insure proper readings. The test shall be in accordance with the applicable requirements of Method 243.1 of Federal Test Method Standard Number 151. At least two hardness readings shall be taken on the specified portion or portions of each sample and the values thus obtained shall comply to the requirements of 3.3.1, 3.3.2, 3.3.3 and 3.7.

4.4.2 Practical cutting test. Chips shall be easily cut from hardwood by striking approximately 10 heavy blows with each sample hatchet. After being tested, the samples shall show no evidence of chipping, dulling, or turning over of the cutting edges, loosening of handle or wedges, or any other damage that indicates inferior material or workmanship.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:37Z
Check the source to verify that this is the current version before use.

4.4.3 Practical nail-drawing test (type B). At least 18 nails, 3 each of small, medium, and large sizes, of both headless and headed nails, shall be drawn from hardwood with each sample of type B claw hatchet. For purposes of this test, the nails shall not extend above the wood surface more than 1/32 inch. After drawing the nails, the samples shall show no evidence of damage of any nature.

4.5 Inspection of preparation for delivery requirements. An inspection shall be made to determine that the preservation, packaging, packing, and marking comply with the requirements in section 5 of this specification. Defects shall be scored in accordance with table VIII. For examination of interior packaging the sample unit shall be one shipping container fully prepared for delivery, selected at random just prior to the closing operations. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot.

Table VIII. Classification of preparation for delivery defects.

Examine	Defects
Markings (exterior and interior)	Omitted; incorrect; illegible; improper size; location, sequence, or method of application.
Materials	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, inadequate stapling. Distortion of container.
Contents (exterior and interior container)	Number per container is more or less than required. Net weight exceeds requirements.

PAGE 6

Delete Section 5 in its entirety and substitute the following:

"5. PREPARATION FOR DELIVERY

5.1 Preservation, packaging, and packing. Unless otherwise specified (see 6.2) the hatchets shall be preserved, packaged, and packed in accordance with MIL-H-15424. The level of preservation and packaging shall be A or C and the level of packing A, B, or C as specified (6.2).

5.2 Marking.

5.2.1 Civil agencies. In addition to markings required by the contract or order, the shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.2.2 Military activities. In addition to markings required by the contract or order, the shipping containers shall be marked in accordance with MIL-STD-129."

PAGE 7

Delete Section 6.5 and the notice that follows in their entireties.

Delete Military Interest and substitute:

"Military Custodians:
Army - GL
Navy -SHIPS
Air Force - MOA"

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:37Z
Check the source to verify that this is the current version before use.