GGG-H-142e
INTERIM AMENDMENT - 2(NAVY-Ships)
November 14, 1967

SUPERSEDING 1/
INTERIM AMENDMENT - 1(NAVY-Ships)
September 13, 1967

INTERIM AMENDMENT TO FEDERAL SPECIFICATION

HELMET, CONSTRUCTION WORKER'S

(This interim amendment was developed by the Department of the Navy, Naval Ship Engineering Center, Washington, D. C. 20360, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to Federal Specification GG-H-142e.)

Page 3, paragraph 3.4.2.3: Add at end of paragraph "nor more than 3/4 inch."

Page 4, paragraph 3.6.2: Delete and substitute:

"3.6.2 Impact resistance. When tested in accordance with 4.5.3, helmets shall not transmit an average force of more than 850 pounds. Individual specimens shall not transmit a force greater than 1,000 pounds. Disengagement of, deformation of, or damage to any component which shall permit the helmet shell to contact the standard head form (test block) or crown straps (suspension) on impact, shall be cause for rejection of the lot represented by the sample."

Page 4, paragraph 3.6.5, lines 1 and 2: Delete "shall not ignite in less than 5 seconds and".

Page 5, paragraph 4.2.1, line 1: Delete "Thirty-six" and substitute "Eighteen".

1/ CHANGES FROM PREVIOUS ISSUE. THE OUTSIDE MARGINS OF THIS DOCUMENT HAVE BEEN MARKED "#" TO INDICATE WHERE CHANGES (DELETIONS, ADDITIONS, ETC.) FROM THE PREVIOUS ISSUE HAVE BEEN MADE. THIS HAS BEEN DONE AS A CONVENIENCE ONLY AND THE GOVERNMENT ASSUMES NO LIABILITY WHATSOEVER FOR ANY INACCURACIES IN THESE NOTATIONS. BIDDERS AND CONTRACTORS ARE CAUTIONED TO EVALUATE THE REQUIREMENTS OF THIS DOCUMENT BASED ON THE ENTIRE CONTENT AS WRITTEN IRRESPECTIVE OF THE MARGINAL NOTATIONS AND RELATIONSHIP TO THE LAST PREVIOUS ISSUE.

FSC 8415

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:38Z
Check the source to verify that this is the current version before use.

Page 7, paragraph 4.5.1: Delete and substitute:

"4.5.1 Preparation of samples. Where it is evident that the sample helmets under test have a protective coating over the basic material, the entire exterior surface of the shell shall be abraded until the basic material is exposed using number 60-grit garnet paper. All samples (including helmets without a protective coating); shall be conditioned in an oven for 96 hours at 50° ± 2°C., then exposed for 40 hours in an atmosphere having 50 ± 2 percent relative humidity and a temperature of 25° ± 2°C. The samples shall then be subjected to the applicable tests specified in 4.5.2 through 4.5.5."

Page 8, paragraph 4.5.3.1: Add the following as subparagraph (e):

"(e) A small quantity of soft putty or a sheet of carbon paper affixed to the top of the test block or suspension shall be used to determine if contact has been made on impact."

Page 11, paragraph 4.5.6.3, line 6: Delete "logitudinal" and substitute "longitudinal."

Page 11, paragraph 4.5.6.3: Delete the last three sentences and substitute: "Upon ignition of specimen, lamp or burner shall be extinquished and burning rate of specimen recorded with a stop watch. (If the specimen does not ignite within one minute, it shall be judged as nonflammable.)"

Page 11, paragraph 4.5.6.4, line 1: Delete "ignition time reported and the".

Page 11, paragraph 4.5.8, line 3: After the word "size" insert "(7-1/2)"; last line of formula, delete "maximum size)."

Preparing activity:
Navy - SH
(Project 8415-N028)

Source: https://assist.dla.mil - Downloaded: 2026-10-26T12:38Z
Check the source to verify that this is the current version before use.