INTERIM AMENDMENT
TO
FEDERAL SPECIFICATION

STONE, ARCHITECTURAL, CAST

This Interim Amendment was developed by the General Services Administration, Federal Supply Service, Washington, D. C., 20406, based upon currently available technical information. It is recommended that Federal Agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized Federal Agencies to use this Interim Amendment as a valid exception to Federal Specification SS-S-721c, dated November 18, 1964.

PAGE 3

Paragraph 3.8.1, 3.8.2, and 3.8.3 - delete and substitute:

3.8.1 Cold water. After immersion in 21°C water in accordance with 4.4.3.1, the average absorption of water by stone castings shall be less than 5 percent by weight.

3.8.2 Boiling water. After immersion in boiling water in accordance with 4.4.3.1, the average absorption of water by stone castings shall be less than 10 percent by weight.

3.8.3 Absorption ratio. If the total absorption after boiling is greater than 6 percent, the ratio of the percent absorption of cold water, determined in accordance with 4.4.3.2, to the percent absorption of hot water, determined in accordance with 4.4.3.3, shall be less than 0.80.

PAGE 5

Paragraph 6.3 - delete in its entirety.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:13Z
Check the source to verify that this is the current version before use.