MIL-G-46898(MI)
19 April 1974
SUPERSEDING
MIS-15739
2 December 1965

MILITARY SPECIFICATION

GASKETING, RF AND PRESSURE

This specification is approved for use by all departments and agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for a flat gasketing made of chloroprene rubber imbedded in aluminum wire cloth, which provides radio frequency energy attenuation and pressure sealing.

2. APPLICABLE DOCUMENTS

2.1 Government documents. The following documents of the issue in effect on the date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

STANDARD

Military

MIL-STD-129	Marking for Shipment and Storage

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated the issue in effect on date of invitation for bids or request for proposal shall apply:

FSC 5330

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:12Z
Check the source to verify that this is the current version before use.

Society of Automotive Engineers
Aeronautical Material Specifications

AMS 3222	Synthetic Rubber, Hot Oil Resistant, High Swell (45-55)
AMS 4182	Aluminum Alloy Wire 5 Mg -0.12 Mn -0.12 Cr (56S-0)

(Application for copies should be addressed to the Society of Automotive Engineers, Inc., Department 010, Two Pennsylvania Plaza, New York, New York 10001.)

Uniform Classification Committee

Uniform Freight Classification Rules

(Application for copies should be addressed to Uniform Classification Committee, 202 Chicago Union Station, Chicago, Illinois, 60606.)

American Trucking Association Publication

National Motor Freight Classification Rules and Container Regulations

(Application for copies should be addressed to the National Classification Board, 1424 Sixteenth Street, N.W., Washington D.C. 20013.)

Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

3. REQUIREMENTS

3.1 Preproduction sample. When specified by the procuring activity (see 6.2) a preproduction sample shall be prepared using the same methods proposed for subsequent production, and shall be subjected to preproduction inspection (see 4.3).

3.2 General. The material shall consist of woven wire cloth into which rubber is embedded. The surfaces of the material shall be ground smooth to give maximum electrical contact area.

3.3 Wire cloth.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:12Z
Check the source to verify that this is the current version before use.

3.3.1 Specifications. The wire cloth shall be made from .0045 inch diameter aluminum wire meeting the requirements of specification AMS 4182.

3.3.2 Mesh. The wire shall be woven to form a 24 mesh cloth.

3.4 Rubber. The rubber shall be chloroprene rubber conforming with the requirements of AMS 3222.

3.5 Dimensions and tolerances.

3.5.1 Thickness. The thickness of the material shall be .020 plus or minus .004 inch.

3.5.2 Width. The width shall be 8 plus 0.25 inches, minus 0.00 inches.

3.5.3 Length. Length shall be as specified in the procurement document.

3.6 Product identification.

3.6.1 Information to be shown. Unless otherwise specified in the procuring document, each separate sheet and strip of material shall have a tag attached showing the following:

a. The number of this specification.

b. Vendor's name or code.

c. Manufacturer's material designation.

d. Date of manufacture (year and quarter).

3.6.2 Marking. Marking shall be in accordance with the requirements of MIL-STD-129.

3.7 Workmanship. The material shall be of high quality and uniformity and shall be free of foreign matter, cuts and holes. Workmanship shall be such as to ensure a product which is in conformance with this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:12Z
Check the source to verify that this is the current version before use.

perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification and tests. The testing of the material shall be classified as follows:

4.2.1 Preproduction inspection. Preproduction inspection see 4.3.

4.2.2 Quality conformance inspection. Quality conformance inspection see 4.4.1.

4.3 Preproduction inspection. Preproduction inspection shall consist of all examinations and tests specified herein and shall be conducted only on preproduction samples. The preproduction samples shall be prepared using the same methods to be used for the manufacture of all subsequent production material.

4.4 Quality conformance inspection.

4.4.1 Inspection tests. Quality conformance inspection tests shall be the examinations and tests required for each production lot. A production lot shall consist of finished material made on any single day by one shift.

4.4.2 Sampling. Two 8 x 12 inch samples of product shall be selected at random from each lot of material. Single test specimens shall be made from each of the two samples selected for subsequent testing in duplicate.

4.4.3 Conformance tests. Quality conformance tests shall include checking dimensions (3.5.1), workmanship (3.7) and surface appearance compared with an approved sample on file at receiving inspection. Failure of any tests shall be cause for rejection of the material.

4.5 Test methods. In order to determine conformance with the requirements of 3.3 and 3.4 the appropriate tests in AMS 4182 and AMS 3222 shall be used.

5. PREPARATION FOR DELIVERY

5.1 Packaging and packing. Unless otherwise specified, packaging and packing shall be Level C.

5.1.1 Level C Packaging. Material shall be packaged without folding to afford adequate protection against deterioration and damage during shipment from the supply source to the first receiving activity (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:12Z
Check the source to verify that this is the current version before use.

5.1.1 Level C Packing. Packages shall be secured and packed in shipping containers in a manner to insure carrier acceptance and safe delivery to destination at the lowest transportation rate. Containers shall comply with Uniform Freight Classification Rules or National Motor Freight Rules as applicable.

5.2 Marking. Marking shall be in accordance with MIL-STD-129 and shall include but shall not necessarily be limited to the following:

a. The number of this specification.

b. Vendor's name.

c. Manufacturer's material designation.

d. Quantity and dimensions.

e. Contract or procurement document number.

6. NOTES

6.1 Intended use. This material is intended for use as a combination RF and pressure seal gasketing.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification.

b. Whether preproduction samples and test reports are required.

c. Special packaging and packing instructions, if required.

d. Other special instructions.

6.3 Standard test method. Due to the lack of a standard test method for determining RF energy attenuation properties, there are no such requirements in this specification. It is therefore recommended that the material be tested in the equipment where it is to be used to assure that it is satisfactory.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:12Z
Check the source to verify that this is the current version before use.

6.4 Rubber hardness. It is recommended that the rubber in the material be examined after the material is in excess of five years of age, according to the date of manufacture. If the rubber is within the hardness limits and shows no evidence of surface cracks on folding, it is suggested that it be considered satisfactory for use.

6.5 Supersession data. This specification includes the requirements of Missile Interim Specification MIS-15739, dated 2 December 1965.

Custodian:
Army-MI

Preparing Activity:
Army-MI
Project No. 5330-A048

☆U.S. GOVERNMENT PRINTING OFFICE: 1974-713-153/5100

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:12Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

[ ] DIRECT GOVERNMENT CONTRACT [ ] SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 68 WHICH MAY BE USED S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:12Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID

DOD-314

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander
US Army Missile Command
ATTN: AMSMI-RCS
Redstone Arsenal, AL 35809

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:12Z
Check the source to verify that this is the current version before use.