MIL-G-46905A(MU)
Amendment 2
22 March 1973
SUPERSEDING
MIL-G-46905A(MU)
Amendment 1
16 February 1970

MILITARY SPECIFICATION

GROMMETS, PLASTIC, FILAMENT WOUND
(FOR SEPARATE LOADED PROJECTILES)

This Amendment forms a part of Military Specification MIL-G-46905A(MU), dated 2 March 1967.

Section 2, Publications, Army: Add "9240898 and 9240899".

Section 4: delete para. 4.3.1 and sub:

"4.3.1 Lot formation.-The term "inspection lot" as used in this specification is defined as an essentially homogeneous collection of units of product from which a representative sample is drawn and inspected to determine conformance with applicable requirements. The sample selected shall represent only that quantitiy of units from which the sample was drawn and shall not be construed to represent any prior or subsequent quantities presented for inspection. Homogeneity shall be considered to exist provided the inspection lot has been produced by one manufacturer, in one unchanged process, in accordance with the same drawing, same drawing revision, same specification and same specification revision and complies with the provisions for submission of product as specified in MIL-STD-105. Changes to the process, specification, or drawing not affecting safety, performance, interchangeability, or storage, as determined by the Government, shall not be deemed to alter the homogeneity of an inspection lot. All material submitted for inspection in accordance with this specification shall comply with the homogeneity criteria specified herein regardless of the type of sampling procedure which is being applied to determine conformance with requirements. Lot numbering, as required, shall be in accordance with MIL-STD-1168."

Paragraph 4.4.3: Add after 7031A "or 7031E."

Add "4.4.4 Resin Content.-The resin content shall be determined on two specimens from each of five grommets (not including the inserts) in accordance with FED-STD-406 Method 7061."

Section 6, Paragraph 6.4: Add "9240898-Grommet, for Shell,

FSC: 8140

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:13Z
Check the source to verify that this is the current version before use.

M499, XM483 (155MM).

9240899 - Grommet Assembly for Projectile, 8 Inch: HE, XM509"

Paragraph 6.5: Add

	Parts by Weight
"a. Material	
Resin - Laminac 4103-4	100.0
Catalyst - USP 245	0.5
Pigment - Olive Drab	2.0

	Parts by Weight
b. Material	
Resin - PE 654A	100.0
Catalyst - MEK Peroxide	0.5 to 1.0

*At the lower range of MEK Peroxide addition of 1 part benzoyl peroxide is permissible to increase Barcol hardness.)

Promoter - Cobalt Napthanate	0.5 to 0.2
Pigments - Olive Drab	2.0

	Parts by Weight
*c. Material	
Resin - Polylite 31-549	100.0
Catalyst - USP 256	1.0
Pigment	2.2

	Parts by Weight
*d. Material	
CoRezyn 1045-32 (Includes cobalt naphthenate and styrene content of 35-40%)	100.0
Pigment, Olive Drab	1.0
Catalyst, Lupersol 256	5.05"

*Asterisk indicates changes in addition to or differing from those of Amendment 1.

Custodian:
Army-MU

Preparing Activity
Army-MU

Project Number: 8140-A101

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:13Z
Check the source to verify that this is the current version before use.