INCH-POUND

MIL-B-18184C(MC)
31 October 1989
SUPERSEDING
MIL-B-18184B(MC)
7 May 1971

MILITARY SPECIFICATION

BELT, COAT, MAN'S: WEBBING, COTTON, WHITE

This specification is approved for use within the U. S. Marine Corps, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers requirements for one type of web belt.

1.2 Classification. The belts shall be the following length.

50 inches

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

UU-P-268 - Paper, Kraft, Wrapping

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to the Commanding General (PSE-C), Marine Corps Research, Development, and Acquisition Command, Washington, DC 20380, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document of by letter.

AMSC N/A

FSC 8440

Distribution Statement A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-W-530	- Webbing, Textile, Cotton, General Purpose, Natural or In Colors.
MIL-B-17757	- Box, Shipping Fiberboard (Modular Sizes).
MIL-B-20269	- Buckle, (Insignia and Plain).

STANDARDS

FEDERAL

FED-STD-191	- Textile Test Methods.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.
MIL-STD-147	- Palletized Unit Loads
MIL-STD-731	- Quality of Wood Members for Containers and Pallets

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Navy Publications and Forms Center (ATTN: NPODS), 5801 Tabor Avenue, Philadelphia, PA 19120-5099.)

2.1.2 Other Government documents and publications. The following other Government documents and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

Laws and Regulations

U. S. Postal Service Manual

(Copies of the manual may be obtained from the Superintendent of Documents, U. S. Government Printing Office, Washington, DC 20402.)

2.2 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation (see 6.2).

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification Rules

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Association, Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for related associated detail specifications, specification sheets or MS standards), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Standard samples. Standard samples are furnished solely for guidance and information to the contractor (see 6.4). Variation from this specification may appear in the standard sample, in which case the specification shall govern.

3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection and approval (see 4.4 and 6.3).

3.3 Material

3.3.1 Webbing, textile, cotton or cotton/polyester. The webbing shall be 1-3/4 inches, +1/16, -1/32 inches wide, bleached white and shall conform to type V, class 2, of MIL-W-530 or the following cotton/polyester webbing woven by the needle-loom construction method may be used: Weight - 2.50 ounces per linear yard, .120 ± .0156 inches thick, 1000 pounds breaking strength and the following:

Ground Warp	238 ends	12/3 K.P. Cotton
Binder	38 ends	20/2 Spun Polyester
Stuffer	117 ends	9/4 K.P. Cotton
Filling	40 Picks/inch	630 D. Polyester Monofilament
Catch Thread	1 end	210 D. Multi-filament Nylon
Lock Stitch	1 end	210 D. Multi-filament Nylon

3.4 Construction. The webbing for the belts shall be cut into the required length (see 1.2). The ends of the belt shall remain unfinished.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise speci-

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

fied in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.4)
b. Quality conformance inspection (see 4.5)

4.3 Inspection conditions. Unless otherwise specified, all inspections shall be performed in accordance with the test conditions specified in MIL-STD-105.

4.4 First article inspection. When a first article is required (see 3.2 and 6.3), it shall be examined for the defects specified in 4.5.3.1 and 4.5.3.2. The presence of any defect may be cause for rejection of the first article. The number of units to be inspected shall be specified by the contracting officer.

4.5 Quality conformance inspection.

4.5.1 Component and material testing. In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards, unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents. The method of testing shall be as specified in FED-STD-191, wherever applicable. All test reports shall contain the individual values used in expressing the final result. The lot shall be unacceptable if one or more sample units fail to meet any of the test requirements specified. The lot size and sample size shall be in accordance with the following:

Lot Size (lot unit)	Sample Size (sample unit)
800 or less	2
801 to 22,000 inclusive	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

4.5.2 In-process inspection. Inspection shall be made at any point or during any phase of the manufacturing process to determine whether operations or assemblies are accomplished as specified herein. The Government reserves the right to exclude from consideration for acceptance any material for which in-process inspection has indicated nonconformance.

4.5.3 Examination of the end item. The defects found during examination shall be classified in accordance with the list shown in 4.5.3.1 and 4.5.3.2. The sample unit for these examinations shall be one belt. The inspection level shall be S-1 (see 6.5).

4.5.3.1 General defects. General defects shall be as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT	CLASSIFICATION		
		MAJOR	MINOR	
			A	B
Webbing (both sides)	Any hole, cut or tear.	101		
	Weak or soft spot.	102		
	Multiple floats, affecting serviceability.	103		
	Multiple or single floats, affecting appearance.		201	
	Large weakening slub: - affecting serviceability. - affecting appearance.	104	202	
	Broken or missing end or picks: - two or more contiguous. - single.	105	203	
	Heavy filling bar or heavy places.		204	
	Fine or light filling bar: - affecting serviceability. - affecting appearance.	106	205	
	Poorly constructed, i.e., not firmly and tightly woven.	107		
	Knot on surfaces or edges. *Knots will be scored only when they exceed the limits on Sears Defect Scale "D" for knots, or when they are in excess of 1/16 inch diameter.		206	
	Slack or tight end or ends, affecting appearance.		207	
Edges	Cut, frayed or scalloped.	108		
	Slack or poorly constructed.	109		
	Grease or oil stains clearly noticeable.	110		
	Small spots or dirt marks: - seriously affecting appearance. - affecting appearance but not seriously.	111	208	

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

4.5.3.2 Examination of belts for dimensions. Belts shall be examined for dimensional defects as listed below. The inspection level shall be S-3 (see 6.5).

Examine	Defect
Overall Length of Webbing (cut length)	Under or over length specified in 1.2 by more than 1/2 inch.
Width of Webbing	Over the width specified in 3.3.1 by more than 1/16 inch or under by more than 1/32 inch.

4.5.4 Examination of preparation for delivery requirements. An examination shall be made to determine compliance with packaging, packing and marking requirements as specified in Section 5. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 (see 6.5).

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence or method of application.
Materials	Any component missing. Any component damaged, affecting serviceability.
Workmanship	Inadequate application of components, such as incomplete closure of case liner, container flaps; loose strapping, and inadequate stapling. Bulging or distortion of containers.
Content	Number of belts per shipping containers is more or less than required. Improper number of intermediate packages per container. For this defect, one intermediate package from each container in the sample be examined.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

4.5.5 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection-level shall be S-1 (see 6.5).

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

5. PACKAGING

5.1 Packaging. Packaging shall be level A or commercial, as specified (see 6.2).

5.1.1 Level A

5.1.1.1 Unit packaging. One belt shall be placed in a polyethylene bag of adequate dimension with a 1-inch lip at the open end if tuck in bag is used or a heat sealed bag without the 1-inch lip may be used. Excess air shall be expelled from the heat sealed bag prior to sealing. Each bag shall contain a label (see 5.3). The polyethylene film shall be 0.0015 inch thick.

5.1.1.2 Intermediate packaging. Ten belts shall be put up in bundles securely tied with twine or tape.

5.1.2 Commercial packaging. The belts shall be packaged in accordance with manufacturer's normal practice.

5.2 Packing. Packing shall be level A, B or commercial as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Method 1. Twelve (12) bundles (120 belts), packaged as specified in 5.1, shall be packed in a fiberboard shipping container conforming to class weather-resistant grade V2s, size 2A of MIL-B-17757. The contents of

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

the container shall be completely covered on top and bottom with a sheet of 60-pound minimum basis-weight kraft paper conforming to grade B of UU-P-268. Each shipping container shall be assembled, closed, and reinforced as specified in the appendix to the box specification.

5.2.1.2 Method 2. When specified (see 6.2), six level B shipping containers (720) shall be overpacked in a fiberboard shipping container conforming to class weather resistant, size 4, of MIL-B-17757, reinforced as specified in the appendix to the box specification.

5.2.2 Level B. Twelve (12) bundles (120 belts), packaged as specified in 5.1, shall be packed in a fiberboard shipping container conforming to class-domestic, size 2A of MIL-B-17757. The fiberboard used for fabricating the container and the liner shall be grade 275 and 200 respectively. The contents of the container shall be completely covered on top and bottom with a sheet of 60-pound minimum basis-weight kraft paper conforming to grade B of UU-P-268. Each shipping container shall be assembled and closed as specified in the appendix to the box specification.

5.2.3 Commercial. Belts shall be packed in a manner to insure carrier acceptance and safe delivery at destination. Containers shall be in accordance with Uniform Freight Classification Rules or regulations of other carriers applicable to the mode of transportation.

5.3 Marking. In addition to any special marking required by the contract or order, the intermediate packages and shipping containers shall be marked in accordance with the requirements of MIL-STD-129. A white paper label with the following information legibly printed or stamped thereon in black shall be inserted within each polyethylene bag in order to permit ready identification:

Nomenclature
Size _____ Stock number _____
Contract number
Contractor

5.4 Palletization. When specified (see 6.2), belts packed as specified in 5.2 shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. If the container is of a size which does does conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The belts described herein are intended for wear with buckles specified in MIL-B-20269 by enlisted male personnel with the dress blue uniform.

6.2 Acquisition requirements. Acquisition documents should specify the following:

(a) Title, number and date of this specification.
(b) When first article is required and the number of units for the first article (see 3.2).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(d) When level A, method 2, packing is required (see 5.2.1.2).
(e) When palletization is required (see 5.4).
(f) Acceptance criteria required (see 6.5).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Sample. For access to samples, address the contracting activity issuing the invitation for bids or request for proposal.

6.5 Acceptance criteria. The acceptance criteria below are recommended for use. The acceptance criteria as specified in the contract or purchase order shall be binding. Unless otherwise specified, the following acceptance criteria are in accordance with MIL-STD-105.

6.5.1 For end item visual examination. An acceptance quality level (AQL), expressed in terms of defects per hundred units, of 2.5 for major defects and 6.5 for total (major and minor combined) defects is recommended.

6.5.2 For end item dimensional examination. An AQL, expressed in terms of defects per hundred units, of 10 is recommended.

6.5.3 For packaging examination. An AQL, expressed in terms of defects per hundred units, of 2.5 is recommended.

6.5.4 For palletization examination. An AQL, expressed in terms of defects per hundred units, of 6.5 is recommended.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.

6.6 Subject term (key word) listing.

Enlisted
Dress blue
Male

6.7 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Preparing Activity
Navy - MC
Project No. 8455-N185

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T11:05Z
Check the source to verify that this is the current version before use.