HH-C-571C
October 17, 1969
SUPERSEDING
Fed. Spec. HH-C-571B
June 23, 1964

FEDERAL SPECIFICATION

CORK, GRANULATED

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers granulated cork.

1.2 Classification. Cork shall be of the following sizes, as specified (see 6.2):

Size A	–	1/2 inch to No. 8
Size B	–	No. 8 to No. 20
Size C	–	No. 20 to No. 40

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

Federal Specifications:

UU-S-48 - Sacks, Shipping, Paper.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies).

FSC 5640

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other Federal Specifications required by activites outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-147 - Palletized and Containerized Unit Loads, 40" x 48" 4-Way (Partial) Pallet Skids, Runners, or Pallet-Type Base.

(Copies of Military Specifications and Standards required by contractors in connection with specification procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Uniform Classification Committee:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, 202 Union Station, 516 West Jackson Boulevard, Chicago, Illinois 60606.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

National Classification Board:

National Motor Freight Classification.

(Application for copies should be addressed to the National Classification Board, Association, Inc., 1616 P Street, N.W., Washington, D. C. 20036.)

American Society for Testing and Materials (ASTM) Standard:

E-11 - Sieve For Testing Purposes (Wire-Cloth and Perforated Plate Sieves).

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103.)

3. REQUIREMENTS

3.1 Material. Material shall be loose granules of baked or regranulated cork.

3.1.1 Cork. Cork shall be the outer layer of bark of the cork oak (Quercus suber).

3.1.2 Regranulated cork. Regranulated cork shall contain only the natural gums of the cork. There shall be no foreign binder in the cork.

3.2 Sizes and weights. The cork shall be of sizes and weights shown in table I, plus or minus 10 percent.

TABLE I. Sizes and weights

Size	Pass through sieve	Retained on sieve	Weight per cu. ft.	
			Min. (pounds)	Max. (pounds)
A	1/2 inch	No. 8	5-1/2	6-1/2
B	No. 8	No. 20	6	7
C	No. 20	No. 40	6-1/2	7-1/2

3.3 Color. The cork shall be a dark brown color characteristic of baked cork.

3.4 Workmanship. The cork shall be dry and free of dust. There shall be no foreign material in the cork.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Classification of inspection. Inspection shall be classified as follows:

(a) Quality conformance inspection (see 4.3).
(b) Inspection of preparation for delivery (see 4.5).

4.3 Quality conformance inspection.

4.3.1 Unit of product. For the purpose of inspection, a filled container of granulated cork shall be considered a unit of product.

4.3.2 Sampling. Sampling for examination and test shall be in accordance with MIL-STD-105.

4.3.3 Examination. Samples selected in accordance with 4.3.2 shall be examined as specified in 4.4.1. AQL shall be 2.5 percent defective.

4.3.4 Tests. Samples selected in accordance with 4.3.2 shall be tested as specified in 4.4.2. AQL shall be 2.5 percent defective.

4.4 Inspection procedure

4.4.1 Examination. The cork shall be examined for the following defects:

101. Material not as specified.
102. Foreign binder present (regranulated cork).
103. Size not as specified.
104. Weight per cubic foot not as specified.
105. Color not as specified.
106. Workmanship not as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

4.4.2 Tests.

4.4.2.1 Sieves. The sieves used in the test shall be of the sizes shown in table I and shall conform to ASTM E11.

4.4.2.2 Shaker. The sieve shaker shall be a mechanically operated device which imparts a rotary motion and which can be adjusted to apply between 140 and 160 taps per minute to the set of sieves.

4.4.2.3 Sieve test procedure. Assemble the sieves with the passing sieve above, the retaining sieve in the middle, and a solid collecting pan below. From the sample, weigh out a 250-gram plus or minus 0.01-gram (g) specimen, place in the top (passing) sieve, and cover to prevent spillage. Operate the shaker for 5 minutes, plus or minus 10 seconds, at a uniform rate between 140 and 160 taps per minute. Then weigh to the nearest 0.01g, the cork remaining in the top sieve and the collecting pan. A weight exceeding 25g of the sum of the weight of the cork in the top sieve and the collecting pan shall constitute failure of this test.

4.4.2.4 Weight test procedure. Weigh a rigid container of 1 cubic foot volume to the closest ounce. Fill with granulated cork. Shake and keep container slightly over full until settlement ceases. Scrape off excess cork. Weigh cork and container to the nearest ounce. Nonconformance with the weights given in table I for the applicable size shall constitute failure of this test.

4.5 Inspection of preparation for delivery.

4.5.1 Quality conformance inspection of pack.

4.5.1.1 Unit of product. For the purpose of inspection, a completed pack prepared for shipment shall be considered a unit of product.

4.5.1.2 Sampling. Sampling for examination shall be in accordance with MIL-STD-105.

4.5.1.3 Examination. Samples selected in accordance with 4.5.1.2 shall be examined for the following defects. AQL shall be 2.5 percent defective.

107.	Containers not as specified. Each incorrect container shall constitute one defect.
108.	Quantities not as specified.
109.	Packing not as specified for level A or B.
110.	Marking illegible, incomplete, incorrect, or missing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. The cork shall be furnished in 1-, 5-, or 35-pound quantities as specified (see 6.2), in containers, in accordance with the suppliers standard commercial practice.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. The cork, packaged as specified in 5.1, shall be packed in a wood cleated-plywood box conforming to PPP-B-601, overseas type, style optional, up to the weight limitation of the box.

5.2.2 Level B. The cork, packaged as specified in 5.1, shall be over-packed in multi-wall shipping sacks conforming to UU-S-48, sack number 8 or 8x, without moisture barrier. When specified (see 6.2), bags shall be palletized in accordance with MIL-STD-147, load type XV.

5.2.3 Level C. The cork, packaged as specified in 5.1, shall be packed for shipment in a manner to assure carrier acceptance and safe delivery to destination at lowest rating in compliance with Uniform Freight Classification rules or National Motor Freight Classification rules.

5.3 Marking.

5.3.1 Military agencies. Packages and containers shall be marked in accordance with MIL-STD-129.

5.3.2 Civil agencies. Packages and containers shall be marked in accordance with Fed. Std. No. 123.

6. NOTES

6.1 Intended use. The granulated cork is intended for use in retarding heat transfer where the use of a pouring insulation is necessary or is practical. It is also intended for use as an anti-sweat agent or camouflage agent in paints and as a filler in plastic compounds.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Size required (see 1.2).
(c) Quantities required (see 5.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

(d) Level of packing required (see 5.2).
(e) When bags are to be palletized (see 5.2.2).

MILITARY CUSTODIANS:

Army - ME
Air Force - 84

Review activity:

Air Force - 85

User activity:

Army - CE

Preparing activity:

Army - ME

Project No. 5640-0182

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.