HH-R-595B
September 2, 1970
SUPERSEDING
Int. Fed. Spec. HH-R-00595A(GSA-FSS)
January 7, 1970 and
Fed. Spec. HH-R-595
December 8, 1964

FEDERAL SPECIFICATION

ROOFING FELT, COAL TAR AND ASPHALT SATURATED ORGANIC FELTS, ROLLS

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers coal tar and asphalt saturated organic felts, in rolls, for use in roofing and waterproofing.

1.2 Classification.

1.2.1 Types and styles. The roofing felt shall be of the following types and styles, as specified (see 6.2):

Type 15A - Asphalt saturated felt
  Style A - Plain
  Style B - Perforated.
Type 30A - Asphalt saturated felt
  Style A - Plain
Type 15C - Coal tar saturated felt
  Style A - Plain
  Style B - Perforated.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

NN-P-71 - Pallets, Material Handling, Wood, Double Faced, Stringer Construction.
UU-P-268 - Paper, Kraft, Untreated, Wrapping.
PPP-S-760 - Strapping, Nonmetallic (And Connectors).
PPP-T-45 - Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing.
PPP-T-60 - Tape, Pressure-Sensitive Adhesive Waterproofing, for Packaging.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of the specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from the established distribution points in their agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

Military Specification:

MIL-R-3423 - Roofing Felt, In Rolls, Packaging of.

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-731 - Quality of Wood Members for Containers and Pallets.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standards:

D 146 - Methods of Sampling and Testing Felted and Woven Fabrics Saturated with Bituminous Substances for Use in Waterproofing and Roofing.
D 226 - Specifications for Asphalt-Saturated Roofing Felt for Use in Waterproofing and in Constructing Built-Up Roofs.
D 227 - Specifications for Coal-Tar Saturated Roofing Felt for Use in Waterproofing and in Constructing Built-Up Roofs.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

Underwriters' Laboratories, Inc. (UL) Standards:

UL 55A - Materials for Use in Construction of Built-Up Roof Coverings.

(Application for copies should be addressed to the Underwriters' Laboratories, Inc., 1285 Walt Whitman Road, Melville, L.I., N.Y. 11746; 207 E. Ohio Street, Chicago, Illinois 60611; and 1655 Scott Boulevard, Santa Clara, California 95050.)

Uniform Classification Committee:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, 202 Union Station, Chicago, Illinois 60606.)

National Classification Board:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Attention: Tariff Order Section, 1616 P Street N. W., Washington, D.C. 20036.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Fire and casualty hazards (see 4.4.2).

3.1.1 Each contractor shall submit to the contracting agency proof that the roofing felt he proposes to supply under this specification conforms to the requirements of the Underwriters' Laboratories, Inc., UL 55A. The label, or listing with re-examination, of the Underwriters' Laboratories, Inc., may be accepted as evidence that the roofing felt conforms to this requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

3.1.2 In lieu of the label, or listing with re-examination, the contractor may submit independent proof, satisfactory to the contracting agency, that the roofing felt conforms to the applicable requirements of the published standards including methods of tests of the Underwriters' Laboratories, Inc., UL 55A.

3.1.3 Compliance with the above preliminary requirements regarding fire and casualty hazards does not absolve the contractor from complete compliance with the specific requirements of this specification in order to secure acceptance of his material.

3.2 Types 15A and 30A. Types 15A and 30A asphalt saturated organic roofing felts shall be in accordance with ASTM D226, except for packing, marking, sampling and rejection, and the requirements hereinafter specified (see 4.4.2).

3.3 Type 15C. Type 15C coal tar saturated organic roofing felt shall be in accordance with ASTM D 227, except for packing, marking, sampling, and rejection, and the requirements hereinafter specified (see 4.4.2).

3.4 Sizes.

3.4.1 Width. Unless otherwise specified (see 6.2), the roofing felt shall be 36 inches wide.

3.4.2 Area of roll. Unless otherwise specified (see 6.2), the number of square feet per roll shall be as follows:

Types 15A and 15C	432 sq. ft.
Type 30A	216 sq. ft.

3.5 Rolls. No roll of roofing shall contain more than two pieces nor shall there be more than 3 percent of rolls in a lot containing two pieces. Rolls shall be tightly wound, shall not be flattened, and ends of rolls shall not be battered.

3.6 Workmanship. The finished roofing felt, while being unrolled at ambient temperature of 50°F. (10°C.) or above, shall not crack or stick together causing tearing or other material damage. The finished roofing felt shall be free of visible external defects such as holes, ragged or untrue edges, rents, cracks, tears, protuberances, and indentations. Protuberances and holes associated with intentionally provided perforations shall not be considered as defects.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling.

4.2.1 Lot. Unless otherwise specified (see 6.2), a lot shall consist of all roofing felt of the same type and style offered for delivery at one time.

4.2.2 Samples for visual and dimensional examination. Sampling for these characteristics shall be in accordance with level S-3 in MIL-STD-105.

4.2.3 Samples for tests. Sampling for tests shall be in accordance with level S-1 in MIL-STD-105.

4.3 Examination.

4.3.1 Visual and dimensional examination. Roofing felt selected in accordance with 4.2.2 shall be examined and measured for defects listed in table I. The Acceptable Quality Levels (AQL's) for defects shall be 2.5 percent defective for major defects and 4.0 percent defective for minor defects. Dimensions shall be determined in accordance with ASTM D 146.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

TABLE I. Classification of defects, end item

Defects	Major	Minor
Type and style not as specified.	X	
Felt not thoroughly and uniformly saturated.	X	
Width not within tolerance.	X	
Average area of rolls less than specified.	X	
Rolls stick, tear, or crack while unrolling.	X	
Roll contains more than 2 pieces or more than 3 percent of rolls in a lot contain 2 pieces.	X	
Rolls not tightly wound.		X
Rolls flattened or ends battered, unusable.	X	
Rolls slightly flattened or end slightly battered, usable.		X
Holes, rents, cracks, indentations, tears, or protuberances.	X	
Ragged or untrue edges.	X	
Damage or defects affecting function or serviceability.	X	
Damage or defects not affecting function or serviceability.		X

4.3.2 Inspection of preparation for delivery. An inspection shall be made to determine that the packaging, packing and marking requirements comply with section 5. Defects shall be scored in accordance with table II. For examination of interior packaging the sample unit shall be one shipping container fully prepared for delivery selected just prior to the closing operations. Sampling shall be in accordance with MIL-STD-105. Defects of closure listed shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 4.0 defects per hundred units.

TABLE II. Classification of preparation for delivery

Examine	Defects
Markings (exterior and interior)	Omitted; incorrect; illegible; improper size, location, sequence or method of application.
Materials	Any component missing, or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, inadequate stapling. Bulging or distortion of container.

4.4 Test methods.

4.4.1 Acceptable quality level. The AQL for tests shall be 4.0 percent defective.

4.4.2 Types 15A, 30A, and 15C. Types 15A, 30A, and 15C roofing felts shall be tested in accordance with ASTM D 146 and applicable test methods in UL 55A (see 3.1, 3.2 and 3.3).

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C, as specified (see 6.2).

5.1.1 Level A. The rolls of roofing felt shall be packaged as specified in MIL-R-3423.

5.1.2 Level B. (see 6.3) Each roll of roofing felt shall be wrapped in paper conforming to UU-P-268, grade B, 60 pound minimum basis weight. The wrapping shall be sealed with tape conforming to PPP-T-60 or PPP-T-45, Type I or II. The wrapping paper shall be of the same width as the roofing felt and shall completely encircle the roll and secured at the overlap in a manner that will prevent it shifting from position. The ends need not be covered.

5.1.3 Level C. The roofing felt shall be packaged in accordance with the supplier's standard practice.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A. The rolls of roofing felt shall be packed as specified in MIL-R-3423.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

5.2.2 Level B. The rolls, packaged as specified in 5.1, arranged on end shall be palletized on a pallet conforming to NN-P-71, type I or II, except the maximum length and width shall be 46 inches by 52 inches. The rolls shall be circumferentially secured with nonmetallic strapping conforming to PPP-S-760, type II or III, with a minimum breaking strength of 680 pounds. Alternatively, the packaged rolls arranged on end shall be palletized on an expendable wooden pallet as described in 5.2.2.1. The top corners of the rolls along the width of the pallet shall be protected by a full length V board as described in 5.2.2.2. The rolls shall be secured circumferentially and girthwise with nonmetallic strapping conforming to PPP-S-760, type II or III, with a minimum breaking strength of 680 pounds. The circumferential strap will be approximately at the center of the roll length. The girthwise strap shall be around the length of the pallet and V boards and as near the center of the load as the center stringer will permit.

5.2.2.1 Expendable wooden pallet. Expendable wooden pallets shall be a maximum of 46 inches long and 52 inches wide. Deckboards and stringers shall be Douglas Fir, standard grade or better. Each deckboard or stringer must be free of decay and any other defect which would render it unfit for satisfactory service in a pallet. Boards may be S1S or S2S, however, thickness must be uniform within 1/16 inch and minimum width must be within 1/2 inch of width specified. Overall pallet height must be uniform within 1/8 inch. Pallets must be square. Deckboards must be evenly spaced and not over 2-5/8 inches apart. The deckboards shall be a minimum of 1 by 6 inches nominal. The stringers shall be a minimum of 2 by 4 inches nominal. The deckboards shall be nailed to the stringers at all contact points with a minimum of two cement coated 8d box nails. One stringer shall be nailed along the center of the deckboards. The two outer stringers will be set in approximately 3 inches from the ends of the deckboard.

5.2.2.2 V Boards. The V-boards shall be constructed of one 1 by 6 inch (nominal) and one 2 by 2 inch (nominal) lumber conforming to MIL-STD-731, class 2, group II or III. The length shall be less than the width of the pallet but long enough to protect all rolls in the outer line. The 1 by 6 shall be nailed to the 2 by 2 in such a manner as to form a V, with a minimum of four 8d cement coated box nails equally spaced.

5.2.3 Level C. The roofing felt packaged as specified in 5.1 shall be packed to assure carrier acceptance and safe delivery at destination in compliance with Uniform Freight Classification Rules or National Motor Freight Classification Rules.

5.3 Marking. In addition to any marking required by the contract or order the rolls and shipping containers shall be marked in accordance with Fed. Std. No. 123 or MIL-STD-129 as applicable.

6. NOTES

6.1 Intended use. Coal tar and asphalt saturated organic roofing felts are intended for use in roofing and water proofing.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and style of roofing felt (see 1.2.1).
(c) Width, if other than specified (see 3.4.1).
(d) Area per roll, if other than specified (see 3.4.2).
(e) Size of lot, if different from 4.2.1.
(f) Selection of applicable level of packaging and packing required (see 5.1 and 5.2).

6.3 Level B packaging (see 5.1.2) has been developed by GSA for civil agency procurement. For Navy procurement details of level B packaging, when required, should be developed at the time of procurement when all conditions are known.

MILITARY INTEREST:

Custodians:

Army - ME
Navy - YD
AF - 84

User Interest:

MC, CE

Preparing activity:

GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.

GENERAL SERVICES ADMINISTRATION - FEDERAL SUPPLY SERVICE

SPECIFICATION COMMENT SHEET

BUDGET BUREAU NO. 29-R0175

INSTRUCTIONS

This form provides a way for users of this specification to inform the originator of problems encountered in its use. It is not to be used to request changes to accommodate proprietary features. All comments and mail to General Services, Adm., FSS (FMSH), Washington, D.C. 20406. fold, staple, and mail.

NOTE: Comments on this form do not constitute or imply authorization to waive any part of the document or serve to amend contractual requirements.

1. SPECIFICATION

HH-R-595B ROOFING FELT, COAL TAR AND ASPHALT SATURATED ORGANIC FELTS, ROLLS

2. CONTRACT NO. *(If any)*	3. QUANTITY ON CONTRACT *(Optional)*	4. DOLLAR VALUE *(Optional)*

5. GENERAL NATURE OF PROBLEM *(e.g., inspection difficulties, manufacturers unable to meet tolerances, containers collapse under normal warehousing conditions, etc.)*

6. SPECIFIC REQUIREMENTS AFFECTED *(Include paragraph number and lines of wording)*

7. SPECIFIC PROBLEMS *(e.g. tests in 4.2.2 will not assure that the battery will last required time; temperature ranges in table 2 do not conform to commercially available items.)*

8. RECOMMENDATIONS

9. NAME OF MANUFACTURER, ASSOCIATION, GOVT., AGENCY, ETC.	10. ADDRESS *(Number, Street, City, State and Zip Code)*

11. NAME AND TITLE OF SUBMITTER	12. DATE

GSA DC 69-9761

FORM GSA FEB 69 2200

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:55Z
Check the source to verify that this is the current version before use.