COMMERCIAL ITEM DESCRIPTION

COVER, TYPEWRITER

The General Services Administration has authorized the use of this commercial item description.

This commercial item description covers gray colored dust covers for non-portable typewriters.

Salient characteristics:

The dust cover shall be made from a coated cotton cloth or a coated polyester cotton cloth. The cloth shall be evenly woven, free from large knots and extraneous material. The coating shall be spread uniformly on one side. The coating compound shall be either natural latex, synthetic latex or synthetic resins. Not more than three pieces of cloth shall be used in the finished product. All edges shall be hemmed with raw edges turned to the inside of the cover. All hems and seams shall be securely and neatly sewn with at least six lock stitches to the inch. The color of the thread, cloth and coating shall be approximately the same color gray.

Class 1 and Class 2 unsupported vinyl film of not less than 0.008 inch pre-embossed thickness, conforming to Type I requirements of Federal Specification L-P-375, shall also qualify as an accepted optional material. Seams (welt) shall be used to join pieces with 3/8 ± 1/8 inch seam allowance using a 7/8 inch film tape binding.

Size shall be as specified in the procurement documents, in accordance with Table I below:

Table I.

Size (inches)	Width (inches)	Depth (inches)	Height (inches)
15	15	16	10
17	17	16	10
19	19	16	10
22	22	16	10
24	24	16	10
26	26	16	10
32	32	16	10
34	34	16	10
40	40	16	10

Note: All measurements are ± 1/4 inch.

Representative samples of the typewriter cover shall be taken in accordance with MIL-STD-105, inspection level S-4, with an Acceptable Quality Level (AQL) of 4.0 per 100 units.

The samples taken shall be visually examined for dimensional accuracy and the defects listed in Table II below:

Table II.

Examine	Defects
Coating	Any uncoated area Any thinly coated area Any separation of the coating from the base of cloth Tacky coating Brittle coating (cracks when flexed) Cracked or checked coating Any blisters or lumps Coating not uniform throughout Any wrinkle or crease not due to normal handling
Workmanship	Any cuts, holes, or tears Any coated surface that is scratched or abraded
Seams and Stitching	Seams twisted or puckered Broken threads Irregular Open seams Raw edges Loose tensions resulting in loose seams Tight tensions resulting in broken stitches when normal strain is applied to seams and stitching

Source: https://assist.dla.mil -- Downloaded: 2026-1-26 10:08 PST
Check the source to verify that this is the current version before use.

Table II. (continued)

Examine	Defects
Unsupported Film	Thickness not uniform throughout Tacky Brittle (cracks when flexed) Cracked or checked Any blisters or lumps Any wrinkles or crease not due to normal handling

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices, and is the same product sold in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements. The manufacturer shall utilize recovered materials to the maximum extent practicable.

Packaging, packing, and marking. The items shall be packaged in accordance with normal commercial practice and packed to assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handling, and storage. The shipping container shall be in compliance with National Motor Freight Classification and Uniform Classification. Shipping containers shall be marked as specified in the contract or order.

Preparing activity:

GSA-FSS

GSA DC-01103837

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:17Z
Check the source to verify that this is the current version before use.