A-A-1964
October 15, 1982

Commercial Item Description

Envelope, Wallet

The General Services Administration has authorized the use of this commercial item description in preference to Envelope, Wallet as specified in Federal Specification UU-J-390C.

Salient characteristics:

Envelope wallets shall be provided with flaps and full height gussets. Envelopes shall be supplied in sizes as specified. The leaves of the envelope shall be two-ply with rounded corners. The color of the outer ply shall be red; the color of the inner ply shall be red, salmon or manila as specified. The flap shall be a continuation of the back leaf and shall overlap the front a minimum of 4 inches when fully expanded. For the 9-1/2 x 4 inch size the flap shall overlap not less than 2 inches. The flap shall be scored horizontially at various locations for folding the flap within the expansive range of the wallet. The gusset shall be one-ply, single piece construction with a reinforcing strip of cloth, polymeric nonwoven material or latex impregnated fiber not less than 5/8 inch wide completely and securely glued to the top of the gusset on the inside face. The gusset shall be the same color as the outer ply of the leaves. The number of gusset folds for each expansion shall be as follows:

Sizes		
9-1/2 x 11-3/4 inches	7/8 inch	expansion - 1 fold
9-1/2 x 14-3/4 inches	1-3/4 inch	expansion - 2 folds
10 x 15 inches	2-5/8 inch	expansion - 3 folds
10 x 16 inches	3-1/2 inch	expansion - 4 folds
9-1/2 x 4 inches		

When specified, the envelope wallets shall be equiped with elastic loops, or ties. The ties shall be either cotton cloth or other suitable material, at least six inches long, which can be securely fastened. The leaves and gussets shall be made of red material conforming to the following requirements:

Characteristic	Requirement		TAPPI test method*
	Gusset	Leaves (2-ply)	
Basis weight (24 x 36-500), pounds	120 min.	240 min.	T-410
Thickness (inch)	0.009 min.	0.018 min.	T-411
Bursting strength (p.s.i.)	95 min.	190 min.	T-403
Tearing strength (grams, average both directions)	280 min.	550 min.	T-414
Fold endurance			
Machine direction	600 min.	---	T-511
Cross direction	375 min.	---	T-511

* The issue of the TAPPI test method in effect on the day of the solicitation shall be used to determine compliance with the requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:18Z
Check the source to verify that this is the current version before use.

The plies of the leaves shall be completely and securely bonded together. When the plies are pulled apart, failure shall be entirely in the paper stock and not the adhesive bond. The gusset shall be completely and securely bonded in place between the plies of the leaves. When The gusset is pulled from the leaves, failure shall be entirely in the paper stock and not the adhesive bond.

Workmanship. The envelope wallets shall be free from holes, tears, creases, wrinkles, blisters, lumps and ply separations. The envelope wallets shall lie flat and shall not warp or buckle. The wallets shall be clean and free of discolorations. There shall be no adhesive on any exposed surface. The side edges of the front and back leaves shall be flush.

Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practical.

Preservation, packaging, packing, labeling and marking. The preservation, packing, packaging, labeling, and marking shall be as specified in the contract or order.

TAPPI test methods are available from the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, Georgia 30341.

PREPARING ACTIVITY

GSA - OPP

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:18Z
Check the source to verify that this is the current version before use.