INCH-POUND


MIL-DTL-32372/2A
7 February 2017
SUPERSEDING
MIL-DTL-32372/2
5 December 2011

DETAIL SPECIFICATION SHEET

FITTING, ADAPTER, 45° ELBOW, HYDRAULIC AND PNEUMATIC, NPTF MALE TO ORFS MALE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-32372.



Dash size	Tube OD nom. inches (mm)	T_1 NPTF ASME B1.20.3	T_2 ORFS SAE J1453-1	D Inside dimension inches (mm)	L_1 +/- .030 inches (mm)	L_2 +/- .030 inches (mm)
-4	.2500 (6.35)	1/4 - 18	9/16 – 18	.172 +/-.003 (4.4)	.890 (22.6)	.780 (19.9)
-6	.3750 (9.53)	1/4 - 18	11/16 – 16	.297 +/-.004 (7.5)	1.060 (26.9)	1.090 (27.7)
-8	.5000 (12.7)	1/2 - 14	13/16 - 16	.391 +/-.004 (9.9)	1.250 (31.8)	1.220 (30)
-10	.6250 (15.88)	1/2 - 14	1-14	.484 +/-.004 (12.3)	1.450 (36.8)	1.470 (37.3)
-12	.7500 (19.05)	3/4 - 14	1-3/16-12	.609 +/-.005 (15.5)	1.660 (42.2)	1.590 (40.4)
-16	1.0000 (25.40)	1-7/16-12	1-7/16-12	.844 +.007/-.005 (21.4)	1.810 (46)	1.970 (50)
-20	1.2500 (31.75)	1-11/16-12	1-11/16-12	1.078 +.008/-.005 (27.4)	2.060 (52.3)	2.380 (60.5)
-24	1.5000 (38.10)	1-1/2-11-1/2	2-12	1.312 +.010/-.005 (33.3)	2.330 (59.2)	2.640 (67.1)

FIGURE 1. Fittings, hydraulic and pneumatic, NPTF to ORFS, 45° male adapter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:59Z
Check the source to verify that this is the current version before use.

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for information only.
3. Break all sharp edges and remove all burrs and slivers.
4. Dimensions and tolerances not shown shall be in accordance with ASME B1.20.3 for NPTF end and SAE J1453-1 for ORFS end.

FIGURE 1. Fittings, hydraulic and pneumatic, NPTF to ORFS, 45° male adapter – Continued.

REQUIREMENTS

Fitting configuration and dimensions shall be as specified on figure 1.

Materials and finishes shall be in accordance with MIL-DTL-32372.

Material and Finish designators. Material and Finish designators shall be as specified in table I. All platings shall be capable of meeting a minimum of 96 hours salt spray test in accordance with ASTM B117. The fittings shall show no evidence of corrosion after 96 hours of salt spray. Fluid passages, other openings, and internal threads shall not be subject to the plating thickness requirement and may have bare areas provided they are protected with a light film of oil.

TABLE I. Material and chemical finish identification codes and chemical finish reference specifications.


Part or Identifying Number (PIN) code material/plating finish	Material	Plating finish
Blank	Steel	Cadmium plating in accordance with SAE AMS-C-81562, type II, class 3 or SAE AMS-QQ-P-416, type II, class 2. 1/
CN		Cadmium plating in accordance with SAE AMS-C-81562, type II, class 3 or SAE AMS-QQ-P-416, type II, class 2 with NAVAIR trivalent chromium pretreatment (TCP) in accordance with MIL-DTL-81706, type 2, class 1A.
E		NAVAIR TCP in accordance with MIL-DTL-81706, type 2, class 1A.
F	Steel	Zinc plate (finish J, P, or R) with NAVAIR TCP in accordance with MIL-DTL-81706, type 2, class 1A.
H	Steel	Aluminum-nickel in accordance with ASTM F1136, grade 3, NC.
J	Steel	Zinc-nickel in accordance with SAE AMS2417, type 1.
M	Nickel-copper alloy UNS N04400	No additional finish.
N	High-chromium nickel alloy UNS N06690	No additional finish.
P	Steel	Zinc phosphate finish in accordance MIL-DTL-16232 type Z, class1.
R	Steel	Zinc plating in accordance with ASTM B633; type VI, Fe/Zn 5. 2/ 3/
S	Corrosion resistant steel	No additional finish. Passivation in accordance with SAE AMS2700, type 6 or 7.
T	Titanium	Anodize in accordance with SAE AMS2488 type 2.
Z	Steel	Zinc plating in accordance with ASTM B633; type II or III, Fe/Zn 5, or ASTM B695, type II, class 5. 3/
ZN	Steel	Zinc plating in accordance with ASTM B633; type II or III, Fe/Zn 5, or ASTM B695, type II, class 5 with NAVAIR TCP in accordance with MIL-DTL-81706, type 2, class 1A. 3/

1/ Embrittlement test need not be run.
2/ Hexavalent chromium free.
3/ Class I and II Ozone Depleting Substances shall not be used in any referenced specifications.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:59Z
Check the source to verify that this is the current version before use.

Maximum operating pressure. Maximum operating pressure shall be in accordance with MIL-DTL-32372.

PIN: The PIN consists of the letter M, the basic specification number, the specification sheet number, a number for fitting size, and a letter for the material finish designator.



PIN example: M32372/2-10P indicates a male, 45°, fitting, 5/8 inch tube OD, steel with zinc phosphate finish.

O-ring is not supplied order separately in accordance with SAE J515.

Cadmium is not recommended. To the users of this document, it is recommended that the use of carbon steel material with cadmium plating be used only when other materials and finishes specified in this document cannot meet performance requirements.

Changes from previous issue. The margins of this specification are marked with vertical lines to indicate where changes from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Referenced documents. In addition to MIL-DTL-32372, this document references the following:

MIL-DTL-16232
MIL-DTL-81706
ASME B1.20.3
ASTM B117
ASTM B633
ASTM B695
ASTM F1136
SAE AMS-C-81562
SAE AMS-QQ-P-416
SAE AMS2417
SAE AMS2488
SAE AMS2700
SAE J1453-1
SAE J1453-3
SAE J515

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:59Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL

Custodians:
Army – AR
Navy – SH
Air Force – 99
DLA – CC

Review activities:
Army – AT, GL
Navy – MC, SA, YD
Air Force – 71

Preparing activity:
DLA – CC

(Project 4730-2017-012)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online data at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T05:59Z
Check the source to verify that this is the current version before use.