The documentation and process conversion measures necessary to comply with this revision shall be completed by 10 October 1998

METRIC

MIL-PRF-19500/586D
10 July 1998
SUPERSEDING
MIL-PRF-19500/586C
20 June 1997

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, SCHOTTKY BARRIER, HERMETIC
TYPES 1N5819-1, 1N5819UR-1, 1N6650-1, 1N6650UR-1, 1N6761-1 AND 1N6761UR-1
JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for silicon, Schottky barrier diodes. Four levels of product assurance are provided for each encapsulated device types as specified in MIL-PRF-19500, and two levels of product assurance for each unencapsulated device type die.

1.2 Physical dimensions. See figure 1 (DO-41), figure 2 (DO-213AB), figures 3 and 4 (JANC die) dimensions.

1.3 Maximum ratings.

Types	V_{RWM}	I_{O1} 3/	I_{FSM}	T_{STG}	T_J
	V (pk)	A dc	A (pk)	C°	C°
1N5819-1, 1N5819UR-1	45 1/	1.0	25	-65°C to +150°C	-65°C to +125°C
1N6650-1, 1N6650UR-1	45 1/	1.0	25	-65°C to +150°C	-65°C to +150°C
1N6761-1, 1N6761UR-1	100 2/	1.0	25	-65°C to +150°C	-65°C to +125°C

1/ Derate linearly at 1.8 V/°C above T_L or T_{EC} = +100°C for 1N5819-1, T_L or T_{EC} = +125°C for 1N6650-1 where T_L is at L = .375 inch.

2/ Derate linearly at 4.0 A/°C above T_L or T_{EC} = +100°C where T_L is at L = .375 inch.

3/ Derate linearly at 14 mA/°C above T_L or T_{EC} = +55°C for 1N5819-1 and 1N6761-1, T_L or T_{EC} = +80°C for 1N6650-1 where T_L is at L = .375 inch.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Defense Supply Center Columbus, ATTN: DSCC-VAT, 3990 East Broad Street, Columbus, OH 43216-5000, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics. Unless otherwise specified, primary electrical characteristics at T_A = +25°C.

Types	Max V_{FM1} I_{FM} = 0.1 A	V_{FM2} I_{FM} = 1.0 A	Max V_{FM3} I_{FM} = 3.1 A	Max I_{RM} @ V_{RWM} pulsed method (see 4.5.1)		Max C_T V_R = 5 V dc	Max $R_{\theta JL}$ or $R_{\theta JEC}$ 3/8 lead length or end cap	Max $Z_{\theta JX}$
				T_J = +25°C I_{RM1}	T_J = +100°C I_{RM2}			
	V (pk)	V (pk)	V (pk)	mA	mA	pF	°C/W	°C/W
1N5819-1	0.34	0.49	0.80	0.05	5.0	70	70	12
1N5819UR-1	0.34	0.49	0.80	0.05	5.0	70	40	12
1N6650-1	0.39	0.56	0.80	0.025	1.0	70	70	12
1N6650UR-1	0.39	0.56	0.80	0.025	1.0	70	40	12
1N6761-1	0.38	0.69	NA	0.010	6.0	70	70	12
1N6761UR-1	0.38	0.69	NA	0.010	6.0	70	40	12

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATION

DEPARTMENT OF DEFENSE

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

STANDARD

MILITARY

MIL-STD-750 - Test Methods for Semiconductor Devices.


(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for related associated specifications or specification sheets), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Qualification. Devices furnished under this specification shall be products that are authorized by the qualifying activity for listing on the applicable qualified products list before contract award (see 4.2 and 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.




Symbol	Dimensions				Notes
	Millimeters		Inches		
	Min	Max	Min	Max	
LD	0.71	0.86	.028	.034	
BD	2.03	2.72	.080	.107	3
BL	4.06	5.21	.160	.205	3
LL	25.40		1.000		
LL_1		1.27		.050	4

NOTES:
1. Dimensions are in metric.
2. Inch pound equivalents are given for general information only.
3. Package contour optional within cylinder of diameter BD and length BL. Slugs if any shall not be included within this cylinder, but shall not be subject to the minimum limit of BD.
4. Lead diameter not controlled in this zone to allow for flash, lead finish build-up, and minor irregularities other than slugs.

FIGURE 1. Physical dimensions, 1N5819-1, 1N6650-1 and 1N6761-1 (DO-41).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.




Symbol	Dimensions			
	Millimeters		Inches	
	Min	Max	Min	Max
BL	4.80	5.21	.189	.205
BL_1	4.04 REF		159 REF	
BD	2.39	2.67	.094	.105
ECT	0.41	0.56	.016	.022
S	0.03		.001	

NOTES:
1. Dimensions are in metric.
2. Inch pounds equivalents are given for general information only.
3. Gap not controlled, shape of body and gap not controlled.

FIGURE 2. Physical dimensions of surface mount family, 1N5819UR-1, 1N6650UR-1 and 1N6761UR-1 (DO-213AB).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.



BACKSIDE IS CATHODE

Symbol	Dimensions			
	Millimeters		Inches	
	Min	Max	Min	Max
A	0.89	0.99	.035	.039
B	0.79	0.84	.031	.033


Design data

Metallization:
Top: (Anode) . . . . . AL
Back: (Cathode). . . . Au

AL thickness . . . . . 25000 Å min
Gold thickness . . . . . 4000 Å min
Chip thickness . . . . . 10 Mils ± 2 Mils

FIGURE 3. JANC (A-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.



BACKSIDE IS CATHODE

Symbol	Dimensions			
	Millimeters		Inches	
	Min	Max	Min	Max
A	0.94	1.04	.037	.041
B	0.84	0.89	.033	.035

Design data

Metallization:
Top: (Anode) . . . . . AL
Back: (Cathode). . . . . Au

AL thickness . . . . . 20000 Å min
Gold thickness . . . . . 5000 Å min
Chip thickness . . . . . 12 Mils ± 2 Mils

FIGURE 4. JANC (B-version) die dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

3.2 Associated specification. The individual item performance requirements shall be in accordance with MIL-PRF-19500, and as specified herein.

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

3.4 Interface requirements and physical dimensions. The interface requirements and physical dimensions shall be as specified in MIL-PRF-19500 and on figures 1, 2, 3, and 4 herein. Plastic packages are prohibited.

3.4.1 Lead material and finish. Lead material shall be copper clad steel with a minimum of 50% copper by weight. Lead finish shall be in accordance with MIL-PRF-19500 and MIL-STD-750. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Diode construction. These devices shall be constructed in a manner and using materials which enable the diodes to meet the applicable requirements of MIL-PRF-19500 and this document.

3.4.2.1 Surface mount. The U version shall be considered structurally identical to the non-U version except for lead attach.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.5.1 Marking for UR devices. UR-suffix devices only, all marking (except 3.6 below) may be omitted from the body, but shall be retained on the initial container.

3.6 Polarity. The polarity of all types shall be indicated with a contrasting color band to denote the cathode end. Alternatively, for UR suffix devices, a minimum of three contrasting color dots spaced around the periphery on the cathode end may be used.

3.7 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I.

3.8 Electrical test requirements. The electrical test requirements shall be the subgroups specified in 4.4.2 and 4.4.3.

4. QUALITY ASSURANCE PROVISIONS

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3)

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500.

4.2.1 JANHC and JANKC devices. Qualification for devices shall be in accordance with MIL-PRF-19500. This testing may be performed on a TO-5 package in lieu of the DO-41 axial leaded package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

4.3 Screening (JAN, JANTX, JANTXV, and JANS levels only). Screening shall be in accordance with appendix E, table IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see Appendix E, table IV of MIL-PRF-19500)	Measurement		
	JANS level	JANTX and JANTXV levels	JAN level
3a	Temperature cycling	Temperature cycling	Temperature cycling in accordance with MIL-PRF-19500, JANTX level
3C 1/	Thermal impedance (see 4.5.4)	Thermal impedance (see 4.5.4)	Thermal impedance (see 4.5.4)
9	I_{R1} and V_{FM2}	Not applicable	Not applicable
10 2/	T_A = 100°C; V_{RWM} = 100 V(pk); 1N6761; T_A = 110°C; V_{RWM} = 45 V(pk); 1N5819, 1N6650, I_O = 0, half sine wave, f = 60 Hz	T_A = 100°C; V_{RWM} = 100 V(pk); 1N6761; T_A = 110°C; V_{RWM} = 45 V(pk); 1N5819, 1N6650, I_O = 0, half sine wave, f = 60 Hz	Not applicable
11	$\lvert\Delta I_{R1}\rvert \leq$ 100 percent of initial reading or .02 mA whichever is greater. $\Delta V_{FM2} \leq \pm$ 50 mV dc.	I_{R1} and V_{FM2}	Not applicable
12	See 4.3.2	See 4.3.2, t = 48 hours	Not applicable
13	Subgroup 2 of table I herein; $\Delta I_{R1} \leq$ 100 percent of initial reading or .02 mA whichever is greater; $V_{FM2} \leq \pm$ 50 mV dc.	Subgroup 2 of table I herein; $\Delta I_{R1} \leq$ 100 percent of initial reading or .02 mA whichever is greater; $V_{FM2} \leq \pm$ 50 mV dc.	Not applicable

1/ Thermal impedance shall be performed any time after sealing provided temperature cycling is performed in accordance with appendix E, table IV of MIL-PRF-19500, screen 3 prior to this thermal test.

2/ Junction temperature (T_J) is not to exceed 115°C at V_{RWM}. T_J is affected by the device mounting thermal resistance when parasitic power is generated by the temperature dependent leakage current. Until this leakage becomes significant near thermal runaway, T_J remains approximately equal to T_A or T_J for I_O = 0.

4.3.1 Screening (JANHC or JANKC). Screening of die shall be in accordance with Discrete Semiconductor Die/Chip Lot Acceptance appendix of MIL-PRF-19500 and die shall be 100 percent probed in accordance with group A, subgroup 2.

4.3.2 Burn-in conditions. Burn-in conditions are as follows: I_F = 1.0 A dc (min), T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5);. Mounting and test conditions in accordance with MIL-STD-750, method 1038, test condition B.

4.3.2.1 Mounting. Devices may be mounted using any convenient method including the temporary attachment of leads on UR suffix devices, provided that the parts are burned-in at an average lot T_J = 110°C (minimum).

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with appendix E, table V of MIL-PRF-19500, and table I herein. The following test conditions shall be used for $Z_{\theta JX}$, group A inspection:

a. I_M measurement current ..... 1 mA to 10 mA.

b. I_H forward heating current ..... 2.0 A.

c. t_H heating time ..... 10 ms.

d. t_{MD} measurement delay time ..... 70 µs maximum.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in appendix E, table VIa (JANS) and table VIb (JAN, JANTX, and JANTXV) of MIL-PRF-19500. Electrical measurements (end-points) shall be in accordance with the applicable inspections of table I, group A, subgroup 2 herein.

4.4.2.1 Group B inspection, appendix E, table VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
3	4066	I_{FSM} = 25 A(pk), condition A 2, I_O = 1.0 A; T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5); 5 surges of 8.3 ms each at 1 minute intervals.
4	1036	I_F = 1.0 A; T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5); $t_{on} = t_{off}$ = 3 minutes minimum for 2,000 cycles.
5	1027	T_A = +75°C ± 25°C; I_F = 1.0 (min) with I_F adjusted as required to achieve an average lot T_J = +125°C +0, -10°C.
6	3101	$R_{\theta JL}$ = 70°C/W; L = .375 inch (9.52 mm) lead length (non-surface mount). $R_{\theta JEC}$ = 40°C/W (surface mount).

4.4.2.2 Group B inspection, appendix E, table VIb (JAN, JANTX and JANTXV of MIL-PRF-19500).

Subgroup	Method	Condition
2	4066	I_{FSM} = 25 A(pk), condition A 2, I_O = 1.0 A; T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5); 5 surges of 8.3 ms each at 1 minute intervals.
3	1027	I_O = 1.0 A; T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5); f = 50-60 Hz, at V_{RWM}.(see 1.3).
4	2075	In accordance with 4.5.2.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in appendix E, table VII of MIL-PRF-19500. Electrical measurements (end-points) shall be in accordance with the applicable inspections of table I, group A, subgroup 2 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

4.4.3.1 Group C inspection, appendix E, table VII of MIL-PRF-19500.

Subgroup	Method	Condition
2	2036	Tension: Test condition A; weight = 10 pounds; t = 15 s. Lead fatigue: Test condition E; weight 1 pounds. NOTE: Both tension and lead fatigue are not applicable for UR devices.
6	1026	I_O = 1.0 A; T_A = room ambient as defined in the general requirements of MIL-STD-750 (see 4.5); f = 50-60 Hz, at V_{RWM} (see 1.3).

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions for subgroup testing in appendix E, table IX of MIL-PRF-19500 and herein. Electrical measurements (end- points) shall be in accordance with the applicable inspections of table I, group A, subgroup 2 herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in (see 4.3.2.1) of MIL-STD-750.

4.5.2 Decap internal visual scribe and break (DPA). Scratch glass at cavity area with diamond scribe. Carefully snap open. Using 30X magnification, examine the area where die or bond material were in contact with the plug and verify metallurgical bonding area.

4.5.3 Steady-state operation life. This test shall be conducted with a half-sine wave of the specified peak voltage impressed across the diode in the reverse direction followed by a half-sine waveform of the specified average rectified current. The forward conduction angle of the rectified current shall not be greater than 180° nor less than 150°.

4.5.4 Thermal impedance ($Z_{\theta JX}$ measurements). The $Z_{\theta JX}$ measurements shall be performed in accordance with MIL-STD-750, method 3101 to identify and remove atypical devices.

4.5.4.1 For initial qualification or requalification. Read and record data ($Z_{\theta JX}$) shall be supplied to the qualifying activity on one lot (random sample of 500 devices minimum). Twenty-two serialized devices shall be sent to the qualifying activity for test correlation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2						
Thermal impedance	3101	See 4.5.4	$Z_{\theta JX}$		12	°C/W
Forward voltage	4011	I_{FM} = .1 A (pk) pulsed (see 4.5.1)	V_{FM1}			V
1N5819-1, 1N5819UR-1					0.34	
1N6650-1, 1N6650UR-1					0.39	
1N6761-1, 1N6761UR-1					0.38	
Forward voltage	4011	I_{FM} = 1.0 A (pk) pulsed (see 4.5.1)	V_{FM2}			V
1N5819-1, 1N5819UR-1					0.49	
1N6650-1, 1N6650UR-1					0.56	
1N6761-1, 1N6761UR-1					0.69	
Forward voltage	4011	I_{FM} = 3.1 A (pk) pulsed (see 4.5.1)	V_{FM3}		0.80	V
Reverse current leakage	4016	Pulse method	I_{RM1}			mA
1N5819-1, 1N5819UR-1		V_{RM} = 45 V (pk)			0.05	
1N6650-1, 1N6650UR-1		V_{RM} = 45 V (pk)			0.025	
1N6761-1, 1N6761UR-1		V_{RM} = 100 V (pk)			0.10	
Subgroup 3						
High temperature operation:		T_A = +100°C				
Reverse current leakage	4016	Pulse method (see 4.5.1)	I_{RM2}			mA
		V_{RM} = 45 V (pk)			5.0	
1N5819-1, 1N5819UR-1		V_{RM} = 45 V (pk)			1.0	
1N6650-1, 1N6650UR-1		V_{RM} = 100 V (pk)			6.0	
1N6761-1, 1N6761UR-1						
1N5819-1, 1N5819UR-1		V_{RM} = 40 V (pk)	I_{RM3}		4.5	
1N6650-1, 1N6650UR-1		V_{RM} = 40 V (pk)			0.7	
1N5819-1, 1N5819UR-1		V_{RM} = 35 V (pk)	I_{RM4}		3.0	
1N6650-1, 1N6650UR-1		V_{RM} = 35 V (pk)			0.5	

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 3 - Continued						
Forward voltage	4011	Pulse method (see 4.5.1) I_F = 1.0 A (pk)	V_{FM4}			V
1N5819-1, 1N5819UR-1					0.45	
1N6650-1, 1N6650UR-1					0.51	
1N6761-1, 1N6761UR-1					0.64	
Low temperature operation:		T_A = -55°C				
Reverse current leakage	4016	Pulse method (see 4.5.1)	I_{RM5}			mA
1N5819-1, 1N5819UR-1					0.2	
1N6650-1, 1N6650UR-1					0.1	
1N6761-1, 1N6761UR-1					0.4	
Forward voltage	4011	Pulse method (see 4.5.1) I_F = 1.0 A (pk)	V_{FM5}			mA
1N5819-1, 1N5819UR-1					0.65	
1N6650-1, 1N6650UR-1					0.65	
1N6761-1, 1N6761UR-1					0.80	
Subgroup 4						
Capacitance	4001	V_R = 5 V dc, .01 ≤ f ≤ 1 MHz, V_{SIG} = 15 mV p-p	C_T		70	pF

1/ For sampling plan, see MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection (all quality levels) for qualification only. 1/

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			22 devices c = 0
Thermal shock (temperature cycling)	1051	500 cycles	
Hermetic seal	1071	Test condition E	
Electrical measurement		See table I, group A, subgroup 2	
Subgroup 2			22 devices c = 0
Steady-state reverse bias	1038	Test condition A; 1,000 hours, See 4.3, screen 10	
Electrical measurement		See table I, group A, subgroup 2	
Subgroup 3			
Not applicable			
Subgroup 4			22 devices c = 0
Thermal resistance, (forward voltage drop diode method)	4081	$R_{\theta JL}$ = 70°C/W maximum at .375" $R_{\theta JL}$ = 70°C/W maximum at .375" $R_{\theta JL}$ = 70°C/W maximum at .375" lead length; $R_{\theta JEC}$ = 40°C/W max.; lead length; $R_{\theta JEC}$ = 40°C/W max.; method 3101 per 4.5.4 except I_H = 1.0 A and T_H = 25 sec (min)	
Subgroup 5			
Not applicable			
Subgroup 6			
Not applicable			

1/ For initial design and process change verification only (one time testing).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. Packaging shall prevent mechanical damage of the devices during shipping and handling and shall not be detrimental to the device. When actual packaging of material is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Points' packaging activity within the Military Department or Defense Agency, or within the Military Departments' System Command. Packaging data retrieval is available from the managing Military Departments' or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

5.2 Marking. Unless otherwise specified (see 6.2), marking shall be in accordance with MIL-PRF-19500.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Notes. The notes specified in MIL-PRF-19500 are applicable to this specification.

6.2 Acquisition requirements. See MIL- PRF-19500.

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Products List QPL No.19500 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or purchase orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from : Commander, Defense Supply Center Columbus, ATTN: DSCC-VQE, 3990 East Broad Street, Columbus, OH 43216-5000.

6.4 Suppliers of die. The qualified die suppliers with the applicable letter version (example JANHCA1N5819) will be identified on the QPL.

JANC ordering information		
	Manufacturer	
PIN	55801	59377
1N5819	JANHCA1N5819 JANKCA1N5819	JANHCB1N5819 JANKCB1N5819
1N5819	JANHCA1N6650 JANKCA1N6650	JANHCB1N6650 JANKCB1N6650
1N5819	JANHCA1N6761 JANKCA1N6761	JANHCB1N6761 JANKCB1N6761

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

Custodians:
Army - CR
Navy - EC
Air Force - 17
NASA - NA

Review activities:
Army - AR, MI, SM
Navy - AS, CG, MC
Air Force - 19, 85, 99

Preparing activity:
DLA - CC

(Project 5961-2024)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.

2. The submitter of this form must complete blocks 4, 5, 6, and 7.

3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	**1. DOCUMENT NUMBER** MIL-PRF-19500/586D	**2. DOCUMENT DATE (YYMMDD)** 980710

3. DOCUMENT TITLE
SEMICONDUCTOR DEVICE, DIODE, SILICON, SCHOTTKY BARRIER, HERMETIC TYPES 1N5819-1, 1N5819UR-1, 1N6650-1, 1N6650UR-1, 1N6761-1 AND 1N6761UR-1 JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) Commercial DSN FAX EMAIL	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. Point of contact: Alan Barone	b. TELEPHONE Commercial 614-692-0510 DSN 850-0510 FAX 614-692-6939 EMAIL alan_barone@dscc.dla.mil
c. ADDRESS: Commander, Defense Supply Center Columbus, ATTN: DSCC-VAT, 3990 East Broad Street, Columbus, OH 43216-5000.	**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:** Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 DSN 289-2340

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T03:45Z
Check the source to verify that this is the current version before use.