MILITARY SPECIFICATION

CLEANING COMPOUND, AIRCRAFT EXTERIOR

This amendment forms a part of military specification MIL-C-85570B, dated 26 August 1987, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 6

Paragraph 3.9, delete in its entirety and substitute the following:

"3.9 Effect on plastic transparencies. The cleaning compound shall not craze, stain or discolor acrylic plastics when tested as specified in 4.6.10. The cleaning compound shall not craze, stain or discolor polycarbonate plastic when tested as specified in 4.6.10."

PAGE 14

Paragraph 4.6.10, delete in its entirety and substitute the following:

"4.6.10 Effect on plastic transparencies. The effect on acrylic materials shall be determined in accordance with ASTM F-484 using Type A and Type C specimens loaded to 3000 and 4500 psi outer fiber stress, respectively. The effect on polycarbonate plastic (MIL-P-83310) shall be determined using the test procedures specified in ASTM F-484 using specimens of the same dimensions stressed for 30 ± 2 minutes to an outer fiber stress of 2000 psi for Types II, III, IV and V and 1000 psi outer fiber stress for Type I. Cleaning compound concentrations shall be as follows:

Type I - as received
10% dilution in distilled water.

Type II - as received.
10% dilution in distilled water.

Type III - as received.

Type IV - as received.

Type V - as received.

AMSC N/A FSC 6850
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:06Z
Check the source to verify that this is the current version before use.

Custodians:
Navy - AS
Air Force - 68

Preparing Activity:
Navy - AS
(Project No. 6850-1036)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:06Z
Check the source to verify that this is the current version before use.