INCH-POUND

MIL-R-82779(OS)
29 December 1989
SUPERSEDING
WS 22162B
9 December 1986
(See 6.5)

MILITARY SPECIFICATION

RING, EXIT, AFT
IN-PROCESS REQUIREMENTS FOR

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the in-process requirements for one type of aft exit ring, referred to herein as the ring (see 6.1). The in-process requirements cover ring characteristics which must be verified prior to assembly and fabrication of the end product.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards and handbooks. The following specifications, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commanding Officer, Naval Ordnance Station, Standardization Branch (3730), Indian Head, MD 20640-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 1340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

TT-I-735 Isopropyl Alcohol

MILITARY

MIL-D-3464 Desiccants, Activated, Bagged, Packaging Use and Static Dehumidification

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from: Military Specifications and Standards, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094).

2.1.2 **Other Government documents, drawings, and publications.** The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

NAVAL SEA SYSTEMS COMMAND (CAGE Code 10001)

WR-43 Preparation of Quality Assurance Provisions (Including Classification of Characteristics)

(Copies of WR-43 are available from the Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120-5099.)

2.2 **Non-Government publications.** The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 740 Methyl Ethyl Ketone (DoD adopted)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

UNITED STATES PHARMACOPEIAL CONVENTION, INC.

The United States Pharmacopeia Absorbent Gauze

(Application for copies should be addressed to the Mack Publishing Company, Easton, PA 18042.)

Source: https://assist.dla.mil -- Downloaded: 202610-23T07:25Z
Check the source to verify that this is the currentversion before use.

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 **Order of precedence.** In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 **In-process.** The ring shall meet the requirements specified herein.

3.2 **Surface condition.** Defects in the surface condition of the outside diametrical surface of the subassembly (which consists of the ATJS graphite ring prior to adhesive application) and the outside diametrical and forward and aft face surfaces of the completed assembly shall not exceed the limits specified in table I.

TABLE I. Surface defect conditions.

Condition 1/	Permissible Condition Extent
1. Blemishes (see 6.3.1)	Blemish shall not exceed 1 inch long, 0.020 inch deep, or 0.050 inch wide. No more than two per part.
2. Delaminations (see 6.3.2)	None allowed.
3. Cracks (see 6.3.3)	None allowed.
4. Wrinkled areas (see 6.3.4)	None allowed.

1/ Any defects in overstock area (see 6.3.5) are acceptable (see figure 1).

3.3 **Cured adhesive surface.** Voids in the cured adhesive shall not exceed 0.050 inch in length and 0.050 inch in width. There shall be no more than one void in any 1-square inch area and no more than five voids per part.

3.4 **Physical properties.** Physical properties of the ring insulation shall be in accordance with table II.

Source: https://assist.dla.mil -- Downloaded: 202640-23T07:25Z
Check the source to verify that this is the currentversion before use.




FIGURE 1. Aft exit ring.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.

TABLE II. Physical properties.

Property	Limits	
	Minimum	Maximum
Specific gravity 23/23 degrees Celsius (°C)	1.42	1.55
Residual volatiles, percent (%)	0.00	3.00
Resin content, %	31.00	41.00
Summation of resin content and residual volatiles, %	31.00	41.50
Compressive strength, pounds per square inch (psi), with ply	21,000	40,000

3.5 **Workmanship.** The ring shall be free from surface contaminants, grease, oil, foreign material, and other defects which could render the part unsuitable for the intended use.

4. QUALITY ASSURANCE PROVISIONS

4.1 **Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 **Responsibility for compliance.** All items shall meet all requirements of section 3. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.

4.2 **Quality conformance inspection.** Quality conformance inspection shall consist of the examination and tests specified in table III.

TABLE III. Quality conformance inspection.

Inspection	Requirement	Test Method
Visual examination	3.2, 3.3 & 3.5	4.3.1
Specific gravity test	3.4	4.3.2
Residual volatiles test	3.4	4.3.3
Resin content test	3.4	4.3.4
Summation of residual volatiles and resin content test	3.4	4.3.5
Compressive strength test	3.4	4.3.6

4.2.1 **Sampling for tests.**

4.2.1.1 **Lot.** For inspection purposes, a lot shall consist of rings which have been overwrapped and cured as a single billet.

4.2.1.2 **Test rings and specimens.** A test ring shall be machined from either end of each billet of sufficient size to obtain all required test specimens for the physical properties tests specified herein. Each test ring shall be stored in a sealed bag and identified with the ring's part number and serial number, and the serial numbers of the other rings in the lot (see 4.2.1.1). Test specimens shall be removed from each ring and prepared for testing as indicated in the applicable test method.

4.2.3 **Classification of characteristics.** The characteristics verified by the tests and examination herein are classified as Major or Minor in accordance with WR-43. Tests that verify Major characteristics are identified by the symbol (M). The number following the classification symbol indicates the serial number of the test. The visual examination herein is not annotated with a classification code or serial number and is classified Minor.

4.3 **Methods of inspection.** The following inspection methods shall be used. Unless otherwise specified in the method, all weights, volumes, temperatures, and times shall be measured to the nearest specified unit or decimal.

Source: https://assist.dla.mil -- Downloaded: 202610-23T07:25Z
Check the source to verify that this is the current version before use.

NOTE: Reagent grade chemicals shall be used for chemical reactions in the conduct of all tests defined herein. Solvents and indicators may be commercial nonreagent grade materials.

4.3.1 Visual examination test. Each ring shall be visually examined to determine conformance to 3.2, 3.3 and 3.5. Noncompliance with any specified requirement shall constitute cause for rejection of the ring. The following solvent wipe method shall be used as an examination aid in determining conformance to 3.2.

a. Wet surface with methyl ethyl ketone (MEK) conforming to ASTM D 740 or isopropyl alcohol conforming to TT-I-735.

b. Wipe off excess solvent with Type VIII absorbent gauze conforming to The United States Pharmacopeia.

c. Allow the part to dry in air. Defects will appear as well-defined wetted lines.

4.3.2 Specific gravity test. (M101) Specific gravity shall be determined in accordance with the following:

a. Remove three test specimens (0.30 $\pm$ 0.06 inch by 0.30 $\pm$ 0.06 inch by 0.60 $\pm$ 0.06 inch) 120 $\pm$ 24 degrees apart, from the test ring.

b. Clean each specimen using a clean cloth or a laboratory towel moistened with MEK or isopropyl alcohol, and allow the specimen to dry in air for a minimum of 20 minutes (see 4.3.1a).

c. Weigh each specimen in air, and record the weight to nearest 0.1 milligram (mg).

d. Weigh each specimen in kerosene, and record the weight to nearest 0.1 mg.

e. Calculate the specific gravity of each specimen as follows:

$$\text{Specific gravity at } 23/23^{\circ}C = \frac{A \times C}{A - B}$$

Where: A = weight of specimen in air, g

B = weight of specimen in kerosene, g

C = specific gravity of kerosene at 23/23°C.

f. Record specific gravity of each specimen to the nearest 0.01 unit.

g. Calculate the average specific gravity of each specimen to the nearest 0.01 unit. Noncompliance of the average reading with the

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.

specific gravity requirement specified in 3.4 shall be cause for rejection of each ring in the lot (see 4.2.1).

4.3.3 **Residual volatiles test.** (M102) Residual volatiles of the ring shall be determined in accordance with the following:

a. Remove three test specimens (0.30 ± 0.06 inch by 0.30 ± 0.06 inch by 0.60 ± 0.06 inch) 120 ± 24 degrees apart, from the test ring.

b. Clean each specimen using a clean cloth or a laboratory towel moistened with MEK or isopropyl alcohol, and allow the specimen to dry in air for a minimum of 20 minutes (see 4.3.1a).

c. Pre-dry the specimens for a minimum of 18 hours in desiccant conforming to MIL-D-3464.

d. Weigh each test specimen to the nearest 0.001 gram (g) in a tared crucible which has been previously heated at 325 ± 10 degrees Fahrenheit (°F) for a minimum of 1 hour and cooled to room temperature in desiccator.

e. Place each crucible and specimen into an air circulating oven which has been preheated to, and maintained at, 325 ± 10°F.

f. Heat the specimens in oven for 4 to 4.5 hours.

g. Remove the crucibles and specimens from the oven, and cool in desiccator to room temperature.

h. Weigh each crucible and contents to nearest 0.001 g. Retain samples for determination of resin content (see 4.3.4).

i. Calculate residual volatiles of each specimen as follows:

$$\text{Percent residual volatiles} = \frac{(A - B)}{A} (100)$$

Where: A = sample weight before heating, g

B = sample weight after heating, g

j. Record average of three determinations to nearest 0.01 percent. Noncompliance of the average determination with the residual volatiles requirement specified in 3.4 shall be cause for rejection of each ring in the lot (see 4.2.1).

4.3.4 **Resin content test.** (+M104) Resin content shall be determined in accordance with the following:

Source: https://assist.dla.mil -- Downloaded: 202640-23T07:25Z
Check the source to verify that this is the currentversion before use.

a. Obtain three test specimens from the residual volatiles test (see 4.3.3).

b. Record the specimen weight to nearest 0.001 g.

c. Place the test specimen in a Vycor tube and tightly attach the tube to test apparatus as shown on figure 2.

d. Start the vacuum pump, and evacuate the system. Check for air leaks by clamping off the hose to the vacuum pump and noting manometer. The leak rate must be less than 5 millimeters (0.2 inch) Hg per minute. Recheck the joints until this level is achieved.

e. With the vacuum on and the pressure stabilized, place a Fisher burner under the specimen. Adjust the flame area to completely cover sample.

NOTE: A tube furnace maintained at 1500 $\pm$ 25°F may be used in place of the Fisher burner.

f. Continue pyrolysis until manometer or gauge reading is the same reading as before pyrolysis.

g. Turn off the burners, and cool under vacuum until the specimen is at room temperature (touch Vycor tube just under the test specimen).

h. Turn off the vacuum, and carefully let air into the system. When pressure equilibrium is reached, remove the specimen from the test tube and weigh to nearest 0.001 g.

i. Repeat b through h for each specimen tested.

j. Calculate the resin content of each specimen as follows:

$$\text{Dry resin content, percent} = (1.00 - \frac{A}{B})\,(100)K$$

Where: A = weight of specimen after pyrolysis, g

B = weight of specimen before pyrolysis, g

K = constant ratio of percent resin (Soxhlet extraction or di-methyl-formamide (DMF) wash) to percent weight loss by pyrolysis (K - U.S. Polymeric = 2.008, K - Fiberite = 2.060.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.




FIGURE 2. Resin content apparatus setup.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.

k. Record resin content average of the three specimens to the nearest 0.01 percent. Noncompliance of the average reading with the resin content requirement specified in 3.4 shall be cause for rejection of each ring in the lot (see 4.2.1).

4.3.5 **Summation of residual volatiles and resin content test.** (M104) The summation of the results of the tests performed in 4.3.3 and 4.3.4 shall be examined for conformance to the summation of residual volatiles and resin content requirement specified in 3.4. Noncompliance with the specified requirement shall be cause for rejection of each ring in the lot (see 4.2.1).

4.3.6 **Compressive strength.** (-M106) Compressive strength of the ring insulation shall be determined in accordance with the following:

a. Remove three test specimens (0.300 ± 0.005 inch by 0.300 ± 0.005 inch by 0.600 ± 0.005 inch) 120 ± 24 degrees apart, from the test ring. Maximum surface roughness shall be 125 microinches root mean square (RMS). Specimens shall be machined such that length of specimen (0.600 inch reference) is tangent (within ± 18 degrees) to test ring curvature.

b. Measure (to nearest 0.001 inch) length, width, and height of each test specimen with a calibrated micrometer. Record all readings on a data sheet. Calculate and record the cross-section of each specimen.

c. Set test specimen on load cell table of an Instron tensile tester equipped with a Model CF load cell, with the length (0.600 inch reference) normal to the faces of the tester.

d. Depress DOWN button to start compression. Cross-head speed should be 0.05 inch-per-minute.

e. When the test sample fails, push RETURN button. This will return the crosshead to ZERO position.

f. Repeat c through e for each test specimen.

g. Calculate the compressive strength of each specimen as follows:

$$\text{Compressive strength} = \frac{C}{A}$$

Where: C = maximum load, pounds

A = cross-sectional area, square inch.

h. Record average compressive strength of each specimen to nearest psi. Noncompliance of the average reading with the compressive

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.

strength requirement specified in 3.4 shall be cause for rejection of each ring in the lot (see 4.2.1).

5. PACKAGING

This section is not applicable to this specification.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory).

6.1 Intended use. The ring specified herein is intended for use as a component in the Standard Missile Mk 104 Dual Thrust Rocket Motor.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of this specification.

b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1, 2.1.2 and 2.2).

6.3 Definitions.

6.3.1 Blemishes. Any superficial imperfection or marks or deformities such as scratches, crazing, gouges, cuts, or stains.

6.3.2 Delamination. A separation between fabric plies which has sharply defined boundaries that are parallel to the fabric plies.

6.3.3 Crack. A parting or separation which extends across the fabric plies.

6.3.4 Wrinkled areas. Distortions in fabric orientation normal to the plane of the fabric.

6.3.5 Overstock area. Excess material which will be removed at a higher level of assembly (see figure 1).

6.4 Subject term (key word) listing.

Rocket Motor, Dual Thrust, Mk 104
Standard Missile

6.5 Supersedure information. MIL-R-82778 incorporates the following engineering change proposals (ECPs), notices of revision (NORs), and specification change notices (SCNs):

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.

ECPs	NORs	SCNs
----	----	SCN 3 (7/8/87)
MTA019C1 (7/1/88)	MTA071.2 (7/27/88)	----
ARC001 (7/27/88)	ARC001.10 (7/27/88)	----
MTA080 (9/29/88)	MTA080.4 (9/29/88)	----

Preparing Activity:
NAVY-OS
(Project 1340-N788)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-R-82779	2. DOCUMENT DATE (YYMMDD) 29 December 1989

3. DOCUMENT TITLE
RING, EXIT, AFT

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY NAVAL ORDNANCE STATION (CODE 3730) INDIAN HEAD, MD 20640-5000

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON
c. ADDRESS (Include Zip Code)	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:25Z
Check the source to verify that this is the current version before use.