INCH-POUND

MIL-DTL-43036C
14 June 2017
SUPERSEDING
MIL-T-43036B
w/AMENDMENT 3
04 January 1993

DETAIL SPECIFICATION

TAPE, PRESSURE-SENSITIVE ADHESIVE, PLASTIC FILM, (FOR SEALING FIBER CONTAINER AND CANS)

Reactivated after 14Jun17 and may be used for new or existing design acquisitions.

This specification is approved for use by the U.S. Army Armament Research Development and Engineering Center (ARDEC), and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers waterproof, water-vapor proof, plastic film, pressure sensitive adhesive tapes designed primarily for the sealing of fiber ammunition containers meeting MIL-DTL-2439, plastic containers and similar applications requiring a tough sealing medium having the properties of the tapes meeting this specification.

1.2 Classification. The tapes covered by this specification are of the following types:

Type I – Reinforced polyester film
Type II - Non-reinforced polyester film

Comments, suggestions or questions on this document should be addressed to: U.S. Army ARDEC, ATTN: RDAR-EIQ-SA, Picatinny Arsenal, NJ 07806-5000 or emailed to ardecstdzn@conus.army.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database https://assist.dla.mil.

AMSC N/A FSC 7510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 or 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-DTL-2439 Container, Ammunition, Fiber Spirally Wound

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-130 Identification Marking of US Military Property
MIL-STD-1168 Lot Numbering of Ammunition
MIL-STD-1916 DOD Preferred Methods for Acceptance of Product

(Copies of these documents are available on line at http://quicksearch.dla.mil.)

2.3 Non-Government publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D3330/D3330M Peel Adhesion of Pressure-Sensitive Tape, Standard Test Method for
ASTM-D3611 Accelerated Aging of Pressure-Sensitive Tapes, Standard Practice for
ASTM D3652/D3652M Thickness of Pressure-Sensitive Tapes, Standard Test Method for
ASTM D3654/D3654M Shear Adhesion of Pressure Sensitive Tapes, Standard Test Method for
ASTM D3715/D3715M Quality Assurance of Pressure-Sensitive Tapes, Standard Practice for
ASTM-D3759 Breaking Strength and Elongation of Pressure-Sensitive Tapes, Standard Test Method for
ASTM-D3811 Unwind Force of Pressure-Sensitive Tapes, Standard Test Method for
ASTM-D3816 Water Penetration Rate of Pressure-Sensitive Tapes, Standard Test Method for
ASTM-D3833 Water Vapor Transmission of Pressure-Sensitive Tapes, Standard Test Method for
ASTM D3951 Standard Practice for Commercial Packaging
ASTM D5486 Standard Specification for Pressure-Sensitive Tape for Packaging, Box Closure, and Sealing

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

(Copies of ASTM Standards may be ordered online at http://www.astm.org/ or from the ASTM International, 100 Barr Harbor Drive, Conshohocken, PA 19428-2959).

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.2.

3.2 Conformance. A sample shall be subjected to conformance inspection in accordance with 4.3.

3.3 Construction.

3.3.1 Type I. Type I tape shall consist of a polyester film, coated on one side with a homogeneous pressure-sensitive tape adhesive containing longitudinal reinforcing filaments. The reinforcing filaments shall be imbedded in the adhesive in a uniform layer throughout the length of the tape. The tape shall require no heat, solvent, or other preparation prior to or after application, and shall remove from the fiber containers without breaking, over a temperature range from -65° to 160°F (-53.9° to 71.1°C). See Table I below, for properties of Type I tape.

3.3.2 Type II. Type II tape shall consist of a biaxially oriented polyester film coated on one side with a homogeneous pressure-sensitive adhesive in a uniform layer throughout the length of the tape. The tape shall not require any preparation prior to or after application, and shall remove from the fiber containers or cans without breaking, over a temperature range from -65° to 160°F (-53.9° to 71.1°C). See Table I below, for properties of Type II tape.

Table I. Properties of Tapes.

Test	Type I		Type II		Method
	Min	Max	Min	Max	
Thickness, inches	--	0.0080	--	0.0040	4.4.1
Tensile breaking strength, lbs/in					4.4.2
Machine Direction	50	--	15	--	
Cross Direction	--	--	20	--	
Elongation, percent	20	35	100	--	4.4.3
Adhesion, oz/in width					4.4.5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

Test	Type I		Type II		Method
	Min	Max	Min	Max	
Initial	30	--	50	--	4.4.5.1
After accelerated aging	24	--	40	--	4.4.5.2
Holding Power, minutes					4.4.6
At 73.5°F (23°C)	1440	--	3000	--	4.4.6.1
At 160°F (71.1°C)	1440	--	2000	--	4.4.6.2
At -65°F (-53.9°C)	1440	--	2000	--	4.4.6.3
Unwind, lbs/in					4.4.7
Initial	--	3.0	--	4.0	4.4.7.1
After accelerated aging	--	4.0	--	4.0	4.4.7.2
Water vapor transmission rate, g/100 sq in/ 24 h	--	2.0	--	2.0	4.4.8
Water penetration rate, g/100 sq in/ 24 h	--	1.0	--	1.0	4.4.9
Roll distortion, inches					4.4.10
Radius	--	0.75	--	0.75	4.4.10.1
Width	--	0.75	--	0.75	4.4.10.2

3.4 Rolls. The tape shall be uniformly and evenly wound in rolls, adhesive side in, on a core of sufficient rigidity to prevent distortion of the roll under conditions of testing, transportation, storage, and use. The inside diameter of the core shall be 3 (-0, + 1/16) inches.

3.4.1 Length. Type I tape shall be furnished in 60 or 240 yard rolls as specified. Type II tape shall be furnished in 60 or 500 yard rolls, as specified. Each roll shall consist of a continuous length of tape, except that any single 60 yard roll shall contain no more than three splices, and 240 and 500 yard rolls shall contain no more than eight splices. The splices shall be made in such a manner that they will not separate when the roll is unwound for inspection or during machine or hand application.

3.4.2 Width. The width of the rolls shall be 1, 1 ½ inches, or other commercially available width as specified. A tolerance of ± 1/32 inch shall be allowed.

3.4.3 Color. The color of Type I tape shall be black. The color of Type II tape shall be transparent.

3.4.4 Thickness. The tape thickness shall meet the requirements of Table I.

3.5 Adhesive. The tape shall meet the applicable requirements of Table I, when applied and tested as specified in 4.4.5. In addition, the tape shall show no visual evidence of curling, buckling or lifting. There shall be no visual evidence of stringiness of the adhesive nor of separation of any of the tape components when unwound during inspection or application. The adhesive shall cause the tape to

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

adhere immediately, uniformly, and firmly to clean, dry surfaces when applied at any temperature within the range of 50° to 155°F (10° to 68.3°C).

3.6 Holding power. The tape specimens with a one-inch area and a 1000 gram load at 73.5°F (23°C), and also a 100 gram load at 160°F (71.1°C) and at -65°F (-53.9°C), adhered to a steel test panel, shall show no visual evidence of creepage in excess of 1/8 inch with the time interval specified in Table I when tested as specified in 4.4.6.

3.7 Unwind properties. When tested as specified in 4.4.7, the tape shall meet the applicable requirements of Table I, in the as received condition and after accelerated aging. The tape shall not break, nor shall the adhesive transfer to the back of the adjacent layer of tape so as to be visually evident during unwinding of the tape as received, or after accelerated aging.

3.8 Accelerated aging . The tape shall pass the accelerated aging tests as described in 4.4.4. The tape shall show no visual evidence of deterioration, separation of components or change in adhesive or breaking when examined after the aging procedure. The tape shall not exhibit sufficient adhesive flow to the sides of the rolls as to cause edge bond to be visually evident between the successive layers of the tape rolls. (Such edge bond would be discernible in unwinding of the rolls (see 4.4.7)).

3.9 Stability on a fiber container. The tape, when tested as specified in 4.4.11, shall show no evidence of buckling, curling or lifting extending toward the center of the tape plies more than ¼ of the width of the tape from either side, and shall remove from the container without breaking. Adhesive transfer to the fiber containers shall not be cause from rejection.

3.10 Low temperature removal. The tape shall be removable from the fiber containers without breaking the tape backing, when tested as specified in 4.4.12.

3.11 Roll distortion. The tape rolls shall show no more distortion than listed in Table I, nor shall there be any visual evidence of distortion of the core when subjected to the accelerated aging procedure as specified in 4.4.10.

3.12 Marking on rolls. Each roll of tape shall be marked in or at the edge of the core with the manufacturer's name and code designation and (full or coded) date of manufacture.

3.13 Water vapor transmission rate. The tape shall not exceed the requirements of Table I when tested in accordance with ASTM-D3833.

3.14 Water penetration. The tape shall not exceed the requirements of Table I when tested in accordance with ASTM-D3816.

3.15 Tensile strength and elongation. The tape shall meet the tensile breaking strength and elongation requirements of Table I.

3.16 Workmanship. The tape shall be fabricated in a thorough, workmanlike manner. It shall be free of foreign matter and defects that detract from its appearance or that may impair its serviceability. The adhesive shall be a smooth uniform coating, evenly applied, covering the entire area of the backing without any bare spots or lumps. The tape shall be securely laminated, have no layer separation nor presence of blisters (applicable to reinforced tapes only). There shall be no holes, tears, cuts, cracks, or

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

sharp creases. The edges of the tape shall be straight, clean cut, unbroken and not sticky. There shall not be any telescoping of the rolls.

3.17 Ammunition lot numbering. Lot numbers shall be applied per MIL-STD-1168.

4. VERIFICATION

TABLE II. Requirement/verification cross reference matrix

Methods of Verification 1 – Examination 2 – Test				Classes of Verification A- First Article B- Conformance/Acceptance		
Section 3 & 5 Requirements	Description	Verification Method		Verification Class		Section 4 Verification
		1	2	A	B	
3.1	First article	X	X	X		4.2
3.2	Conformance	X	X		X	4.3
3.3	Construction	X		X	X	4.3.2
3.4	Rolls	X		X	X	4.3.2, 4.4.1
3.5	Adhesive		X	X	X	4.4.5
3.6	Holding power		X	X	X	4.4.6
3.7	Unwind properties		X	X	X	4.4.7
3.8	Accelerated aging		X	X	X	4.4.4
3.9	Stability on a fiber container		X	X	X	4.4.11
3.10	Low temperature removal		X	X	X	4.4.12
3.11	Roll distortion		X	X	X	4.4.10
3.12	Marking on rolls	X		X	X	4.3.2
3.13	Water vapor transmission rate		X	X	X	4.4.8
3.14	Water penetration		X	X	X	4.4.9
3.15	Tensile strength and elongation		X	X	X	4.4.2, 4.4.3
3.16	Workmanship	X		X	X	4.3.2
3.17	Lot numbering	X		X	X	4.3.2
5.1	Packaging and packing	X		X	X	4.5.1
5.2	Marking	X		X	X	4.5.2

4.1 Classification of inspections. The verification requirements specified herein are classified as follows:

a. First article inspection (see 4.2).

b. Conformance inspection (see 4.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

4.2 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with Table II.

4.2.1 First article quantity. First article verification shall be performed on a quantity of 5 rolls of tape which have been produced using the same production processes, procedures, and equipment as will be used in production. Materials shall be produced from the same source of supply as regular production.

4.2.2 Inspections to be performed. Samples may be subjected to any or all of the examination of tests specified in this specification.

4.2.3 First article rejection. If any item fails to comply with requirements, the first article sample shall be rejected.

4.3 Conformance inspection.

4.3.1 Inspection lot formation. Lotting criteria and lot size shall be as specified in ASTM-D3715. Units of product selected for inspection shall represent only the inspection lot from which drawn and shall not be construed to represent any prior or subsequent quantities presented for inspection. Lot numbering, shall be in accordance with MIL-STD-1168.

4.3.2 Classification of characteristics.

a. Sampling requirements. The sampling and testing for end item testing shall be as specified in ASTM-D3715 and conducted at an Acceptable Quality Level (AQL) of 4 percent.

b. Conformance inspection. For all conformance inspections the same sample specimen may be used for all non-destructive examinations or tests.

c. Alternative Inspections. Alternative conformance inspections may be submitted and approved in accordance with ASTM D3715/D3715M.

4.3.3	Pressure Sensitive Tape			Drawing Number
Classification	Examination or Test	Conformance Criteria	Requirement Paragraph	Next Higher Assembly Inspection Method Reference
Critical	None Defined			
Major				
101	Tensile breaking strength	4.3.2	3.14	4.4.2
102	Elongation	4.3.2	3.14	4.4.3
103	Accelerated aging	4.3.2	3.8	4.4.4
104	Initial adhesion	4.3.2	3.5	4.4.5.1
105	Adhesion after accelerated aging	4.3.2	3.5	4.4.52
106	Holding power ambient	4.3.2	3.6	4.4.6.1

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

4.3.3	Pressure Sensitive Tape			Drawing Number
Classification	Examination or Test	Conformance Criteria	Requirement Paragraph	Next Higher Assembly Inspection Method Reference
107	Holding power hot	4.3.2	3.6	4.4.6.2
108	Holding power cold	4.3.2	3.6	4.4.6.3
109	Initial unwind properties	4.3.2	3.7	4.4.7.1
110	Unwind properties after accelerated aging	4.3.2	3.7	4.4.7.3
111	Water vapor transmission rate	4.3.2	3.13	4.4.8
112	Water penetration rate	4.3.2	3.14	4.4.9
113	Stability on fiber containers	4.3.2	3.9	4.4.11
114	Low temp removal	4.3.2	3.10	4.4.12
115	Packaging and packing	4.3.2	5.1	4.5.1
116	Marking	4.3.2	3.12, 5.2	4.5.2
Minor				
201	Thickness		3.4.4	4.4.1
202	Roll/radius distortion	4.3.2	3.11, 3.4.1	4.4.10, 4.4.10.1
203	Roll/width distortion	4.3.2	3.11, 3.4.1	4.4.10, 4.4.10.2
204	Width	4.3.2	3.4.2	Gage
205	Color	4.3.2	3.4.3	Visual

4.4 Test methods and procedures.

4.4.1 Thickness. The thickness of the tape shall be determined as specified in ASTM D3652/D3652M.

4.4.2 Tensile breaking strength. The tensile breaking strength shall be performed in accordance with ASTM-D3759.

4.4.2.1 Type I Tape. Procedure B shall be used to determine the Machine Direction tensile breaking strength.

4.4.2.2 Type II Tape. Procedure A shall be used to determine the Machine Direction tensile breaking strength. Procedure D shall be used to determine the Cross Direction tensile breaking strength.

4.4.3 Elongation. The elongation of the tape shall be determined in accordance with ASTM-D3759.

4.4.4 Accelerated aging. The accelerated aging of the tape shall be determined in accordance with ASTM-D3611.

4.4.5 Adhesive.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

4.4.45.1 Initial adhesion. The initial adhesion of the tape shall be determined in accordance with Test Method A of ASTM D3330/D3330M.

4.4.5.2 Adhesion after accelerated aging. The accelerated aging of the tape shall be performed in accordance with 4.4.4. Then, the adhesion of the tape shall be determined on accordance with Test Method A of ASTM D3330/D3330M.

4.4.6 Holding power. The holding power of the tape shall be determined in accordance with ASTM D3654/D3654M.

4.4.6.1 At 73.5°F (23°C). Procedure A shall be used to determine the holding power (sheer adhesion) of the tape.

4.4.6.2 At 160°F (71.1°C). Procedure H shall be used to determine the holding power (sheer adhesion) of the tape.

4.4.6.3 At -65°F (-53.9°C). Procedure H shall be used to determine the holding power (sheer adhesion) of the tape.

4.4.7 Unwind properties.

4.4.7.1 Initial unwind properties. The initial unwind properties of the tae shall be determined in accordance with ASTM-D3811.

4.4.7.2 Unwind properties after accelerated aging. The accelerated aging of the tape shall be performed in accordance with 4.4.4. Then, the unwind properties of the tape shall be determined in accordance with ASTM-D3811.

4.4.8 Water vapor transmission rate. The water vapor transmission rate shall be performed in accordance with ASTM-D3833.

4.4.9 Water penetration rate. The water penetration rate shall be in accordance with ASTM-D3816.

4.4.10. Roll distortion. The determination shall be made by comparing the two principal dimensions of the sample rolls of tape obtained in as received condition and after accelerated aging (as performed in accordance with 4.5.4). Measurements shall be made to the nearest 1/32 of an inch, by means of a ruler graduated to that dimension. The values obtained as received and after accelerated aging on the same rolls will be recorded and the differences between the initial values and those obtained after aging will be roll distortion. The individual values are averaged and reported to the nearest 1/32 of an inch.

4.4.10.1 Radius distortion. Radius distortion shall be measured by placing each of the rolls flat on its side on a sheet of paper. The circumference (periphery) is traced and the greatest radius (distance from the center to the farthest point on the circumference) of the outline is measured to the nearest 1/32 of an inch.

4.4.10.2 Width distortion. The width of the test rolls shall be determined to the same accuracy as in 4.5.10.1 by placing each roll flat on its side and measuring the vertical distance from the base to the uppermost ply of the tape to the nearest 1/32 of an inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

4.4.11 Determination of stability on fiber containers. Stability of the tape on fiber containers shall be determined as follows: Two (2) fiber containers shall be used for this test, one asphalt (Type III) and one PolyLam (Type V) per MIL-DTL-2439. Specimens of one inch wide tape shall be applied to a fiber container two to six inches in diameter, so that it extends once around the container perpendicular to the main axis of the container and onto itself a distance of approximately two inches. A tape release tab, at least six inches in length, shall be provided by folding the extending tape back upon itself. The assembly shall then be placed in a temperature cabinet maintained at 160°F ± 3.5°F (71.7°C ± 2°C) for ten days. At the end of that time, the assembly shall be removed from the cabinet, conditioned at 73.5°F (23°C) for a minimum of two hours and the tape removed at a rate of approximately three feet per second as roughly represented by a sharp yank or pull. One test shall be made per sample roll selected on each container.

4.4.12 Determination of low temperature removal. Specimens of the tape shall be applied to one Type III (Asphalt) and one Type V (PolyLam) ammunition fiber container per a MIL-DTL-2439 as described in 4.5.11. Place the assemblies in an air circulating oven maintained at 155°F ± 3.5°F (68.3°C ± 2°C) for a period of 24 hours. Then transfer the assemblies to a compartment maintained at -65°F ± 3.5°F (-53.9°C ± 2°C) for two hours. At the end of this conditioning period, remove the tape from the assemblies at a rate of approximately three feet per second as roughly represented by a sharp yank or pull. Care shall be taken to keep the assemblies at the low temperature during removal ofthe tape. One test shall be made for each sample roll on each containers.

4.5 Packaging inspections.

4.5.1 Packaging and packing inspection. Inspect in accordance with ASTM D5486 AND ASTM D3951 at the level specified in the contract or purchase order.

4.5.2 Marking inspection. Packaging shall be visually inspected to ensure markings are in accordance with the requirements of ASTM D5486 and ASTM D3951 and the documents forming part of this specification.

5. PACKAGING. The inspection level and acceptance quality level for the packaging, packing and marking of the tape shall be as specified in ASTM D5486 and ASTM D3951.

5.1 Packaging and packing. Unless otherwise specified, the rolls of tape shall be bulk packed in accordance with the requirements in ASTM D5486 and ASTM D3951 at the level specified in the contract or purchase order.

5.2 Marking. Containers of tape shall be marked in accordance with the requirements of ASTM D5486 and ASTM D3951 and those documents forming a part of thatspecification.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful but is not mandatory.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

6.1 Intended use. The pressure sensitive tapes covered by this specification are designed primarily for sealing fiber containers meeting MIL-DTL-2439. It may be used in other applications where waterproof, water vapor proof, medium tensile strength tape possessing good low temperature removal properties is required.

6.2 Acquisition Requirements. Acquisition documents should specify the following:

a. Title, number and date of this specification.
b. Quality required and delivery schedule.
c. Quality conformance inspection, if other than specified in Section 4 of this specification.
d. First article sample requirements, if other than specified in Section 4 of this specification.
e. Packaging requirements, if other than specified in Section 5 of this specification.
f. Certificates of conformance for each lot of shipment of product.
g. Level of packaging and packing.
h. Width of tape required.
i. Length of roll required.

6.3 Application. The following steps are recommended in applying these types of tape to telescoping tubes, slip cover cans and similar circular containers to ensure a moisture-vapor-tight seal.

Step 1. Press the cap of the tube onto the body and hold under tension until the pressure inside equalizes with pressure outside the tube. This can be checked by releasing the cap and if it does not tend to come off, pressures have equalized.

Step 2. With the cap firmly pressed in place, apply a short length of the tape placed so that one-half of the width falls on each side of the joint between the cap and the body.

Press the tape firmly into place and continue to apply the tape around the tube maintaining approximately a 10 pound tension on the tape until 1 ¼ laps have been applied. Release tension, cut the tape from the roll leaving a free end of approximately ½ inch which is folded adhesive to adhesive to form a tab to aid in removing the tape.

Step 3. After application of the tape, the tube and tape should be allowed to condition under standard conditions for approximately 24 hours before testing of any tape is begun.

6.3 Storage. The tape should be stored in the original container in a cool location. It should not be stored close to steam pipes, radiators or other sources of heat, or in locations where it may be exposed to the direct rays of the sun.

6.4 Subject term (key-word) listing.

Adhesion
Fiber
Holding
Vapor
Waterproof

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.

changes with respect to the previous issue due to the extent of the changes.

CONCLUDING INFORMATION

Custodians:
Army-AR
Navy-AS
Air Force-99

Preparing Activity:
Army-AR
Project No.: 7510-2017-001

Review Activities:
Army-GL
Navy-OS
Air Force-69

User Activities:
Army-MI
Navy-SH, SA, OS

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:25Z
Check the source to verify that this is the current version before use.