MIL-T-43512B
5 December 1986
SUPERSEDING
MIL-T-43512A
7 December 1970

MILITARY SPECIFICATION

TENTS, MISSILE SYSTEM EQUIPMENT CONSOLE, (HIGH-POWER ILLUMINATOR HAWK)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers two frame-supported console tents for use with the Hawk Missile System. A cover for each tent with its frame components is furnished to afford protection during storage and transport.

1.2 Classification. The console tents consist of the following items:

Tent, Console, High-Power Illuminator, Hawk System, Front
Tent, Console, High-Power Illuminator, Hawk System, Aft

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Documents. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

T-T-871	- Twine, Cotton, Wrapping
T-T-911	- Twine, Fibrous, Jute
V-F-106	- Fasteners, Slide, Interlocking

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

V-T-285	- Thread, Polyester
TT-P-595	- Preservative Coating, Canvas
UU-T-94	- Tape, Embossing
CCC-C-429	- Cloth, Osnaburg, Cotton
CCC-C-467	- Cloth, Burlap, Jute (or Kenaf)
DDD-L-20	- Label; For Clothing, Equipage and Tentage (General Use)
PPP-B-601	- Boxes, Wood, Cleated-Plywood
PPP-B-636	- Boxes, Shipping, Fiberboard

MILITARY

MIL-C-496	- Clips, End, Strap
MIL-W-530	- Webbing, Textile, Cotton General Purpose, Natural or in Colors
MIL-B-543	- Buckles, Tongueless and Web Strap
MIL-R-1670	- Rope, Tent-Lay
MIL-L-1709	- Lines, Tent
MIL-S-1734	- Slips, Tent Line
MIL-C-2399	- Cement, Liquid, Tent Patching
MIL-C-10799	- Cloth, Coated, Cotton, Vinyl Coated, Fire and Mildew Resistant
MIL-G-16491	- Grommet, Metallic
MIL-F-21840	- Fastener Tapes, Hook and Pile, Synthetic
MIL-R-30500	- Rope, Polyester
MIL-L-35078	- Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For
MIL-T-40625	- Tubing, Bias Sewn (Burlap or Osnaburg) Cloth
MIL-C-43256	- Cord, Polyester, Solid Braid
MIL-T-43566	- Tape, Textile, Cotton, General Purpose, Natural or in Colors
MIL-C-43627	- Cloth, Duck, Cotton, Plied Yarns, Fire, Water, Weather and Mildew Resistant Treated, Lightdry Finish
MIL-W-44049	- Webbing, Textile and Tape, Textile, Polypropylene, General Purpose, Natural or in Colors
MIL-A-52194	- Adhesive, Epoxy (For Bonding Glass Reinforced Polyester)

STANDARDS

FEDERAL

FED-STD-191	- Textile Test Methods
FED-STD-751	- Stitches, Seams, and Stitchings

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
MS-27183	- Washer, Flat-Round, Steel, Cadmium Plated, General Purpose
MS-27980	- Fasteners, Snap, Style 2 (Regular Wire Spring Clamp Type)
MS-35307	- Screw, Cap, Hexagon (Finished Hexagon Bolt), Steel Corrosion Resisting, Passivated UNC-2A
MS-51967	- Nut, Plain, Hexagon-Carbon, Steel, Cadmium Plated, UNC-2B

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

5-4-1103	- Frame, Tent, High Power Illuminator, Front and Aft; Assembly Complete
5-4-1104	- Corner Support Assembly and Details
5-4-1105	- Pallet Adapter Assembly and Details
5-4-1116	- Tents, Console, High Power Illuminator, Hawk Systems, Front; Assembly Complete
5-4-1117	- Front Wall Assembly
5-4-1118	- Front Wall Sections and Details
5-4-1119	- Piece "A" and Piece "B" Assemblies and Details
5-4-1120	- Left Wall & Right Wall Assemblies & Details
5-4-1121	- Left Wall & Right Wall Details & Sections
5-4-1122	- Rear Wall Assembly
5-4-1123	- Rear Wall Details
5-4-1124	- Roof Assembly
5-4-1125	- Ground Cloth Assembly, Miscellaneous Details
5-4-1126	- Cover Assembly
5-4-1127	- Cover Details and Sections
5-4-1128	- Erection Instructions
5-4-1129	- Tents, Console, High Power Illuminator, Hawk System, Aft; Assembly Complete
5-4-1130	- Front Wall Assembly
5-4-1131	- Piece "A" Assembly and Details
5-4-1132	- Piece "B" Assembly and Details
5-4-1133	- Left Wall and Right Wall Assemblies and Details
5-4-1134	- Rear Wall Assemblies
5-4-1135	- Roof Assembly

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

5-4-1136 - Ground Cloth Assembly, Miscellaneous Details
5-4-1137 - Cover Assembly
5-4-1138 - Erection Instructions

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.1.2 Other Government documents. The following other Government documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

Department of the Army Field Manual FM 10-16 - General Repair of Tents, Canvas and Webbing

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 1788 - Rigid Acrylonitrile-Butadiene-Styrene (ABS) Plastics
D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society For Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

3.2 Materials and components. (See 6.5)

3.2.1 Cloth, duck, cotton. The cotton cloth used for the tent shall conform to MIL-C-43627, and the color shall be Olive Drab 7.

3.2.2 Cloth, coated. Cloth used for the tent and frame cover and for roof reinforcement panels shall conform to type II, class 1, Olive Drab 7 of MIL-C-10799.

3.2.3 Cloth, polyester. The polyester cloth used for the light ports shall be water repellent, shade natural, and shall conform to the following requirements when tested as specified in 4.4.1.1:

a. Physical properties as follows:
Fiber - Polyester
Weave - Plain, 1 by 1
Texture, threads per inch, minimum
Warp - 80
Filling - 64
Breaking strength (grab), pounds, minimum
Warp - 290
Filling - 265
Weight - 5.5 ± 0.5 oz. per sq. yd.
Water resistance - spray rating 90, 90, 80 (three determinations)

b. Finishing properties as follows:
(1) A water repellent of the silicone type is specified. However, other water-repellent compounds may be used if approved by the contracting officer.
(2) The fabric shall be scoured, calendered, and heat set. The color shall be natural; the fabric shall have a maximum air permeability of 1.5 cu. ft. per minute per sq. ft., and a minimum luminous transmission of 40 percent.

* 3.2.4 Tape, textile, cotton. The tape shall conform to type I, class 4, 3/4 inch, 1 1/2-inch, and 2-inch widths of MIL-T-43566 and shall be Olive Drab 7. Alternatively, the tape shall be polypropylene conforming to type I, class 4, Olive Drab 7 of MIL-W-44049.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

f Association of the (Application for copies should be addressed to the Naval

* 3.2.5 Webbing, textile, cotton. The webbing shall conform to type IIB, class 4, 1-inch width of MIL-W-530 and shall be Olive Drab 7. Alternatively, the webbing shall be polypropylene conforming to type IIb, class 4, Olive Drab 7 of MIL-W-44049.

3.2.6 Thread, polyester. The thread shall be type I, class 1, sub-class B, dyed to match shade S-1 (Cable No. 66022) of V-T-285. The dyed thread shall show fastness to weathering equal to or better than a standard shade sample (see 6.4). If no standard shade sample is available, the dyed thread shall show good fastness to weathering. Thread sizes shall be as follows:

a. For all stitching except bartacking, stitching on cover, and stitching indicated by "Z" on the drawings, use size F for needle and bobbin.

b. For all stitching on cover, use size FF for needle and bobbin.

c. For stitching indicated by "Z" on the drawings, use size F for needle and size E for looper.

d. For bartacking, use size E.

3.2.7 Grommets, metallic. Rolled rim grommets with spur washers shall conform to type III, class 3, sizes 2 and 4 of MIL-G-16491.

* 3.2.8 Fasteners, slide, interlocking. Slide fasteners shall conform to type III, style 1, with wire stirrup pull on each side, conforming to size H of V-F-106. Slide fastener chains and sliders shall be fabricated of brass. Alternatively, the slide fastener chain shall be polyester continuous monofilament in a ladder or coil type configuration, conforming to requirements in 3.2.8.1. Color of the chain, slider, pull, and stops shall approximately match the tape color.

3.2.8.1 Length. The length of slide fastener chains shall be such that, after the slide fastener is sewed on, the tape shall not be puckered and the slider shall operate freely.

3.2.8.2 Tape. Slide fastener tape shall be dyed to match Olive Drab S (Cable No. 66519) and shall be water-repellent and mildew-resistant treated. The color of the tape after treatment will be considered acceptable. The tape shall show good fastness to weathering.

3.2.9 Fastener tape, hook and pile. Nylon hook-and-pile fastener tapes shall be dyed to match Olive Green 106 and shall conform to type II, 1-inch and 2-inch widths of MIL-F-21840.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

* 3.2.10 Rope, tent-lay. Tent-lay rope used in the securing lug shall conform to type I, class 2, 1/4-inch diameter of MIL-R-1670. Alternatively, tent-lay rope shall conform to polyester rope of 1/4-inch diameter of MIL-R-30500, and the color shall be Olive Drab 7.

* 3.2.11 Lines, tent. The tent lines shall conform to class A of MIL-L-1709 or polyester rope conforming to MIL-R-30500, in the following types:

I - Footstep
XV - Reefing line
XXVIII - Guy line

3.2.12 Slips, tent line. Tent line slips shall conform to type II of MIL-S-1734.

3.2.13 Clip, end, strap. End clips shall conform to type I, class 1 or 2, size 1 inch of MIL-C-496.

3.2.14 Buckle, tongueless. Buckles shall conform to type IV, class 3 of MIL-B-543.

3.2.15 Fastener, snap. The snap fastener on the pocket of the cover shall consist of the following components: button, conforming to MS 27980-1B; socket, conforming to MS 27980-6B; stud, conforming to MS 27980-7B; and eyelet, conforming to MS 27980-8B.

3.2.16 Eyelet tab, plastic. Plastic eyelet tabs for 1/4-turn stud fasteners shall be acrylic-nitrile butadiene styrene (ABS) (see 6.8a) conforming to ABS 5-2-2 of ASTM D 1788 in 1/16-inch thick sheet form. The material shall be Olive Drab 7 (or other dark color). Adulteration due to extenders, modifiers, or resin type other than ABS, excluding pigments, is limited to 5 percent by weight.

3.2.17 Frame components.

3.2.17.1 Supports. Plastic tube, square bar, and round bar support components shall be fabricated from reinforced fiberglass polyester resin material (see 6.8b).

3.2.17.2 Fittings. Plastic tees and elbows shall be fabricated from reinforced fiberglass epoxy resin material (see 6.8c).

3.2.17.3 Hardware, miscellaneous. The corrosion-resistant hexagon head cap screw shall conform to MS 35307-121; the steel hexagon nut shall conform to MS 51967-14; the cadmium plated steel washer shall conform to MS 27183-19; and the corrosion-resistant slotted truss head (or binding head) machine screw, 1/4-28 UNF-2A by 1 1/2 inches long shall be standard commercial.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

3.2.18 Cord, polyester. The solid braided polyester cord shall be 1/8-inch diameter conforming to MIL-C-43256.

3.2.19 Adhesive, epoxy. The two-part epoxy cement for joining fittings and supports shall conform to MIL-A-52194.

3.2.20 Tape, plastic, embossing. Plastic embossing tape used to identify components shall conform to class 2, color black of UU-T-94.

3.2.21 Ink, vinyl. Vinyl ink, color black with compatible thinner, for marking on coated fabric cover shall conform to Code No. 1A 26.17 of the Atlas Coatings Corp., or equivalent.

3.3 Construction. The construction shall conform to Drawings 5-4-1103 through 5-4-1105 and 5-4-1116 through 5-4-1138 and as specified herein.

3.3.1 Stitching, machine.

3.3.1.1 Types of stitching. Stitching types shall conform to FED-STD-751 as follows:

a. For all stitching except bartacking and stitching indicated by "Z" on drawings, use type 301, 5 to 7 stitches per inch.

b. For stitching indicated by "Z" on drawings, use type 401, 5 to 7 stitches per inch. Chain portion of stitching shall not appear on outside of tent or cover.

c. For bartacking, use 7/8-inch bartack, plus or minus 1/16-inch long, with 1/8-inch bight and containing 42 stitches.

3.3.1.2 Thread breaks. Thread breaks in stitching shall be overstitched not less than 1 inch at each break on stitch type 301 and not less than 1 1/2 inches at each break on stitch type 401. Thread breaks in type 401 stitching may be overstitched with stitch type 301. Bartacks shall be free of thread breaks.

3.3.1.3 Skipped stitches. Two or more consecutively skipped stitches occurring in type 301 stitching shall be overstitched not less than 1 inch. Any skipped stitches in type 401 stitching shall be overstitched not less than 1 1/2 inches. Skipped stitches in 401 stitching may be overstitched with type 301 stitching.

3.3.1.4 Stitching ends. Stitching ends shall be overstitched not less than 1 inch on stitch type 301, except where ends are turned under in a hem, where ends are held down by other stitching, or where stitching is performed

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

automatically. When stitch patterns such as box, box with cross-stitch, "W" stitching, or straight line tacking are performed automatically, at least three tying, overlapping, or back stitches shall be used to secure the ends of stitching.

3.3.1.5 Lubrication of thread. The addition of any lubricant to the polyester sewing thread prior to or during the sewing operation is prohibited.

* 3.3.2 Setting of grommets. Holes punched to receive grommets shall be smaller than the outside diameter of the grommet barrel so that the grommet must be forced through the hole. Grommets shall be securely clinched without cutting the materials. Roll of clinched grommet shall not contain more than three scores (splits).

3.3.3 Setting of end clips. The webbing shall be inserted the full depth of the clip. Clips shall be securely attached without cutting the webbing, and the webbing shall be flat at the point of entrance.

* 3.3.4 Setting of snap fasteners. If a hole is punched before inserting the male or female part of the fastener, the hole shall be smaller than the outside diameter of the fastener tube so that the tube must be forced through the hole. Fastener components shall be securely clinched without cutting the material. The roll of the clinched eyelet of the assembled fastener component shall not contain more than three scores (splits).

3.3.5 Attachment of slide fasteners. Care shall be exercised to trim all thread ends and maintain specified distances between edges of fabric attached to slide fastener tape so that there will be no interference with the operation of the slider.

3.3.6 Location of holes in plastic tabs. The tolerance for location of holes in plastic tabs for mating with quarter-turn stud fasteners shall be limited to plus or minus 1/8 inch (noncumulative).

3.3.7 Adhesive bonding. The surfaces of frame components to be joined by bonding (inside of couplings and ends of rods) shall be cleaned with denatured alcohol. The adhesive specified in 3.2.19 shall be applied to mating surfaces, and the junctions cured in accordance with contractor's instructions.

* 3.3.8 Repairs. All necessary repairs shall be effected in accordance with Department of the Army Field Manual FM 10-16, except that hand-sewn patches or cemented patches other than as specified herein will not be acceptable. Cemented patches on holes, cuts, or tears not more than 1 inch in diameter or length, using cement specified in MIL-C-2399, shall be permitted. A maximum of three cemented patches per tent shall be allowed without prior

Source: https://assist.dla.mil -- Downloaded: 20261O-21T21:35Z
Check the source to verify that this is the current version before use.

authorization. All other repairs shall require contracting officer authorization. Repairs required as a result of failure of the cup test shall be performed by treating with a compound conforming to type I, class 1 of TT-P-595 prior to retesting (see 6.7).

3.3.9 Wicking of sewing thread (cup test). There shall be no seepage of water through the tent stitching when the tent is tested as specified in 4.4.8. The cup test is intended to ensure that nonwicking thread has been utilized and that no lubrication has been added to the polyester thread during the sewing operation.

3.4 Marking. All markings and labels shall conform to DDD-L-20.

3.4.1 Special marking. The nomenclature and the letters "US" shall be printed or stenciled on the tents and covers in the size characters and in the locations indicated on the drawings and shall conform to the requirements for type IV, class 9 labels. Class 9 marking shall be clearly legible after subjection to accelerated weathering. To ensure conformance with fastness requirements on covers (coated fabric), vinyl ink specified in 3.2.21 should be used. Frame assembly components should be identified as indicated on applicable drawings using embossing tape specified in 3.2.20.

* 3.4.2 Identification labels. Identification labels shall be stitched to the tents in the locations shown on the drawings and shall conform to the requirements for type VI, class 6 labels. The label size shall be 3 1/2 inches by 5 1/2 inches minimum, and a blank space of at least 1 1/4 inches shall be provided at the bottom for the Department of Defense Inspector's stamp.

* 3.4.3 Instruction labels. Instruction labels for erection, care, and maintenance of the tent shall conform to the requirements for type VI, class 7 labels and shall be stitched to the tents and covers in the locations shown on the drawings. The label shall be a proportionate copy of Drawing 5-4-1128 or 5-4-1138, as applicable, reproduced from a glossy print of the appropriate drawing as furnished by the contracting officer. The size of the label shall be, borderline to borderline, 15 inches ± 1/4 inch in the longer dimension with a minimum 1/2 inch margin outside of the borderline on all sides.

3.5 Workmanship. Cloth components shall be clean and free from holes, cuts, tears, or cloth defects such as multiple floats or broken or missing yarns. Coated fabric shall be free from blisters, tunnels, or other delaminations; abraded areas resulting in thin or weak places; or areas of no coating. Webbing and tape shall not have frayed or scalloped edges, and rope components shall be free of cuts or breaks. Thread tension shall be maintained so that there will be no loose stitching, and seam allowance shall

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:35Z
Check the source to verify that this is the currentversion before use.

be maintained so that no run-offs, twists, pleats, or open seams result. All thread ends shall be trimmed to 1/2 inch or less. Care shall be taken to see that no needle chews occur. Frame components shall be free of burrs or sharp edges and shall not be broken or malformed. Cemented joints shall be firm, clean, and free of excess adhesive.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.3 through 4.4.7 and tested as specified in 4.5.2. The presence of any defect or failure of any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:35Z
Check the source to verify that this is the currentversion before use.

4.4.1.1 Component testing. In addition to the quality assurance provisions of subsidiary documents and drawings, tests shall be performed in accordance with FED-STD-191 and as specified in table I on the component listed for the characteristics shown. All requirements are applicable to the individual sample unit. The lot shall be expressed in units of yards. The sample unit shall be 1 1/2 yards full width. The inspection level shall be S-1 and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 6.5.

TABLE I. Component tests

Component	Characteristic	Requirement paragraph	Test method or paragraph
Cloth, polyester	Material identification	3.2.3	1600
	Weave	3.2.3	Visual
	Texture	3.2.3	5050
	Breaking strength	3.2.3	5100
	Weight	3.2.3	5041
	Water resistance	3.2.3	5526
	Air permeability	3.2.3	5450
	Light transmittance	3.2.3	4.5.1

4.4.2 In-process inspection. Inspection shall be made to determine that the following are as specified:

a. There shall be no lubrication of polyester thread prior to or during sewing operations for compliance with 3.3.1.5.

b. Holes punched to receive grommets shall be in compliance with 3.3.2.

c. Holes punched to receive male or female parts of snap fasteners shall be in compliance with 3.3.4.

d. Surfaces to be bonded shall be cleaned and cemented in compliance with 3.3.7.

Whenever nonconformance is noted, correction shall be made to the item affected and to the process.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

* 4.4.3 Tent and cover visual examination. The completely fabricated tent or cover, as applicable, shall be examined for the defects listed in table II. The lot size shall be expressed in units of tents or covers, as applicable. The sample unit shall be one tent or cover, as applicable. The inspection level shall be I. For tents, the AQL, expressed in terms of defects per hundred units, shall be 6.5 for major defects, 15.0 for combined major and minor A defects, and 65.0 for total combined (major, minor A, and minor B) defects. For covers, the AQL shall be 4.0 for major defects, 10.0 for combined major and minor A defects, and 25.0 for total combined (major, minor A, and minor B) defects.

TABLE II. Tent and cover visual defects

Examine	Defect	Classification		
		Major	Minor	
			A	B
Fabric	Cut or tear longer than 1/8 inch; hole (including exposed drill hole) larger than 1/8 inch diameter:			
	-on roof	X		
	-on walls		X	
	-on cover or sod cloth			X
	Cut, tear, or hole (including exposed drill holes) 1/8 inch or less in length or diameter			
	-on roof:			
	-more than four	X		
	-more than one but not more than four		X	
	-on cover, walls, or sod cloth more than four			X
	Broken or missing yarn; multiple floats		X	
Coated fabric	Blister, tunnel, or delamination of coating	X		
	Abrasion, resulting in thin or weak place	X		
	Coating missing or thin	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE II. Tent and cover visual defects - Continued

Examine	Defect	Classification		
		Major	Minor	
			A	B
Webbing and tape	Frayed or scalloped edges; not firmly or tightly woven			X
Hardware	Broken	X		
	Malformed:			
	-fails to perform intended function	X		
	-but will perform intended function		X	
	Corroded area			X
	Burr or sharp edge which may cause injury in handling or damage to fabric	X		
Clip ends	Improperly clinched (i.e., webbing not flat at point of entrance into clip)			X
	Clinched excessively tight, cutting webbing	X		
Grommets	Improperly set, two or more teeth exposed (except where grommet is set as specified but is in an area of uneven thickness which prevents uniform clinching)			X
	Clinched loosely, allowing grommet to rotate in hole			X
	Clinched excessively tight, cutting fabric:			
	-on tent	X		
	-on cover		X	
	Roll of a grommet contains more than three scores (splits)			X
Buckles	Not assembled to strap as specified (i.e., reversed failing to effect a secure fastening of straps)	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE II. Tent and cover visual defects - Continued

Examine	Defect	Classification		
		Major	Minor	
			A	B
Hardware - continued				
Snap fasteners	Clinched excessively tight cutting fabric or insecurely clinched		X	
	Roll of a clinched eyelet fastener assembly contains more than three scores (splits)			X
Hook and pile fastener tapes	Mismatch of components	X		
Rope components	Any cut or any break:			
	-on guy line		X	
	-on any other line			X
	Free ends of rope not finished as specified			X
	Eye splice not as specified			X
	Eye splice omitted		X	
Seams and stitching	Open seam on stitch type 301:			
	-for more than 1 inch		X	
	-for more than 1/4 inch but not more than 1 inch			X
	Open seam on stitch type 401:			
	-one row of stitching open for 1 inch or less on tent or cover			X
	-one row of stitching open for more than 1 inch:			
	-on tent		X	
	-on cover			X
	-both rows of stitching open (not necessarily at same location):			
	-on tent	X		
	-on cover			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE II. Tent and cover visual defects - Continued

Examine	Defect	Classification		
		Major	Minor A	Minor B
Seams and stitching - continued				
	NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken, or when one or more consecutive skipped or run-off stitches occur. On double-stitched seams, a seam shall be considered open when either one or both sides of the seam are open.			
	Raw edges caught in stitching:			
	-more than 3 inches		X	
	-more than 1 inch but not more than 3 inches			X
	Thread breaks:			
	-overstitched less than 1 1/2 inches on stitch type 401			X
	-overstitched less than 1 inch on stitch type 301			X
	NOTE: Thread breaks not overstitched shall be classified as open seams.			
	Skipped stitches overstitched less than:			
	-1 inch on stitch type 301			X
	-1 1/2 inches on stitch type 401			X
	NOTE: Skipped stitches not overstitched shall be classified as open seams. Needle chews, tear, or hole (see cut, tear, or hole defect for Fabric examination).			
	One or more required rows of stitching omitted (except on boxstitching)	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE II. Tent and cover visual defects - Continued

Examine	Defect	Classification		
		Major	Minor A	Minor B
Seams and stitching - continued				
Stitching ends	Overstitched less than 1 inch on stitch type 301 (except where ends are held down by other stitching, turned under in a hem or where stitching is performed automatically)		X	
	Secured with less than three tying, overlapping, or back stitches when automatic stitching is performed			X
Seams	Seam pleated -on roof		X	
	-on wall			X
Seam type	Wrong seam type	X		
Stitch type	Wrong stitch type	X		
Stitch tension	Loose, resulting in exposed bobbin or top thread for more than 6 inches		X	
	Tight as evidenced by puckering on fabric for more than 6 inches		X	
Stitches per inch	Less than minimum specified (except on panel joining seams): -one stitch			X
	-two or more stitches		X	
	Less than minimum specified on panel joining seams		X	
	More than maximum specified: -one stitch			X
	-two or more stitches		X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE II. Tent and cover visual defects - Continued

Examine	Defect	Classification		
		Major	Minor A	Minor B
Seams and stitching - continued				
NOTE:	Variation in the number of stitches per inch caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places or in turning corners shall be classified as follows: a. Within the minor A defect classification - minor B defect b. Within the minor B defect classification - no defect			
Stitching gage	Not as specified		X	
NOTE:	Applicable when double needle machine is used. When two rows of stitching are applied with a single needle machine, tolerance for stitching margin shall apply.			
Stitching margin	Larger than specified by more than 3/16 inch:			
	-less than 4 inches in length			X
	-4 inches or more in length		X	
	Less than specified:			
	-less than 4 inches in length			X
	-4 inches or more in length		X	
Stitching indicated by "Z" on drawings	Chain portion of stitching shows on outside of tent or cover		X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE II. Tent and cover visual defects - Continued

Examine	Defect	Classification		
		Major	Minor A	Minor B
Seams and stitching - continued				
Boxstitching	Incomplete:			
	-one row of stitching omitted			X
	-two or more rows of stitching omitted		X	
	-less than specified length by more than 1/8 inch			X
Mends, darns, or patches	Repairs not in accordance with Department of the Army Field Manual FM 10-16 or not authorized by the contracting officer (see 3.3.8)	X		
Components and assembly	Any component part not fabricated of applicable referenced material	X		
	Any operation, construction, or configuration omitted or not in accordance with drawings (unless otherwise specified herein)	X		
Hems	Twisted or pleated			X
	Constructed with partial turnunder when double turnunder is required		X	
Reinforcements	Improperly applied, causing excessive fullness on reinforcements or reinforced parts			X
Slide fastener tapes	Slider jams or fails to interlock chain	X		
	Any tape improperly assembled, causing failure of chain to effect a smooth and secure closure	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE II. Tent and cover visual defects - Continued

Examine	Defect	Classification		
		Major	Minor	
			A	B
Marking "US", identification labels, erection instruction labels, special marking on covers	Omitted, incorrect, illegible, or misplaced			X
Cleanness	Grease or oil stains			X
	Thread ends not trimmed to 1/2 inch or less (except in slide fastener area)			X
	Thread ends not trimmed to 1/2 inch or less in slide fastener area		X	

* 4.4.4 Tent and cover dimensional examination. The completely fabricated tent or cover, as applicable, shall be examined for the defects listed in table III. The lot size shall be expressed in units of tents or covers, as applicable. The sample unit shall be one tent or cover, as applicable. The inspection level shall be S-3. For tents, the AQL, expressed in terms of defects per hundred units, shall be 2.5 for major defects, 15.0 for combined major and minor A defects, and 40.0 for total combined (major, minor A, and minor B) defects. For covers, the AQL shall be 2.5 for major defects, 6.5 for combined major and minor A defects, and 25.0 for total combined (major, minor A, and minor B) defects.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:35Z
Check the source to verify that this is the currentversion before use.

TABLE III. Tent and cover dimensional defects

Examine	Defect	Classification		
		Major	Minor	
			A	B
Overall dimensions	Smaller than specified dimensions less applicable minus tolerances indicated on drawings	X		
	Larger than specified dimensions and applicable plus tolerances indicated on drawings		X	
Location dimensions (unless otherwise specified)	Not within specified tolerances: -not exceeding twice the applicable tolerance			X
	-exceeding twice the applicable tolerance		X	
Plastic tabs	Any hole in plastic tab misplaced: -by more than 1/4 inch	X		
	-by more than 1/8 inch but not more than 1/4 inch		X	
Rope components	Guy lines less than specified finished length: -by more than 12 inches	X		
	-by more than 4 inches, but not more than 12 inches		X	
	-by not more than 4 inches			X
	Any other line less than specified finished length: -by more than 6 inches	X		
	-by more than 2 inches but not more than 6 inches		X	
	-by not more than 2 inches			X
	Eye on line or footstop, less than specified by more than 1/2 inch		X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE III. Tent and cover dimensional defects - Continued

Examine	Defect	Classification		
		Major	Minor A	Minor B
Hems	Width of hems less than specified by more than 1/4 inch			X
Reinforcements	Finished dimensions of reinforcements less than specified by more than 1/2 inch			X

* 4.4.5 Frame assembly visual examination. The completely fabricated frame shall be examined for the defects listed in table IV. The lot size shall be expressed in units of frames. The sample unit shall be one frame. The inspection level shall be I and the AQL, expressed in terms of defects per hundred units, shall be 4.0 for major defects, 10.0 for combined major and minor A defects, and 15.0 for total combined (major, minor A, and minor B) defects.

TABLE IV. Frame assembly visual defects

Examine	Defect	Classification		
		Major	Minor A	Minor B
Construction and workmanship (applicable to all components and assemblies)	Component missing	X		
	Component fractured, split, or broken	X		
	Component punctured, twisted, malformed, or otherwise impaired		X	
	Not connected or joined as specified, or attachment is poorly accomplished		X	
	Any subassembly that cannot be joined with companion assembly	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

TABLE IV. Frame assembly visual defects - Continued

Examine	Defect	Classification		
		Major	Minor	
			A	B
Construction and workmanship (applicable to all components and assemblies) - continued	Assembly holes in square member missing or misplaced	X		
	Thread damaged or stripped on any threaded component		X	
	Sharp break at shoulder end of length of round taper			X
	Holes not drilled clean			X
	Drilled-through holes out of round			X
	Components not color coded			X
	Evidence of burr or sharp edge		X	
	Corners not rounded for snug or telescoping fit as specified		X	
	Not chamfered as specified			X
	Sharp edge or parting line on fitting			X
	Cut end of braided cord not seared			X
	Cord not required length			X
	Cementing not accomplished as specified		X	
	Machined surfaces not weather sealed with coat of lacquer			X
	Surface of bar or tube slivered, rough, pitted, or blistered			X
	Any repair or mend on bar or tube	X		
	Length of "round" on square rods not accomplished as specified			X
	Machined bars or tubes not smooth (i.e., loose glass fibers which could cause injury to user)		X	
Marking	Missing, not specified type or size, not legible, incorrect, incomplete, not in specified location, or not applied in specified manner			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

* 4.4.6 Frame assembly dimensional examination. The completely fabricated frame shall be examined for the dimensions specified on the drawings. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of frames. The sample unit shall be one frame. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

* 4.4.7 Frame erection examination. Frames shall be erected and adjusted to maximum and minimum height positions to determine ease of assembly and fit of mating parts. Defects shall be scored in accordance with table V. The lot size shall be expressed in units of frames. The sample unit shall be one frame. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

TABLE V. Frame erection defects

Examine	Defect
Assembly	Any component that cannot be connected or joined with companion part Not readily assembled (i.e., assembling requires realignment of parts, drilling, or enlargement of holes, or use of drift pin or other mechanical means) Assembly hole missing or misplaced Any component missing (e.g., check all bolts, nuts, washers, pins)

4.4.8 Tent testing. Tents shall be tested for seam leakage as specified in 4.5.2. The lot size shall be expressed in units of completely fabricated tents. The sample unit shall be one tent. The inspection level shall be S-3. Failure in any area shall be cause for rejection of the lot.

4.4.9 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Bulged or distorted container

4.5 Methods of inspection.

4.5.1 Light transmittance of polyester fabric.

4.5.1.1 Equipment.

4.5.1.1.1 Light source. The light source shall consist of an artificial daylight lamp (e.g., MacBeth 7500K) or natural north daylight. The luminance at the sample position shall not be less than 100 footcandles.

4.5.1.1.2 Light meter. The light meter shall be corrected for its photosensitivity function. A Weston Photronic Foot Candle Meter, Model 614, may be used to measure this function.

4.5.1.2 Method. Place the photosensitive detector of the light meter on a plane essentially perpendicular to the direction of the incident light. Measure the luminance of the incident light and record in footcandles (Io). This measurement of intensity may fluctuate if natural daylight is used on a day with variable cloudiness. Place the sample directly over the detector on the light meter, and record the luminence of the transmitted light in footcandles (I).

4.5.1.3 Calculations. Record the ratio I/Io for at least three samples. Multiply the mean-ratio for the replicates by 100 and report as percent. A luminous transmission value of less than 40 percent shall be classified as a defect.

* 4.5.2 Wicking of sewing thread (cup test). The tent shall be tested once on a roof panel seam and once on a seam joining the roof to the wall. Lay the test area over a hoop with a diameter of 6 inches (± 1/8 inch) so as to form a depression 1 ± 1/4 inch deep, with the seam to be tested running through

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

the center of the depression. Slowly pour 500 mL of water at 77° ± 4°F into the depression and observe the under surface of the seam. Any wicking of water in either test area along the sewing thread, identified by a discoloration or darkening of the thread within 5 minutes after pouring the water, shall be considered a test failure. Water leakage through the needle holes or between the plies of the lapped seamed fabrics shall not be considered a failure.

* 5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Tent, only. Each front and aft tent shall be smoothly folded, with guy lines tucked in the folds and blackout flaps unrolled, in such a manner that the rope hem retainer strip portion of the tent will be on top and each tent will fit in its respective cover case.

5.1.1.2 Frame assembly. The frame assembly components of each front and aft tent shall be inserted into their designated locations within the separator provided on each cover. The retainer assembly holding the frame assembly in place shall then be secured. The hold-down bolts for each tent shall be placed into their respective bolt pocket and each pocket snap fastened.

5.1.1.3 Tent, complete. Each folded front and aft tent shall be placed on top of their respective frame assembly within the cover, and the cover closed and secured with the four attached straps.

5.1.1.4 Components (when procured separately).

5.1.1.4.1 Tent. Each tent shall be neatly and compactly folded, with guy lines tucked in the folds and blackout flaps unrolled. The folded tent shall be secured from unfolding.

5.1.1.4.2 Frame. Each frame shall be disassembled, components nested and secured with tape, cord, or twine and then unit packed in a snug-fitting fiberboard box conforming to type CF (variety SW) or SF, class domestic, grade 275, style optional of PPP-B-636. Each box shall be securely closed.

5.1.1.4.3 Cover. Each cover shall be neatly and compactly folded and secured from unfolding.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

5.1.2 Commercial. Each tent (front and aft) and components, when procured separately, shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

5.2.1 Level A packing. Tents of one description only (front and aft), preserved as specified in 5.1, shall be packed in a close-fitting cleated-plywood box conforming to overseas type, style A of PPP-B-601. Boxes and skids (when necessary) shall be fabricated in accordance with the gross weight and load-type requirements in PPP-B-601. Each shipping container shall be closed and reinforced in accordance with the appendix of PPP-B-601.

5.2.1.1 Components (when procured separately). Tents, frames, and covers of one description only, preserved as specified in 5.1.1.4, shall be packed in a snug-fitting fiberboard shipping container conforming to grade V2s, style RSC of PPP-B-636. Shipping containers for tents and covers shall be provided with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636. The gross weight of each shipping container shall not exceed 90 pounds. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Each tent (front or aft), preserved as specified in 5.1, shall be wrapped in cotton osnaburg conforming to class 2 of CCC-C-429 or burlap cloth conforming to class 3 of CCC-C-467. The wrapping shall be securely hand sewn with type I or II, 16-ply cotton twine conforming to T-T-871 or type I, size No. 2 jute twine conforming to T-T-911, with approximately one stitch to the inch and every third stitch knotted. Alternatively, the seams of the wrap may be machine sewn. In lieu of the sewn wrap, bias sewn tubing conforming to MIL-T-40625 may be used. A minimum of 5 inches of wrapping or tubing shall be gathered together on each of the four corners and securely sewed into ears for handles. Whenever machine sewing is used, the thread type, stitch type, and number of stitches per inch shall conform to requirements specified in MIL-T-40625. The polyester thread used to manufacture the end item may be used for effecting the machine sewn closure of the wrapping or tubing.

5.2.2.1 Components (when procured separately). Tents, frames, and covers of one description only, preserved as specified in 5.1.1.4, shall be packed in a snug-fitting fiberboard shipping container conforming to type CF (variety SW) or SF, class domestic, grade 275, style RSC of PPP-B-636. Shipping containers for tents and covers shall be provided with a box liner conforming

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II of the appendix of PPP-B-636. Alternatively, tents and covers shall be packed as specified in 5.2.2. The gross weight of each shipping container or cloth covered bundle shall not exceed 90 pounds.

5.2.2.2 Weather-resistant containers. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of PPP-B-636.

5.2.3 Commercial packing. Tents of one description only (front or aft) or components of one description only, when procured separately, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The console shelters are designed to provide protection for personnel during operation of one element of the Hawk Missile System in cold or cold-wet weather or to fulfill blackout requirements.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. Stock number.
c. When a first article is required (see 3.1, 4.3, and 6.3).
d. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
e. Type and class of unit load required (see 5.2.1.1).
f. When weather-resistant containers are required for level B packing (see 5.2.2.2).

* 6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.4 Standard sample. For access to samples, address the contracting activity issuing the invitation for bids.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

* 6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this document (see 3.2).

6.6 Additional components. Additional components necessary for the erection of Tents, Console, High Power Illuminator, Front and Aft are as follows:

Front - 17 each, Pin, Tent, Wood, 16 Inch (FSN 8340-261-9750)
17 each, Pin, Tent, Metal, 12 Inch (FSN 8340-823-7451)

Aft - 15 each, Pin, Tent, Wood, 16 Inch (FSN 8340-261-9750)
15 each, Pin, Tent, Metal, 12 Inch (FSN 8340-823-7451)

6.7 Seam repair. A satisfactory method of applying the textile compound for the repair of leaking seams is as follows:

a. A suitable volume of textile compound conforming to type I, class 1 of TT-P-595 shall be thoroughly stirred and diluted with an equal volume of petroleum solvent (Stoddard solvent or equivalent). Thoroughly stir the mixture again before use.

b. Prior to application of the compound, the tents must be dry. Special attention must be taken to ensure adequate ventilation and that proper fire preventive measures are taken, since the compound is flammable.

c. Two coats of the textile compound shall then be applied to the seams (on the outside of the tent only). A 4-inch wide stiff brush is recommended for use. The first coat shall be air dried for a minimum of 4 hours prior to application of the second coat. Elapsed time between coats may be reduced by providing a supply of hot air to evaporate the solvent more quickly. In this manner, a second coat may be applied as soon as the first coat is dry to the touch. After the application of the second coat, the treated tent shall be allowed to air dry for a period of at least 24 hours.

6.7.1 Seams to be treated. Seams that have failed the test specified in 4.5.2 shall be treated as follows:

a. Failure at roof panel lap seams - treat all roof panel lap seams.

b. Failure at stitching joining roof and wall, including reinforcement on roof - treat all stitching on eave and roof reinforcement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

6.8 Equivalent products.

a. Royalite, No. 40 series ABS plastic of U.S. Rubber Co., has been found to satisfactorily meet the requirement specified in 3.2.16.

b. Tubing and bar (plastic) fabricated from "Extren 500" (Koppers Co. Inc.; Joseph T. Ryerson & Sons) or an equivalent material are acceptable (see 3.2.17.1).

c. Pipe fittings, tees and elbows (plastic) fabricated from "P.J. Line Pipe" (Fiberglass Resources Inc.) or an equivalent material are acceptable (see 3.2.17.2).

* 6.9 International standardization agreements. Certain provisions of this document are the subject of international standardization agreement as cited in NATO, STANAG No. 2882, relative to camouflage requirements for tents, shelters and subsidiary components. When amendment, revision, or cancellation of this document is proposed that will affect or violate the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

* 6.10 Subject term (key word) listing.

Tent, console
Hawk missile system

6.11 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, as written, irrespective of the marginal notations and relationship to the last previous issue.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:35Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Navy - NU

Review activities:

Army - MD, MI
DLA - CT

User activities:

Navy - MC
Air Force - 82

Preparing activity:

Army - GL

Project No. 8340-0488

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:35Z
Check the source to verify that this is the current version before use.

STRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use mitting comments and suggestions for improvements. All users of military standardization documents are invited to prov gestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, a iled. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the blems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an nowledgement will be mailed to you within 30 days to let you know that your comments were received and are being sidered.

TE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of cification requirements on current contracts. Comments submitted on this form do not constitute or imply authorizatio waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

PARTMENT OF THE ARMY
Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTA
NECESSA
IF MAILE
IN THE
UNITED STA

FICIAL BUSINESS
IALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:35Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-T-43512B	Tent, Missile System Equipment Console, (High-Power Illuminator Hawk)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP, 1 Apr 84

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:35Z
Check the source to verify that this is the current version before use.