[METRIC]
A-A-1501B
March 30, 1994
SUPERSEDES
A-A-1501A
November 18, 1992

COMMERCIAL ITEM DESCRIPTION

PAPER SET, DUPLICATING, MASTER

The General Services Administration has authorized the use of this Commercial Item Description, for all federal agencies.

This description covers three-part duplicating paper sets of stub construction consisting of a master sheet, a protective sheet and a duplicating carbon sheet.

1. Salient characteristics:
   A. Master duplicating paper. Master duplicating paper shall conform to the following physical requirements in Table 1. The issue of each TAPPI test method in effect on the date of solicitation shall be used to determine compliance with these requirements.

Table 1

Characteristic	Requirement	TAPPI
Paper Stock	Free from groundwood pulp	T401
Basis Weight	81.4 g/m^2 +/- 5% (55 lb. (25x38-500))	T410
Thickness	0.072 +/- 0.0127 mm (0.0030 +/- 0.0005 inch)	T411
Smoothness, avg., each side	50-125 Sheffield units (118-33 Seconds Bekk)	UM 518
Surface Strength	Paper shall withstand a No. 4A Dennison wax test on both sides of the sheet without disturbance of the coating.	T459

Beneficial comments, recommendations, additions, deletions, clarification's, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, NY 10278

Distribution Statement A:
Approved for public release;
distribution is unlimited.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:14Z
Check the source to verify that this is the current version before use.

Master duplicating paper shall be white and shall be coated on both sides. The coating shall be uniform and free from mottle and any particles which will pick or lift during normal use. The master paper shall lie flat with no tendency to curl. Master paper shall not be affected by the duplicating fluid to such an extent that it interferes with satisfactory performance. Grain direction of the master duplicating paper shall parallel the glue line joining master and carbon together.

B. Protective sheet. The protective sheet shall be suitable for preventing transfer of carbon coating between the carbon substrate and the master sheet.

C. Carbon paper. Paper used for base paper stock shall consist of bleached chemical wood, groundwood, or a similar base stock. Basis weight of the paper stock shall be not less than 51 g\m^2 (35 lbs (25 x 38-500)) when tested in accordance with TAPPI T 410. The base paper stock shall be coated with suitable waxes, dyes, and other necessary ingredients to ensure the quality and performance requirements. The carbon-coated side of the sheet shall be overcoated with a protective film which shall prevent the carbon surface from crystallizing, shall seal in the dye, and shall prevent smearing, smudging, soiling the hands, or discoloration of the master paper. Edges shall be sealed with a protective material to destroy permanently the aniline dyes. The carbon paper shall have a smooth and calendered finish and shall give perfect release of the dye coating from the paper when impressed by type face, stylus or other means of transfer.

D. Paper set. Paper sets shall be the width specified, with a tolerance of +/- 1.6 mm (1/16 inch). The master sheet shall be the length specified (See Section 6), with a tolerance of +/- 3.2 mm (1/8 inch), plus a margin of 12.7 mm (1/2 inch) maximum for clamping the sheet in the reproduction equipment. The specified size shall indicate the reproduction area of the master sheet.

The master sheet shall be perforated across its width 12.7 +/- 3.2 mm (1/2 +/- 1/8 inch) from the top edge, and the carbon sheet shall be glued to the stub formed by the perforations and the top edge of master sheet. The carbon paper shall be positioned with the carbon coating facing the master sheet and shall have an uncoated margin along the bottom edge which shall extend beyond bottom of master. The protective sheet shall be loosely inserted between the carbon sheet and master sheet, shall cover the entire area of the master, and shall have a margin at the bottom to grip for removal.

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T08:14Z
Check the source to verify that this is the currentversion before use.
administrative, morale or public information purposes

Color of reproductions shall be purple. The duplicating master sets shall he capable of reproducing at least 300 purple copies. All copies shall be clearly legible and shall be free from smudges, blurs, or smears.

E. Bleaching: To obtain an acceptable brightness, a chemical bleaching process may be used. When specified, (See Section 6), the bleaching process shall not include the use of chlorine, chlorine dioxide, or hypochlorite. Certification of compliance shall be made available upon request by the Government.

F. Workmanship. The paper sets shall be clean, uniformly coated, and free from pinholes, uncoated areas, or other defects which might affect the appearance or quality of reproduction.

2. Quality Assurance Provisions. Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this commercial item description where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirement.

Table 2

Examine	Inspection Levels	AQLs (% defect)
Visual/Workmanship Defects	I	2.5
Dimensional Defects	S-3	4.0
Paper Characteristics	TAPPI	N/A
Preparation for Delivery	S-2	2.5

Sampling for examination and tests shall be performed in accordance with MIL-STD-105, using the plans as specified in Table 2, unless otherwise stated. For the purpose of sampling, a lot shall consist of duplicating paper sets. The sample unit shall be 1 paper set for visual/workmanship and dimensional examination and one fully prepared shipping container for preparation for delivery examination, unless specified otherwise.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:14Z
Check the source to verify that this is the current version before use.

when providing rated current to a circuit

3. Regulatory requirements.
The contractor shall certify that the minimum content standard of the paper used as the protective sheet shall be no less than 50% recovered materials including 20% postconsumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993 (See definition of postconsumer materials and recovered materials in sections 203 and 205). As an alternative to meeting the standards of section 504(b) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

For the paper used to make the master sheet and the carbon sheet, the offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

3.1 Labeling of recycled content. The recycled content shall be marked on the product or unit pack.

4. Preservation, packaging, packing, labeling, and marking.
Preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

5. Application for copies of technical documents referenced herein: The issue date in effect on date of invitation for bids or request for proposal shall be apply.

(1) TAPPI test methods are available from the Technical Association of the Pulp and Paper Industry, P.O. Box 105113, Atlanta, GA 30348.
(2) MIL-STD-105 is available from Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.
(3) Public Law 94-580 Resource Conservation and Recovery Act (Part of U.S. Code, Title 42). Copies of the U.S. Code may be obtained through the Congressional Sales Office, U.S. Government Printing Office, Washington D.C. 20402.
(4) Executive Order 12873, dated Oct. 20, 1993 is available from the White House Publications Office, New Executive Office Building, White House, Washington, DC 20500, Att: Publications. Phone (202) 395-7332.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:14Z
Check the source to verify that this is the current version before use.

6. Ordering Data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

A) Packaging, packing and marking.
B) Dimensions.
C) Whether bleaching without use of chlorine, chlorine dioxide, or hypochlorite is required.

MILITARY INTERESTS:

DOD has waived coordination of this document

CIVIL AGENCY COORDINATING ACTIVITY:
COMMERCE-NIST

PREPARING ACTIVITY:
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:14Z
Check the source to verify that this is the current version before use.