INCH-POUND
A-A-52105A
December 6, 2018
SUPERSEDING
A-A-52105
May 7, 1991

COMMERCIAL ITEM DESCRIPTION

CLOTH, INTERFACING, COTTON, OR SYNTHETIC WARP, AND SPUN HAIR-WOOL, RAYON OR SYNTHETIC FILLING

The General Services Administration has authorized the use of this Commercial Item Description (CID) by all federal agencies.

1. SCOPE. This CID covers the requirements for an interfacing cloth comprised of cotton or synthetic warp yarns and a blend of spun hair-wool, rayon or 100 percent synthetic filling yarns intended for use in various dress clothing items. (Note: The term interfacing instead of interlining is the correct term to describe the cloths cited in this document).

2. CLASSIFICATION. This CID shall be available in the following types as specified.

2.1 Types.

Type I - Light weight
Type II - Medium weight
Type III - Heavy weight

3. SALIENT CHARACTERISTICS.

3.1 Description. The warp yarns shall be either 100 percent natural fibers or a blend of natural and synthetic fibers. The filling yarns shall be a blend of wool, goat hair and rayon, or 100 percent polyester monofilament yarns and shall meet the requirements specified in Table I. The cloth shall be plain weave and shall be preshrunk.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Attn: DLA Troop Support, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, you may want to verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil/.

AMSC N/A FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

3.2 Color. The color of the finished cloth shall be natural or dyed as specified (see 7.5) and shall meet the colorfastness requirements when tested as specified in 3.3. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyed cloth shall be "Free" of labile sulfur when tested as specified in 3.4.

3.3 Physical characteristics and requirements. The finished cloth shall conform to the physical characteristics specified in Table I when tested in accordance with test methods in Table I.

TABLE I. Physical characteristics and test methods.

Characteristic	Requirement			Test method
	Type I	Type II	Type III	
Yarn identification				AATCC 20 (see 7.4)
Cotton	3.1	3.1	3.1	
Synthetic	3.1	3.1	3.1	
Animal hair	3.1	3.1	3.1	
Colorfastness (min.) 1/:				
Dry-cleaning	3-4	3-4	3-4	AATCC 132 2/
Dry and wet pressing	3-4	3-4	3-4	AATCC 133 2/, 3/
Weight, oz./sq.yd.				ASTM D3776/D3776M
Minimum	5.0	6.8	7.5	
Maximum	6.7	8.0	9.0	
Yarns per inch (min.)				ASTM D3775
Warp	42	42	42	
Filling	30	30	30	
Breaking strength, lbs. (min.)				ASTM D5034
Warp	50	50	50	
Filling	45	45	45	
Stiffness, inch-pound (min) 4/				
Initial	0.003	0.005	0.008	ASTM D747
After dry-cleaning	0.003	0.005	0.008	AATCC 158 & ASTM D747
Dimensional stability to dry-cleaning, percent (max.)				AATCC 158
Warp	3.0	3.0	3.0	
Filling	2.0	2.0	2.0	

1/ Testing shall be performed on colored cloth only.
2/ Rated using the AATCC Evaluation Procedure 2, Gray Scale for Staining only.
3/ Pressing shall be conducted between 340-375°F.
4/ Measure parallel with the filling direction only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

3.4 Presence of labile sulfur. In the determination of labile sulfur in textile materials with lead acetate, two (2) 1.50 gram (± 0.01) gram samples from each material submitted for evaluation shall be tested. Each of the two (2) samples shall be cut into very small pieces and placed into separate test tubes. The samples shall be submersed in a stannous chloride solution that contains 100 grams of stannous chloride crystals ACS in 100 millimeters of hydrochloric acid ACS (35 percent concentration) and 50 milliliters of distilled water. A filter paper wet out with a 5.0 percent lead acetate solution shall be placed over the top of the test tube. The lead acetate solution contains 5.0 grams of lead acetate CP reagent grade and enough distilled water to make up a 100 milliliter solution; if the solution is not clear, add a few drops (one at a time) of glacial acetic acid until the solution is clear. The test tube containing the textile sample, stannous chloride and wet filter paper shall be heated over a low flame until the solution is boiling. The solution should not be heated for more than 15 seconds. A brown to black stain on the filter paper should be evaluated as follows.

Free	-	The filter paper shows no discoloration of staining of any kind.
Slight	-	The filter paper shows a light tan to light brown discoloration stain.
Moderate	-	The filter paper shows a dark brown discoloration stain.
Severe	-	The filter paper shows a black color stain.

3.5 Labels. Each roll of finished cloth shall be labeled or ticked for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act.

3.6 Workmanship. The finished cloth shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the contractor's own quality assurance standards and the quality assurance standards defined by the technical data in the bid package.

4. REGULATORY REQUIREMENTS. Unless otherwise specified the offer/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The finished cloth provided shall meet the salient characteristics of this CID, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptance. This finished cloth must have been sold to the commercial market or the Government.

5.3 End item inspection procedures. Sampling for inspection shall be conducted in accordance with ANSI/ASQ Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.3).

5.4 Visual examination. The finished cloth shall be examined for the defects listed below as defined in ASTM D3990:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

Any hole, cut, or tear. Puckered, wrinkled or creased/pleated material. Label missing, incorrect, or illegible. Required information missing from the label. Not packaged in accordance with the contract or purchase order.

5.5 Acceptance criteria. Acceptance criteria shall be as specified in the contract or purchase order (see 7.5).

6. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or purchase order (see 7.5).

7. NOTES.

7.1 Sources of Government documents.

7.1.1 Copies of Government documents are available online at https://quicksearch.dla.mil.

7.1.2 Rules and Regulations under the Textile Fiber Products Identification Act are available online at https://www.ftc.gov.

7.2 Sources for Non-Government documents.

7.2.1 AATCC test methods are available online at https://www.aatcc.org.

7.2.3 ANSI/ASQ Z1.4 – Sampling Procedures are available online at https://www. asq.org.

7.2.2 ASTM Standards are available online at https://www.astm.org.

7.3 Intended use. This cloth is intended to be used as interfacing for use in coat fronts of dress clothing items.

7.4 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for stated requirement.

7.5 Ordering data. The contract or order should specify the following:

a. Title, number, and date of this commercial item description
b. Type required (see 2.1)
c. Color required (see 3.2)
d. Product conformance provisions (see 5.1)
e. Acceptance criterial provisions (see 5.5)
f. Packaging requirement (see 6.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

7.6 Key words.

Animal fiber
Interlining
Polyester
Rayon

MILITARY INTERESTS:

CIVIL COORDINATING AGENCY ACTIVITY

GSA-FAS

Custodians:
Army - GL
Navy -NU
Air Force - 11

Preparing Activity:
DLA-CT

(Project: 8305-2019-006)

Review Activities
Army - MD
Navy - MC

Note: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.