INCH-POUND
A-A-52110B
August 24, 2021
SUPERSEDING
A-A-52110A
January 9, 2008

COMMERCIAL ITEM DESCRIPTION

CLOTH, PLAIN WEAVE, POLYESTER/COTTON for POCKETS (WATER REPELLENT)

The General Services Administration has authorized the use of this Commercial Item Description for all federal agencies.

1. SCOPE. This Commercial Item Description covers water repellent polyester/cotton plain weave cloth intended for use as pockets in clothing items.

2. CLASSIFICATION. The cloth shall be of one (1) type and in the following classes:

2.1 Classes.

Class 1 - Camouflage Green 483
Class 2 – Tan 499

3. SALIENT CHARACTERISTICS.

3.1 Description. The cloth shall be plain weave and the yarns for the warp shall be 100 percent textured continuous multifilament polyester with the filling yarns spun singles made from a blend of 30 to 60 percent carded or combed cotton and the remaining percentage polyester. The width of the cloth shall be as specified in the contract or purchase order (see 7.7) and shall be the minimum acceptable width inclusive of the selvage when fly shuttle looms or shuttleless looms with tuck-in selvages are used. For all other shuttles looms, the width measurement shall be made between the last warp yarn on each side excluding the protruding fringe(s). The cloth shall be given a durable water repellent treatment and shall conform to the hydrostatic pressure and spray rating requirements as specified in Table I.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Attn: DLA Troop Support, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil/.

FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

3.2 Color. The color shall be Camouflage Green 483 or Tan 499 or as specified in the contract or purchase order. The finished cloth shall match the standard sample for shade and appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced.

3.2.1 Visual shade matching. The color and appearance of the material shall match the standard sample when viewed using the AATCC EP 9, Option C (see7.9), with sources simulating artificial daylight D_{75} illuminant with a color temperature of 7500K (± 200) illumination of 100 (±20) foot candles, and shall be a good match to the standard sample under incandescent A illuminant with a color temperature of 2856K (± 200).

3.3 Physical requirements. The finished cloth shall conform to the requirements listed in Table I.

TABLE I. Physical and colorfastness requirements.

Characteristic	Requirement	Test method
Fiber Identification		
Polyester	See 3	AATCC TM20 (see 7.5)
Cotton	See 3	AATCC TM20 (see 7.5)
Fiber Content, Yarn (%)		AATCC TM20A (see 7.5)
Filling	30-60% Cotton and the rest polyester	
Warp	100% Polyester	AATCC TM20A (see 7.5)
Colorfastness to:		
Laundering (after 3 cycles)	3-4 min.	AATCC TM61 Test 3A 1/, 2/
Perspiration (acid & alkaline)	3-4 min.	AATCC TM15 1/, 2/
Crocking	3.5 min.	AATCC TM8 3/
Weave	Plain	Visual
Width (min.)	See 7.7	ASTM D3774
Weight, oz./sq. yd. (min.)	5.0	ASTM D3776/D3776M
Breaking Strength, lbs. (min.)		
Warp	250	ASTM D5034
Filling	100	ASTM D5034
Yarns per inch, (min.)		
Warp	105	ASTM D3775
Filling	68	ASTM D3775
Tearing Strength, lbs. (min.)		
Warp	7.5	ASTM D1424
Filling	2.5	ASTM D1424

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

TABLE I. Physical and colorfastness requirements. – Continued

Characteristic	Requirement	Test method
Spray rating: Initial After 3 launderings	100, 100, 90 80, 80, 70	AATCC TM22 AATCC TM96, Test VIc, and AATCC TM22 4/
Hydrostatic resistance, cm (min) Initial After 3 launderings	 30 30	AATCC TM127, AATCC TM96, Test VIc, andAATCC TM127 4/
Dimensional stability, %, (max) Warp Filling	 3.0 2.0	 AATCC TM96, VIc 5/ AATCC TM96, VIc 5/

1/ AATCC EP1
2/ AATCC EP 2
3/ AATCC EP 8
4/ An additional laundry procedure shall be performed without the use of any detergent
5/ The dimensional stability shall be performed after one (1) cycle. The cloth shall not be pressed after tumble drying prior to measurement.

3.4 Labile sulfur. The use of dyes and compounds containing sulfur capable of oxidation to sulfuric acid is prohibited. The cloth shall be "Free" of labile sulfur when tested as specified in 3.4.1.

3.4.1 Presence of labile sulfur test. Two (2) 1.50 (± 0.01) gram samples from each sample unit shall be tested. Each of the two (2) samples shall be cut into very small pieces and placed into separate test tubes. Prepare an acidic tin(II) chloride (stannous chloride) solution by dissolving 100 g SnCl2 (ACS grade) in 100 mL of 35% hydrochloric acid (ACS grade) and adding the mixture to 50 mL of distilled water. Prepare a lead acetate solution by dissolving 5.0 g of lead acetate (CP reagent grade) in a small amount of distilled water and diluting to a total of 100 mL. If the solution is not clear, add a few drops (one at a time) of glacial acetic acid until the solution is clear. The samples shall be submersed in the acidic tin(II) chloride solution. A filter paper wet out with the lead acetate solution shall be placed over the top of the test tube. The test tube containing the textile sample, tin(II) chloride and wet filter paper shall be heated over a low flame until the solution is boiling. The solution should not be heated for more than 15 seconds. A brown to black stain on the filter paper should be evaluated as follows:

Free - The filter paper shows no discoloration or staining of any kind.
Slight - The filter paper shows a light tan to light brown discoloration stain.
Moderate - The filter paper shows a dark brown discoloration stain.
Severe - The filter paper shows a black color stain.
The rating shall be recorded. The results shall be recorded as "pass" or "fail.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

3.5 Toxicity. The finished cloth shall not present a health hazard and shall show compatibility with prolonged, direct skin contact when tested as specified in 3.5.1. Chemicals recognized by the Environmental Protection Agency (EPA) as human carcinogens shall not be used. (See 7.2.4).

3.5.1 Toxicity test. When required (see 7.7), an acute dermal irritation study and a skin sensitization study shall be conducted. When the results of the studies indicate the cloth is not a sensitizer or irritant, a Repeat Insult Patch Test shall be performed in accordance with the Modified Draize Procedure (see 7.6). If the toxicity requirement (see 3.5) can be demonstrated with historical use data, on the finishing treatments used, toxicity testing may not be required (see 7.7).

3.6 Length and put-up. For Government procurements only, unless otherwise specified (see 7.7), the cloth shall be furnished in continuous lengths, each not less than 40 yards. Each length shall be put-up full width on a roll.

3.7 Fiber identification. Each roll of finished cloth shall be labeled or ticked for fiber content in accordance 16 CRF Part 303 with the Rules and Regulations under the Textile Fiber Products Identification Act (see 7.1.2).

3.8 Workmanship. The finished cloth shall conform to the quality of product established in this document. The finished cloth shall be free from defects which would affect its serviceability, appearance, uniformity and quality assurance standards defined by the technical data in the bid package.

4. REGULATORY REQUIREMENTS. Unless otherwise specified, the offeror/contractor is encouraged to use recovered, recycled, bio based, and environmentally preferable materials to the maximum extent practicable, in accordance with paragraph 23.403, 23.404(b) of the Federal Acquisition Regulation FAR, or the sustainable acquisition of EO 13693; as applicable. (See 7.2.4).

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The finished cloth shall meet the salient characteristics of this Commercial Item Description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptability. The finished cloth offered or generic equivalent, must have been sold to the government or commercial market.

5.3 End item inspection procedures. Sampling for inspection shall be conducted in accordance with ASQ/ANSI Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.2).

5.4 Visual examination. The finished cloth shall be examined for the defects listed in Table II as defined in ASTM D3990.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

TABLE II. Visual examination defects.

Material	Any hole, cut, or tear. Puckered, wrinkled or creased/pleated material.
Label	Label missing, incorrect, or illegible. Required information missing from the label.
Packaging	Not packaged in accordance with the contract or purchase order.

5.5 Acceptance criteria. Acceptance criteria shall be as specified in the contract or purchase order (see 7.7).

6. PACKAGING.

6.1 Packaging. Preservation, packing, and marking shall be as specified in the contract or order.

7. NOTES.

7.1 Source of Government documents.

7.1.1 Copies of Government documents are available online at https://quicksearch.dla.mil.

7.1.2 16 CFR Rules and Regulations under the Textile Fiber Products Identification Act are available online at https://www.ftc.gov.

7.2 Sources for Non-Government documents.

7.2.1 AATCC test methods are available online at https://www.aatcc.org.

7.2.2 ASQ/ANSI Z1.4 – Sampling Procedures and Tables for Inspection of Attributes are available online at https://www.asq.org.

7.2.3 ASTM Standards are available online at https://www.astm.org.

7.2.4 EPA and EO 13693 information are available online at https://www.epa.gov.

7.2.5 Federal Acquisition Regulations (FAR) are available online at https://acquisition.gov

7.3 Intended use. This cloth is intended to be used in clothing pockets.

7.4 Standard samples. For access to standard shade samples of cloth, address the contracting activity issuing the invitation for bids or request for proposal.

7.5 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for stated requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

7.6 Modified Draize Procedure (Repeat Insult Patch Test): Principles and Methods of Toxicology, A Wallace Hayes (editor) is available online at https://www.crcpress.com.

7.7 Ordering data. The contract or order should specify the following:

a. Title, number, and date of this commercial item description
b. Class required (see 2.1).
c. Width of cloth required (see 3.1)
d. When toxicity testing is required. (see 3.5)
e. Length required (see 3.1, 3.6)
f. Product conformance provisions. (see 5.1)
g. Acceptance criteria (see 5.5)
h. Packaging requirements (see 6.1).

7.8 Key words.

Clothing
Fabric

7.9 Visual shade matching. In 2017, Option A of AATCC Evaluation Procedure 9, Visual Assessment of Color Difference of Textiles was changed to Option C. NOTE: In case of confusion, the viewing geometry should be "The specimen plane and illumination source will be parallel to each other and aligned so that the light flux is incident at the center of the specimen plane, which is set at a 35 (± 5°) angle relative to the horizontal. The observer will view the specimens at a 90° angle, relative to the plane of the specimens".

7.10 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

MILITARY INTERESTS:

Custodian:
Army – GL
Navy – NU
Air Force – 11

Review Activity:
Army - MD
Navy – MC

CIVIL AGENCY COORDINATING ACTIVITY:
GSA - FAS

Preparing Activity:
DLA – CT

(Project: 8305-2021-020)

Note: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, verify the currency of the information above using ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.