INCH-POUND

A-A-52124
March 31, 1993

COMMERCIAL ITEM DESCRIPTION

REPAIR KIT, TAPE, PRESSURE SENSITIVE ADHESIVE (PSA)

The General Services Administration has authorized the use of this Commercial Item Description.

Abstract. This commercial item description covers a pressure sensitive adhesive (psa) tape repair kit for the Parka and Trousers, Extended Cold Weather Clothing System (ECWCS).

1. SALIENT CHARACTERISTICS

1.1 Description. The repair kit shall consist of a zip lock (resealable) poly bag containing a highly aggressive pressure sensitive adhesive tape (3 by 15 inches) with a rubber based adhesive specifically formulated for cold temperatures below $0^{\circ}F$, a thermoset polyurethane barrier coating and a nylon tricot knit substrate, set on a differential silicone coated release liner (folded, not rolled); and an unfolded instruction sheet on how to and where to apply the tape, instructions facing out.

1.2 Material.

1.2.1 Kit bag. The kit bag shall be poly bag with zip lock (resealable) closure. The finished dimensions of the bag shall be 6-1/2 $\pm$ 1/2 inches in length and 4-1/2 $\pm$ 1/2 inches in width. The bag shall have two heat sealed side seams.

1.2.2 Physical properties of tape. The physical properties of tape shall be as follows:

Adhesive thickness, inch	0.005
Peel strength, pli (Pounds per linear yard) min. 1/	8.0
Peel bond @ 1 second g min. 2/	1500

Beneficial comments, (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5019 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 7510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T09:06Z
Check the source to verify that this is the current version before use.

NOTE:

1/ Peel strength is measured using Pressure Sensitive Tape Council (PSTC) No. 1. Test Method: Peel Adhesion for Single Coated Pressure Sensitive Tape 180° Angle.

2/ Peel Bond is measured using commercial industries Polyten Tack Test Method.

1.2.3 Barrier tape coating. The barrier tape coating in between the adhesive and the tricot knit substrate shall be thermoset polyurethane and with a thickness of 2 ± 0.25 mil.

1.2.4 Cloth, for adhesive tape. The cloth for adhesive tape shall be made of nylon, tricot knit and weigh 1.5 ± 0.3 oz. per square yard.

1.2.5 Dimensions. The finished dimensions of the repair tape shall be 3 ± 1/16 by 15 ± 1/4 inches.

1.2.6 Color. The color of the tape shall be Olive Green 106.

1.2.7 Paper release liner. The paper release liner shall be differential silicone coated release liner.

1.3 Instructions sheet for use. The instructions sheet for use shall be unfolded and placed inside the sealed kit with the wording facing out on the opposite side of the item description label (see 1.3.1) and shall be as follows:

ECWCS Parka and Trousers
Repair Kit

INSTRUCTIONS FOR USE

* Best adhesion results are achieved with a clean, dry surface.

* Cut a desired length of tape with a pocket knife. Dimensions should be 1 inch longer and wider than the rip/tear. Use the full width (3 inches) of the tape whenever possible.

* Remove paper backing with knife blade along tape

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

edge. Turn garment inside out (parka can be turned through the middle back lining). Place tape over rip/tear on the inside of garment.

* Use paper backing as shield over tape and apply pressure with handle of knife. APPLY VIGOROUS PRESSURE to the entire patch.

1.3.1 Labeling. The kit bag shall have an adhesive label affixed to the outside with the following information:

Item Description
NSN
Contract Number
Contractor's Name

2. QUALITY ASSURANCE

2.1 Certification. The contractor shall certify, and maintain substantiating evidence, that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of of the contract.

2.2 Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practical.

2.3 Metric product. Products manufactured using metric units will be considered on an equal basis with those manufactured using inch-pound units, provided that the product measurements fall within specified tolerances using conversion tables contained in the latest revision of FED-STD-376 and that all other requirements of this CID are met.

3. PACKAGING

3.1 Overseas.

3.1.1 Packaging. The kit shall be closed and stacked.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

3.1.2 Packing. Five hundred kits shall be packed in a fiberboard box conforming to style RSC-L, grade 275 of PPP-B-636. The inside dimensions of the box shall be approximately 23-1/2 inches in length, 10 inches in width, and 10 inches in depth. The box shall be closed in accordance with the appendix of PPP-B-636.

3.1.3 Palletization. Boxes shall be palletized on a 4-way entry winged pallet in accordance with load type Ia of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C accordance with the appendix of MIL-STD-147.

3.1.4 Marking. Marking shall be in accordance with MIL-STD-129.

3.2 Domestic.

3.2.1 Preservation, packing, marking, and palletization. Unless otherwise specified in the contract, packaging, marking and palletization shall be in accordance with ASTM D 3951, Standard Practice for Commercial Packaging as specified for shipments to the Department of Defense, including Section 7.

4. NOTES

4.1 Ordering data.

a. Title, number and date of this document.

4.2 Sources of documents.

4.2.1 Sources of government documents. Copies of military and federal documents are available from:

Standardization Documents Order Desk
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

4.2.2 Sources of Non-Government documents.

ASTM D 3951 - Standard Practices for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

PSTC-1 - Test Methods For Pressure Sensitive Tapes

(Developed by the Specifications and Technical Committee of the Pressure Sensitive Tape council, 1800 Pickwick Avenue, Glenview, IL 60025-1377.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians

Army - GL
Air Force - 99

Review Activities

Army - MD
Navy - MC
Air Force - 82
DLA - CT

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - FSS

PREPARING ACTIVITY:

Army - GL

Project 7510-0374

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-52124	1993 March 31

3. DOCUMENT TITLE

REPAIR KIT, TAPE, PRESSURE SENSITIVE ADHESIVE (PSA)

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
U.S. Army Natick RD&E Center	(1) Commercial 508-651-4532	(2) AUTOVON/DSN 256-4532
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: SATNC-IRS Natick, MA 01760-5019	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.