MIL-N-36214B
18 April 1968
Superseding
MIL-N-36214A(DM)
29 October 1964 and
MIL-N-36214(DM)
25 May 1964

MILITARY SPECIFICATION

NEEDLES, HYPODERMIC, SPINAL ANESTHESIA, DISPOSABLE

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers sterile, disposable, pyrogen-free spinal puncture needles for use in spinal anesthesia.

1.2 Classification. Needles shall be of the following sizes, (gages and lengths) as specified (see 6.1):

Size 1 - 25 gage, 3-1/2 inch
Size 2 - 22 gage, 3-1/2 inch

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein:

SPECIFICATIONS

Federal

GG-I-526	Instruments, Dental and Surgical; General Specifications.
PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Box, Setup.

Military

MIL-L-10547	Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the current version before use.

STANDARDS

Federal

Fed. Test Method Std. No. 151 Metals; Test Methods.

Military

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 Marking for Shipment and Storage.

(Copies of specifications, standards, and drawings required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply:

UNITED STATES OF AMERICA (USA) STANDARDS INSTITUTE

USA Z70.1-1955 American Standard Dimensions of Glass and Metal Luer Tapers for Medical Applications.

(Application for copies should be addressed to the United States of America Standards Institute, 10 East 40th Street, New York, New York 10016.)

U.S. PHARMACOPOEIAL CONVENTION, INC.

Pharmacopeia of the United States.

(Application for copies should be addressed to the Mack Printing Company, Easton, Pa.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Cannula. Cannula shall be fabricated from seamless drawn, or welded and drawn tubing; material shall be class 3, type 304 in accordance with GG-I-526.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:13Z
Check the source to verify that this is the current version before use.

3.1.2 Hub. Hub shall be fabricated from brass, nickel plated, or chromium over nickel plated in accordance with plating requirements for class 8, type 260 material of GG-I-526. The corrosion tests shall be the salt-spray and boil tests. The hub shall be polished.

3.1.3 Stylet.

3.1.3.1 Stylet wire. The wire of the stylet shall be fabricated from class 3, type 304 material in accordance with GG-I-526.

3.1.3.2 Style knob. The stylet knob shall be fabricated from brass, nickel plated, or chromium over nickel plated in accordance with plating requirements for class 8, type 260 material of GG-I-526. The corrosion tests shall be the salt-spray and boil tests. As an alternate, the stylet knob shall be fabricated from austenitic corrosion-resisting steel; the corrosion tests shall be in accordance with GG-I-526 for class 3 material.

3.2 Style, design, and construction. The spinal anesthesia needles shall be disposable, sterile, pyrogen-free hypodermic needles, with special (spinal) bevel points, packaged in individual sealed containers as hereinafter specified. The sealed containers shall maintain the sterility of their contents, and shall be so designed as to permit ready dispensing of the needle by sterile techniques.

3.2.1 Cannula. The cannula shall be a straight tube with a special (spinal) bevel point on the distal end. The point shall be ground concave or flat and may have a center ridge at the distal end to strengthen the tip. The point shall be so ground at the outer end as to enhance the keenness of the tip and cutting edges. Both outer and inner edges of point shall be free from burrs and slivers. The tip of the point shall be straight and strong, and of maximum keenness. The proximal end of the cannula shall extend into the hub sufficiently to allow for secure staking. The cannula shall be centered in the distal end (opposite the end with the female taper) of the hub in such a manner as to provide a straight continuous fluid path from the hub cavity. In accordance with standard practice, the extension of the needle cannula into the hub shall not be such as to prevent the stylet from being readily inserted into the lumen of the needle cannula or to create areas for possible accumulation of materials. The cannula shall be securely swaged (not soldered) into the hub so as to be concentric with the hub cavity. There shall be no cementing of any kind at the cannula and hub junction. The cannula shall not deviate from the central longitudinal axis of the needle by more than 3 degrees. The word "lumen" wherever used in this specification shall refer only to the passageway through the needle cannula.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the current version before use.

3.2.1.1 Dimensions (cannula and point). Dimensions of cannula and point shall be as indicated in table I.

Table I. Dimensions of Cannula and Point

Size	Cannula			Point
	Length (inch)*	Outside diameter, limits (inch)	Inside diameter, minimum (inch)**	Length, limits (inch)***
1	3-1/2 ± 1/8	0.020 ± 0.005	0.0095	0.042 ± 0.007
2	3-1/2 ± 1/8	0.028 ± 0.005	0.0155	0.070 ± 0.010

* Measured from the tip of the point to the junction with the hub.
** Measured at point.
*** Measured from heel to tip parallel with longitudinal axis of cannula.

3.2.2 Hub. The hub shall be Luer-lock type, so shaped as to provide means for facilitating attachment to, and removal from, a syringe. Hub and hub cavity shall be in accordance with figure 3 of USA Standard Z70.1-1955. The hubs shall be tested for diameter and depth of hub cavity as specified in 4.4.1. Hubs which do not fit the plug gage within the "GO" - "NO GO" limits specified in 4.4.1, shall be considered not acceptable. In addition, when the hub is fitted onto the plug gage as specified in 4.4.1, there shall be no movement of the hub on the gage when the cannula is pressed lightly from side to side in all directions. The entire hub cavity wall, down to the entrance of the lumen, as well as the exterior of the hub shall be well plated. The edge of the hub shall be slotted to reveive the guide provided on the knob of the stylet.

3.2.3 Stylet. Each needle shall be fitted with a stylet. The stylet wire shall extend into the stylet knob to allow for secure staking or crimping. The stylet wire shall be securely swaged or crimped (not soldered or cemented) into the stylet knob in a concentric manner, to allow proper and easy insertion and withdrawal of the stylet into and from the needle hub and cannula.

3.2.3.1 Stylet wire. The stylet wire shall be capable of easy and proper insertion into, and withdrawal from, the needle. The wire shall be of adequate length to permit one end to be permanently secured into the stylet knob, and the opposite end to be ground flush with the cutting edge of the cannula (that is, the beveled point of the cannula). The wire shall be of sufficient diameter so as to prevent such movement of the stylet which might permit the cut tip of the stylet to be bent while the stylet is in position in the needle (that is, bevel of the stylet tip shall blend with bevel of point of the cannula presenting a single uniform surface with point of cannula).

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:13Z
Check the source to verify that this is the current version before use.

3.2.3.2 Stylet knob. The stylet knob shall be of conventional design having a taper tip that shall properly fit the Luer taper slip of the needle hub, and a guide of adequate style and design to make a positive fit into the slotted edge of the needle hub and hold the ground edge of the wire stylet in proper position. The slot and guide shall be aligned with, and on the same side as the beveled surface of the cannula point.

3.3 Freedom from foreign matter. When tested as specified in 4.4.3, the hub cavity shall be substantially free from chips and other foreign matter. In addition, a visual examination of the lumen of the cannula shall reveal no presence of foreign matter, chips, burrs, or occlusion of the lumen.

3.4 Security of assembly. When tested as specified in 4.4.4, the cannula shall not loosen or pull out of the hub, and the stylet wire shall not pull out of the stylet knob.

3.5 Resistance to breakage. When tested as specified in 4.4.5, there shall be no breakage.

3.6 Stiffness. When tested as specified in 4.4.6, the maximum deflection of the cannula shall not exceed the deflection shown in table V, column (3).

3.7 Elasticity. When tested as specified in 4.4.7, the cannula shall show no permanent set (that is, after being released the cannula shall return fully to the starting point).

3.8 Fluid tightness. When tested as specified in 4.4.8, the connection of the cannula with the hub, and the Luer connection of the hub with the tapered test gage, shall not show leakage exceeding the formation of a falling drop.

3.9 Sterility. When tested as specified in 4.4.9, needles shall comply with the sterility test requirements of the current edition of the Pharmacopeia of the United States (U.S.P.).

3.10 Freedom from pyrogens. When tested as specified in 4.4.10, needles shall comply with the pyrogen test requirements of the current edition of the U.S.P.

3.11 Certificates. For destination inspection only, certificates of sterility, and freedom from pyrogens, as specified herein, shall be submitted by the contractor directly to Defense Personnel Support Center, Directorate of Medical Materiel, Technical Operations Division, 2800 South 20th Street, Philadelphia, Pa. 19101, Attention: Quality Control Branch, and one copy of each shall be forwarded with each shipment to the consignee.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the current version before use.

3.11.1 Certificate of sterility. A certificate of sterility, listing all sterility lot or control numbers, shall state that samples from each sterility lot or control have been tested for sterility, as required in 3.9 and 4.4.9, and were found to be sterile. The certificate shall reference the method used in determining sterility.

3.11.2 Certificate of freedom from pyrogens. A certificate of freedom from pyrogens, listing all lot or control numbers, shall state that samples from each lot or control have been tested for pyrogens as specified in 3.10 and 4.4.10 and were found to comply with such requirements. The certificate shall reference the method used in determining freedom from pyrogens.

3.12 Identification marking. The spinal puncture needles shall have the gage number and contractor's name or registered trademark permanently and legibly marked on the needle hubs.

3.13 Finish. The cannula shall show a smooth finished outer surface free from pits and tool marks, and inner surface free from scale, deep pits, deep furrows, or die marks. The stylet shall show a smooth finished surface free from pits and tool marks. The hub and hub cavity shall have a smooth bright finish.

3.14 Workmanship. Workmanship shall be first class throughout. Needles shall be free from defects which detract from their appearance or may impair their serviceability. The lumen of the cannula and the hub cavity shall be free from chips, dirt, or other foreign matter. Needles shall be sharp, not blunt or bent, and points shall be free of feathered edges, burrs, or other defects, when examined under 7 power magnification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the current version before use.

4.1.2 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and as indicated in table II.

Table II. Sampling Criteria for Examination

Type defect	Inspection level *	AQL (percent defective)
Major A	S-4	1.0
Major B	S-1	1.0
Minor A	S-4	6.5
Minor B	S-1	4.0

* If acceptance number is not exceeded, lot shall be acceptable. If rejection number is equaled or exceeded, then the inspection at level II may be performed to determine the final rejection or acceptance.

4.2.2 For tests.

4.2.2.1 Sterility test. Sampling for sterility test shall be as indicated for Liquids and Suspensions under Sterility Tests in the current edition of the U.S.P.

4.2.2.2 For freedom from pyrogens. The number of samples required for test (see 4.4.10) shall be taken from each sterility lot for test.

4.2.2.3 For other tests. Sampling for other tests shall be conducted in accordance with MIL-STD-105, and as indicated in table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

Table III. Sampling Criteria for Tests

Component	Characteristic	Reqmt.	Test Procedure	Unit of Product	Insp. Level	AQL
Needle cannula and stylet wire	Boil Test	GG-I-526	GG-I-526	1-needle	S-2	*
Needle hub and stylet knob	Boil Test (For all material)	3.1.2 & 3.1.3.2	GG-I-526	1-needle	S-2	*
	Salt-Spray (For all plated brass)	3.1.2 & 3.1.3.2	GG-I-526	1-needle	S-2	*
	Plating Test	3.1.2 & 3.1.3.2	GG-I-526	1-needle	S-2	*
Needle Cannula	Dimensions	3.2.1.1	---	1-needle	S-2	*
	Resistance to Breakage	3.5	4.4.5	1-needle	S-2	*
	Stiffness Test	3.6	4.4.6	1-needle	S-2	*
	Elasticity Test	3.7	4.4.7	1-needle	S-2	*
Needle hub	Diameter and Depth of Luer Hub Cavity	3.2.2	4.4.1	1-needle	S-2	*
Hypodermic Needle	Freedom from Foreign Matter	3.3	4.4.3	1-needle	S-2	*
	Security of Assembly	3.4	4.4.4	1-needle	S-2	*
	Fluid Tightness	3.8	4.4.8	1-needle	S-2	*

* Acceptance number shall be zero for all sample sizes.

4.2.3 Raw materials. A sufficient quantity of each lot of metal used in the construction of the needles shall be selected for chemical analysis.

4.2.4 Sample unit usage. Where feasible, the same sample unit shall be used for the determination of two or more test characteristics.

4.3 Examination. The needles shall be examined to determine compliance with all requirements contained in this specification. Examination shall be conducted as specified in tables II and IV. Inspection, however, shall not be restricted to defects listed in table IV. Any needles in the sample containing one or more defects shall be rejected and, if the number of defective needles in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:13Z
Check the source to verify that this is the current version before use.

Table IV. Classification of defects in accordance with MIL-STD-105

Categories	
Critical:	None defined
Major A:	
101	Cannula lumen not free of obstructions.
102	Cannula lumen not free of scale, burrs, chips, dirt, deep pits, deep furrows, die marks, or other foreign material.
103	Cannula outer surface not smoothly finished or free of pits, tool marks, burrs, scale, or corrosion.
104	Cannula not free of cracks.
105	Cannula not concentric with hub.
106	Cannula outside diameter not as specified.
107	Point missing.
108	Cannula or stylet point blunt or bent, not sharp, not symmetrical or properly formed, or not free of burrs, feathered edges, or other detrimental defects (examined under 7X magnification).
109	Point does not face flat of hub.
110	Hub not free of cracks, pits or tool marks.
111	Hub not free of burrs, slivers, or plating not free of flaking.
112	Hub not plated down to entrance of lumen, as well as exterior.
113	Hub cavity diameter and depth not in accordance with USA Standard as specified.
114	Hub indexing slot missing, or does not make proper fit with stylet lug.
115	Hub indexing slot not lined up with cannula point.
116	Stylet missing.
117	Stylet tip not flush with cannula point.
118	Stylet outside diameter prohibits free entry into cannula.
119	Stylet lug missing, or not effective.
120	Stylet makes sloppy or binding fit with needle.
121	Stylet wire not straight.
122	Needle container not free of foreign matter.
Major B:	
151	Cannula inside diameter not as specified.
152	Point length not as specified.
Minor A:	
201	Discoloration of outside surfaces of needle or stylet.
202	Cannula length not as specified.
203	Cannula not straight (i.e., not within 3°).
204	Gage number on hub is missing or not legible.
Minor B:	(Unit of product - Unit package and contents)
251	Average count per unit package not a minimum of 50 needles.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the current version before use.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Diameter and depth of hub cavity. Hub cavity shall be tested on the male Luer taper gage in accordance with plug gage of figure 5 of USA Standard Z70.1-1955. (This gage shall be as shown in the USA Standard, except that it shall be constructed with a suitable fluid path to permit performance of the fluid tightness test specified in 4.4.8). The hub shall be slipped onto this gage with very light pressure. The fit of the hub on this gage shall be tested by means of the feeler gage in accordance with figures 5 and 6 of USA Standard Z70.1-1955.

4.4.2 Corrosion-resistance of hub and plated brass stylet knob. The hub or stylet knob shall be boiled in distilled water for 30 minutes, and then shall remain immersed for 24 hours in distilled water. At the end of the 24 hours, the hub or stylet knob shall be allowed to dry by evaporation, and shall then be examined for evidence of corrosion. This test shall be made in a glass vessel.

4.4.3 Freedom from foreign matter test. The hub cavity shall be examined under 7X magnification, and good illumination, for chips and other foreign matter. In addition, a cotton swab tightly wrapped on the end of a small wooden applicator shall be vigorously turned down into the bottom of cavity, withdrawn, and examined for chips and other foreign matter under 7X magnification and good illumination. The cannula shall be tested for blockage by inserting a wire through the lumen of the cannula.

4.4.4 Security of assembly. A straight pull of 10 pounds shall be applied between the cannula and hub, and the stylet wire and stylet knob for a period of one minute for 22 gage needles. For the 25 gage needles, a straight pull of 5 pounds shall be applied in the same manner as for the 22 gage needles (cannula and hub, and stylet wire and stylet knob).

4.4.5 Resistance to breakage test. The needle hub shall be clamped in a fixed position, and a force shall be applied to the cannula, at a distance as specified in table V, column (6), in order to bend the cannula in a clockwise direction through an arc of 25 degrees from the original or neutral position. The operation shall then be reversed (that is, bent through an arc of 25 degrees from the neutral position in a counter-clockwise direction), and finally, the cannula shall be returned to the neutral position. This completes operation (or cycle) which shall be repeated 20 times.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the currentversion before use.

4.4.6 Stiffness test. The cannula shall be placed across two test edges (0.002 inch radius maximum) separated by a distance indicated in table V, column (4). A load as specified in table V, column (2), shall be applied to the center of the span and the resulting maximum deflection of the cannula shall be measured using a gage with graduations of at least 0.001 inch. The force shall be applied through an edge with a maximum radius of 0.036 inch, and centered to within ± 0.003 inch (see 6.2).

4.4.7 Elasticity test. With the hub in a fixed position, the cannula shall be bent to one side for an amount of 12 degrees at contact distances specified in table V, column (6) from the hub, and then released.

4.4.8 Fluid tightness test. With the needle in a horizontal position, the hub shall be attached by means of a plug gage as shown in figure 5 of USA Standard Z70.1-1955 (except that gage shall have been provided with a fluid path) to a water pressure source having a pressure gage. The water shall be permitted to run through the needle so as to fill any hub cavity space and the lumen of the cannula. The lumen shall then be sealed by a piece of solid rubber pressed on to the point. A pressure of 45 pounds per square inch gage shall be applied for 10 seconds.

4.4.9 Sterility test. The sterility test shall be performed as described under Sterility Tests in the current edition of the U.S.P.

4.4.10 Freedom from pyrogens test. Place 10 needles in a sterile, pyrogen-free flask, pour 250 milliliters (ml.) of sterile, pyrogen-free saline test solution (U.S.P.) into the flask and then heat the contents of the flask at not less than 40° Centigrade (C.) nor higher than 50° C. for one (1) hour. The resulting saline extract shall be submitted to the "Pyrogen Test" as described in the current edition of the U.S.P.

Table V. Tests

Gage	Stiffness			Elasticity	
	Needle				
	Under load of (ounces)	Shall deflect maximum (inch)	Separation of test edges	Without permanent set shall bend (degrees)	Contact distance, from hub (inches)
(1)	(2)	(3)	(4)	(5)	(6)
25	25	0.026	1/2	12	7/16
22	50	0.029	5/8	12	11/16

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the currentversion before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. One package containing fifty needles, as specified, constitute one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in table V shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in procurement document.

Table VI. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	Not required	12 units

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Individual package. Each needle shall be packaged in an individual rigid plastic container. The individual container shall protect the needle point from damage and permit ready opening. The package design shall be such as to permit ready dispensing of the needle from the package, by sterile techniques and by attaching the syringe to the hub of the needle without touching the needle with hands or other instruments. The completed sealed individual package shall be substantially free from foreign matter and shall maintain the degree of sterility as specified in 3.9 until such time as seal is broken or package is opened. The rigid plastic container shall be extruded or moulded in two parts of a thermo-plastic resin. The lower part of the container shall be designed with interior fittings to maintain the needle in a vertical position with sufficient area of the hub exposed to permit the attaching of the syringe. The upper part or cap shall fit over the lower part in such a manner as to permit sealing of the two parts. Sealing of the two parts shall be accomplished by means of a thermo-plastic area approximately 1/4 inch wide, in such a manner that it shall be tamperproof (that is, an opened container (broken seal) shall be easily discernible, in that the upper part or cap of container shall be easily separated from the lower part without exerting any effort, and shall be cause for rejection).

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:13Z
Check the source to verify that this is the current version before use.

5.1.3.2 Unit package. Fifty individual packages shall be packaged in a carton of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676, except that commercial colors are acceptable. The individual packages shall be oriented within the carton in a neat manner. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 3 use; PPP-B-601, table II, using type I, class 1 plywood; PPP-B-621, table III; or PPP-B-636, type CF, class weather-resistant.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.1.3 Closure. Closure of wood boxes shall be in accordance with appendix of applicable box specification. Closure of each fiberboard box shall be as specified in the appendix of PPP-B-636. In addition, waterproofing shall be in accordance with 30.4.

5.2.1.4 Strapping. Strapping, when required, shall be in accordance with appendix of applicable box specification.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall conform to PPP-B-601, table I, using type III, class 1 plywood, or shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 2 use; or PPP-B-621, table I; or PPP-B-636, type CF, class domestic, fabricated from not less than 200-pound test fiberboard. Closure shall be in accordance with the appendix of the applicable box specification.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:13Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 Individual package. Each individual package shall be marked with needle size, name or registered trade-mark of manufacturer, and legend indicating that needle is sterile, pyrogen-free, and disposable type. In addition, marking shall include the legend: "Use Once and destroy."

5.3.2 Unit package. At least one side face of each unit carton shall be provided with instructions describing the proper techniques for dispensing the sterile needles, as applicable, from the containers and preparing them for use. In addition, information as to methods for destroying needles, as applicable, to prevent their re-use shall also be shown. The following information shall be printed on the carton or applied by means of a label:

Federal stock number.
Item identification.
Quantity and unit.
Names of manufacturer and contractor.
Lot (control) number.
Legend indicating that needles are sterile, pyrogen-free, and disposable type.
Contract number.
Level of preservation and date.

5.3.3 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129. Lot (control) numbers shall be shown. Marking shall include a legend indicating that needles are sterile, pyrogen-free, and disposable type.

NOTE: The quantity and unit shall be designated on interior packages and exterior container, as follows:

Unit package: "1 Pkg (of 50 needles)."

Exterior container: "12 Pkg"

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Number and date of this specification.
(b) Gage and length required (see 1.2).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

6.2 The apparatus for stiffness test described in 4.4.8 may be obtained from the Federal Products Corp., Providence, Rhode Island.

6.3 This specification does not include all types, classes, grades, sizes, etc., of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types, etc., which are normally procured to meet Military requirements.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document (s) or serve to amend contractual requirements .

SPECIFICATION

MIL-N-36214B

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 65 1426 REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:13Z
Check the source to verify that this is the current version before use.