MIL-P-36215A
13 August 1968
Superseding
MIL-P-36215(DM)
25 May 1964

MILITARY SPECIFICATION

PILLOWCASE, PAPER, WHITE, DISPOSABLE

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers a disposable, white paper pillowcase for use in protecting the pillow from blood, pus, and perspiration during aeromedical evacuation of casualties.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

V-T-276	Thread, Cotton.
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-T-76	Tape, Pressure-Sensitive Adhesive Paper, (for Carton Sealing).

Military

MIL-L-10547	Liners, Case, and Sheet, Overwrap, Water-Vaporproof or Waterproof, Flexible.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13
Check the source to verify that this is the current version before use.

STANDARDS

Federal

FED-STD-751 Stitches, Seams, and Stitchings.

Military

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 Marking for Shipment and Storage.

DRAWING

Defense Personnel Support Center

2193 Cabinet for Fire Resistance Test of Paper Products.

(Copies of specifications, standards, and drawing required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY

T402-m-49 Conditioning Paper and Paperboard for Testing.

T403-ts-63 Bursting Strength of Paper.

T404-ts-66 Tensile Breaking Strength of Paper and Paperboard.

T410-os-61 Basis Weight of Paper and Paperboard.

T414-ts-65 Internal Tearing Resistance of Paper.

T456-m-49 Wet Tensile Breaking Strength of Paper and Paperboard.

T461-m-48 Flammability of Treated Paper and Paperboard.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 360 Lexington Avenue, New York, N.Y. 10017.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

TECHNICAL MANUAL AND YEAR BOOK OF THE AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

(Application for copies of the AATCC Manual should be addressed to the Secretary, American Association of Textile Chemists and Colorists, Post Office Box 886, Durham, North Carolina.)

3. REQUIREMENTS

3.1 Sample. When available, samples are furnished solely for guidance and information to the contractor. Variations from this specification may appear in the sample, in which case this specification shall govern (see 6.1).

3.2 Material. The pillowcases shall be fabricated with the laminated material specified in 3.2.1. The material shall be such as to result in a finished pillowcase approaching the comfort of the conventional textile pillowcase. No known irritating or toxic elements shall be present in the finished material. The material shall be white in color and shall offer a soft pliable surface which shall be lint free and free from objectionable noises when used by a restless patient. The material shall be free of objectionable odors. Masking agents may be employed to mask objectionable odors with another more pleasant odor providing the odor of the finished pillowcase is faint and in no way objectionable. The material shall be rendered water-resistant and shall have a spray rating of at least 50 when tested as specified in 4.2.2.2. The material shall be rendered fire-resistant, and, when tested as specified in 4.2.2.3, shall show not more than 4-1/2 inches char in 12 seconds and 3 seconds afterglow. Material shall show an immediate extinguishing of flame when the lighted match is removed.

3.2.1 Laminated material. The laminated material shall have a nylon core in both directions or a nylon, rayon core (nylon in one direction and rayon in the other direction), which has a minimum of 5 by 5 threads per inch and four layers of cellulose wadding (two layers on each side of the core). The cellulose wadding shall consist of fully bleached chemical fibers. The material shall conform to the minimum requirements listed in table I and 3.2, when tested as specified in 4.2.2.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

Table I. Physical requirements

Requirements	Laminated material (see 3.2.1)
Basis weight (24 by 36-500 sheets) pounds	48
Dry tensile breaking strength-pounds per 15 millimeters width.	
Machine direction	5
Cross direction	2
Wet tensile breaking strength-pounds per 15 millimeters width, after 15 ± 3 seconds water immersion	
Each direction	1.0
Bursting strength, Mullen, points	10
Tear-resistance, grams	
Machine direction	300
Cross direction	200

3.2.2 Thread, cotton. The thread shall be white cotton thread, ticket No. 50, 3 ply, conforming to type I/2 of V-T-276.

3.2.3 Adhesive. The adhesive used to glue seams shall be a suitable polyvinyl acetate adhesive.

3.3 Construction. The pillowcase shall be of the slip-on envelope type and shall be made of material specified in 3.2.1. The pillowcase shall be constructed of one or two pieces of material. When constructed from one piece the material shall be folded so that only the sides shall be joined or folded so that only one side and one end are joined, leaving the opposite end open. When constructed from two pieces of material one end and the sides shall be superimposed and joined. The seams shall be straight and even. Folding or overlapping of seams is prohibited.

3.3.1 Seams. All seams shall be glued or sewed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

3.3.1.1 Glued seams. The glued seams shall adhere securely throughout their entire area and shall be free from wrinkles. The seams shall be stronger than the adjoining material when separation by hand is attempted. The glued seam width shall be 1/8 to 3/16 inch for the side seams and 1/8 to 1/4 inch wide for the bottom seam. The side seams shall start not more than 1/16 inch from the side edge of the material, and the bottom seam shall start not more than 3/8 inch from the bottom edge of the material. There shall be no excess glue nor pronounced discoloration along the seam area. The adhesive used shall be as specified in 3.2.3.

3.3.1.2 Sewed seams. Stitches, seams and stitching used for sewed seams shall conform to FED-STD-751. The seam type shall be SSa-1, and the stitch type shall conform to an over edge stitch type in the 500 series. There shall be six to ten stitches per inch.

3.3.2 Dimensions. The finished overall flat dimensions shall be 31-1/2 inches ± 1/4 inch long and 20-1/2 inches ± 1/4 inch wide.

3.4 Workmanship. The finished pillowcase shall be clean, free from breaks, tears, holes, wrinkles, uneven or ragged edges, lint, and other defects which detract from its appearance or may impair its serviceability. The occurrence of defects shall not exceed the limits set by the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificates of [illegible]. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

Component	Characteristic
Laminated material	Composition of nylon rayon case. Texture of nylon rayon case. Material water-resistant, fire-resistant, nonirritating and nontoxic. Cellulose wadding, fully bleached, chemical fiber.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

4.2 Inspection for acceptance. Inspection shall be made in accordance with MIL-STD-105, except where otherwise indicated herein.

4.2.1 In-process inspection. Inspection shall be made at any point or during any phase of the manufacturing process to determine whether operations or assemblies are accomplished as specified. The Government reserves the right to exclude from consideration for acceptance any material or service for which in-process inspection has indicated nonconformance. In-process inspection shall be conducted to see that accomplishment of the following is in accordance with the specification requirements:

Requirement, operation, or assembly
Four layers of cellulose wadding are laminated to core (two layers on each side)

4.2.2 Component and material inspection. In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specification, drawings, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase documents.

4.2.2.1 Testing of components. The method of testing as listed in table II shall be followed. When the data in the "number of determinations" and "results reported as" columns are not specified in the table they shall be as required by the referenced test method. The values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes, as specified in the applicable test method. All test reports shall contain the individual values utilized in expressing the final result. The sample unit shall be 4 yards full width of the finished material. The lot size shall be expressed in units of one yard. The lot size shall be unacceptable if either one or more of the sample units fails to meet any test requirement specified. The inspection level (number of sample units) shall be in accordance with S-1 of MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the current version before use.

Table II. Test methods

Characteristic	Requirement paragraph	Test method TAPPI	Number of determinations per unit	Results reported as
Water-resistance (spray rating)	3.2	Para 4.2.2.2	3	Rating of 100, 90, 80, 70, 50 or 0
Fire-resistance: Char length 4-1/2"	3.2	Para 4.2.2.3	3	Nearest 0.1 inch
After glow			3	Nearest second
Self-extinguishing			3	Pass or fail
Basis weight (24 x 36 - 500 sheets)	Table I	T-410-os-61	1	Nearest 0.1 lb.
Dry tensile breaking strength	Table I	T-404-ts-66		
Machine direction			10	Nearest 0.1 lb. (Avg.)
Cross direction			10	Nearest 0.1 lb. (Avg.)
Wet tensile breaking strength	Table I	T-456-m-49		
Machine direction			10	Nearest 0.1 lb. (Avg.)
Cross direction			10	Nearest 0.1 lb. (Avg.)
Bursting strength	Table I	T-403-ts-63	10	
Tear-resistance	Table I	T-414-ts-65		
Machine direction			5	Nearest 1 gram
Cross direction			5	Nearest 1 gram

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

4.2.2.2 Water-resistance test. Water-resistance shall be tested as specified in the American Association of Textile Chemists and Colorists, Standard Test Method 22-1964.

4.2.2.3 Fire-resistance. The material shall be conditioned in accordance with TAPPI Method T-402-m-49. The test shall be as described in TAPPI Method T-461-m-48 and shall be conducted in a cabinet constructed as shown in the drawing.

4.2.3 Examination of end item. The defects found during this examination shall be classified in accordance with defects listed in 4.2.3.1 through 4.2.4. The sample unit shall be one pillowcase.

4.2.3.1 Classification of defects. All visual defects shall be classified as indicated below. The inspection level shall be level II of MIL-STD-105. The acceptable quality level shall be 4.0 for major defects and 10.0 for total defects (major and minor combined) per hundred units.

Defect	Classification	
	Major	Minor
Material defects and workmanship damages		
a. Any breaks, holes (other than pin holes).	X	
b. Needle chew 2/	X	
c. Any cuts or tears.	X	
d. Thin or weak spot which may result in a hole or rupture.	X	
e. Not soft to skin.		X
f. Color not as specified.	X	
g. Objectionable odor	X	
h. Mends, or patch.		X
Cleanness		
a. Spots, streaks or stains, clearly visible. 1/	X	
b. Not free of lint.		X
c. Glued area discolored affecting appearance. 3/		X
d. Excess glue affecting appearance. 3/		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

Defects	Classification Major	Minor
Seams and stitching		
a. Thread breaks not repaired. 2/		X
b. Loose or untrimmed threads. 2/		X
c. Stitch type not as specified. 2/		X
d. Stitches per inch not as specified. 2/	X	
e. Seams neither straight nor even.		X
f. Open seams; seam width not as specified.	X	
g. Distance seams from edge of material not as specified.		X
h. Glued seams wrinkled. 3/		X
i. Seams poorly glued; do not adhere securely throughout their entire area. 3/	X	
j. Glued seams not stronger than adjoining material when separation by hand is attempted. 3/	X	
k. Seams not located where specified.	X	
Assembly		
Pillowcase made of more than two pieces of material.	X	
Pillowcase not constructed as specified.	X	
Pillowcase not free of objectionable noise.	X	

1/ Clearly visible at normal inspection distance (approximately 3 feet).

2/ Applicable to sewed seams only.

3/ Applicable to glued seams only.

4.2.3.2 Examination for dimensional defects. During this examination any measurement deviating from the nominal dimension and tolerances specified in 3.3.2 shall be scored as a size measurement defect. The sample unit for this examination shall be one pillowcase. The sample size shall be selected in accordance with inspection level S-3 of MIL-STD-105. The acceptable quality level shall be 4.0 (one class) defects per 100 units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

4.2.4 Examination of preparation for delivery requirements. An examination shall be made to determine that packaging, packing, and marking requirements of section 5 of this specification are complied with. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per 100 units.

Examination	Defect
Markings, (exterior and interior)	Incorrect, illegible, of improper size, location, sequence, or method of application.
	Size or stock number on end item does not correspond to size or stock number marking of intermediate or shipping container.
Materials	Any nonconforming component; component missing, damaged, or otherwise defective affecting serviceability.
Workmanship	Inadequate application of components such as incomplete closure of case liners, container flaps, loose strapping, etc.
Weight or content	Number of intermediate packages is more or less than required: gross net weight exceeds requirements.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. One (1) pillowcase, as specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in table III shall be packaged in each intermediate and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table III. Packaging quantities

Unit package	Intermediate package	Exterior container
Not required	50 units	300 units

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

5.1.2.1 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Intermediate package. Fifty pillowcases shall be packaged flat (not folded) or, as an alternate, all fifty pillowcases may be folded in half in such a manner as to prevent a permanent crease. The pillowcases shall further be packaged in a carton of appropriate size constructed in accordance with PPP-B-636, class weather-resistant grade W5c or W5s, style RSC.

5.1.3.2 Closure. Closure shall be effected by means of tape conforming to the requirements of PPP-T-76. The tape shall be not less than 2 inches wide and shall be applied to both top and bottom so that the center seams are covered their full length. Tape shall extend at least 2 inches onto each of the end panels. Tape shall not be required on manufacturer's joint.

5.1.4 Level B.

5.1.4.1 Intermediate package. Intermediate package shall be a carton of appropriate size constructed in accordance with PPP-B-636. Closure shall be adequate to prevent spillage of contents under normal handling.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 3 use; PPP-B-601, table II, using type III, class 1 plywood; PPP-B-621, table III; or PPP-B-636, type CF, class weather-resistant. Closure and strapping shall be in accordance with applicable box specification.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.2 Level B.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

5.2.2.1 Exterior container. Exterior container shall conform to PPP-B-601, table I, using type III, class 1 plywood; or shall be designed for type 2 load, and constructed in accordance with PPP-B-585, style 3, for class 2 use; PPP-B-621, table I; or PPP-B-636, type CF, class domestic.

5.3 Marking.

5.3.1 Intermediate package. Each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129. Contract data marking shall be composed of the following information:

(a) Contract number.
(b) Name of address of contractor.
(c) Shipment number as shown in block 17 of DD Form 250.
(d) Name and address of manufacturer if other than contractor.
(e) Container number (consecutively numbered, from each shipping point, for duration of contract).

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Availability of guide sample (see 3.1).
(c) Inspection responsibility, methods, and tests (see section 4).
(d) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2 This specification does not include all types, classes, grades, and sizes of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types which are normally procured to meet Military requirements.

Custodians:
Army - MD
Navy - BuMed
Air Force - AFMSG

Preparing activity:
Defense Supply Agency. - DM

Review activities:
Army - MD
Navy - BuMed
Air Force - AFMSG

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:13Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document (s) or serve to amend contractual requirements.

SPECIFICATION

MIL-P-36215A

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENTS CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO (If "yes", in what way?)

4. REMARKS (Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)

SUBMITTED BY (Printed or typed name and activity - Optional)

DATE

DD FORM 1426 REPLACES EDITION OF 1 OCT 54, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:13Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER **ON ANY** CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM **SINCE ANY CHANGES** OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER **NON-RESPONSIVE** IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL Code DPSC-ATS
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

☆ U. S. GOVERNMENT PRINTING OFFICE: 1968-341-511/A-1556

DPSC FORM 1418
AUG 66

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:13Z
Check the source to verify that this is the current version before use.